EPA SAMPLE NO.

MC0AZ0

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-01

% Solids: 30.3 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	3900		01/28/2025	2001
7440-36-0	Antimony	1500	*	01/28/2025	2001
7440-38-2	Arsenic	210	*	01/28/2025	2001
7440-39-3	Barium	110		01/28/2025	2001
7440-41-7	Beryllium	11	*	01/28/2025	2001
7440-43-9	Cadmium	3.3		01/28/2025	2001
7440-70-2	Calcium	24000		01/28/2025	2001
7440-47-3	Chromium	140000	D	01/29/2025	1613
7440-48-4	Cobalt	35000	D	01/29/2025	1625
7440-50-8	Copper	920	*	01/28/2025	2001
7439-89-6	Iron	38000		01/28/2025	2001
7439-92-1	Lead	590		01/28/2025	2001
7439-95-4	Magnesium	3500		01/28/2025	2001
7439-96-5	Manganese	620	*	01/28/2025	2001
7440-02-0	Nickel	29000	D	01/29/2025	1625
7440-09-7	Potassium	600	J	01/28/2025	2001
7782-49-2	Selenium	120	*	01/28/2025	2001
7440-22-4	Silver	2.4	J*	01/28/2025	2001
7440-23-5	Sodium	10000		01/28/2025	2001
7440-28-0	Thallium	6.9	U	01/28/2025	2001
7440-62-2	Vanadium	500		01/28/2025	2001
7440-66-6	Zinc	1400	*	01/28/2025	2001

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0AZ1

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-02

% Solids: 30.3 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	12000		01/27/2025	1834
7440-36-0	Antimony	17	*	01/27/2025	1834
7440-38-2	Arsenic	31	*	01/27/2025	1834
7440-39-3	Barium	81		01/27/2025	1834
7440-41-7	Beryllium	1.2	J*	01/27/2025	1834
7440-43-9	Cadmium	2.2		01/27/2025	1834
7440-70-2	Calcium	8900		01/27/2025	1834
7440-47-3	Chromium	7400		01/27/2025	1834
7440-48-4	Cobalt	3400	D	01/29/2025	1618
7440-50-8	Copper	360	*	01/27/2025	1834
7439-89-6	Iron	34000		01/27/2025	1834
7439-92-1	Lead	810		01/27/2025	1834
7439-95-4	Magnesium	5200		01/27/2025	1834
7439-96-5	Manganese	250	*	01/27/2025	1834
7440-02-0	Nickel	3400	D	01/29/2025	1618
7440-09-7	Potassium	2700		01/27/2025	1834
7782-49-2	Selenium	8.7	J*	01/27/2025	1834
7440-22-4	Silver	0.33	J*	01/27/2025	1834
7440-23-5	Sodium	8900		01/27/2025	1834
7440-28-0	Thallium	7.1	U	01/27/2025	1834
7440-62-2	Vanadium	75		01/27/2025	1834
7440-66-6	Zinc	550	*	01/27/2025	1834

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0AZ2

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-03

% Solids: 44.6 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	8000		01/27/2025	1838
7440-36-0	Antimony	4.6	J*	01/27/2025	1838
7440-38-2	Arsenic	18	*	01/27/2025	1838
7440-39-3	Barium	70		01/27/2025	1838
7440-41-7	Beryllium	1.6	*	01/27/2025	1838
7440-43-9	Cadmium	3.3		01/27/2025	1838
7440-70-2	Calcium	3600		01/27/2025	1838
7440-47-3	Chromium	400		01/27/2025	1838
7440-48-4	Cobalt	1900	D	01/28/2025	2013
7440-50-8	Copper	260	*	01/27/2025	1838
7439-89-6	Iron	21000		01/27/2025	1838
7439-92-1	Lead	340		01/27/2025	1838
7439-95-4	Magnesium	2000		01/27/2025	1838
7439-96-5	Manganese	120	*	01/27/2025	1838
7440-02-0	Nickel	1200	D	01/28/2025	2013
7440-09-7	Potassium	610	J	01/27/2025	1838
7782-49-2	Selenium	6.1	J*	01/27/2025	1838
7440-22-4	Silver	0.54	J*	01/27/2025	1838
7440-23-5	Sodium	4600		01/27/2025	1838
7440-28-0	Thallium	5.4	U	01/27/2025	1838
7440-62-2	Vanadium	33		01/27/2025	1838
7440-66-6	Zinc	490	*	01/27/2025	1838

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0AZ3

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-04

% Solids: 67.2 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	4300		01/27/2025	1842
7440-36-0	Antimony	1.5	J*	01/27/2025	1842
7440-38-2	Arsenic	6.2	*	01/27/2025	1842
7440-39-3	Barium	14	J	01/27/2025	1842
7440-41-7	Beryllium	0.27	J*	01/27/2025	1842
7440-43-9	Cadmium	0.32	J	01/27/2025	1842
7440-70-2	Calcium	1800		01/27/2025	1842
7440-47-3	Chromium	26		01/27/2025	1842
7440-48-4	Cobalt	180		01/27/2025	1842
7440-50-8	Copper	21	*	01/27/2025	1842
7439-89-6	Iron	13000		01/27/2025	1842
7439-92-1	Lead	63		01/27/2025	1842
7439-95-4	Magnesium	1200		01/27/2025	1842
7439-96-5	Manganese	59	*	01/27/2025	1842
7440-02-0	Nickel	78		01/27/2025	1842
7440-09-7	Potassium	530	J	01/27/2025	1842
7782-49-2	Selenium	2.3	J*	01/27/2025	1842
7440-22-4	Silver	0.098	J*	01/27/2025	1842
7440-23-5	Sodium	2300		01/27/2025	1842
7440-28-0	Thallium	3.0	U	01/27/2025	1842
7440-62-2	Vanadium	14		01/27/2025	1842
7440-66-6	Zinc	45	*	01/27/2025	1842

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0AZ4

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-05

% Solids: 30.5 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	17000		01/27/2025	1846
7440-36-0	Antimony	4.6	J*	01/27/2025	1846
7440-38-2	Arsenic	20	*	01/27/2025	1846
7440-39-3	Barium	59		01/27/2025	1846
7440-41-7	Beryllium	1.5	*	01/27/2025	1846
7440-43-9	Cadmium	2.4		01/27/2025	1846
7440-70-2	Calcium	5000		01/27/2025	1846
7440-47-3	Chromium	1000		01/27/2025	1846
7440-48-4	Cobalt	1300	D	01/28/2025	2017
7440-50-8	Copper	130	*	01/27/2025	1846
7439-89-6	Iron	40000		01/27/2025	1846
7439-92-1	Lead	280		01/27/2025	1846
7439-95-4	Magnesium	6900		01/27/2025	1846
7439-96-5	Manganese	310	*	01/27/2025	1846
7440-02-0	Nickel	970		01/27/2025	1846
7440-09-7	Potassium	3900		01/27/2025	1846
7782-49-2	Selenium	8.0	*	01/27/2025	1846
7440-22-4	Silver	0.59	J*	01/27/2025	1846
7440-23-5	Sodium	10000		01/27/2025	1846
7440-28-0	Thallium	5.7	U	01/27/2025	1846
7440-62-2	Vanadium	46		01/27/2025	1846
7440-66-6	Zinc	460	*	01/27/2025	1846

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0AZ5

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-06

% Solids: 34.7 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	16000		01/27/2025	1850
7440-36-0	Antimony	4.9	J*	01/27/2025	1850
7440-38-2	Arsenic	18	*	01/27/2025	1850
7440-39-3	Barium	54		01/27/2025	1850
7440-41-7	Beryllium	1.2	*	01/27/2025	1850
7440-43-9	Cadmium	1.3		01/27/2025	1850
7440-70-2	Calcium	2800		01/27/2025	1850
7440-47-3	Chromium	2500		01/27/2025	1850
7440-48-4	Cobalt	770		01/27/2025	1850
7440-50-8	Copper	99	*	01/27/2025	1850
7439-89-6	Iron	33000		01/27/2025	1850
7439-92-1	Lead	150		01/27/2025	1850
7439-95-4	Magnesium	6500		01/27/2025	1850
7439-96-5	Manganese	280	*	01/27/2025	1850
7440-02-0	Nickel	710		01/27/2025	1850
7440-09-7	Potassium	3500		01/27/2025	1850
7782-49-2	Selenium	6.1	J*	01/27/2025	1850
7440-22-4	Silver	0.56	J*	01/27/2025	1850
7440-23-5	Sodium	10000		01/27/2025	1850
7440-28-0	Thallium	5.8	U	01/27/2025	1850
7440-62-2	Vanadium	46		01/27/2025	1850
7440-66-6	Zinc	280	*	01/27/2025	1850

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0AZ6

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-07

% Solids: 42 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	6000		01/27/2025	1854
7440-36-0	Antimony	12	U*	01/27/2025	1854
7440-38-2	Arsenic	3.3	*	01/27/2025	1854
7440-39-3	Barium	64		01/27/2025	1854
7440-41-7	Beryllium	4.5	*	01/27/2025	1854
7440-43-9	Cadmium	1.9		01/27/2025	1854
7440-70-2	Calcium	6300		01/27/2025	1854
7440-47-3	Chromium	19		01/27/2025	1854
7440-48-4	Cobalt	35		01/27/2025	1854
7440-50-8	Copper	36	*	01/27/2025	1854
7439-89-6	Iron	11000		01/27/2025	1854
7439-92-1	Lead	57		01/27/2025	1854
7439-95-4	Magnesium	3000		01/27/2025	1854
7439-96-5	Manganese	230	*	01/27/2025	1854
7440-02-0	Nickel	51		01/27/2025	1854
7440-09-7	Potassium	1100		01/27/2025	1854
7782-49-2	Selenium	2.0	J*	01/27/2025	1854
7440-22-4	Silver	2.1	U*	01/27/2025	1854
7440-23-5	Sodium	10000		01/27/2025	1854
7440-28-0	Thallium	5.2	U	01/27/2025	1854
7440-62-2	Vanadium	12		01/27/2025	1854
7440-66-6	Zinc	94	*	01/27/2025	1854

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0AZ7

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-08

% Solids: 41.4 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	5600		01/27/2025	1858
7440-36-0	Antimony	1.3	J*	01/27/2025	1858
7440-38-2	Arsenic	17	*	01/27/2025	1858
7440-39-3	Barium	110		01/27/2025	1858
7440-41-7	Beryllium	3.9	*	01/27/2025	1858
7440-43-9	Cadmium	1.7		01/27/2025	1858
7440-70-2	Calcium	3600		01/27/2025	1858
7440-47-3	Chromium	38		01/27/2025	1858
7440-48-4	Cobalt	54		01/27/2025	1858
7440-50-8	Copper	53	*	01/27/2025	1858
7439-89-6	Iron	11000		01/27/2025	1858
7439-92-1	Lead	170		01/27/2025	1858
7439-95-4	Magnesium	2600		01/27/2025	1858
7439-96-5	Manganese	84	*	01/27/2025	1858
7440-02-0	Nickel	56		01/27/2025	1858
7440-09-7	Potassium	1200		01/27/2025	1858
7782-49-2	Selenium	5.6	J*	01/27/2025	1858
7440-22-4	Silver	2.2	U*	01/27/2025	1858
7440-23-5	Sodium	7800		01/27/2025	1858
7440-28-0	Thallium	5.5	U	01/27/2025	1858
7440-62-2	Vanadium	19		01/27/2025	1858
7440-66-6	Zinc	120	*	01/27/2025	1858

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0B00

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-11

% Solids: 45.1 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	5300		01/27/2025	1913
7440-36-0	Antimony	6.4	J*	01/27/2025	1913
7440-38-2	Arsenic	27	*	01/27/2025	1913
7440-39-3	Barium	150		01/27/2025	1913
7440-41-7	Beryllium	0.82	J*	01/27/2025	1913
7440-43-9	Cadmium	5.1		01/27/2025	1913
7440-70-2	Calcium	7500		01/27/2025	1913
7440-47-3	Chromium	27		01/27/2025	1913
7440-48-4	Cobalt	14		01/27/2025	1913
7440-50-8	Copper	79	*	01/27/2025	1913
7439-89-6	Iron	71000		01/27/2025	1913
7439-92-1	Lead	190		01/27/2025	1913
7439-95-4	Magnesium	4700		01/27/2025	1913
7439-96-5	Manganese	240	*	01/27/2025	1913
7440-02-0	Nickel	45		01/27/2025	1913
7440-09-7	Potassium	1300		01/27/2025	1913
7782-49-2	Selenium	12	*	01/27/2025	1913
7440-22-4	Silver	2.0	U*	01/27/2025	1913
7440-23-5	Sodium	7600		01/27/2025	1913
7440-28-0	Thallium	5.0	U	01/27/2025	1913
7440-62-2	Vanadium	24		01/27/2025	1913
7440-66-6	Zinc	880	*	01/27/2025	1913

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0B01

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: SOIL Lab Sample ID: Q1151-12

% Solids: 40.2 Date Received: 01/22/2025

Analytical Method: ICP_AES

Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): mg/kg

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	8200		01/27/2025	1930
7440-36-0	Antimony	1.7	J*	01/27/2025	1930
7440-38-2	Arsenic	8.3	*	01/27/2025	1930
7440-39-3	Barium	39		01/27/2025	1930
7440-41-7	Beryllium	0.45	J*	01/27/2025	1930
7440-43-9	Cadmium	0.80	J	01/27/2025	1930
7440-70-2	Calcium	1200		01/27/2025	1930
7440-47-3	Chromium	42		01/27/2025	1930
7440-48-4	Cobalt	13		01/27/2025	1930
7440-50-8	Copper	66	*	01/27/2025	1930
7439-89-6	Iron	16000		01/27/2025	1930
7439-92-1	Lead	76		01/27/2025	1930
7439-95-4	Magnesium	2400		01/27/2025	1930
7439-96-5	Manganese	76	*	01/27/2025	1930
7440-02-0	Nickel	21		01/27/2025	1930
7440-09-7	Potassium	1300		01/27/2025	1930
7782-49-2	Selenium	2.8	J*	01/27/2025	1930
7440-22-4	Silver	0.37	J*	01/27/2025	1930
7440-23-5	Sodium	7700		01/27/2025	1930
7440-28-0	Thallium	4.3	U	01/27/2025	1930
7440-62-2	Vanadium	27		01/27/2025	1930
7440-66-6	Zinc	140	*	01/27/2025	1930

NOTE: Hardness (total) is reported in mg/L

Comments:

EPA SAMPLE NO.

MC0B02

FORM 1 - IN

INORGANIC ANALYSIS DATA SHEET

Lab Name: Alliance Technical Group, LLC Contract: 68HERH20D0011

Lab Code: ACE Case No.: 51973 MA No. : SDG No.: MC0AZ0

Matrix: Water Lab Sample ID: Q1151-13

% Solids: Date Received: 01/22/2025

Analytical Method: ICP_AES


Concentration Units (µg/L, mg/L, mg/kg dry weight, µg, or µg/cm²): ug/L

CAS No.	Analyte	Concentration	Q	Date Analyzed	Time Analyzed
7429-90-5	Aluminum	200	U	02/06/2025	1436
7440-36-0	Antimony	60	U	02/06/2025	1436
7440-38-2	Arsenic	10	U	02/06/2025	1436
7440-39-3	Barium	200	U	02/06/2025	1436
7440-41-7	Beryllium	5.0	U	02/06/2025	1436
7440-43-9	Cadmium	5.0	U	02/06/2025	1436
7440-70-2	Calcium	5000	U	02/06/2025	1436
7440-47-3	Chromium	10	U	02/06/2025	1436
7440-48-4	Cobalt	50	U	02/06/2025	1436
7440-50-8	Copper	25	U	02/06/2025	1436
7439-89-6	Iron	100	U	02/06/2025	1436
7439-92-1	Lead	10	U	02/06/2025	1436
7439-95-4	Magnesium	5000	U	02/06/2025	1436
7439-96-5	Manganese	15	U	02/06/2025	1436
7440-02-0	Nickel	40	U	02/06/2025	1436
7440-09-7	Potassium	5000	U	02/06/2025	1436
7782-49-2	Selenium	35	U	02/06/2025	1436
7440-22-4	Silver	1.3	J	02/06/2025	1436
7440-23-5	Sodium	5000	U	02/06/2025	1436
7440-28-0	Thallium	25	U	02/06/2025	1436
7440-62-2	Vanadium	50	U	02/06/2025	1436
7440-66-6	Zinc	60	U	02/06/2025	1436

NOTE: Hardness (total) is reported in mg/L

Comments:

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




As 189.042 {479}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000095	Re-Slope:	1.000000
A1 (Gain):	0.059662	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999390	Status:	OK.
Std Error of Est:	0.000035		
Predicted MDL:	0.002457		
Predicted MQL:	0.008189		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00009	.000	1
S1	.01000	.01029	.000	2.88	.00052	.000	1
S3	2.5000	2.4575	-.042	-1.70	.14626	.001	1
S4	5.0000	4.8008	-.199	-3.98	.28580	.001	1
S5	10.000	10.314	.314	3.14	.61422	.001	1
S2	1.2500	1.1769	-.073	-5.85	.06999	.000	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Tl 190.856 {477}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000071	Re-Slope:	1.000000
A1 (Gain):	0.069429	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999038	Status:	OK.
Std Error of Est:	0.000079		
Predicted MDL:	0.001848		
Predicted MQL:	0.006160		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	.00007	.000	1
S1	.02500	.02747	.002	9.87	.00190	.000	1
S3	2.5000	2.7049	.205	8.19	.18451	.002	1
S4	5.0000	5.0228	.023	.457	.34209	.000	1
S5	10.000	9.6755	-.325	-3.25	.65840	.003	1
S2	1.2500	1.3445	.094	7.56	.09174	.000	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Pb 220.353 {453}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000310	Re-Slope:	1.000000
A1 (Gain):	0.222865	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999836	Status:	OK.
Std Error of Est:	0.000151		
Predicted MDL:	0.001400		
Predicted MQL:	0.004666		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00031	.000	1
S1	.01000	.01088	.001	8.83	.00210	.000	1
S3	12.500	13.016	.516	4.13	2.8982	.013	1
S4	25.000	24.860	-.140	-.561	5.5354	.014	1
S5	50.000	49.483	-.517	-1.03	11.018	.036	1
S2	6.2500	6.3902	.140	2.24	1.4227	.004	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Se 196.090 {472}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000360	Re-Slope:	1.000000
A1 (Gain):	0.065763	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999690	Status:	OK.
Std Error of Est:	0.000051		
Predicted MDL:	0.002760		
Predicted MQL:	0.009200		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00036	.000	1
S1	.03500	.03109	-.004	-11.2	.00240	.000	1
S3	2.5000	2.5131	.013	.524	.16411	.001	1
S4	5.0000	4.8339	-.166	-3.32	.31522	.001	1
S5	10.000	10.200	.200	2.00	.66505	.002	1
S2	1.2500	1.2075	-.043	-3.40	.07901	.000	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Sb 206.833 {463}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000341	Re-Slope:	1.000000
A1 (Gain):	0.153719	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999434	Status:	OK.
Std Error of Est:	0.000216		
Predicted MDL:	0.001476		
Predicted MQL:	0.004920		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00034	.000	1
S1	.06000	.05582	-.004	-6.96	.00890	.000	1
S3	2.5000	2.4541	-.046	-1.83	.38272	.001	1
S4	5.0000	4.8153	-.185	-3.69	.75080	.002	1
S5	10.000	10.309	.309	3.09	1.6055	.004	1
S2	1.2500	1.1759	-.074	-5.93	.18366	.001	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Al 396.152 { 85}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000040	Re-Slope:	1.000000
A1 (Gain):	0.011994	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999605	Status:	OK.
Std Error of Est:	0.000210		
Predicted MDL:	0.008158		
Predicted MQL:	0.027193		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00005	.000	.000	-.00004	.000	1
S1	.20000	.17715	-.023	-11.4	.00209	.000	1
S3	77.500	74.572	-2.93	-3.78	.89546	.002	1
S4	155.00	146.15	-8.85	-5.71	1.7551	.012	1
S5	310.00	313.76	3.76	1.21	3.7675	.018	1
S2	38.750	35.516	-3.23	-8.35	.42648	.002	1
S6	800.00	811.28	11.3	1.41	9.7303	.144	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Ba 493.409 { 68}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.006465	Re-Slope:	1.000000
A1 (Gain):	0.409719	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999252	Status:	OK.
Std Error of Est:	0.001685		
Predicted MDL:	0.000826		
Predicted MQL:	0.002752		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00003	.000	.000	.00648	.000	1
S1	.20000	.18702	-.013	-6.49	.08309	.000	1
S3	5.0000	4.9434	-.057	-1.13	2.0319	.008	1
S4	10.000	9.5043	-.496	-4.96	3.9006	.015	1
S5	20.000	20.692	.692	3.46	8.4844	.137	1
S2	2.5000	2.3732	-.127	-5.07	.97881	.006	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Be 234.861 {144}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000041	Re-Slope:	1.000000
A1 (Gain):	4.426662	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999796	Status:	OK.
Std Error of Est:	0.000334		
Predicted MDL:	0.000074		
Predicted MQL:	0.000247		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00004	.000	1
S1	.00500	.00531	.000	6.13	.02350	.000	1
S3	.25000	.25983	.010	3.93	1.1452	.003	1
S4	.50000	.49669	-.003	-.662	2.1888	.005	1
S5	1.0000	.98825	-.012	-1.18	4.3548	.017	1
S2	.12500	.12993	.005	3.94	.57269	.001	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Cd 214.438 {457}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000032	Re-Slope:	1.000000
A1 (Gain):	2.534050	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999759	Status:	OK.
Std Error of Est:	0.000467		
Predicted MDL:	0.000077		
Predicted MQL:	0.000258		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00003	.000	1
S1	.00500	.00511	.000	2.14	.01292	.000	1
S3	1.2500	1.3100	.060	4.80	3.3259	.021	1
S4	2.5000	2.4996	-.000	-.016	6.3466	.016	1
S5	5.0000	4.9232	-.077	-1.54	12.501	.041	1
S2	.62500	.64206	.017	2.73	1.6301	.004	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Ca 373.690 { 90}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000014	Re-Slope:	1.000000
A1 (Gain):	0.008023	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999920	Status:	OK.
Std Error of Est:	0.000355		
Predicted MDL:	0.009472		
Predicted MQL:	0.031572		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00014	.000	.000	.00002	.000	1
S2	62.500	61.418	-1.08	-1.73	.49276	.001	1
S3	125.00	127.08	2.08	1.66	1.0196	.002	1
S4	250.00	243.18	-6.82	-2.73	1.9510	.013	1
S5	500.00	504.32	4.32	.864	4.0461	.014	1
S1	5.0000	4.9509	-.049	-.982	.03973	.000	1
S6	800.00	801.55	1.55	.194	6.4307	.037	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Cr 267.716 {126}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000008	Re-Slope:	1.000000
A1 (Gain):	0.153956	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999231	Status:	OK.
Std Error of Est:	0.000178		
Predicted MDL:	0.000420		
Predicted MQL:	0.001401		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00001	.000	1
S1	.01000	.01133	.001	13.3	.00174	.000	1
S3	7.7500	8.3114	.561	7.24	1.2799	.003	1
S4	15.500	15.589	.089	.575	2.4006	.010	1
S5	31.000	30.068	-.932	-3.01	4.6304	.015	1
S2	3.8750	4.1548	.280	7.22	.63980	.001	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Co 228.616 {448}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000003	Re-Slope:	1.000000
A1 (Gain):	0.830442	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999855	Status:	OK.
Std Error of Est:	0.000377		
Predicted MDL:	0.000260		
Predicted MQL:	0.000866		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00000	.000	1
S1	.05000	.04980	-.000	-.394	.04151	.000	1
S3	1.2500	1.2993	.049	3.95	1.0830	.005	1
S4	2.5000	2.4817	-.018	-.733	2.0688	.005	1
S5	5.0000	4.9559	-.044	-.882	4.1314	.012	1
S2	.62500	.63828	.013	2.12	.53202	.002	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Cu 324.754 {104}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.003692	Re-Slope:	1.000000
A1 (Gain):	0.140741	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999418	Status:	OK.
Std Error of Est:	0.000220		
Predicted MDL:	0.002482		
Predicted MQL:	0.008273		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00369	.000	1
S1	.02500	.02924	.004	17.0	.00781	.000	1
S3	7.5000	7.4981	-.002	-.025	1.0589	.002	1
S4	15.000	14.239	-.761	-5.07	2.0075	.005	1
S5	30.000	30.849	.849	2.83	4.3450	.011	1
S2	3.7500	3.6594	-.091	-2.42	.51866	.003	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Fe 259.837 {130}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000000	Re-Slope:	1.000000
A1 (Gain):	0.004964	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999886	Status:	OK.
Std Error of Est:	0.000033		
Predicted MDL:	0.006491		
Predicted MQL:	0.021637		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	-.00000	.000	1
S1	.10000	.10574	.006	5.74	.00051	.000	1
S3	75.000	78.612	3.61	4.82	.38984	.001	1
S4	150.00	148.70	-1.30	-.866	.73738	.004	1
S5	300.00	303.79	3.79	1.26	1.5065	.009	1
S2	37.500	38.315	.815	2.17	.19000	.001	1
S6	800.00	793.08	-6.92	-.865	3.9368	.026	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Mn 257.610 {131}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000006	Re-Slope:	1.000000
A1 (Gain):	0.088554	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999851	Status:	OK.
Std Error of Est:	0.000054		
Predicted MDL:	0.000347		
Predicted MQL:	0.001158		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00001	.000	1
S1	.01500	.01530	.000	2.01	.00135	.000	1
S3	7.5000	7.6812	.181	2.42	.67974	.001	1
S4	15.000	14.615	-.385	-2.56	1.2933	.010	1
S5	30.000	30.247	.247	.824	2.6767	.007	1
S2	3.7500	3.7060	-.044	-1.17	.32795	.001	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Mg 279.079 {121}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000033	Re-Slope:	1.000000
A1 (Gain):	0.002199	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999715	Status:	OK.
Std Error of Est:	0.000183		
Predicted MDL:	0.017983		
Predicted MQL:	0.059944		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00099	.001	.000	-.00003	.000	1
S2	62.500	59.083	-3.42	-5.47	.12986	.000	1
S3	125.00	123.55	-1.45	-1.16	.27159	.001	1
S4	250.00	238.70	-11.3	-4.52	.52476	.003	1
S5	500.00	506.65	6.65	1.33	1.1139	.005	1
S1	5.0000	4.4331	-.567	-11.3	.00971	.000	1
S6	800.00	810.08	10.1	1.26	1.7809	.008	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Ni 231.604 {446}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000339	Re-Slope:	1.000000
A1 (Gain):	0.589180	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999743	Status:	OK.
Std Error of Est:	0.000318		
Predicted MDL:	0.000410		
Predicted MQL:	0.001366		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00034	.000	1
S1	.04000	.04087	.001	2.18	.02377	.000	1
S3	1.2500	1.3120	.062	4.96	.77441	.004	1
S4	2.5000	2.4868	-.013	-.526	1.4683	.004	1
S5	5.0000	4.9294	-.071	-1.41	2.9108	.009	1
S2	.62500	.64589	.021	3.34	.38107	.001	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Ag 328.068 {103}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000242	Re-Slope:	1.000000
A1 (Gain):	0.274548	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999741	Status:	OK.
Std Error of Est:	0.000051		
Predicted MDL:	0.000381		
Predicted MQL:	0.001269		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00024	.000	1
S1	.01000	.00961	-.000	-3.85	.00238	.000	1
S3	.62500	.61931	-.006	-.911	.16374	.000	1
S4	1.2500	1.2174	-.033	-2.61	.32190	.002	1
S5	2.5000	2.5495	.049	1.98	.67553	.001	1
S2	.31250	.30169	-.011	-3.46	.07956	.000	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Na 818.326 { 41}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.002157	Re-Slope:	1.000000
A1 (Gain):	0.002512	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999515	Status:	OK.
Std Error of Est:	0.000242		
Predicted MDL:	0.411716		
Predicted MQL:	1.372387		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00066	.001	.000	-.00216	.001	1
S2	37.500	35.728	-1.77	-4.73	.08758	.000	1
S3	75.000	73.637	-1.36	-1.82	.18279	.001	1
S4	150.00	137.76	-12.2	-8.16	.34384	.002	1
S5	300.00	304.59	4.59	1.53	.76285	.002	1
S1	5.0000	4.9289	-.071	-1.42	.01022	.001	1
S6	800.00	810.86	10.9	1.36	2.0344	.008	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




V 292.402 {115}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear
Weighting:	1/Conc		

A0 (Offset):	0.000019	Re-Slope:	1.000000
A1 (Gain):	0.153878	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999774	Status:	OK.
Std Error of Est:	0.000082		
Predicted MDL:	0.001978		
Predicted MQL:	0.006595		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	.00002	.000	1
S1	.05000	.05375	.004	7.51	.00827	.000	1
S3	1.2500	1.3009	.051	4.07	.18895	.001	1
S4	2.5000	2.4512	-.049	-1.95	.35471	.000	1
S5	5.0000	4.9784	-.022	-.433	.72108	.001	1
S2	.62500	.64053	.016	2.48	.09296	.000	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Zn 213.856 {158}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000350	Re-Slope:	1.000000
A1 (Gain):	0.280008	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999642	Status:	OK.
Std Error of Est:	0.000535		
Predicted MDL:	0.001750		
Predicted MQL:	0.005832		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00035	.000	1
S1	.06000	.05876	-.001	-2.06	.01690	.000	1
S3	7.5000	7.5956	.096	1.27	2.1351	.007	1
S4	15.000	14.411	-.589	-3.92	4.0515	.020	1
S5	30.000	30.613	.613	2.04	8.6039	.055	1
S2	3.7500	3.6312	-.119	-3.17	1.0211	.004	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




K 769.896 { 44}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.005618	Re-Slope:	1.000000
A1 (Gain):	0.003607	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999515	Status:	OK.
Std Error of Est:	0.000232		
Predicted MDL:	0.050504		
Predicted MQL:	0.168346		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00086	.001	.000	.00562	.000	1
S2	37.500	34.965	-2.54	-6.76	.13174	.001	1
S3	75.000	73.605	-1.39	-1.86	.27112	.001	1
S4	150.00	146.23	-3.77	-2.51	.53308	.004	1
S5	300.00	308.14	8.14	2.71	1.1171	.006	1
S1	5.0000	4.5657	-.434	-8.69	.02209	.000	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




P 177.495 {490}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.001331	Re-Slope:	1.000000
A1 (Gain):	0.045827	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999766	Status:	OK.
Std Error of Est:	0.000017		
Predicted MDL:	0.002255		
Predicted MQL:	0.007517		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00133	.000	1
S1	.01000	.00894	-.001	-10.6	-.00092	.000	1
S3	2.5000	2.5075	.007	.299	.11276	.000	1
S4	5.0000	4.8696	-.130	-2.61	.22019	.001	1
S5	10.000	10.175	.175	1.75	.46168	.000	1
S2	1.2500	1.1992	-.051	-4.06	.05322	.000	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




B 249.678 {135}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.002008	Re-Slope:	1.000000
A1 (Gain):	0.479883	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998901	Status:	OK.
Std Error of Est:	0.000322		
Predicted MDL:	0.000728		
Predicted MQL:	0.002426		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00201	.000	1
S1	.01000	.00009	-.010	-99.1	.00181	.000	1
S3	2.5000	2.6489	.149	5.96	1.0967	.003	1
S4	5.0000	5.0390	.039	.780	2.0672	.002	1
S5	10.000	9.7469	-.253	-2.53	3.9735	.021	1
S2	1.2500	1.3261	.076	6.09	.55015	.002	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Mo 202.030 {467}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000108	Re-Slope:	1.000000
A1 (Gain):	0.574900	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999867	Status:	OK.
Std Error of Est:	0.000157		
Predicted MDL:	0.000337		
Predicted MQL:	0.001122		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00011	.000	1
S1	.01000	.01039	.000	3.91	.00608	.000	1
S3	2.5000	2.5197	.020	.789	1.4487	.005	1
S4	5.0000	4.8758	-.124	-2.48	2.8032	.007	1
S5	10.000	10.122	.122	1.22	5.8192	.012	1
S2	1.2500	1.2322	-.018	-1.42	.70850	.002	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




S 182.034 {485}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000163	Re-Slope:	1.000000
A1 (Gain):	0.026990	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999634	Status:	OK.
Std Error of Est:	0.000039		
Predicted MDL:	0.003823		
Predicted MQL:	0.012744		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00002	.000	.000	.00016	.000	1
S1	.10000	.08619	-.014	-13.8	.00249	.000	1
S3	2.5000	2.4922	-.008	-.310	.06751	.000	1
S4	5.0000	4.8784	-.122	-2.43	.13200	.001	1
S5	10.000	10.216	.216	2.16	.27624	.001	1
S2	1.2500	1.1769	-.073	-5.85	.03197	.000	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Si 251.611 {134}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000497	Re-Slope:	1.000000
A1 (Gain):	0.056705	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.995170	Status:	OK.
Std Error of Est:	0.000298		
Predicted MDL:	0.003364		
Predicted MQL:	0.011213		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00013	-.000	.000	.00049	.000	1
S1	.10000	.23234	.132	132.	.01367	.000	1
S3	2.5000	2.5216	.022	.865	.14391	.001	1
S4	5.0000	4.7964	-.204	-4.07	.27333	.000	1
S5	10.000	10.068	.068	.679	.57310	.001	1
S2	1.2500	1.2320	-.018	-1.44	.07057	.000	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Sn 189.989 {478}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000104	Re-Slope:	1.000000
A1 (Gain):	0.148914	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999776	Status:	OK.
Std Error of Est:	0.000044		
Predicted MDL:	0.000799		
Predicted MQL:	0.002662		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00010	.000	1
S1	.00700	.00739	.000	5.52	.00116	.000	1
S3	2.5000	2.6191	.119	4.76	.38897	.002	1
S4	5.0000	4.9869	-.013	-.262	.74042	.002	1
S5	10.000	9.8631	-.137	-1.37	1.4642	.005	1
S2	1.2500	1.2805	.030	2.44	.19021	.001	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Ti 336.121 {100}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.002398	Re-Slope:	1.000000
A1 (Gain):	0.434672	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999794	Status:	OK.
Std Error of Est:	0.000469		
Predicted MDL:	0.000930		
Predicted MQL:	0.003101		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	.00239	.000	1
S1	.10000	.10479	.005	4.79	.04795	.000	1
S3	2.5000	2.5878	.088	3.51	1.1273	.003	1
S4	5.0000	4.8600	-.140	-2.80	2.1149	.004	1
S5	10.000	10.023	.023	.227	4.3590	.002	1
S2	1.2500	1.2747	.025	1.97	.55645	.002	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Li 670.784 { 50}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000594	Re-Slope:	1.000000
A1 (Gain):	0.140049	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998631	Status:	OK.
Std Error of Est:	0.000151		
Predicted MDL:	0.001300		
Predicted MQL:	0.004334		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00059	.000	1
S5	10.000	10.478	.478	4.78	1.4681	.009	1
S4	5.0000	4.7224	-.278	-5.55	.66196	.007	1
S3	2.5000	2.4128	-.087	-3.49	.33850	.001	1
S1	.01500	.01364	-.001	-9.09	.00250	.000	1
S2	1.2500	1.1379	-.112	-8.97	.15996	.001	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Sr 407.771 { 83}

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000018	Re-Slope:	1.000000
A1 (Gain):	1.518358	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999713	Status:	OK.
Std Error of Est:	0.001934		
Predicted MDL:	0.000064		
Predicted MQL:	0.000213		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00004	.000	1
S1	.10000	.08751	-.012	-12.5	.13288	.001	1
S3	2.5000	2.5407	.041	1.63	3.8577	.039	1
S4	5.0000	4.8403	-.160	-3.19	7.3493	.103	1
S5	10.000	10.164	.164	1.64	15.432	.206	1
S2	1.2500	1.2179	-.032	-2.57	1.8492	.025	1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4




Y 224.306 {450}*

Date of Fit:	1/27/2025 1:59:51	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.000000	Status:	Warning Zero Gain
Std Error of Est:	0.000000		
Predicted MDL:	n/a		
Predicted MQL:	n/a		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



Y 360.073 { 94}*


Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

A2 (Curvature):	0.000000					
n (Exponent):	1.000000					
Correlation:	0.000000		Status:	Warning	Zero Gain	
Std Error of Est:	0.000000					
Predicted MDL:	n/a					
Predicted MQL:	n/a					

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis




Y 371.030 { 91}*

Date of Fit:	<not fit>		Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):		0.000000		Re-Slope:	1.000000	
A1 (Gain):		0.000000		Y-int:	0.000000	
A2 (Curvature):		0.000000				
n (Exponent):		1.000000				
Correlation:		0.000000		Status:	Warning	Zero Gain
Std Error of Est:		0.000000				
Predicted MDL:		n/a				
Predicted MQL:		n/a				

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis


Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4



Y 224.306 {150}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):	0.000000		Re-Slope:	1.000000	
A1 (Gain):	0.000000		Y-int:	0.000000	
A2 (Curvature):	0.000000				
n (Exponent):	1.000000				
Correlation:	0.000000		Status:	Warning	Zero Gain
Std Error of Est:	0.000000				
Predicted MDL:	n/a				
Predicted MQL:	n/a				

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



In 230.606 {446}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):	0.000000		Re-Slope:	1.000000	
A1 (Gain):	0.000000		Y-int:	0.000000	

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

A2 (Curvature):		0.000000					
n (Exponent):		1.000000					
Correlation:		0.000000		Status:	Warning	Zero Gain	
Std Error of Est:		0.000000					
Predicted MDL:		n/a					
Predicted MQL:		n/a					

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S0 Acquired: 1/27/2025 14:23:39 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00009**	**.00007**	**-.00031**	**.00036**	**.00034**	**-.00004**	**.00648**	**.00004**
Stddev	.00009	.00001	.00007	.00006	.00014	.00013	.00023	.00016
%RSD	98.992	20.708	23.596	15.946	41.468	325.66	3.5651	427.59
#1	-.00001	.00006	-.00039	.00041	.00046	.00007	.00642	-.00013
#2	-.00020	.00009	-.00028	.00030	.00038	-.00000	.00673	.00020
#3	-.00007	.00006	-.00026	.00037	.00018	-.00018	.00628	.00004

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00003**	**.00002**	**-.00001**	**-.00000**	**.00369**	**-.00000**	**-.00001**	**-.00003**
Stddev	.00012	.00002	.00001	.00007	.00007	.00001	.00004	.00004
%RSD	356.51	152.65	172.95	1514.4	1.9402	2914.3	600.91	114.57
#1	.00007	-.00001	-.00002	.00007	.00377	-.00000	.00004	-.00003
#2	-.00016	.00002	.00001	-.00002	.00363	.00002	-.00002	.00000
#3	-.00001	.00003	-.00001	-.00006	.00368	-.00001	-.00003	-.00007

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00034**	**-.00024**	**-.00216**	**.00002**	**.00035**	**.00562**	**-.00133**	**.00201**
Stddev	.00018	.00002	.00078	.00014	.00029	.00006	.00006	.00021
%RSD	51.843	9.0647	36.208	787.77	82.517	1.1126	4.2043	10.266
#1	-.00014	-.00024	-.00126	-.00014	.00068	.00557	-.00135	.00203
#2	-.00043	-.00022	-.00256	.00009	.00024	.00560	-.00127	.00221
#3	-.00046	-.00026	-.00265	.00011	.00014	.00569	-.00138	.00180

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00011**	**.00016**	**.00049**	**.00010**	**.00239**	**.00059**	**.00004**
Stddev	.00014	.00004	.00006	.00013	.00011	.00014	.00004
%RSD	130.31	21.427	12.633	123.40	4.6816	23.748	100.19
#1	.00014	.00013	.00056	.00012	.00250	.00053	.00007
#2	-.00005	.00020	.00046	-.00003	.00228	.00050	-.00001
#3	.00023	.00016	.00045	.00022	.00240	.00076	.00006

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S0 Acquired: 1/27/2025 14:23:39 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3721.3	77141.	10941.	2574.2	4698.6
Stddev	4.9	412.	38.	15.0	4.0
%RSD	.13119	.53411	.34829	.58186	.08615
#1	3722.6	76665.	10933.	2557.2	4699.0
#2	3725.5	77385.	10907.	2580.1	4702.4
#3	3716.0	77373.	10982.	2585.3	4694.4

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S1 Acquired: 1/27/2025 14:27:55 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00052**	**.00190**	**.00210**	**.00240**	**.00890**	**.00209**	**.08309**	**.02350**
Stddev	.00007	.00009	.00016	.00018	.00008	.00005	.00045	.00019
%RSD	12.945	4.7803	7.6163	7.5152	.89797	2.3760	.54737	.82349
#1	.00053	.00197	.00215	.00259	.00883	.00204	.08342	.02329
#2	.00045	.00194	.00192	.00238	.00889	.00208	.08327	.02366
#3	.00058	.00180	.00223	.00223	.00899	.00214	.08257	.02357

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.01292**	**.03973**	**.00174**	**.04151**	**.00781**	**.00051**	**.00135**	**.00971**
Stddev	.00006	.00008	.00003	.00031	.00008	.00002	.00002	.00004
%RSD	.49572	.21208	1.9312	.74433	.99954	3.0568	1.5932	.44953
#1	.01287	.03983	.00175	.04145	.00772	.00053	.00137	.00968
#2	.01289	.03970	.00176	.04124	.00788	.00050	.00134	.00976
#3	.01299	.03967	.00170	.04185	.00782	.00052	.00133	.00970

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.02377**	**.00238**	**.01022**	**.00827**	**.01690**	**.02209**	**-.00092**	**.00181**
Stddev	.00011	.00004	.00057	.00031	.00029	.00014	.00008	.00017
%RSD	.46023	1.8549	5.5395	3.7022	1.6864	.65111	9.0244	9.2530
#1	.02382	.00243	.00996	.00858	.01668	.02225	-.00098	.00162
#2	.02364	.00234	.00984	.00797	.01680	.02198	-.00096	.00187
#3	.02384	.00237	.01087	.00827	.01723	.02203	-.00083	.00194

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00608**	**.00249**	**.01367**	**.00116**	**.04795**	**.00250**	**.13288**
Stddev	.00012	.00014	.00010	.00010	.00029	.00016	.00116
%RSD	1.9889	5.7832	.75431	9.0330	.60796	6.4551	.87243
#1	.00602	.00252	.01371	.00127	.04819	.00234	.13404
#2	.00601	.00233	.01356	.00106	.04802	.00251	.13289
#3	.00622	.00261	.01375	.00114	.04762	.00266	.13172

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S1 Acquired: 1/27/2025 14:27:55 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3608.8**	**74781.**	**11122.**	**2485.3**	**4475.5**
Stddev	10.9	95.	43.	6.9	10.5
%RSD	.30306	.12766	.38471	.27731	.23468
#1	3600.2	74890.	11171.	2478.9	4466.1
#2	3621.1	74713.	11107.	2484.4	4486.9
#3	3605.2	74739.	11089.	2492.6	4473.4

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S2 Acquired: 1/27/2025 14:32:08 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.06999**	**.09174**	**1.4227**	**.07901**	**.18366**	**.42648**	**.97881**	**.57269**
Stddev	.00049	.00015	.0043	.00022	.00055	.00168	.00593	.00096
%RSD	.70044	.16698	.30216	.28250	.30047	.39280	.60573	.16766
#1	.06979	.09178	1.4202	.07926	.18340	.42736	.98428	.57309
#2	.06963	.09186	1.4202	.07883	.18329	.42754	.97964	.57160
#3	.07055	.09157	1.4276	.07894	.18430	.42455	.97251	.57338

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**1.6301**	**.49276**	**.63980**	**.53202**	**.51866**	**.19000**	**.32795**	**.12986**
Stddev	.0040	.00134	.00059	.00154	.00264	.00069	.00086	.00025
%RSD	.24463	.27255	.09190	.29023	.50959	.36342	.26083	.19265
#1	1.6294	.49329	.63992	.53128	.52134	.19000	.32824	.12999
#2	1.6265	.49376	.64033	.53099	.51860	.19069	.32861	.13003
#3	1.6344	.49123	.63917	.53380	.51605	.18931	.32698	.12958

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.38107**	**.07956**	**.08758**	**.09296**	**1.0211**	**.13174**	**.05322**	**.55015**
Stddev	.00100	.00016	.00045	.00045	.0041	.00066	.00007	.00202
%RSD	.26192	.20462	.51297	.47873	.39940	.49969	.12618	.36799
#1	.38075	.07968	.08707	.09274	1.0198	.13202	.05316	.54983
#2	.38027	.07938	.08774	.09266	1.0256	.13222	.05321	.54830
#3	.38219	.07962	.08793	.09347	1.0178	.13099	.05329	.55231

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.70850**	**.03197**	**.07057**	**.19021**	**.55645**	**.15996**	**1.8492**
Stddev	.00157	.00013	.00043	.00083	.00197	.00109	.0249
%RSD	.22139	.41849	.61128	.43489	.35436	.67914	1.3466
#1	.70795	.03194	.07027	.18957	.55677	.16120	1.8315
#2	.70729	.03212	.07106	.18992	.55825	.15950	1.8384
#3	.71027	.03186	.07038	.19114	.55434	.15918	1.8777

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S2 Acquired: 1/27/2025 14:32:08 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3402.2**	**71247.**	**11035.**	**2344.1**	**4008.7**
Stddev	6.9	252.	19.	9.3	6.0
%RSD	.20303	.35357	.17140	.39675	.14891
#1	3403.3	71187.	11049.	2343.3	4013.6
#2	3408.5	71030.	11014.	2335.2	4010.3
#3	3394.8	71523.	11043.	2353.7	4002.0

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S3 Acquired: 1/27/2025 14:36:11 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.14626	.18451	2.8982	.16411	.38272	.89546	2.0319	1.1452
Stddev	.00084	.00180	.0127	.00093	.00146	.00194	.0080	.0030
%RSD	.57208	.97649	.43951	.56961	.38140	.21675	.39400	.25991
#1	.14572	.18407	2.8957	.16379	.38341	.89401	2.0319	1.1454
#2	.14583	.18297	2.8869	.16338	.38104	.89766	2.0239	1.1422
#3	.14722	.18649	2.9120	.16517	.38370	.89469	2.0399	1.1481

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3.3259	1.0196	1.2799	1.0830	1.0589	.38984	.67974	.27159
Stddev	.0208	.0016	.0031	.0052	.0019	.00119	.00102	.00077
%RSD	.62671	.15480	.23829	.47984	.18148	.30541	.15051	.28365
#1	3.3201	1.0178	1.2764	1.0820	1.0605	.38865	.67855	.27070
#2	3.3086	1.0202	1.2809	1.0783	1.0568	.39103	.68030	.27202
#3	3.3491	1.0207	1.2823	1.0886	1.0594	.38985	.68035	.27205

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.77441	.16374	.18279	.18895	2.1351	.27112	.11276	1.0967
Stddev	.00441	.00035	.00120	.00086	.0067	.00066	.00029	.0026
%RSD	.56965	.21179	.65809	.45626	.31244	.24170	.26084	.23818
#1	.77290	.16341	.18199	.18852	2.1414	.27074	.11261	1.0946
#2	.77095	.16410	.18221	.18994	2.1281	.27188	.11257	1.0960
#3	.77938	.16372	.18418	.18839	2.1357	.27075	.11310	1.0996

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.4487	.06751	.14391	.38897	1.1273	.33850	3.8577
Stddev	.0053	.00032	.00066	.00174	.0026	.00063	.0389
%RSD	.36788	.47831	.46069	.44845	.22762	.18598	1.0082
#1	1.4478	.06732	.14413	.38810	1.1249	.33901	3.8163
#2	1.4439	.06734	.14317	.38784	1.1270	.33869	3.8636
#3	1.4544	.06789	.14444	.39098	1.1300	.33780	3.8934

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S3 Acquired: 1/27/2025 14:36:11 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3245.2**	**69389.**	**10947.**	**2265.9**	**3791.4**
Stddev	6.4	181.	33.	3.4	9.6
%RSD	.19820	.26100	.30296	.14817	.25231
#1	3245.3	69598.	10970.	2264.1	3792.3
#2	3251.6	69281.	10962.	2263.9	3800.5
#3	3238.8	69288.	10909.	2269.8	3781.5

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S4 Acquired: 1/27/2025 14:40:20 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.28580	.34209	5.5354	.31522	.75080	1.7551	3.9006	2.1888
Stddev	.00113	.00028	.0143	.00149	.00236	.0117	.0153	.0047
%RSD	.39707	.08166	.25774	.47241	.31425	.66489	.39237	.21323
#1	.28647	.34192	5.5434	.31580	.75250	1.7630	3.9182	2.1857
#2	.28449	.34194	5.5189	.31353	.74811	1.7417	3.8912	2.1941
#3	.28644	.34241	5.5438	.31633	.75181	1.7605	3.8922	2.1865

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	6.3466	1.9510	2.4006	2.0688	2.0075	.73738	1.2933	.52476
Stddev	.0159	.0126	.0104	.0045	.0048	.00430	.0104	.00278
%RSD	.25091	.64504	.43457	.21920	.23939	.58319	.80713	.52966
#1	6.3550	1.9594	2.4092	2.0722	2.0126	.73995	1.3004	.52655
#2	6.3283	1.9365	2.3890	2.0636	2.0030	.73242	1.2813	.52156
#3	6.3566	1.9570	2.4037	2.0705	2.0071	.73978	1.2982	.52618

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.4683	.32190	.34384	.35471	4.0515	.53308	.22019	2.0672
Stddev	.0044	.00214	.00193	.00024	.0197	.00383	.00058	.0018
%RSD	.30071	.66483	.56221	.06636	.48658	.71833	.26533	.08849
#1	1.4717	.32308	.34409	.35445	4.0699	.53585	.22042	2.0666
#2	1.4633	.31943	.34563	.35477	4.0307	.52871	.21953	2.0692
#3	1.4699	.32319	.34179	.35491	4.0538	.53469	.22063	2.0657

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2.8032	.13200	.27333	.74042	2.1149	.66196	7.3493
Stddev	.0069	.00053	.00039	.00242	.0042	.00682	.1034
%RSD	.24512	.40080	.14409	.32633	.19833	1.0298	1.4069
#1	2.8067	.13253	.27377	.74199	2.1196	.66662	7.3167
#2	2.7953	.13147	.27302	.73764	2.1114	.65414	7.2662
#3	2.8076	.13201	.27319	.74163	2.1137	.66512	7.4651

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S4 Acquired: 1/27/2025 14:40:20 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3053.6	66585.	10684.	2171.8	3563.6
Stddev	6.7	285.	36.	5.4	8.5
%RSD	.21983	.42832	.33826	.24854	.23879
#1	3051.1	66349.	10681.	2165.5	3558.6
#2	3061.2	66902.	10649.	2174.7	3573.5
#3	3048.6	66503.	10721.	2175.1	3558.8

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S5 Acquired: 1/27/2025 14:44:24 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.61422**	**.65840**	**11.018**	**.66505**	**1.6055**	**3.7675**	**8.4844**	**4.3548**
Stddev	.00084	.00328	.036	.00155	.0042	.0182	.1367	.0173
%RSD	.13731	.49778	.32769	.23261	.26125	.48293	1.6108	.39722
#1	.61368	.65536	11.032	.66357	1.6027	3.7710	8.5342	4.3414
#2	.61379	.65797	10.977	.66492	1.6035	3.7478	8.3298	4.3743
#3	.61519	.66187	11.045	.66666	1.6103	3.7837	8.5892	4.3486

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**12.501**	**4.0461**	**4.6304**	**4.1314**	**4.3450**	**1.5065**	**2.6767**	**1.1139**
Stddev	.041	.0144	.0151	.0121	.0107	.0088	.0072	.0053
%RSD	.32608	.35540	.32555	.29160	.24686	.58360	.26733	.47786
#1	12.503	4.0598	4.6364	4.1352	4.3358	1.5151	2.6714	1.1187
#2	12.459	4.0474	4.6416	4.1179	4.3425	1.4975	2.6848	1.1082
#3	12.540	4.0311	4.6133	4.1411	4.3568	1.5068	2.6737	1.1146

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2.9108**	**.67553**	**.76285**	**.72108**	**8.6039**	**1.1171**	**.46168**	**3.9735**
Stddev	.0086	.00069	.00203	.00060	.0555	.0060	.00037	.0206
%RSD	.29409	.10209	.26565	.08386	.64456	.53475	.07972	.51773
#1	2.9144	.67529	.76117	.72133	8.6382	1.1222	.46187	3.9534
#2	2.9011	.67499	.76228	.72040	8.5399	1.1106	.46125	3.9945
#3	2.9170	.67631	.76510	.72153	8.6336	1.1185	.46191	3.9726

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**5.8192**	**.27624**	**.57310**	**1.4642**	**4.3590**	**1.4681**	**15.432**
Stddev	.0124	.00053	.00085	.0051	.0016	.0095	.206
%RSD	.21242	.19249	.14789	.35099	.03650	.64487	1.3318
#1	5.8112	.27624	.57223	1.4658	4.3582	1.4716	15.602
#2	5.8129	.27571	.57314	1.4585	4.3580	1.4573	15.490
#3	5.8334	.27678	.57392	1.4684	4.3608	1.4753	15.204

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S5 Acquired: 1/27/2025 14:44:24 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2711.8	63463.	10454.	2066.7	3262.4
Stddev	5.2	203.	40.	12.6	7.9
%RSD	.19081	.31934	.38586	.61172	.24204
#1	2715.1	63229.	10453.	2053.2	3261.3
#2	2714.5	63568.	10414.	2078.2	3270.8
#3	2705.8	63590.	10494.	2068.7	3255.1

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: S6 Acquired: 1/27/2025 14:48:59 Type: Cal
Method: EPA SFAM01.0(v56) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S06 Custom ID2: Custom ID3:
Comment:

Elem	Al3961	Ca3736	Fe2598	Mg2790	Na8183
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**9.7303**	**6.4307**	**3.9368**	**1.7809**	**2.0344**
Stddev	.1439	.0367	.0258	.0083	.0081
%RSD	1.4785	.57019	.65535	.46546	.39768
#1	9.7072	6.4327	3.9087	1.7726	2.0342
#2	9.5994	6.3931	3.9421	1.7809	2.0264
#3	9.8843	6.4663	3.9595	1.7892	2.0426

Int. Std.	Y_3600	Y_3710
Units	Cts/S	Cts/S
Avg	**59621.**	**10065.**
Stddev	202.	74.
%RSD	.33883	.73435
#1	59774.	9980.5
#2	59698.	10099.
#3	59392.	10116.

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: ICV003 Acquired: 1/27/2025 15:41:59 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICV003 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.9268194**	**1.079328**	**1.012936**	**.9539148**	**1.025221**	**2.487107**
Stddev	.0036777	.005877	.000404	.0013201	.003029	.016441
%RSD	.3968092	.5445195	.0398446	.1383903	.2954529	.6610406
#1	.9270146	1.075816	1.012530	.9528703	1.021725	2.473938
#2	.9230480	1.086113	1.013337	.9534757	1.027068	2.505534
#3	.9303957	1.076056	1.012942	.9553986	1.026869	2.481850

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.5138612**	**.5108384**	**.5008677**	**9.544351**	**.5664082**	**.5016677**
Stddev	.0016271	.0007536	.0005825	.010181	.0019084	.0002766
%RSD	.3166368	.1475239	.1163065	.1066680	.3369322	.0551449
#1	.5123908	.5099695	.5013425	9.536093	.5642494	.5019179
#2	.5156092	.5112313	.5002176	9.555726	.5678707	.5013707
#3	.5135836	.5113144	.5010429	9.541234	.5671046	.5017147

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4975535**	**10.03601**	**.4897166**	**5.966106**	**.5106198**	**.2346933**
Stddev	.0037554	.02693	.0013586	.041378	.0009282	.0007654
%RSD	.7547670	.2683606	.2774184	.6935528	.1817722	.3261089
#1	.5013085	10.00877	.4881526	5.989458	.5112191	.2342847
#2	.4937978	10.06263	.4903939	5.990528	.5095507	.2355762
#3	.4975542	10.03662	.4906035	5.918330	.5110896	.2342189

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**10.23930**	**.5033207**	**.9719463**	**9.576793**	F **.0031986**	F **.0417262**
Stddev	.28515	.0028168	.0035653	.094688	.0010260	.0001652
%RSD	2.784859	.5596352	.3668161	.9887256	32.07459	.3959791
#1	10.34695	.5047458	.9696371	9.576546	.0027411	.0416065
#2	9.91600	.5000761	.9701492	9.671604	.0043737	.0419147
#3	10.45495	.5051401	.9760524	9.482228	.0024810	.0416574

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: ICV003 Acquired: 1/27/2025 15:41:59 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICV003 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F -.000526	F .0035762	F -.001806	F .0001571	F -.001084	F .0004090
Stddev	.000043	.0019492	.000691	.0005499	.000397	.0013689
%RSD	8.186578	54.50289	38.27061	350.1518	36.66506	334.6759
#1	-.000478	.0013448	-.001501	-.000399	-.001417	.0017183
#2	-.000563	.0044375	-.002597	.000701	-.001190	.0005215
#3	-.000535	.0049464	-.001320	.000169	-.000644	-.001013

Elem	Sr4077
Units	ppm
Avg	F .0011221
Stddev	.0000143
%RSD	1.278112
#1	.0011357
#2	.0011071
#3	.0011235

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3607.403	74343.97	11244.17	2450.872	4435.499
Stddev	4.825	122.40	8.10	1.994	5.311
%RSD	.1337529	.1646373	.0720624	.0813469	.1197400
#1	3612.593	74454.85	11246.80	2448.614	4431.042
#2	3606.564	74212.63	11250.62	2451.612	4441.375
#3	3603.053	74364.44	11235.07	2452.389	4434.079

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: ICB003 Acquired: 1/27/2025 15:45:56 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICB003 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0008965**	**.0007413**	**.0001810**	**-.000761**	**.0004518**	**.0095554**	**-.002458**
Stddev	.0008502	.0010532	.0005983	.001852	.0006579	.0027009	.000218
%RSD	94.82789	142.0851	330.6057	243.3800	145.6246	28.26578	8.872469
#1	.0014925	-.000158	.0007818	.000517	.0005030	.0071201	-.002223
#2	-.000077	.001900	-.000415	.000085	-.000230	.0124603	-.002498
#3	.001274	.000482	.000176	-.002885	.001083	.0090857	-.002654

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000009**	**-.000018**	**.0077181**	**.0000843**	**.0000042**	**.0011649**	**.0053115**
Stddev	.000087	.000059	.0038883	.0003430	.0002699	.0016597	.0018910
%RSD	964.1065	321.3854	50.37812	406.9291	6463.498	142.4739	35.60243
#1	.000044	.000045	.0040433	.0004344	-.000097	.0030013	.0071417
#2	-.000109	-.000030	.0117894	.0000695	-.000201	.0007218	.0033651
#3	.000039	-.000070	.0073217	-.000251	.000310	-.000228	.0054277

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0000506**	**-.012748**	**.0001415**	**-.000319**	**.0431904**	**-.000499**	**.0002598**
Stddev	.0001894	.009890	.0002080	.000170	.1997997	.002363	.0007708
%RSD	374.7125	77.57912	147.0655	53.28983	462.6020	473.6773	296.6780
#1	.0000816	-.001328	-.000051	-.000125	-.006975	.002217	-.000627
#2	.0002225	-.018468	.000362	-.000390	-.126746	-.002083	.000772
#3	-.000152	-.018448	.000114	-.000442	.263292	-.001631	.000634

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.137754**	**-.000456**	**-.000781**	**.0004223**	**-.001718**	**-.001545**	**.0005172**
Stddev	.011066	.001336	.000390	.0001292	.002902	.001428	.0005590
%RSD	8.032964	292.6814	49.98969	30.58574	168.9466	92.41084	108.0946
#1	-.142207	-.000878	-.001212	.0003105	.000141	-.000071	.0011297
#2	-.125156	-.001531	-.000451	.0005638	-.000232	-.001643	.0003875
#3	-.145900	.001039	-.000680	.0003927	-.005062	-.002922	.0000344

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: ICB003 Acquired: 1/27/2025 15:45:56 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICB003 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0007881	-.001043	.0000239
Stddev	.0004265	.000388	.0000374
%RSD	54.11917	37.22026	156.0228
#1	.0011805	-.001402	.0000251
#2	.0008498	-.001096	.0000607
#3	.0003341	-.000631	-.000014

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3587.037	75359.44	10979.58	2471.211	4501.347
Stddev	5.986	76.31	49.29	12.971	5.941
%RSD	.1668753	.1012663	.4489030	.5248984	.1319748
#1	3590.968	75332.65	10995.96	2478.130	4506.565
#2	3580.148	75445.54	10924.19	2456.247	4494.882
#3	3589.996	75300.14	11018.60	2479.256	4502.594

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: ICSA003 Acquired: 1/27/2025 15:56:30 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSA003 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0008332**	**.0019135**	**.0054677**	**.0200191**	**.0069128**	**224.9219**
Stddev	.0021578	.0006698	.0013166	.0006985	.0009632	1.5235
%RSD	258.9784	35.00276	24.08021	3.489249	13.93310	.6773515
#1	.0033197	.0011473	.0061675	.0194753	.0069287	224.2694
#2	-.000549	.0022057	.0062867	.0197751	.0078680	223.8333
#3	-.000271	.0023876	.0039490	.0208069	.0059418	226.6630

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0079114**	**-.000704**	**.0005059**	**240.1774**	**.0598314**	**.0008650**
Stddev	.0010199	.000015	.0000947	1.3583	.0005113	.0002977
%RSD	12.89204	2.159878	18.72470	.5655377	.8545223	34.42024
#1	.0080498	-.000718	.0005626	238.9588	.0603057	.0005864
#2	.0088550	-.000688	.0003966	239.9315	.0592898	.0011787
#3	.0068293	-.000705	.0005587	241.6418	.0598987	.0008299

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.007643**	**98.70624**	**.0099967**	**233.1837**	**.0030492**	**-.001155**
Stddev	.001806	.68818	.0001777	1.3583	.0002908	.000514
%RSD	23.63399	.6972006	1.777336	.5825166	9.535827	44.54493
#1	-.005571	98.22936	.0098980	232.2472	.0027367	-.000938
#2	-.008883	98.39419	.0102018	232.5622	.0030992	-.001742
#3	-.008476	99.49516	.0098902	234.7415	.0033118	-.000785

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.437481**	**-.006219**	**-.009572**	**-.104753**	**.0040572**	F **.4115306**
Stddev	.442460	.001361	.002259	.029624	.0004122	.0037103
%RSD	101.1380	21.88895	23.60059	28.28004	10.16035	.9015936
#1	-.812233	-.005859	-.008897	-.100545	.0035854	.4092660
#2	.050630	-.005074	-.007727	-.077458	.0043476	.4095132
#3	-.550840	-.007724	-.012092	-.136257	.0042386	.4158125

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: ICSA003 Acquired: 1/27/2025 15:56:30 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSA003 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000630**	**.0184330**	**.0033632**	**-.003177**	**-.002776**	**.0050316**
Stddev	.000052	.0071957	.0018756	.000659	.000673	.0006052
%RSD	8.318534	39.03694	55.76902	20.75754	24.24558	12.02891
#1	-.000690	.0206295	.0037216	-.003096	-.002700	.0053030
#2	-.000595	.0103950	.0050336	-.002561	-.002144	.0054538
#3	-.000604	.0242744	.0013342	-.003873	-.003483	.0043382

Elem	Sr4077
Units	ppm
Avg	**.0902908**
Stddev	.0005857
%RSD	.6487207
#1	.0897310
#2	.0902420
#3	.0908994

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3319.126**	**68087.90**	**10715.90**	**2309.467**	**3747.999**
Stddev	6.489	114.35	52.74	5.539	8.174
%RSD	.1955095	.1679498	.4921557	.2398414	.2180991
#1	3326.619	68158.99	10710.36	2308.385	3756.479
#2	3315.444	68148.74	10666.15	2304.548	3740.169
#3	3315.315	67955.99	10771.19	2315.467	3747.350

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: ICSAB003 Acquired: 1/27/2025 16:01:16 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSAB003 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0976883**	**.1102426**	**.0575089**	**.0643529**	**.5629873**	**233.0849**
Stddev	.0034526	.0014409	.0017930	.0039875	.0013113	.5378
%RSD	3.534314	1.306995	3.117839	6.196297	.2329164	.2307233
#1	.0963757	.1118592	.0557536	.0608170	.5616332	233.5284
#2	.1016048	.1090937	.0574356	.0635669	.5630774	233.2395
#3	.0950846	.1097750	.0593374	.0686749	.5642512	232.4867

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4944284**	**.5163196**	**1.018637**	**246.0646**	**.6147760**	**.5115692**
Stddev	.0018489	.0023077	.002769	.5286	.0020814	.0010141
%RSD	.3739396	.4469513	.2717962	.2148192	.3385709	.1982389
#1	.4962536	.5139367	1.017108	245.9041	.6126866	.5104024
#2	.4944749	.5164783	1.016969	245.6349	.6147921	.5120665
#3	.4925567	.5185439	1.021833	246.6549	.6168494	.5122387

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4874980**	**101.9497**	**.5098181**	**239.3722**	**1.023512**	**.2040284**
Stddev	.0028075	.0995	.0005996	.6962	.002576	.0010920
%RSD	.5758964	.0976343	.1176209	.2908304	.2516465	.5352245
#1	.4849502	102.0267	.5092815	238.9622	1.020581	.2051830
#2	.4870358	101.8373	.5097074	238.9784	1.024542	.2038901
#3	.4905078	101.9850	.5104654	240.1760	1.025414	.2030122

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.538449**	**.4883120**	**.9731382**	**-.333603**	**.0054921**	F **.4263345**
Stddev	.257399	.0017105	.0108594	.041952	.0035009	.0009798
%RSD	47.80380	.3502825	1.115917	12.57555	63.74436	.2298277
#1	-.830204	.4896811	.9851528	-.381587	.0014846	.4274655
#2	-.343441	.4863946	.9640221	-.303853	.0079556	.4257943
#3	-.441703	.4888604	.9702399	-.315368	.0070362	.4257436

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: ICSAB003 Acquired: 1/27/2025 16:01:16 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSAB003 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000345	.0182632	-.000782	-.003199	-.003958	.0059729
Stddev	.000105	.0059853	.001983	.001615	.000385	.0003247
%RSD	30.54911	32.77222	253.7488	50.49538	9.722520	5.435427
#1	-.000261	.0189484	.001334	-.002986	-.003595	.0062678
#2	-.000463	.0238763	-.001080	-.001701	-.004361	.0056250
#3	-.000311	.0119648	-.002599	-.004911	-.003917	.0060259

Elem	Sr4077
Units	ppm
Avg	.0916935
Stddev	.0000850
%RSD	.0926876
#1	.0917029
#2	.0916042
#3	.0917734

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3269.239	67487.32	10790.51	2244.903	3725.423
Stddev	4.144	187.94	52.39	7.727	8.559
%RSD	.1267532	.2784772	.4855581	.3442214	.2297373
#1	3273.053	67609.28	10828.93	2236.735	3732.962
#2	3269.835	67581.80	10811.78	2252.098	3727.185
#3	3264.830	67270.89	10730.82	2245.875	3716.120

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCV021 Acquired: 1/27/2025 16:10:42 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV021 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.247377**	**5.035009**	**25.83331**	**5.244305**	**5.258986**	**403.6074**
Stddev	.019788	.018661	.06789	.009859	.015989	5.5892
%RSD	.3770933	.3706258	.2628153	.1879939	.3040390	1.384813
#1	5.231176	5.017067	25.80165	5.238012	5.254742	402.0050
#2	5.241525	5.054314	25.78703	5.239236	5.245546	409.8227
#3	5.269430	5.033645	25.91125	5.255667	5.276669	398.9943

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**9.912933**	**.5337179**	**2.606693**	**402.6336**	**16.23518**	**2.607961**
Stddev	.088502	.0009603	.003626	2.1912	.04532	.005374
%RSD	.8927946	.1799332	.1391004	.5442089	.2791773	.2060663
#1	9.916769	.5331971	2.603991	402.3945	16.24172	2.604958
#2	9.999455	.5348261	2.605274	404.9345	16.27688	2.604759
#3	9.822575	.5331304	2.610814	400.5718	16.18694	2.614165

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**14.72845**	**407.3363**	**14.97760**	**399.6196**	**2.605308**	**1.340373**
Stddev	.05236	.7099	.03974	1.1442	.008465	.002669
%RSD	.3555323	.1742679	.2653196	.2863209	.3248965	.1991125
#1	14.69115	407.5141	14.96391	399.5059	2.602383	1.342502
#2	14.78832	407.9404	15.02238	400.8164	2.598695	1.341238
#3	14.70589	406.5545	14.94652	398.5365	2.614848	1.337379

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**384.5646**	**2.514594**	**15.29756**	**159.3561**	**5.307222**	F **6.273370**
Stddev	2.1134	.010542	.03079	.1424	.013777	.011893
%RSD	.5495603	.4192382	.2012976	.0893765	.2595897	.1895773
#1	382.8799	2.505585	15.33310	159.4506	5.296940	6.262618
#2	386.9359	2.526188	15.27898	159.4253	5.301849	6.286145
#3	383.8779	2.512010	15.28059	159.1923	5.322876	6.271349

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCV021 Acquired: 1/27/2025 16:10:42 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV021 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.111177**	**5.337638**	**4.770677**	**5.218744**	**5.001700**	**5.019914**
Stddev	.011153	.008687	.018360	.008869	.014360	.007362
%RSD	.2182100	.1627483	.3848445	.1699507	.2871038	.1466601
#1	5.103810	5.327904	4.769514	5.219682	4.999300	5.023971
#2	5.105711	5.344603	4.789591	5.209444	5.017109	5.024355
#3	5.124008	5.340408	4.752927	5.227108	4.988691	5.011416

Elem	Sr4077
Units	ppm
Avg	**5.006941**
Stddev	.027015
%RSD	.5395558
#1	5.030959
#2	4.977694
#3	5.012171

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2819.142**	**62661.27**	**10087.71**	**2017.870**	**3252.446**
Stddev	7.076	203.20	42.13	5.860	6.431
%RSD	.2509942	.3242758	.4176850	.2904170	.1977397
#1	2821.757	62566.29	10084.22	2011.530	3254.903
#2	2824.539	62522.95	10047.42	2023.088	3257.286
#3	2811.131	62894.56	10131.48	2018.993	3245.148

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCB021 Acquired: 1/27/2025 16:14:59 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB021 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000240**	**.0002790**	**.0017592**	**-.000893**	**.0008431**	**.0039258**	**.0007473**
Stddev	.000879	.0007821	.0006710	.001433	.0009156	.0008733	.0002446
%RSD	365.4732	280.3640	38.14375	160.5431	108.5972	22.24577	32.73223
#1	.000711	.0003364	.0018781	-.002517	.0001107	.0029898	.0006869
#2	-.000409	.0010308	.0010366	-.000356	.0005489	.0047189	.0010164
#3	-.001023	-.000530	.0023628	.000195	.0018695	.0040687	.0005385

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000076**	**.0000199**	**.0097190**	**.0002771**	**.0000192**	**-.000888**	**.0096743**
Stddev	.000025	.0000294	.0059402	.0001956	.0002774	.001065	.0042439
%RSD	32.61273	147.6864	61.11933	70.60548	1446.458	119.8381	43.86771
#1	-.000058	.0000081	.0044118	.0004571	-.000290	-.001318	.0119023
#2	-.000067	.0000534	.0086095	.0003052	.000245	.000324	.0047804
#3	-.000105	-.000002	.0161358	.0000689	.000103	-.001671	.0123402

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0001748**	**-.018069**	**-.000023**	**-.000099**	**.0479992**	**.0004691**	**.0003386**
Stddev	.0000801	.009409	.000093	.000078	.0474877	.0009046	.0010801
%RSD	45.80385	52.07001	407.8628	78.54391	98.93426	192.8232	319.0232
#1	.0002426	-.015457	.000025	-.000188	.1024950	.0013194	.0012255
#2	.0000865	-.028507	-.000130	-.000067	.0260184	-.000481	.0006546
#3	.0001955	-.010242	.000036	-.000043	.0154843	.000569	-.000864

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0689899**	**.0007276**	**.0031957**	**.0003724**	**-.000084**	**.0002979**	**.0002368**
Stddev	.0327522	.0005464	.0004544	.0003805	.002627	.0023676	.0007130
%RSD	47.47394	75.09454	14.21803	102.1678	3131.081	794.6583	301.0318
#1	.0341189	.0001134	.0037006	-.000058	-.000440	.0010287	-.000221
#2	.0991029	.0009096	.0030665	.000663	-.002515	.0022141	-.000127
#3	.0737480	.0011597	.0028199	.000512	.002703	-.002349	.001058

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCB021 Acquired: 1/27/2025 16:14:59 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB021 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	-.000204	.0002154	.0000720
Stddev	.000300	.0004162	.0000280
%RSD	147.0522	193.2214	38.87164
#1	-.000155	.0002608	.0000419
#2	-.000526	-.000222	.0000767
#3	.000068	.000607	.0000973

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3690.812	75557.42	11181.15	2532.458	4640.577
Stddev	10.126	306.60	101.94	16.100	5.080
%RSD	.2743567	.4057839	.9117476	.6357350	.1094706
#1	3698.779	75362.68	11094.48	2529.985	4640.441
#2	3694.241	75398.73	11155.49	2517.738	4645.724
#3	3679.417	75910.83	11293.47	2549.651	4635.566

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1106-01DLX2 Acquired: 1/27/2025 16:19:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8G3 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.001871**	**-.001071**	**.0030862**	**-.008672**	**.0009223**	**-.137540**
Stddev	.002764	.002676	.0005973	.001402	.0011066	.006925
%RSD	147.6776	249.9592	19.35302	16.17118	119.9753	5.035109
#1	.000036	.000656	.0036614	-.008467	.0006992	-.129787
#2	-.000610	.000286	.0024691	-.010165	-.000056	-.143111
#3	-.005041	-.004154	.0031282	-.007383	.002123	-.139723

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1096313**	**.0000008**	**-.000081**	**522.2007**	**.1250440**	**-.001130**
Stddev	.0009902	.0000348	.000001	2.8420	.0004822	.000115
%RSD	.9032193	4473.689	1.484374	.5442290	.3856149	10.21092
#1	.1099157	.0000310	-.000080	523.5069	.1250837	-.001024
#2	.1085300	.0000086	-.000083	518.9405	.1245432	-.001253
#3	.1104481	-.000037	-.000081	524.1548	.1255051	-.001114

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.001462**	**.0074229**	**.0004559**	**.0155994**	**-.000473**	**-.000675**
Stddev	.001145	.0044260	.0000357	.0178105	.000341	.000332
%RSD	78.31914	59.62625	7.835522	114.1742	72.10715	49.22786
#1	-.000969	.0124926	.0004379	.0338911	-.000842	-.000340
#2	-.000646	.0054483	.0004971	.0145943	-.000170	-.000680
#3	-.002770	.0043279	.0004328	-.001687	-.000406	-.001005

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**13.18763**	**-.000263**	**.0177900**	**56.27371**	**-.002708**	**.0259589**
Stddev	.25285	.000769	.0031812	.36109	.001061	.0011546
%RSD	1.917308	292.2133	17.88178	.6416701	39.19262	4.447589
#1	13.01954	-.000674	.0178167	56.33760	-.001608	.0260759
#2	13.47841	-.000740	.0209577	55.88494	-.003726	.0270505
#3	13.06493	.000624	.0145955	56.59859	-.002791	.0247503

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1106-01DLX2 Acquired: 1/27/2025 16:19:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8G3 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0922617	F 123.5439	.0844550	-.003562	-.015946	.1352333
Stddev	.0004247	.2640	.0023689	.000232	.000668	.0006820
%RSD	.4603109	.2136568	2.804964	6.513970	4.189379	.5043109
#1	.0917756	123.2619	.0818698	-.003408	-.016079	.1358757
#2	.0924486	123.5849	.0865217	-.003450	-.015221	.1345176
#3	.0925609	123.7850	.0849736	-.003829	-.016538	.1353065

Elem	Sr4077
Units	ppm
Avg	2.609138
Stddev	.021437
%RSD	.8216290
#1	2.586212
#2	2.612515
#3	2.628686

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3292.852	69482.23	10377.93	2320.423	3792.576
Stddev	13.238	381.90	37.74	6.702	11.513
%RSD	.4020292	.5496343	.3636287	.2888085	.3035798
#1	3308.053	69470.81	10403.28	2318.972	3805.861
#2	3286.648	69869.71	10334.56	2327.731	3786.378
#3	3283.855	69106.17	10395.96	2314.566	3785.490

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1106-02DLX2 Acquired: 1/27/2025 16:23:32 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8G5 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0040213**	**.0034701**	**.0127578**	**.0075141**	**.0040239**	**30.02319**
Stddev	.0019886	.0010105	.0008136	.0016958	.0005879	.13712
%RSD	49.45223	29.11911	6.377400	22.56850	14.61041	.4567023
#1	.0022106	.0023089	.0126242	.0087038	.0038240	30.11996
#2	.0037037	.0039519	.0120193	.0082661	.0035620	30.08333
#3	.0061496	.0041495	.0136300	.0055723	.0046857	29.86628

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0368667**	**.0069503**	**.0047413**	**76.77702**	**.2047697**	**.2994923**
Stddev	.0005268	.0001912	.0000834	.15736	.0009317	.0005317
%RSD	1.428827	2.750438	1.759667	.2049538	.4550173	.1775447
#1	.0363245	.0069577	.0047210	76.92572	.2050937	.2996489
#2	.0368990	.0067556	.0046699	76.79309	.2037192	.2988999
#3	.0373765	.0071377	.0048330	76.61224	.2054962	.2999282

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.6014398**	**75.83876**	**16.48684**	**24.66050**	**.1138826**	**-.000369**
Stddev	.0012387	.25188	.05339	.06355	.0005768	.000176
%RSD	.2059629	.3321229	.3238510	.2577084	.5064702	47.76793
#1	.6021431	76.07169	16.51405	24.71928	.1134540	-.000198
#2	.6000094	75.87314	16.52115	24.59306	.1136554	-.000551
#3	.6021667	75.57147	16.42533	24.66917	.1145384	-.000359

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**7.727452**	**.2146035**	**.6237325**	**4.386278**	**1.532138**	**.6440730**
Stddev	.421141	.0023784	.0052419	.063672	.004807	.0014898
%RSD	5.449937	1.108281	.8404071	1.451620	.3137597	.2313021
#1	8.192109	.2171566	.6292212	4.446446	1.526801	.6456448
#2	7.619345	.2142035	.6231981	4.392788	1.533486	.6438923
#3	7.370903	.2124505	.6187783	4.319602	1.536128	.6426818

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1106-02DLX2 Acquired: 1/27/2025 16:23:32 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8G5 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0022023	F 202.6793	F 13.18894	-.000486	.0006017	.0297822
Stddev	.0003349	.4070	.01345	.000641	.0006920	.0003959
%RSD	15.20495	.2008132	.1019849	132.0815	115.0102	1.329444
#1	.0018557	202.3328	13.17342	-.001224	.0007909	.0293381
#2	.0022273	202.5776	13.19724	-.000169	-.000165	.0299103
#3	.0025240	203.1275	13.19615	-.000064	.001179	.0300982

Elem	Sr4077
Units	ppm
Avg	.5119958
Stddev	.0030156
%RSD	.5889811
#1	.5135558
#2	.5139118
#3	.5085198

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3966.383	84162.42	11975.70	2756.612	4189.398
Stddev	11.636	68.18	58.58	2.439	12.542
%RSD	.2933703	.0810076	.4891890	.0884778	.2993759
#1	3975.612	84110.91	12012.98	2754.291	4195.084
#2	3970.225	84239.73	12005.94	2759.154	4198.090
#3	3953.312	84136.62	11908.17	2756.391	4175.020

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1106-07DLX2 Acquired: 1/27/2025 16:27:29 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8H1 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0765547**	**-.007371**	**.0101642**	**.0437739**	**.0236069**	**7.258971**
Stddev	.0022352	.001444	.0024278	.0011102	.0011332	.028874
%RSD	2.919812	19.59397	23.88580	2.536308	4.800361	.3977706
#1	.0786102	-.005727	.0077369	.0426457	.0230087	7.250235
#2	.0741751	-.007951	.0101631	.0438108	.0249139	7.235474
#3	.0768786	-.008436	.0125925	.0448652	.0228982	7.291205

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0513011**	**.0039154**	**.0056602**	**60.85525**	**.0492562**	**.3535934**
Stddev	.0005609	.0002408	.0001082	.03489	.0003343	.0006770
%RSD	1.093397	6.150129	1.910976	.0573294	.6785928	.1914510
#1	.0510566	.0041468	.0057806	60.88187	.0490958	.3529025
#2	.0509040	.0039334	.0056287	60.81575	.0496404	.3536223
#3	.0519428	.0036662	.0055712	60.86812	.0490324	.3542555

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.009171**	**306.5822**	**18.82885**	**17.54589**	**.0940428**	**.0012567**
Stddev	.000936	.1289	.03667	.01330	.0005437	.0008006
%RSD	10.20411	.0420333	.1947456	.0757819	.5781751	63.70693
#1	-.008091	306.4344	18.86191	17.54276	.0943622	.0008951
#2	-.009671	306.6710	18.78941	17.56047	.0934150	.0007007
#3	-.009750	306.6413	18.83523	17.53444	.0943512	.0021742

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**3.748085**	**.3968887**	**.4734223**	**2.854195**	**.3303186**	**1.553936**
Stddev	.229886	.0024936	.0070826	.042190	.0010931	.001669
%RSD	6.133417	.6282736	1.496039	1.478181	.3309139	.1073743
#1	3.996679	.3985377	.4770234	2.817343	.3293845	1.554790
#2	3.704399	.3981084	.4652628	2.900216	.3300506	1.555004
#3	3.543177	.3940201	.4779808	2.845026	.3315208	1.552013

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1106-07DLX2 Acquired: 1/27/2025 16:27:29 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8H1 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.003715	F 191.2106	4.509870	-.000277	-.000797	.0029586
Stddev	.000361	.3568	.008763	.000379	.000787	.0007551
%RSD	9.708998	.1866150	.1942976	137.0270	98.72948	25.52068
#1	-.003734	191.2549	4.505096	-.000433	.000030	.0038287
#2	-.003344	190.8338	4.519983	.000156	-.001537	.0025716
#3	-.004065	191.5433	4.504531	-.000553	-.000885	.0024755

Elem	Sr4077
Units	ppm
Avg	.5081389
Stddev	.0015674
%RSD	.3084605
#1	.5096678
#2	.5065357
#3	.5082131

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3740.447	77854.06	11928.67	2557.659	4218.931
Stddev	13.682	229.78	56.84	3.681	13.870
%RSD	.3657742	.2951412	.4765135	.1439084	.3287631
#1	3754.800	77887.88	11941.90	2554.541	4231.700
#2	3738.988	77609.25	11866.39	2561.719	4220.920
#3	3727.554	78065.06	11977.74	2556.717	4204.174

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1106-12DLX2 Acquired: 1/27/2025 16:31:28 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8H6 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0033932**	**.0046568**	**.0061094**	**.0007923**	**-.000234**	**34.49029**
Stddev	.0023400	.0003692	.0015152	.0008397	.001975	.23009
%RSD	68.96097	7.927845	24.80111	105.9906	842.5493	.6671264
#1	.0006942	.0050708	.0066647	.0011199	.001465	34.23203
#2	.0046327	.0043618	.0072686	.0014187	-.002402	34.56540
#3	.0048527	.0045377	.0043949	-.000162	.000233	34.67345

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0429292**	**.0092938**	**.0039972**	**124.1793**	**.0217645**	**.3746265**
Stddev	.0005916	.0000630	.0000300	.4599	.0001318	.0006695
%RSD	1.378099	.6776033	.7518933	.3703424	.6057791	.1787057
#1	.0431233	.0093080	.0040091	123.6571	.0218493	.3743495
#2	.0422649	.0092250	.0039631	124.5239	.0218315	.3741399
#3	.0433993	.0093485	.0040196	124.3570	.0216126	.3753900

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.8261859**	**36.60855**	**29.54168**	**30.52424**	**.1044800**	**.0032825**
Stddev	.0011335	.12533	.29967	.09323	.0002706	.0001973
%RSD	.1371901	.3423585	1.014407	.3054455	.2589642	6.009848
#1	.8251606	36.46660	29.37197	30.41775	.1042447	.0031775
#2	.8274030	36.70394	29.36538	30.56380	.1047757	.0031599
#3	.8259942	36.65511	29.88769	30.59117	.1044197	.0035100

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**13.88668**	**.1492915**	**1.123658**	**12.51410**	**4.962538**	**.4269650**
Stddev	.23901	.0010405	.006799	.11301	.009519	.0006203
%RSD	1.721180	.6969507	.6051118	.9030802	.1918184	.1452859
#1	13.65929	.1491025	1.117482	12.38502	4.965667	.4274693
#2	13.86490	.1483585	1.130944	12.59523	4.951848	.4262723
#3	14.13583	.1504136	1.122548	12.56205	4.970098	.4271532

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1106-12DLX2 Acquired: 1/27/2025 16:31:28 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8H6 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000897	F 226.2879	F 16.59609	-.001728	-.002615	.0308780
Stddev	.000281	.0461	.04745	.000538	.000149	.0002590
%RSD	31.37630	.0203604	.2859251	31.10310	5.686860	.8386527
#1	-.001173	226.3068	16.64826	-.001412	-.002756	.0305929
#2	-.000907	226.2354	16.58452	-.001424	-.002630	.0309425
#3	-.000610	226.3216	16.55549	-.002349	-.002459	.0310986

Elem	Sr4077
Units	ppm
Avg	.6979582
Stddev	.0037697
%RSD	.5401034
#1	.6937754
#2	.7010930
#3	.6990063

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3975.070	83843.82	13030.79	2763.387	4005.833
Stddev	1.519	388.15	41.50	6.033	.412
%RSD	.0382028	.4629461	.3184464	.2183273	.0102762
#1	3974.028	84237.58	13003.08	2768.494	4005.792
#2	3974.370	83832.36	13078.50	2756.730	4006.264
#3	3976.813	83461.53	13010.80	2764.937	4005.444

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1045-17DLX2 Acquired: 1/27/2025 16:39:31 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: GCQ12 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0221622	-.003568	.5047582	-.002136	.0100102	14.59530
Stddev	.0018003	.000697	.0010083	.004792	.0005898	.06943
%RSD	8.123368	19.53768	.1997627	224.3641	5.892011	.4757280
#1	.0204450	-.004093	.5036082	.000207	.0105792	14.67345
#2	.0240354	-.003833	.5051758	-.007648	.0100497	14.57177
#3	.0220061	-.002777	.5054906	.001034	.0094016	14.54070

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	18.98728	.0019890	.0034838	F 906.0691	.0522391	.0243162
Stddev	.14036	.0000785	.0000421	7.9233	.0002950	.0004460
%RSD	.7392081	3.948276	1.208736	.8744746	.5646355	1.834349
#1	18.98675	.0019551	.0035276	904.0242	.0525783	.0244169
#2	19.12790	.0019331	.0034800	899.3687	.0520970	.0247033
#3	18.84719	.0020787	.0034437	914.8145	.0520422	.0238284

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.202630	63.78684	7.411170	459.5242	.0282611	-.000391
Stddev	.006199	.28654	.024115	1.2357	.0006157	.000316
%RSD	.5154605	.4492166	.3253822	.2689141	2.178442	80.78744
#1	1.207922	64.10439	7.438886	460.8338	.0287015	-.000085
#2	1.195810	63.70854	7.394990	459.3601	.0275576	-.000371
#3	1.204159	63.54759	7.399634	458.3788	.0285242	-.000716

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F -1.21669	.0728870	.7639608	1.597042	1.678404	.2882971
Stddev	.05847	.0002159	.0083913	.046310	.002908	.0012750
%RSD	4.805811	.2962653	1.098396	2.899744	.1732619	.4422369
#1	-1.27679	.0730845	.7550303	1.621808	1.676576	.2890939
#2	-1.15999	.0726564	.7651706	1.543614	1.681757	.2889708
#3	-1.21330	.0729200	.7716816	1.625702	1.676878	.2868267

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1045-17DLX2 Acquired: 1/27/2025 16:39:31 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: GCQ12 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0014713	6.443462	5.708219	-.001184	.3076573	.0276306
Stddev	.0000920	.004112	.016460	.000017	.0021794	.0004775
%RSD	6.255516	.0638127	.2883506	1.410870	.7083937	1.728330
#1	.0015403	6.447573	5.689354	-.001197	.3096275	.0274336
#2	.0015069	6.443465	5.719652	-.001189	.3080282	.0281751
#3	.0013668	6.439349	5.715651	-.001165	.3053162	.0272830

Elem	Sr4077
Units	ppm
Avg	.3989473
Stddev	.0019730
%RSD	.4945455
#1	.4012175
#2	.3979776
#3	.3976469

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3126.716	66020.81	10636.49	2166.701	3414.465
Stddev	2.733	80.85	39.66	11.464	5.444
%RSD	.0874072	.1224682	.3728349	.5291104	.1594378
#1	3123.671	65927.57	10678.15	2171.936	3408.307
#2	3128.955	66071.61	10632.10	2174.614	3418.637
#3	3127.522	66063.24	10599.20	2153.554	3416.452

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166225TB Acquired: 1/27/2025 16:43:49 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LEB225 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0010425**	**.0013899**	**.0006659**	**-.000616**	**-.001122**	**-.002431**	**.0041765**
Stddev	.0010358	.0005279	.0003721	.001087	.000746	.007445	.0008370
%RSD	99.35564	37.97937	55.88445	176.4421	66.50573	306.2388	20.04122
#1	.0003438	.0019965	.0007529	-.001598	-.001856	-.008757	.0050291
#2	.0005512	.0011382	.0002580	.000552	-.001147	.005773	.0041442
#3	.0022326	.0010350	.0009868	-.000802	-.000364	-.004309	.0033560

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000031**	**.0000408**	**.0191408**	**-.000068**	**-.000049**	**-.001684**	**.0097478**
Stddev	.000051	.0000607	.0110816	.000241	.000041	.000600	.0043964
%RSD	164.2834	149.0309	57.89510	357.2788	82.58917	35.61057	45.10099
#1	-.000070	.0000923	.0304511	-.000307	-.000032	-.001177	.0132161
#2	-.000049	-.000026	.0083030	.000175	-.000020	-.002345	.0112241
#3	.000026	.000056	.0186683	-.000071	-.000096	-.001529	.0048033

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0017155**	**.0018228**	**.0001478**	**-.000129**	**-.171517**	**.0003380**	**.0014895**
Stddev	.0001351	.0095514	.0002484	.000422	.391376	.0009110	.0014100
%RSD	7.873417	523.9997	168.0029	328.1876	228.1850	269.5213	94.66141
#1	.0018634	-.004693	.0002941	-.000613	-.612298	.0003915	-.000054
#2	.0016847	.012787	.0002883	.000160	-.037496	.0012211	.002710
#3	.0015986	-.002625	-.000139	.000067	.135242	-.000599	.001812

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-1.43935**	**.0014230**	**-.001665**	**.0000709**	**7.549383**	**-.001865**	**-.000140**
Stddev	.02563	.0007661	.000729	.0002335	.010912	.003302	.000109
%RSD	1.780927	53.83860	43.79692	329.5988	.1445385	177.0168	78.07670
#1	-1.46828	.0022875	-.001223	-.000157	7.561151	.001740	-.000023
#2	-1.43030	.0008280	-.002507	.000310	7.547400	-.002595	-.000239
#3	-1.41947	.0011537	-.001265	.000059	7.539599	-.004741	-.000157

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166225TB Acquired: 1/27/2025 16:43:49 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LEB225 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0010247	-.002276	-.000014
Stddev	.0002770	.001172	.000008
%RSD	27.03123	51.50718	52.48912
#1	.0010203	-.003089	-.000023
#2	.0007499	-.000932	-.000009
#3	.0013039	-.002808	-.000011

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3815.796	79421.72	11486.41	2670.094	4838.271
Stddev	17.913	538.06	69.37	15.303	14.903
%RSD	.4694406	.6774712	.6039401	.5731163	.3080199
#1	3834.858	78822.23	11565.65	2658.646	4854.874
#2	3813.219	79862.77	11456.98	2687.475	4833.885
#3	3799.311	79580.17	11436.61	2664.163	4826.053

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-01 Acquired: 1/27/2025 16:47:57 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F5 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0060448	.0050903	.0109529	.0047741	.0002074	77.99161
Stddev	.0020790	.0003040	.0013435	.0016701	.0011297	.47931
%RSD	34.39287	5.971580	12.26631	34.98357	544.7990	.6145650
#1	.0082447	.0052638	.0115859	.0028948	-.000130	78.30807
#2	.0041128	.0047393	.0094098	.0060887	-.000715	77.44015
#3	.0057768	.0052677	.0118630	.0053387	.001467	78.22661

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0943564	.0034820	.0121082	93.30189	.0583490	1.490300
Stddev	.0011167	.0001043	.0000284	.33712	.0002815	.002560
%RSD	1.183434	2.996657	.2343524	.3613257	.4825291	.1717450
#1	.0956075	.0033693	.0121393	93.64214	.0586741	1.487351
#2	.0934606	.0035015	.0121013	92.96798	.0581857	1.491943
#3	.0940012	.0035752	.0120839	93.29554	.0581871	1.491607

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.8522279	47.26364	11.83362	46.82327	.7991922	.0003580
Stddev	.0005327	.13160	.05604	.12298	.0015810	.0002125
%RSD	.0625119	.2784288	.4735913	.2626433	.1978186	59.36746
#1	.8528102	47.35589	11.88838	46.96441	.7974634	.0005751
#2	.8521086	47.11295	11.77637	46.76626	.7995486	.0003486
#3	.8517650	47.32208	11.83611	46.73914	.8005645	.0001503

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	6.305030	.1471073	1.035040	9.769803	4.615478	.6530935
Stddev	.255728	.0020456	.006641	.081928	.008949	.0028691
%RSD	4.055942	1.390566	.6416469	.8385851	.1938835	.4393146
#1	6.079594	.1468367	1.034931	9.782437	4.620512	.6535967
#2	6.582918	.1492748	1.028454	9.682291	4.620776	.6556778
#3	6.252578	.1452104	1.041735	9.844680	4.605146	.6500061

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-01 Acquired: 1/27/2025 16:47:57 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F5 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000538	F 327.7085	F 28.08739	-.002787	.0956077	.1101415
Stddev	.000247	.5630	.12764	.001455	.0003903	.0011923
%RSD	45.94328	.1717987	.4544558	52.20403	.4082674	1.082541
#1	-.000271	327.2385	28.17352	-.002364	.0959875	.1111506
#2	-.000759	328.3325	28.14791	-.004407	.0956281	.1088258
#3	-.000584	327.5546	27.94075	-.001591	.0952076	.1104480

Elem	Sr4077
Units	ppm
Avg	.3989891
Stddev	.0030409
%RSD	.7621518
#1	.4010249
#2	.3954935
#3	.4004488

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4380.197	91004.34	14095.90	3041.527	4135.943
Stddev	13.553	92.09	82.61	17.068	10.361
%RSD	.3094191	.1011939	.5860753	.5611506	.2505007
#1	4393.689	90917.66	14103.04	3055.849	4147.883
#2	4380.319	91101.02	14009.95	3046.090	4130.623
#3	4366.584	90994.34	14174.72	3022.641	4129.324

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-02 Acquired: 1/27/2025 16:56:08 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0146953**	**.0072248**	**.0088653**	**-.003959**	**-.003280**	**32.01960**
Stddev	.0011960	.0009187	.0010527	.000727	.000788	.20203
%RSD	8.138760	12.71578	11.87384	18.35634	24.04128	.6309524
#1	.0154020	.0062729	.0089186	-.003441	-.002811	31.97911
#2	.0133144	.0072954	.0077871	-.004790	-.004190	31.84087
#3	.0153694	.0081062	.0098904	-.003646	-.002838	32.23880

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0394623**	**.0026067**	**.0016662**	**54.41217**	**.0293643**	**.1098856**
Stddev	.0005846	.0000199	.0000761	.32742	.0003179	.0002392
%RSD	1.481376	.7651375	4.565057	.6017358	1.082426	.2176906
#1	.0398189	.0026268	.0017488	54.44298	.0290969	.1101490
#2	.0387877	.0025869	.0016508	54.07043	.0292802	.1096819
#3	.0397804	.0026063	.0015991	54.72309	.0297157	.1098259

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1203837**	**11.50054**	**2.237321**	**23.99326**	**.1030756**	**-.002314**
Stddev	.0003464	.07753	.010144	.18445	.0005389	.000063
%RSD	.2877549	.6741274	.4533944	.7687730	.5228178	2.722136
#1	.1199937	11.50316	2.237865	24.03815	.1036880	-.002386
#2	.1205015	11.42174	2.226915	23.79051	.1028655	-.002284
#3	.1206559	11.57673	2.247181	24.15113	.1026735	-.002272

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**2.780586**	**.0234275**	**.5252356**	**13.52778**	**.6660636**	**.3095265**
Stddev	.177834	.0004196	.0021782	.12495	.0008540	.0020473
%RSD	6.395551	1.791124	.4147049	.9236865	.1282235	.6614314
#1	2.576558	.0229817	.5270634	13.49922	.6654154	.3106181
#2	2.902709	.0238148	.5228254	13.41958	.6670314	.3107966
#3	2.862489	.0234859	.5258181	13.66454	.6657441	.3071647

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-02 Acquired: 1/27/2025 16:56:08 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0001577	F 320.3987	F 11.05320	-.002038	.0120930	.0234766
Stddev	.0001738	.2985	.05481	.001249	.0000875	.0007521
%RSD	110.1595	.0931642	.4958897	61.27886	.7232231	3.203746
#1	.0000656	320.7324	11.10429	-.002982	.0121489	.0226280
#2	.0003582	320.3065	11.06001	-.002510	.0121378	.0240609
#3	.0000494	320.1571	10.99530	-.000622	.0119922	.0237410

Elem	Sr4077
Units	ppm
Avg	.2763597
Stddev	.0016163
%RSD	.5848446
#1	.2763826
#2	.2747321
#3	.2779644

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7597.578	159977.2	24561.43	5246.753	4129.489
Stddev	19.721	548.3	137.67	34.345	9.273
%RSD	.2595737	.3427189	.5605233	.6545931	.2245650
#1	7620.349	160032.9	24478.10	5237.933	4139.534
#2	7585.984	160495.4	24485.85	5284.648	4127.677
#3	7586.401	159403.1	24720.34	5217.679	4121.255

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1105-01DLX5 Acquired: 1/27/2025 17:00:07 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8G3 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0656971**	**.0001636**	**.0698264**	**.0006272**	**.0057649**	**23.05545**
Stddev	.0038691	.0007090	.0018252	.0013550	.0019793	.10822
%RSD	5.889318	433.4070	2.613943	216.0247	34.33386	.4694002
#1	.0692397	.0005807	.0698381	-.000367	.0039624	23.16519
#2	.0662833	.0005651	.0716458	.002171	.0054492	22.94881
#3	.0615684	-.000655	.0679954	.000078	.0078831	23.05235

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2357544**	**.0009555**	**.0030419**	**553.2820**	**.0797812**	**.0113204**
Stddev	.0013556	.0000443	.0000403	2.2756	.0001595	.0002174
%RSD	.5750148	4.639231	1.323916	.4112882	.1998890	1.920023
#1	.2365787	.0009856	.0030026	550.6623	.0799370	.0114542
#2	.2341898	.0009764	.0030399	554.4156	.0796183	.0110696
#3	.2364947	.0009046	.0030831	554.7681	.0797884	.0114374

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0731189**	**31.92654**	**1.064574**	**7.207608**	**.0301768**	**-.000609**
Stddev	.0021673	.12517	.006641	.039268	.0000614	.000415
%RSD	2.964093	.3920639	.6238461	.5448101	.2035442	68.10831
#1	.0750303	32.06313	1.068409	7.246843	.0302378	-.001015
#2	.0735621	31.81731	1.056906	7.168308	.0301778	-.000626
#3	.0707642	31.89917	1.068408	7.207673	.0301149	-.000186

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.3461497**	**.1261801**	**.4939139**	**6.325316**	**.5918018**	**.1650954**
Stddev	.0677551	.0011234	.0011058	.053945	.0036404	.0005611
%RSD	19.57392	.8902807	.2238856	.8528501	.6151415	.3398498
#1	.3345839	.1249765	.4950878	6.345309	.5879339	.1650628
#2	.2849220	.1272008	.4928919	6.264228	.5951613	.1645514
#3	.4189432	.1263631	.4937621	6.366410	.5923101	.1656721

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1105-01DLX5 Acquired: 1/27/2025 17:00:07 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8G3 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0926339	F 12.18106	1.885746	.0040527	1.346987	.0309748
Stddev	.0003166	.03607	.006763	.0008172	.003486	.0007464
%RSD	.3417974	.2961211	.3586245	20.16390	.2588273	2.409826
#1	.0926814	12.19142	1.881104	.0037955	1.344718	.0309472
#2	.0922962	12.14094	1.882629	.0049676	1.345240	.0317347
#3	.0929241	12.21081	1.893505	.0033951	1.351001	.0302426

Elem	Sr4077
Units	ppm
Avg	.5863565
Stddev	.0050921
%RSD	.8684353
#1	.5915014
#2	.5813189
#3	.5862492

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3319.201	69850.79	10945.93	2311.046	3712.855
Stddev	3.366	205.63	76.54	5.135	6.362
%RSD	.1014023	.2943799	.6992610	.2221891	.1713559
#1	3315.451	69951.69	11033.55	2313.371	3705.510
#2	3321.960	69986.48	10912.18	2305.160	3716.439
#3	3320.193	69614.20	10892.07	2314.608	3716.618

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-03 Acquired: 1/27/2025 17:04:17 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0152263**	**.0054877**	**.0074558**	**-.002623**	**-.003462**	**31.74589**
Stddev	.0015723	.0006744	.0018942	.000432	.000841	.08404
%RSD	10.32620	12.28864	25.40574	16.46064	24.30105	.2647124
#1	.0144038	.0057737	.0075108	-.002493	-.004357	31.69793
#2	.0142358	.0047175	.0093220	-.003105	-.003341	31.84292
#3	.0170392	.0059720	.0055348	-.002271	-.002688	31.69682

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0410652**	**.0026765**	**.0016509**	**54.55599**	**.0291932**	**.1091885**
Stddev	.0003593	.0000425	.0000343	.17085	.0001008	.0001778
%RSD	.8749177	1.586545	2.078986	.3131589	.3451618	.1628289
#1	.0414687	.0027198	.0016202	54.65499	.0292951	.1093322
#2	.0409470	.0026350	.0016445	54.65426	.0291907	.1089897
#3	.0407799	.0026746	.0016879	54.35871	.0290936	.1092435

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1222387**	**11.44020**	**2.271326**	**24.11338**	**.1017429**	**-.002560**
Stddev	.0007545	.02061	.007946	.06782	.0004882	.000180
%RSD	.6172579	.1801372	.3498290	.2812648	.4798204	7.028492
#1	.1228597	11.42995	2.278380	24.16140	.1022993	-.002767
#2	.1213990	11.46392	2.272881	24.14295	.1013864	-.002471
#3	.1224574	11.42672	2.262718	24.03580	.1015430	-.002441

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**2.993151**	**.0245857**	**.5220601**	**13.29924**	**.6864713**	**.3123202**
Stddev	.208066	.0006501	.0042167	.08781	.0032009	.0011700
%RSD	6.951414	2.644084	.8076996	.6602837	.4662847	.3746296
#1	2.768918	.0238979	.5262359	13.22340	.6900884	.3120533
#2	3.030561	.0246693	.5178037	13.39544	.6840043	.3113066
#3	3.179975	.0251899	.5221407	13.27887	.6853213	.3136006

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-03 Acquired: 1/27/2025 17:04:17 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7D Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0000714	F 321.7125	F 11.40273	-.001358	.0116570	.0239460
Stddev	.0000408	1.0756	.04116	.000388	.0003529	.0002275
%RSD	57.15944	.3343459	.3609461	28.58299	3.027142	.9500525
#1	.0000998	322.5493	11.45016	-.001803	.0112547	.0238840
#2	.0000898	320.4993	11.37633	-.001187	.0119143	.0241981
#3	.0000246	322.0891	11.38172	-.001085	.0118020	.0237560

Elem	Sr4077
Units	ppm
Avg	.2785562
Stddev	.0010410
%RSD	.3737124
#1	.2784354
#2	.2796523
#3	.2775808

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7633.366	160162.5	24234.49	5379.271	4140.956
Stddev	11.566	74.0	82.18	26.985	9.335
%RSD	.1515190	.0462248	.3390916	.5016507	.2254363
#1	7646.688	160092.5	24156.22	5349.900	4150.403
#2	7627.515	160154.9	24320.08	5402.969	4140.726
#3	7625.894	160240.0	24227.17	5384.944	4131.737

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-02LX5 Acquired: 1/27/2025 17:08:16 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0052004**	**.0008728**	**.0024617**	**-.002073**	**-.001698**	**10.57208**
Stddev	.0015544	.0006597	.0017661	.000749	.000419	.05116
%RSD	29.88908	75.58023	71.74420	36.10319	24.66358	.4839095
#1	.0069199	.0010885	.0006126	-.001224	-.001899	10.52067
#2	.0047865	.0001323	.0026414	-.002637	-.001979	10.62298
#3	.0038950	.0013977	.0041310	-.002358	-.001217	10.57260

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0122575**	**.0009101**	**.0002418**	**18.20564**	**.0099149**	**.0213033**
Stddev	.0008015	.0000562	.0000662	.10482	.0000388	.0001014
%RSD	6.538551	6.173710	27.40004	.5757756	.3914376	.4757493
#1	.0120106	.0009479	.0002822	18.08516	.0098880	.0212579
#2	.0131533	.0008455	.0001653	18.27593	.0099594	.0212326
#3	.0116084	.0009369	.0002779	18.25583	.0098972	.0214195

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0426056**	**3.900429**	**.7636094**	**7.936518**	**.0201207**	**-.001125**
Stddev	.0009304	.021865	.0049122	.034016	.0004661	.000133
%RSD	2.183748	.5605879	.6432833	.4285966	2.316494	11.80679
#1	.0431653	3.875749	.7580854	7.897264	.0202672	-.001270
#2	.0431199	3.917382	.7674865	7.957324	.0195989	-.001009
#3	.0415316	3.908156	.7652563	7.954967	.0204959	-.001096

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.7899448**	**.0084408**	**.1734866**	**4.250642**	**.1288588**	**.1120423**
Stddev	.1757672	.0012575	.0035375	.044590	.0012643	.0016504
%RSD	22.25057	14.89777	2.039055	1.049007	.9811662	1.473060
#1	.6024390	.0071436	.1697325	4.233932	.1294548	.1138827
#2	.9509680	.0085246	.1767578	4.216822	.1297150	.1106935
#3	.8164274	.0096544	.1739696	4.301173	.1274067	.1115508

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-02LX5 Acquired: 1/27/2025 17:08:16 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7L Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0002004	F 61.55930	3.888666	-.000660	.0043662	.0079643
Stddev	.0003422	.10074	.001119	.000373	.0003962	.0009854
%RSD	170.7360	.1636423	.0287828	56.60599	9.074269	12.37271
#1	-.000182	61.47419	3.888250	-.000336	.0048232	.0068283
#2	.000478	61.53319	3.889934	-.001068	.0041546	.0085886
#3	.000305	61.67052	3.887815	-.000574	.0041206	.0084759

Elem	Sr4077
Units	ppm
Avg	.0914938
Stddev	.0005927
%RSD	.6477625
#1	.0908124
#2	.0917796
#3	.0918893

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4529.693	93399.80	13616.40	3112.835	4496.200
Stddev	6.441	175.94	81.74	18.706	1.990
%RSD	.1421853	.1883722	.6003409	.6009370	.0442530
#1	4523.787	93544.90	13532.41	3133.262	4494.653
#2	4528.731	93450.41	13695.69	3108.702	4495.504
#3	4536.560	93204.11	13621.10	3096.541	4498.445

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-04 Acquired: 1/27/2025 17:12:18 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7S Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0313922	.0528880	.0276423	.0423731	.0383515	33.47322
Stddev	.0004567	.0011993	.0014590	.0011370	.0001345	.15224
%RSD	1.454746	2.267611	5.278252	2.683230	.3506104	.4548004
#1	.0308795	.0525535	.0289325	.0432302	.0383080	33.29936
#2	.0317553	.0542190	.0279354	.0410833	.0382441	33.53765
#3	.0315418	.0518914	.0260590	.0428059	.0385023	33.58264

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.9068185	.0261158	.0516259	55.55499	.1290278	.5995280
Stddev	.0065448	.0000744	.0000718	.21717	.0002632	.0003301
%RSD	.7217322	.2850422	.1391495	.3909171	.2039629	.0550631
#1	.8993203	.0261994	.0517055	55.31925	.1293292	.5998868
#2	.9113843	.0260918	.0516064	55.74692	.1289107	.5992373
#3	.9097509	.0260564	.0515659	55.59880	.1288435	.5994598

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.2370482	12.17516	2.531310	24.51287	.5992398	.0153733
Stddev	.0009556	.04105	.013259	.05268	.0018094	.0000545
%RSD	.4031226	.3371209	.5237831	.2149105	.3019419	.3542126
#1	.2360077	12.13088	2.519590	24.48553	.5977888	.0154345
#2	.2372501	12.18267	2.545700	24.57360	.5986634	.0153549
#3	.2378866	12.21193	2.528638	24.47949	.6012671	.0153304

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	2.730885	.2512766	.7589184	13.66786	.6565574	.3093127
Stddev	.135791	.0003638	.0059688	.06052	.0045831	.0008817
%RSD	4.972415	.1447684	.7864908	.4427939	.6980496	.2850382
#1	2.575643	.2512550	.7520264	13.59838	.6548193	.3102082
#2	2.789423	.2516507	.7624104	13.70904	.6617553	.3084455
#3	2.827589	.2509241	.7623184	13.69618	.6530976	.3092844

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-04 Acquired: 1/27/2025 17:12:18 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7S Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0001299	F 312.2732	F 11.27596	-.002844	.0112634	.0250535
Stddev	.0001539	.3386	.01853	.001653	.0001897	.0006125
%RSD	118.5316	.1084339	.1643265	58.12501	1.684113	2.444717
#1	.0000505	312.5714	11.28613	-.004602	.0114257	.0250458
#2	.0000318	311.9051	11.28718	-.001320	.0110549	.0256697
#3	.0003072	312.3432	11.25458	-.002610	.0113096	.0244448

Elem	Sr4077
Units	ppm
Avg	.2850887
Stddev	.0015318
%RSD	.5373211
#1	.2835999
#2	.2866602
#3	.2850059

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7660.760	158822.1	24707.24	5241.464	4201.707
Stddev	12.862	282.7	68.37	20.668	5.656
%RSD	.1678999	.1780176	.2767069	.3943198	.1346080
#1	7670.811	159137.7	24629.83	5265.230	4206.404
#2	7665.204	158591.9	24759.37	5231.465	4203.290
#3	7646.265	158736.7	24732.53	5227.697	4195.429

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-05 Acquired: 1/27/2025 17:16:13 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F8 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0051659	.0080284	.0045420	-.002454	-.001698	52.58885
Stddev	.0013046	.0016762	.0018105	.002368	.001464	.18162
%RSD	25.25360	20.87857	39.86051	96.49439	86.18673	.3453650
#1	.0039481	.0068748	.0024622	-.004235	-.000059	52.79854
#2	.0050070	.0072594	.0057654	-.003359	-.002164	52.48734
#3	.0065427	.0099512	.0053984	.000233	-.002873	52.48068

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0537353	.0024195	.0050992	92.31056	.0301248	.3219934
Stddev	.0006727	.0000520	.0001156	.39285	.0003151	.0010091
%RSD	1.251956	2.148719	2.267699	.4255745	1.045861	.3133772
#1	.0544578	.0023846	.0050009	92.76398	.0297802	.3211286
#2	.0536210	.0023946	.0050700	92.09571	.0303981	.3217497
#3	.0531269	.0024792	.0052266	92.07199	.0301960	.3231020

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1971299	17.96318	5.633731	35.89504	.3134176	-.001314
Stddev	.0009113	.07113	.027801	.17203	.0004718	.000052
%RSD	.4622903	.3959935	.4934697	.4792453	.1505436	3.952799
#1	.1978885	18.04468	5.662826	36.04204	.3133635	-.001274
#2	.1961190	17.93129	5.607437	35.93723	.3129751	-.001373
#3	.1973823	17.91357	5.630929	35.70584	.3139141	-.001295

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	3.769775	.0021921	.7399914	6.727267	.2123960	.3886646
Stddev	.200345	.0007401	.0046028	.067824	.0030088	.0003792
%RSD	5.314518	33.76389	.6220058	1.008200	1.416621	.0975606
#1	4.000039	.0029891	.7394904	6.802008	.2106336	.3890740
#2	3.673939	.0015264	.7356597	6.669637	.2106842	.3885943
#3	3.635348	.0020608	.7448242	6.710155	.2158702	.3883255

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-05 Acquired: 1/27/2025 17:16:13 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F8 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000400	F 328.4756	F 20.15239	-.001986	.0111241	.0523991
Stddev	.000352	.5327	.07429	.000887	.0001244	.0002973
%RSD	88.08178	.1621650	.3686608	44.67055	1.118182	.5673217
#1	-.000786	329.0106	20.23551	-.002482	.0110647	.0524136
#2	-.000319	328.4709	20.09246	-.000962	.0110407	.0520948
#3	-.000095	327.9453	20.12921	-.002514	.0112671	.0526888

Elem	Sr4077
Units	ppm
Avg	.5205397
Stddev	.0029637
%RSD	.5693589
#1	.5236052
#2	.5176895
#3	.5203245

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	6111.966	131382.3	20364.95	4240.821	4045.383
Stddev	11.896	153.1	33.86	14.595	7.324
%RSD	.1946405	.1165641	.1662813	.3441558	.1810538
#1	6099.767	131207.2	20372.75	4254.454	4042.335
#2	6123.535	131491.5	20327.87	4242.585	4053.739
#3	6112.597	131448.2	20394.24	4225.425	4040.074

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-06 Acquired: 1/27/2025 17:20:10 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E3 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0649583**	**.0037192**	**.5889364**	**-.001837**	**.0015253**	**28.92558**
Stddev	.0041580	.0035359	.0008769	.000489	.0013519	.08115
%RSD	6.401062	95.07320	.1489025	26.64546	88.63401	.2805576
#1	.0617158	-.000274	.5895694	-.001682	.0003683	28.83332
#2	.0696461	.004978	.5879355	-.002385	.0011963	28.98594
#3	.0635128	.006453	.5893044	-.001444	.0030114	28.95748

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0733786**	**.0086223**	**.0206620**	**120.2955**	**.0338231**	**.3450497**
Stddev	.0008762	.0000251	.0001289	.2437	.0003528	.0006772
%RSD	1.194017	.2914176	.6238548	.2025673	1.043035	.1962723
#1	.0724304	.0085951	.0206044	120.1896	.0342282	.3448035
#2	.0735473	.0086272	.0205720	120.1228	.0335837	.3445300
#3	.0741582	.0086446	.0208097	120.5742	.0336574	.3458156

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.320301**	**33.57976**	**17.26317**	**45.75559**	**.3821590**	**.0013749**
Stddev	.005230	.11140	.03529	.12171	.0002421	.0001981
%RSD	.3961051	.3317569	.2044146	.2660018	.0633465	14.40791
#1	1.325939	33.45508	17.24751	45.64541	.3820190	.0013524
#2	1.315608	33.61466	17.23842	45.73512	.3820194	.0015833
#3	1.319357	33.66953	17.30358	45.88624	.3824385	.0011891

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**9.304636**	**.0431899**	**3.381917**	**6.733963**	**.3025923**	**1.153607**
Stddev	.315688	.0007789	.020876	.037241	.0009047	.003698
%RSD	3.392799	1.803476	.6172933	.5530284	.2989687	.3205809
#1	9.013940	.0424227	3.392210	6.695508	.3035740	1.157812
#2	9.640459	.0431670	3.357892	6.769857	.3024105	1.150862
#3	9.259510	.0439800	3.395647	6.736526	.3017923	1.152147

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-06 Acquired: 1/27/2025 17:20:10 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E3 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.001662**	F **337.0246**	F **10.12680**	**-.002645**	**.0048544**	**.0177647**
Stddev	.000226	.4403	.01746	.000511	.0007995	.0005693
%RSD	13.60881	.1306328	.1724001	19.32172	16.46933	3.204734
#1	-.001831	336.5190	10.14692	-.003164	.0040605	.0175797
#2	-.001750	337.2317	10.11779	-.002143	.0056593	.0184035
#3	-.001405	337.3232	10.11569	-.002627	.0048434	.0173108

Elem	Sr4077
Units	ppm
Avg	**.8780764**
Stddev	.0050601
%RSD	.5762692
#1	.8836022
#2	.8769576
#3	.8736693

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**4059.311**	**90445.88**	**13685.08**	**2868.480**	**4067.723**
Stddev	8.012	204.94	36.07	14.512	7.561
%RSD	.1973798	.2265901	.2635866	.5059092	.1858812
#1	4067.318	90564.17	13647.15	2856.353	4076.009
#2	4059.323	90564.24	13718.96	2884.558	4065.962
#3	4051.293	90209.23	13689.13	2864.528	4061.198

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-07 Acquired: 1/27/2025 17:24:13 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E4 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0237312**	**.0005166**	**.0138606**	**.0130153**	**.0059713**	**71.97623**
Stddev	.0014283	.0032539	.0010037	.0015973	.0006709	.38087
%RSD	6.018807	629.8127	7.241633	12.27270	11.23594	.5291641
#1	.0227159	.0033416	.0133310	.0137158	.0053303	71.84652
#2	.0231132	.0012495	.0150182	.0111874	.0059149	71.67716
#3	.0253645	-.003041	.0132325	.0141428	.0066686	72.40502

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0846911**	**.0065217**	**.0051412**	**85.73584**	**.0890874**	**.2521792**
Stddev	.0004743	.0000868	.0000939	.30832	.0002761	.0010670
%RSD	.5600794	1.330728	1.825441	.3596155	.3098866	.4231133
#1	.0841631	.0065020	.0051593	85.58854	.0892749	.2532244
#2	.0850812	.0066166	.0052247	85.52880	.0892169	.2510916
#3	.0848291	.0064464	.0050396	86.09018	.0887704	.2522217

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.3590273**	**110.5699**	**8.184525**	**71.45542**	**.3879786**	**-.000062**
Stddev	.0015901	.4301	.035627	.23757	.0013897	.000204
%RSD	.4428811	.3889669	.4353018	.3324741	.3581946	327.4755
#1	.3586456	110.4290	8.152942	71.42745	.3895735	-.000100
#2	.3576628	110.2279	8.177488	71.23307	.3870271	.000158
#3	.3607734	111.0528	8.223147	71.70574	.3873353	-.000246

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**15.18044**	**.0943229**	**1.985829**	**2.998007**	**.2204876**	**1.686733**
Stddev	.14762	.0010972	.010041	.036916	.0033437	.004697
%RSD	.9724260	1.163209	.5056114	1.231342	1.516509	.2784399
#1	15.09212	.0939365	1.974474	3.022204	.2213310	1.690078
#2	15.35086	.0955610	1.993531	2.955517	.2168029	1.688757
#3	15.09834	.0934711	1.989483	3.016299	.2233288	1.681363

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-07 Acquired: 1/27/2025 17:24:13 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E4 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.001592	F 613.0205	F 26.69356	-.001363	.0186545	.0596581
Stddev	.000137	1.4544	.03138	.000996	.0007644	.0013183
%RSD	8.579628	.2372549	.1175579	73.01530	4.097599	2.209757
#1	-.001691	613.9802	26.70277	-.000697	.0190570	.0581394
#2	-.001437	611.3471	26.71930	-.002508	.0177730	.0603281
#3	-.001650	613.7341	26.65860	-.000886	.0191336	.0605068

Elem	Sr4077
Units	ppm
Avg	.6343842
Stddev	.0039636
%RSD	.6247918
#1	.6318053
#2	.6323993
#3	.6389481

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4675.119	96939.80	15473.21	3178.663	4130.867
Stddev	9.613	41.16	84.41	13.120	12.544
%RSD	.2056272	.0424578	.5455400	.4127569	.3036681
#1	4666.493	96952.24	15434.40	3185.366	4117.446
#2	4685.483	96973.30	15415.19	3163.545	4142.296
#3	4673.380	96893.85	15570.05	3187.077	4132.858

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-08 Acquired: 1/27/2025 17:28:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E5 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0101751	.0028440	.0067236	-.001021	.0002590	36.48779
Stddev	.0014887	.0021977	.0013575	.001316	.0009535	.07613
%RSD	14.63032	77.27734	20.18958	128.9135	368.0623	.2086438
#1	.0086824	.0038045	.0056805	-.002502	.0008233	36.40369
#2	.0116597	.0003295	.0062319	-.000575	.0007956	36.50770
#3	.0101833	.0043979	.0082583	.000015	-.000842	36.55199

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1109657	.0025176	.0005600	143.2165	.0362005	.0253966
Stddev	.0006193	.0001029	.0000884	.1895	.0003035	.0003764
%RSD	.5580869	4.087787	15.79378	.1322936	.8382805	1.482066
#1	.1111282	.0025534	.0006621	143.3746	.0365198	.0250546
#2	.1102814	.0025979	.0005126	143.0065	.0361657	.0253354
#3	.1114876	.0024016	.0005054	143.2685	.0359159	.0257998

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1640946	28.21181	2.597806	109.7811	.2058504	-.000421
Stddev	.0011429	.02164	.003564	.1136	.0004195	.000296
%RSD	.6964962	.0766976	.1372084	.1035203	.2037960	70.34235
#1	.1641050	28.19109	2.601564	109.9003	.2053890	-.000347
#2	.1629465	28.21007	2.594473	109.6739	.2059534	-.000747
#3	.1652322	28.23426	2.597382	109.7690	.2062089	-.000169

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	17.76384	.0747643	1.588113	1.619744	.0625102	1.319696
Stddev	.03896	.0004597	.005582	.042123	.0004703	.002255
%RSD	.2193235	.6149100	.3514828	2.600603	.7524215	.1708746
#1	17.77759	.0743936	1.582262	1.649378	.0627423	1.318265
#2	17.79406	.0752787	1.588697	1.638329	.0628193	1.322295
#3	17.71987	.0746206	1.593380	1.571525	.0619689	1.318527

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-08 Acquired: 1/27/2025 17:28:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E5 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000871	F 348.3328	F 20.59377	-.004148	.0082838	.0549839
Stddev	.000059	.5863	.07179	.000238	.0008198	.0004466
%RSD	6.795040	.1683040	.3486125	5.726807	9.896904	.8122537
#1	-.000893	347.8682	20.66992	-.003886	.0091737	.0548696
#2	-.000915	348.1387	20.58408	-.004350	.0075592	.0546055
#3	-.000804	348.9915	20.52732	-.004208	.0081185	.0554765

Elem	Sr4077
Units	ppm
Avg	.9591637
Stddev	.0020144
%RSD	.2100160
#1	.9601093
#2	.9568504
#3	.9605313

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3540.759	76154.68	11466.55	2500.913	4060.067
Stddev	11.904	46.56	35.52	3.711	14.490
%RSD	.3362060	.0611373	.3097439	.1483697	.3569022
#1	3549.796	76168.29	11453.29	2504.523	4071.968
#2	3545.209	76102.84	11439.57	2501.106	4064.302
#3	3527.270	76192.93	11506.79	2497.110	4043.931

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-09 Acquired: 1/27/2025 17:32:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E6 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.2679724	.0024836	.1150756	.0032574	.0011077	9.270709
Stddev	.0004943	.0004461	.0004512	.0014604	.0008812	.040387
%RSD	.1844641	17.96302	.3921007	44.83127	79.55164	.4356367
#1	.2674639	.0019743	.1147790	.0016133	.0014358	9.238525
#2	.2680020	.0028055	.1155949	.0044040	.0017779	9.257575
#3	.2684512	.0026708	.1148530	.0037550	.0001095	9.316028

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0820676	.0009172	.0068778	56.66956	.0354074	.0281982
Stddev	.0009516	.0000043	.0000258	.18427	.0000934	.0001640
%RSD	1.159527	.4723792	.3749884	.3251733	.2637751	.5816993
#1	.0810194	.0009179	.0068500	56.49216	.0353061	.0283758
#2	.0823061	.0009125	.0068824	56.65650	.0354261	.0280524
#3	.0828772	.0009211	.0069009	56.86001	.0354901	.0281663

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.8418186	21.56944	.3878933	7.256366	.2139934	-.000621
Stddev	.0031331	.10124	.0010691	.030561	.0010451	.000180
%RSD	.3721804	.4693794	.2756103	.4211607	.4883877	29.04399
#1	.8404958	21.46848	.3870426	7.240414	.2130425	-.000425
#2	.8453961	21.56890	.3875440	7.237081	.2138253	-.000781
#3	.8395639	21.67096	.3890934	7.291602	.2151123	-.000658

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	6.662496	.0322170	.7986590	3.277232	F 23.30781	.6869935
Stddev	.295624	.0005633	.0026440	.041991	.06591	.0033704
%RSD	4.437137	1.748560	.3310604	1.281301	.2827694	.4906036
#1	6.895980	.0328653	.7957788	3.271273	23.23253	.6908549
#2	6.761409	.0318465	.7992219	3.238539	23.33581	.6854839
#3	6.330098	.0319392	.8009763	3.321885	23.35510	.6846419

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-09 Acquired: 1/27/2025 17:32:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E6 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0013176	F 345.7872	4.860927	-.002182	.0060003	.0126905
Stddev	.0001393	1.0829	.012771	.000989	.0005115	.0006194
%RSD	10.57383	.3131714	.2627315	45.30860	8.525159	4.881034
#1	.0012651	344.5600	4.870521	-.003230	.0056946	.0131280
#2	.0014755	346.1930	4.865829	-.002053	.0065908	.0129617
#3	.0012121	346.6086	4.846431	-.001265	.0057154	.0119817

Elem	Sr4077
Units	ppm
Avg	.5899891
Stddev	.0024087
%RSD	.4082630
#1	.5872327
#2	.5910457
#3	.5916890

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3936.968	84671.35	12817.56	2811.068	4396.985
Stddev	10.473	113.96	71.15	10.773	11.298
%RSD	.2660212	.1345911	.5550893	.3832403	.2569450
#1	3948.038	84595.25	12738.03	2814.575	4409.520
#2	3935.650	84802.37	12839.46	2819.651	4393.849
#3	3927.216	84616.42	12875.17	2798.979	4387.587

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-10 Acquired: 1/27/2025 17:36:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E7 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.036306**	**.0001567**	**.1072746**	**.0026781**	**.0037340**	**24.69129**
Stddev	.005469	.0010509	.0015764	.0018464	.0004640	.03177
%RSD	.5276916	670.7230	1.469504	68.94653	12.42784	.1286741
#1	1.031313	-.000619	.1088880	.0030831	.0032773	24.68658
#2	1.035456	.001353	.1071978	.0006628	.0037196	24.66213
#3	1.042150	-.000264	.1057380	.0042884	.0042050	24.72515

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0635124**	**.0082794**	**.0126491**	**132.2111**	**.0833354**	**.0866976**
Stddev	.0003074	.0001177	.0001298	.3282	.0001827	.0003485
%RSD	.4840189	1.422029	1.025902	.2482589	.2192709	.4019505
#1	.0632270	.0082721	.0127989	132.2909	.0831531	.0869092
#2	.0638379	.0084006	.0125770	132.4921	.0835186	.0862954
#3	.0634723	.0081654	.0125712	131.8504	.0833346	.0868883

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0776568**	**54.51224**	**1.104892**	**21.19798**	**1.460985**	**-.002625**
Stddev	.0022067	.05869	.005648	.02836	.002534	.000172
%RSD	2.841583	.1076691	.5111674	.1337996	.1734315	6.559085
#1	.0790841	54.47650	1.109314	21.17630	1.462010	-.002823
#2	.0751152	54.48025	1.106832	21.23008	1.458099	-.002543
#3	.0787712	54.57998	1.098530	21.18757	1.462846	-.002509

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.938383**	**.0599271**	**1.579983**	**3.572895**	F **63.73352**	**.7046771**
Stddev	.047178	.0010489	.012695	.015517	.01933	.0014343
%RSD	.7944585	1.750279	.8034721	.4342839	.0303254	.2035372
#1	5.912839	.0587242	1.573885	3.581262	63.71717	.7059346
#2	5.909486	.0604065	1.594576	3.554990	63.72853	.7049818
#3	5.992825	.0606507	1.571487	3.582432	63.75485	.7031150

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-10 Acquired: 1/27/2025 17:36:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E7 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000255	F 342.9296	F 11.67344	-.002807	.0003494	.0467821
Stddev	.000325	.6410	.08983	.000128	.0003567	.0012359
%RSD	127.6202	.1869329	.7695454	4.567565	102.0949	2.641785
#1	.000011	342.4598	11.73254	-.002953	.0007581	.0454386
#2	-.000618	342.6690	11.71770	-.002709	.0001011	.0478705
#3	-.000159	343.6599	11.57006	-.002761	.0001888	.0470371

Elem	Sr4077
Units	ppm
Avg	.8514446
Stddev	.0117614
%RSD	1.381351
#1	.8546171
#2	.8612944
#3	.8384223

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4896.774	102650.4	15394.56	3337.967	4200.743
Stddev	7.107	297.0	71.72	15.555	5.865
%RSD	.1451361	.2893298	.4658468	.4660085	.1396211
#1	4903.529	102858.6	15395.36	3355.548	4196.619
#2	4897.432	102310.3	15322.45	3325.992	4207.458
#3	4889.361	102782.4	15465.87	3332.361	4198.153

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-11 Acquired: 1/27/2025 17:40:14 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E8 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0114080**	**.0041858**	**.0657403**	**.0118900**	**.0039465**	**44.93761**
Stddev	.0011816	.0013853	.0012297	.0015387	.0003305	.17998
%RSD	10.35769	33.09621	1.870580	12.94122	8.375507	.4005100
#1	.0101156	.0027532	.0661082	.0108530	.0039202	44.73146
#2	.0124329	.0042857	.0643686	.0136580	.0042893	45.01789
#3	.0116756	.0055185	.0667441	.0111591	.0036299	45.06348

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0737391**	**.0059673**	**.0250555**	**77.81420**	**.1606986**	**.0379511**
Stddev	.0005584	.0001140	.0000930	.17215	.0006200	.0003401
%RSD	.7572618	1.911146	.3712243	.2212346	.3858170	.8960872
#1	.0742371	.0060092	.0249600	77.77104	.1603897	.0381167
#2	.0738446	.0060543	.0250607	78.00383	.1614124	.0375600
#3	.0731354	.0058382	.0251458	77.66774	.1602937	.0381767

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0524678**	**84.48269**	**1.085738**	**23.18435**	**.2487825**	**-.001511**
Stddev	.0013903	.23369	.001339	.07782	.0006324	.000348
%RSD	2.649753	.2766187	.1233365	.3356456	.2541869	23.05572
#1	.0519732	84.27322	1.087221	23.18863	.2495031	-.001395
#2	.0513924	84.73475	1.085378	23.25994	.2483202	-.001235
#3	.0540377	84.44010	1.084616	23.10448	.2485241	-.001902

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.153134**	**.1245943**	**2.064897**	**11.07030**	F **30.36292**	**.8363844**
Stddev	.250344	.0002896	.006383	.07064	.04597	.0014060
%RSD	4.858083	.2324383	.3091387	.6381373	.1514152	.1681069
#1	5.037545	.1248920	2.059555	10.99063	30.38810	.8372633
#2	5.440387	.1243135	2.063170	11.12531	30.30986	.8371272
#3	4.981470	.1245775	2.071966	11.09497	30.39081	.8347628

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-11 Acquired: 1/27/2025 17:40:14 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E8 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0012894	F 330.4668	F 19.77319	-.002149	.0096765	.0473262
Stddev	.0003265	.5046	.09423	.001547	.0006276	.0006338
%RSD	25.32209	.1527022	.4765521	72.02242	6.485528	1.339157
#1	.0010486	330.2642	19.88183	-.001770	.0103582	.0480304
#2	.0016610	330.0949	19.72408	-.000825	.0091228	.0468017
#3	.0011585	331.0412	19.71365	-.003850	.0095485	.0471464

Elem	Sr4077
Units	ppm
Avg	.2913034
Stddev	.0011583
%RSD	.3976208
#1	.2905534
#2	.2907195
#3	.2926375

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4246.851	88730.18	13844.74	2895.281	4274.823
Stddev	5.189	320.41	64.80	7.522	3.643
%RSD	.1221848	.3611038	.4680226	.2598175	.0852231
#1	4245.650	88942.67	13804.97	2903.542	4274.952
#2	4252.535	88361.64	13809.73	2893.477	4278.399
#3	4242.367	88886.22	13919.51	2888.825	4271.116

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-12 Acquired: 1/27/2025 17:44:11 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D1 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0069505**	**.0028762**	**.0101157**	**-.000179**	**-.002359**	**78.54679**
Stddev	.0023363	.0025393	.0028328	.001672	.000777	.33624
%RSD	33.61414	88.28476	28.00373	934.8931	32.93581	.4280706
#1	.0092189	.0036668	.0097674	-.000311	-.003169	78.86909
#2	.0070807	.0049262	.0131066	.001555	-.001620	78.19816
#3	.0045517	.0000357	.0074732	-.001780	-.002289	78.57312

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0854820**	**.0040633**	**.0091428**	**167.7603**	**.0802023**	**.8256059**
Stddev	.0004683	.0000505	.0001293	.3204	.0003465	.0018114
%RSD	.5478242	1.243643	1.414628	.1909669	.4320066	.2194060
#1	.0859985	.0041170	.0092379	168.1260	.0798703	.8236344
#2	.0853622	.0040560	.0089955	167.5290	.0805616	.8259866
#3	.0850852	.0040168	.0091949	167.6260	.0801748	.8271967

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2695093**	**14.66318**	**13.55782**	**73.13506**	**.5911144**	**.0018053**
Stddev	.0008104	.00946	.02904	.13296	.0017342	.0002150
%RSD	.3006982	.0645406	.2142098	.1818059	.2933695	11.90760
#1	.2690318	14.66869	13.59081	73.26860	.5899096	.0015681
#2	.2690511	14.65225	13.54653	73.13389	.5903317	.0018605
#3	.2704450	14.66859	13.53612	73.00267	.5931019	.0019873

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**7.393821**	**.0098201**	**1.251488**	**5.304848**	**1.501797**	**.6307729**
Stddev	.210270	.0015896	.006359	.014143	.008339	.0019675
%RSD	2.843861	16.18711	.5080783	.2666036	.5552885	.3119173
#1	7.151050	.0105822	1.258610	5.300388	1.497777	.6285011
#2	7.512027	.0108851	1.249472	5.320683	1.496229	.6319229
#3	7.518386	.0079929	1.246381	5.293472	1.511385	.6318948

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-12 Acquired: 1/27/2025 17:44:11 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D1 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000385**	F **363.6503**	F **34.89908**	**-.002668**	**-.001743**	**.1728548**
Stddev	.000111	.7229	.06300	.000657	.000620	.0020598
%RSD	28.73565	.1987857	.1805341	24.61445	35.59520	1.191610
#1	-.000504	363.1550	34.89786	-.003049	-.002458	.1751146
#2	-.000367	363.3160	34.96269	-.001910	-.001428	.1710826
#3	-.000285	364.4798	34.83670	-.003046	-.001343	.1723672

Elem	Sr4077
Units	ppm
Avg	**1.132124**
Stddev	.003733
%RSD	.3296977
#1	1.131723
#2	1.136040
#3	1.128607

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**4216.196**	**90443.20**	**14372.87**	**2923.512**	**3992.914**
Stddev	8.777	136.88	81.74	12.048	13.397
%RSD	.2081644	.1513483	.5687063	.4121171	.3355312
#1	4224.629	90563.50	14444.30	2910.211	4004.355
#2	4216.846	90294.26	14283.73	2933.695	3996.211
#3	4207.112	90471.85	14390.58	2926.630	3978.176

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCV022 Acquired: 1/27/2025 17:57:23 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV022 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**4.927239**	**4.585303**	**24.24443**	**4.799041**	**4.838258**	**396.1362**
Stddev	.008675	.058521	.02554	.018675	.005590	6.3614
%RSD	.1760625	1.276272	.1053328	.3891468	.1155438	1.605874
#1	4.937225	4.652877	24.27386	4.810396	4.840449	403.4034
#2	4.922930	4.551443	24.22811	4.809240	4.831904	391.5760
#3	4.921563	4.551588	24.23133	4.777487	4.842420	393.4291

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**10.10107**	**.4860494**	**2.426584**	**401.8904**	**15.21873**	**2.431059**
Stddev	.04306	.0035858	.006067	2.3190	.12688	.002082
%RSD	.4262987	.7377333	.2500368	.5770334	.8336975	.0856560
#1	10.12369	.4867430	2.433337	403.9036	15.36089	2.432237
#2	10.05141	.4892376	2.424820	399.3547	15.17832	2.432285
#3	10.12810	.4821675	2.421593	402.4128	15.11698	2.428655

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**14.96209**	**402.3464**	**14.98204**	**393.8580**	**2.423222**	**1.267053**
Stddev	.10530	2.4413	.08366	2.4098	.001274	.010274
%RSD	.7037919	.6067661	.5583687	.6118468	.0525757	.8108917
#1	14.88812	405.0737	15.07528	396.6221	2.423673	1.278586
#2	15.08265	401.6003	14.95731	392.7534	2.424209	1.263698
#3	14.91549	400.3652	14.91355	392.1984	2.421784	1.258875

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**394.5294**	**2.436838**	**15.05304**	**154.8304**	**5.032598**	F **5.906798**
Stddev	3.0251	.012407	.08001	.7880	.011595	.032788
%RSD	.7667556	.5091602	.5315004	.5089571	.2303980	.5550872
#1	392.5425	2.431298	15.14514	155.7238	5.044957	5.916028
#2	398.0109	2.451050	15.01330	154.5331	5.021959	5.933981
#3	393.0350	2.428166	15.00069	154.2343	5.030880	5.870384

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCV022 Acquired: 1/27/2025 17:57:23 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV022 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**4.769774**	**4.945264**	F **3.116080**	**4.880760**	**4.946312**	**5.161619**
Stddev	.009066	.013581	.015077	.008337	.038046	.025375
%RSD	.1900710	.2746276	.4838585	.1708170	.7691809	.4916084
#1	4.780178	4.960732	3.116106	4.889115	4.931084	5.184791
#2	4.765574	4.939770	3.131144	4.880724	4.989613	5.165563
#3	4.763569	4.935291	3.100989	4.872440	4.918238	5.134503

Elem	Sr4077
Units	ppm
Avg	**4.824743**
Stddev	.015999
%RSD	.3316128
#1	4.807500
#2	4.827619
#3	4.839109

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2936.858**	**65065.92**	**10709.19**	**2121.625**	**3366.945**
Stddev	3.204	437.03	56.54	14.513	2.762
%RSD	.1090964	.6716681	.5279990	.6840590	.0820212
#1	2935.055	64562.55	10722.89	2104.895	3365.579
#2	2940.558	65286.57	10647.05	2130.834	3370.123
#3	2934.962	65348.63	10757.63	2129.145	3365.132

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCB022 Acquired: 1/27/2025 18:01:41 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB022 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0005722	.0003532	.0008554	.0008276	.0001706	.0034339	-.002395
Stddev	.0009579	.0003024	.0011805	.0016708	.0017160	.0081677	.000508
%RSD	167.3887	85.60831	138.0004	201.8857	1005.937	237.8572	21.19724
#1	.0016658	.0001190	.0017567	.0022160	-.000444	-.005084	-.002905
#2	.0001688	.0006945	-.000481	-.001027	.002109	.011200	-.002390
#3	-.000118	.0002460	.001290	.001294	-.001153	.004186	-.001889

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000083	.0000509	.0072949	.0004607	-.000058	-.000698	.0054757
Stddev	.000025	.0000079	.0060509	.0002145	.000111	.000493	.0013887
%RSD	30.38888	15.54500	82.94712	46.55501	190.6103	70.56862	25.36041
#1	-.000097	.0000543	.0089015	.0003098	.000066	-.001209	.0045854
#2	-.000097	.0000565	.0006028	.0007062	-.000093	-.000660	.0070758
#3	-.000054	.0000419	.0123805	.0003661	-.000148	-.000226	.0047659

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0001599	.0012677	-.000154	-.000681	-.231025	-.001817	.0000305
Stddev	.0001074	.0110158	.000374	.000325	.268275	.000362	.0018059
%RSD	67.17711	868.9694	242.4245	47.71457	116.1240	19.92451	5921.057
#1	.0000516	-.002192	-.000010	-.000347	.078681	-.001960	-.001884
#2	.0002663	.013598	.000126	-.000700	-.380092	-.001405	.001704
#3	.0001616	-.007603	-.000579	-.000996	-.391663	-.002086	.000272

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0300465	.0002984	.0063706	.0004121	.0121522	-.001977	.0006184
Stddev	.0102863	.0011686	.0006315	.0004525	.0023244	.000597	.0005800
%RSD	34.23475	391.6700	9.913266	109.8017	19.12692	30.18437	93.78338
#1	.0198449	-.000976	.0069104	.0002747	.0143160	-.001814	.0000117
#2	.0298790	.001320	.0065252	.0009174	.0124455	-.001479	.0011674
#3	.0404156	.000551	.0056761	.0000443	.0096952	-.002639	.0006763

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCB022 Acquired: 1/27/2025 18:01:41 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB022 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0000205	-.000108	.0000588
Stddev	.0007217	.000976	.0000467
%RSD	3516.252	901.2215	79.37170
#1	-.000812	.000252	.0000281
#2	.000407	.000636	.0000358
#3	.000467	-.001213	.0001126

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3720.159	77571.77	11431.70	2565.133	4713.809
Stddev	10.188	155.77	9.00	19.343	9.803
%RSD	.2738598	.2008111	.0787356	.7540863	.2079661
#1	3718.972	77644.47	11427.10	2576.528	4710.141
#2	3730.888	77392.94	11442.07	2542.799	4724.917
#3	3710.616	77677.91	11425.92	2576.072	4706.368

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-13 Acquired: 1/27/2025 18:05:49 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D2 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0218079**	**.0022105**	**.2063470**	**.0044802**	**-.000059**	**15.39725**
Stddev	.0005952	.0012405	.0007203	.0020484	.001014	.08517
%RSD	2.729332	56.11827	.3490903	45.72125	1719.969	.5531269
#1	.0222978	.0007990	.2071537	.0050430	-.000748	15.30741
#2	.0211454	.0031275	.2061193	.0022092	.001105	15.47680
#3	.0219803	.0027050	.2057681	.0061884	-.000534	15.40755

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0822107**	**.0030173**	**.0110307**	**60.31322**	**.0083907**	**.0609977**
Stddev	.0009872	.0000190	.0000480	.24666	.0003166	.0003213
%RSD	1.200846	.6286217	.4354331	.4089598	3.773654	.5267382
#1	.0815090	.0030386	.0110519	60.15610	.0087467	.0607955
#2	.0833395	.0030022	.0109757	60.59751	.0081408	.0613682
#3	.0817835	.0030112	.0110644	60.18605	.0082845	.0608294

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.7297264**	**22.35151**	**.2731521**	**15.07962**	**.1241558**	**-.001011**
Stddev	.0048707	.08371	.0006624	.06755	.0003552	.000137
%RSD	.6674743	.3745048	.2425053	.4479790	.2860819	13.54308
#1	.7353114	22.29087	.2731699	15.09299	.1240368	-.001165
#2	.7275080	22.44701	.2738054	15.13950	.1245552	-.000901
#3	.7263598	22.31664	.2724810	15.00639	.1238754	-.000969

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.282435**	**.0102906**	**1.231145**	**4.781665**	F **17.40595**	**.6395184**
Stddev	.145462	.0005004	.008451	.061825	.04357	.0048378
%RSD	2.753701	4.862672	.6864313	1.292965	.2503069	.7564789
#1	5.449891	.0108431	1.226733	4.713955	17.42470	.6438897
#2	5.210027	.0098679	1.240889	4.795928	17.43701	.6343206
#3	5.187387	.0101607	1.225814	4.835112	17.35615	.6403448

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-13 Acquired: 1/27/2025 18:05:49 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D2 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0001375	F 318.8297	8.299502	-.002434	.0037568	.0295021
Stddev	.0002657	.1299	.046693	.000766	.0001352	.0005112
%RSD	193.2357	.0407290	.5625947	31.47040	3.597437	1.732818
#1	.0000324	318.9705	8.350439	-.002661	.0038545	.0300924
#2	-.000060	318.8039	8.258727	-.001580	.0036025	.0292016
#3	.000440	318.7146	8.289340	-.003062	.0038133	.0292124

Elem	Sr4077
Units	ppm
Avg	.3634763
Stddev	.0020926
%RSD	.5757140
#1	.3612795
#2	.3654462
#3	.3637031

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3971.866	83903.88	12920.73	2738.668	4489.841
Stddev	16.338	123.71	79.95	8.242	14.491
%RSD	.4113414	.1474469	.6187654	.3009413	.3227526
#1	3990.578	84040.48	12854.31	2743.643	4506.574
#2	3964.588	83799.37	13009.46	2743.206	4481.500
#3	3960.431	83871.79	12898.40	2729.154	4481.449

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-14 Acquired: 1/27/2025 18:09:47 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D4 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0129883**	**.0040969**	**.0119754**	**-.001047**	**-.000150**	**41.02401**
Stddev	.0014683	.0010991	.0013694	.001623	.001819	.08291
%RSD	11.30500	26.82630	11.43490	155.0267	1210.711	.2021105
#1	.0146772	.0050761	.0116408	.000637	.000360	41.02588
#2	.0122723	.0029082	.0108043	-.002602	.001359	41.10597
#3	.0120153	.0043066	.0134810	-.001176	-.002170	40.94018

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0953616**	**.0053150**	**.0031493**	**118.0642**	**.0528001**	**.2276926**
Stddev	.0003352	.0000925	.0000320	.1888	.0001144	.0002200
%RSD	.3515188	1.740846	1.017189	.1598787	.2166497	.0966193
#1	.0952891	.0054211	.0031618	118.2655	.0526809	.2276805
#2	.0957271	.0052729	.0031732	118.0360	.0528105	.2274788
#3	.0950685	.0052511	.0031129	117.8912	.0529090	.2279183

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2145257**	**32.64713**	**8.349551**	**94.67799**	**.4627882**	**.0006373**
Stddev	.0016995	.06978	.007913	.14591	.0007219	.0002503
%RSD	.7922304	.2137427	.0947714	.1541097	.1559891	39.28200
#1	.2164757	32.70079	8.341340	94.84076	.4620145	.0004194
#2	.2133594	32.67235	8.357128	94.55896	.4629063	.0005817
#3	.2137422	32.56824	8.350185	94.63424	.4634437	.0009107

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.623759**	**.0198153**	**1.191274**	**2.111376**	**.6215360**	**.7123496**
Stddev	.176401	.0013250	.006609	.050814	.0050119	.0049004
%RSD	3.136703	6.686650	.5548067	2.406657	.8063722	.6879235
#1	5.490837	.0211755	1.184830	2.163096	.6273233	.7149117
#2	5.823884	.0197421	1.190956	2.061520	.6186549	.7066992
#3	5.556556	.0185285	1.198037	2.109511	.6186299	.7154378

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-14 Acquired: 1/27/2025 18:09:47 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D4 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000398**	F **344.2602**	F **18.20372**	**-.002662**	**.0033545**	**.0844205**
Stddev	.000295	.5252	.06125	.000396	.0004477	.0004644
%RSD	74.26629	.1525629	.3364881	14.89639	13.34645	.5501412
#1	-.000060	344.0510	18.24554	-.002689	.0036995	.0845280
#2	-.000528	344.8578	18.13341	-.003044	.0035155	.0848217
#3	-.000605	343.8719	18.23221	-.002252	.0028486	.0839117

Elem	Sr4077
Units	ppm
Avg	**.7002508**
Stddev	.0018009
%RSD	.2571721
#1	.6988912
#2	.7022932
#3	.6995680

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3943.453**	**85672.91**	**13458.06**	**2757.149**	**4066.652**
Stddev	18.642	207.71	79.16	5.675	10.890
%RSD	.4727292	.2424465	.5882231	.2058186	.2677840
#1	3964.140	85494.91	13404.40	2763.699	4079.225
#2	3938.261	85901.13	13548.98	2753.710	4060.482
#3	3927.957	85622.71	13420.79	2754.038	4060.248

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-15 Acquired: 1/27/2025 18:13:46 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C3 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0079218**	**.0034909**	**.0117135**	**-.000286**	**-.000526**	**79.09333**
Stddev	.0014132	.0014719	.0023882	.003189	.001316	.65830
%RSD	17.83883	42.16485	20.38853	1116.349	249.9452	.8323089
#1	.0079339	.0046018	.0141358	.003392	.000207	79.74467
#2	.0093288	.0040494	.0093609	-.002286	-.002046	78.42828
#3	.0065026	.0018214	.0116439	-.001963	.000259	79.10702

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1020343**	**.0025927**	**.0066270**	**130.2663**	**.0769533**	**.5152044**
Stddev	.0001165	.0000317	.0000967	.7015	.0002350	.0016079
%RSD	.1141989	1.222250	1.459138	.5385281	.3053467	.3120865
#1	.1021675	.0025607	.0065260	130.9807	.0769390	.5141718
#2	.1019510	.0026241	.0066362	129.5784	.0771951	.5143844
#3	.1019844	.0025932	.0067187	130.2397	.0767258	.5170569

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2482853**	**29.05583**	**9.671455**	**65.73241**	**.4336911**	**.0023038**
Stddev	.0015344	.18134	.061859	.40997	.0011631	.0004320
%RSD	.6179975	.6241221	.6396057	.6236982	.2681981	18.75061
#1	.2470725	29.23514	9.740971	66.15338	.4328285	.0021029
#2	.2500103	28.87252	9.622478	65.33440	.4332308	.0020089
#3	.2477732	29.05983	9.650915	65.70945	.4350139	.0027996

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**6.884595**	**.0110342**	**1.276829**	**4.536592**	**1.646714**	**.6798226**
Stddev	.259331	.0002605	.005937	.030680	.008061	.0043858
%RSD	3.766826	2.361216	.4649772	.6762829	.4895303	.6451442
#1	6.994087	.0108104	1.283371	4.544236	1.642873	.6755420
#2	6.588475	.0113202	1.271782	4.502813	1.641291	.6843066
#3	7.071222	.0109721	1.275336	4.562728	1.655977	.6796193

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-15 Acquired: 1/27/2025 18:13:46 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C3 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000519	F 354.8120	F 31.20367	-.002969	.0005461	.1769289
Stddev	.000174	1.4359	.07223	.000404	.0003610	.0012049
%RSD	33.50507	.4046831	.2314682	13.60894	66.10493	.6810236
#1	-.000555	353.3993	31.18351	-.003323	.0004891	.1783069
#2	-.000329	354.7666	31.28384	-.002529	.0002170	.1760734
#3	-.000671	356.2700	31.14368	-.003056	.0009322	.1764065

Elem	Sr4077
Units	ppm
Avg	.9033037
Stddev	.0091838
%RSD	1.016688
#1	.9133485
#2	.8953372
#3	.9012255

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4016.608	85570.96	13513.20	2804.364	4072.735
Stddev	11.807	91.40	108.37	5.863	10.756
%RSD	.2939504	.1068073	.8019902	.2090553	.2640932
#1	4027.475	85476.37	13619.77	2798.077	4082.308
#2	4018.305	85658.78	13403.10	2805.336	4074.802
#3	4004.045	85577.72	13516.73	2809.680	4061.096

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-17 Acquired: 1/27/2025 18:17:43 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D5 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0041927**	**-.004643**	**.0108053**	**.0185473**	**.0159180**	**.1464988**
Stddev	.0018536	.001520	.0011042	.0032384	.0018160	.0087925
%RSD	44.21019	32.72612	10.21879	17.46010	11.40824	6.001782
#1	.0023787	-.004497	.0095365	.0160357	.0166261	.1524931
#2	.0060835	-.003202	.0113309	.0174039	.0172732	.1505982
#3	.0041158	-.006231	.0115484	.0222023	.0138547	.1364052

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0777842**	**.0001191**	**.0050217**	**364.6004**	**-.001003**	**.0599431**
Stddev	.0000226	.0000909	.0000846	2.0725	.000536	.0002133
%RSD	.0290323	76.38610	1.684029	.5684396	53.42821	.3558085
#1	.0778097	.0000175	.0049445	363.8270	-.000398	.0601838
#2	.0777670	.0001467	.0051121	363.0257	-.001417	.0597774
#3	.0777758	.0001930	.0050086	366.9484	-.001195	.0598681

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.013093**	**201.1998**	**10.41929**	**100.3719**	**.0795656**	**-.003793**
Stddev	.001383	.5327	.03792	.1352	.0006326	.000047
%RSD	10.56534	.2647813	.3639795	.1346852	.7950276	1.251917
#1	-.012369	200.9865	10.45281	100.2838	.0795145	-.003769
#2	-.012223	200.8068	10.37813	100.3044	.0789602	-.003847
#3	-.014688	201.8062	10.42694	100.5275	.0802222	-.003762

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**3.927522**	**-.017498**	**.4102036**	**1.532265**	**.0057480**	**1.039566**
Stddev	.204511	.000759	.0042010	.039707	.0033431	.003192
%RSD	5.207132	4.335392	1.024115	2.591395	58.16067	.3070120
#1	3.936241	-.016812	.4147673	1.578081	.0021878	1.038345
#2	4.127534	-.017370	.4064979	1.510865	.0062360	1.037165
#3	3.718790	-.018313	.4093456	1.507848	.0088203	1.043187

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1136-17 Acquired: 1/27/2025 18:17:43 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D5 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.001668	F 376.1387	2.678027	-.003533	-.010704	.0113325
Stddev	.000335	1.2301	.012334	.000848	.000074	.0006542
%RSD	20.07307	.3270448	.4605646	23.99804	.6869743	5.773262
#1	-.002007	375.4730	2.689862	-.003611	-.010673	.0109812
#2	-.001658	375.3849	2.678970	-.002649	-.010651	.0120873
#3	-.001338	377.5583	2.665248	-.004339	-.010788	.0109288

Elem	Sr4077
Units	ppm
Avg	3.850540
Stddev	.038400
%RSD	.9972549
#1	3.857861
#2	3.809007
#3	3.884753

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3489.308	75365.86	11543.44	2434.497	3837.083
Stddev	11.925	347.47	21.00	9.392	13.107
%RSD	.3417540	.4610465	.1819455	.3857909	.3415815
#1	3502.905	75549.68	11565.33	2432.218	3852.216
#2	3484.388	75582.81	11541.53	2444.818	3829.315
#3	3480.630	74965.09	11523.46	2426.453	3829.719

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166225BL Acquired: 1/27/2025 18:21:59 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: PBW225 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000623**	**.0005352**	**.0008322**	**.0013114**	**.0001719**	**-.000119**	**-.003365**
Stddev	.001272	.0006912	.0001620	.0015875	.0005950	.001599	.000592
%RSD	204.0651	129.1527	19.46529	121.0538	346.0423	1343.159	17.58660
#1	-.002080	-.000241	.0009753	.0003872	-.000402	.000515	-.002713
#2	-.000063	.000764	.0008650	.0031445	.000786	-.001937	-.003515
#3	.000272	.001083	.0006563	.0004026	.000132	.001066	-.003868

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000013**	**.0000011**	**.0075288**	**-.000103**	**.0001393**	**.0008206**	**.0035664**
Stddev	.000009	.0000321	.0017054	.000054	.0000742	.0010620	.0042617
%RSD	70.40643	2974.829	22.65102	52.62722	53.29549	129.4162	119.4958
#1	-.000011	.0000240	.0092286	-.000165	.0002177	-.000207	-.001221
#2	-.000006	.0000149	.0075400	-.000069	.0001299	.001914	.006946
#3	-.000024	-.000036	.0058179	-.000073	.0000701	.000755	.004975

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000071**	**.0013373**	**.0002350**	**-.000146**	**.1657949**	**.0000811**	**.0002356**
Stddev	.000294	.0092197	.0004424	.000099	.2263315	.0013124	.0004649
%RSD	411.7839	689.4341	188.2795	67.95640	136.5129	1617.873	197.3271
#1	.000122	.0103863	.0001843	-.000038	.0119731	.0015521	.0002658
#2	.000073	.0016697	-.000180	-.000168	.0597302	-.000970	-.000244
#3	-.000409	-.008044	.000701	-.000233	.4256815	-.000339	.000685

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.260876**	**.0012495**	**.0026252**	**.0001890**	**.0371799**	**-.002169**	**.0008306**
Stddev	.040015	.0021619	.0003609	.0000640	.0036812	.000693	.0002358
%RSD	15.33873	173.0220	13.74762	33.88274	9.901026	31.94046	28.38491
#1	-.305360	.0024806	.0030088	.0002503	.0413220	-.002140	.0008157
#2	-.249457	.0025147	.0022924	.0001943	.0359354	-.002876	.0010735
#3	-.227812	-.001247	.0025744	.0001225	.0342822	-.001492	.0006027

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166225BL Acquired: 1/27/2025 18:21:59 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: PBW225 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0008117	-.001002	.0001151
Stddev	.0007696	.000334	.0000434
%RSD	94.82008	33.32943	37.72200
#1	.0012434	-.001290	.0000742
#2	.0012685	-.001081	.0001607
#3	-.000077	-.000636	.0001104

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3580.647	75253.79	10856.19	2459.633	4487.391
Stddev	22.160	93.58	24.71	4.304	38.169
%RSD	.6188722	.1243558	.2275677	.1750000	.8505906
#1	3555.851	75159.28	10836.03	2454.663	4443.524
#2	3587.576	75346.42	10848.79	2462.170	4505.632
#3	3598.514	75255.67	10883.75	2462.067	4513.018

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166225BS Acquired: 1/27/2025 18:26:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LCS225 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0185689**	**.0525976**	**.0209437**	**.0646695**	**.1090086**	**.3736171**	**.3784682**
Stddev	.0030094	.0016518	.0012724	.0031029	.0009538	.0067394	.0102444
%RSD	16.20672	3.140395	6.075457	4.798146	.8749376	1.803823	2.706797
#1	.0197590	.0507247	.0223470	.0658456	.1079306	.3813329	.3898330
#2	.0208014	.0532213	.0206192	.0611505	.1097428	.3688823	.3699436
#3	.0151465	.0538467	.0198649	.0670125	.1093522	.3706359	.3756280

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0103090**	**.0101636**	**9.933772**	**.0218915**	**.0989978**	**.0543569**	**.2133373**
Stddev	.0001088	.0001411	.252902	.0006377	.0009608	.0007707	.0076814
%RSD	1.055178	1.388471	2.545877	2.912899	.9705002	1.417873	3.600590
#1	.0102039	.0100323	10.22523	.0226221	.0982802	.0547063	.2214377
#2	.0103018	.0101457	9.77229	.0214467	.0986239	.0534733	.2061579
#3	.0104211	.0103128	9.80380	.0216057	.1000893	.0548909	.2124165

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0304609**	**8.900605**	**.0810664**	**.0190965**	**9.475852**	**.1035723**	**.1175361**
Stddev	.0007721	.162163	.0008108	.0005338	.312641	.0022558	.0028979
%RSD	2.534663	1.821930	1.000139	2.795456	3.299339	2.177987	2.465505
#1	.0312404	9.086095	.0803988	.0197035	9.337120	.1020930	.1197691
#2	.0296964	8.830035	.0808318	.0187003	9.256585	.1024552	.1142614
#3	.0304458	8.785685	.0819686	.0188856	9.833852	.1061686	.1185778

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**9.237858**	**.0193891**	**.0022918**	**.0203635**	**.1964343**	**.4562112**	**.0144799**
Stddev	.236709	.0010240	.0004319	.0004503	.0046984	.0085886	.0006215
%RSD	2.562379	5.281546	18.84557	2.211515	2.391832	1.882601	4.292290
#1	9.511177	.0193672	.0018663	.0198447	.1910269	.4514677	.0151389
#2	9.103111	.0204239	.0027298	.0205925	.1987572	.4510405	.0139042
#3	9.099286	.0183762	.0022792	.0206534	.1995187	.4661255	.0143966

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166225BS Acquired: 1/27/2025 18:26:09 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LCS225 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.2072024	.0280845	.1786881
Stddev	.0022485	.0009741	.0042913
%RSD	1.085174	3.468492	2.401543
#1	.2066280	.0289221	.1835024
#2	.2052967	.0270155	.1752650
#3	.2096823	.0283157	.1772970

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3626.429	74409.76	11428.59	2453.117	4445.966
Stddev	18.895	1647.87	93.89	52.941	26.749
%RSD	.5210450	2.214583	.8215770	2.158114	.6016518
#1	3631.023	72528.31	11498.71	2393.640	4455.710
#2	3642.604	75104.36	11465.16	2470.622	4466.478
#3	3605.660	75596.60	11321.92	2495.088	4415.711

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-01 Acquired: 1/27/2025 18:30:12 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	s 2.900808	kF -1.05253	k 1.986246	s .5507783	sF 28.47547	k 17.91555
Stddev	.091714	.00958	.007872	.0227655	.95201	.07725
%RSD	3.161679	.9099603	.3963126	4.133336	3.343276	.4311708
#1	s 2.848463	k -1.04384	k 1.985788	s .5301500	s 27.99546	k 17.89200
#2	s 2.847253	k -1.05096	k 1.978613	s .5469815	s 27.85901	k 18.00184
#3	s 3.006708	k -1.06280	k 1.994337	s .5752036	s 29.57193	k 17.85283

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.3752152	k -.011689	k .0166001	88.01727	F 316.9976	F 114.5901
Stddev	.0016217	.000151	.0001565	.19787	1.2418	.6192
%RSD	.4322073	1.295276	.9430301	.2248055	.3917347	.5404037
#1	.3757795	k -.011833	k .0166808	87.95264	315.6101	114.7910
#2	.3764794	k -.011531	k .0164197	88.23937	318.0047	115.0839
#3	.3733867	k -.011702	k .0166998	87.85979	317.3780	113.8953

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	k 3.125149	k 139.5769	k 2.166465	12.79844	F 96.79248	k -.029902
Stddev	.016956	.3593	.003891	.04258	.23599	.000350
%RSD	.5425790	.2574081	.1795885	.3326846	.2438129	1.170451
#1	k 3.134917	k 139.4204	k 2.164499	12.78361	96.52015	k -.029960
#2	k 3.134959	k 139.9879	k 2.170946	12.84646	96.92038	k -.029526
#3	k 3.105569	k 139.3225	k 2.163949	12.76527	96.93691	k -.030219

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	36.86520	k .1714895	k 4.842877	2.100792	k 3.046386	k .2076306
Stddev	.28075	.0093044	.028360	.019419	.019136	.0001832
%RSD	.7615698	5.425636	.5856021	.9243643	.6281470	.0882157
#1	37.18677	k .1607728	k 4.847734	2.123206	k 3.028632	k .2074415
#2	36.74006	k .1761885	k 4.868494	2.090129	k 3.043871	k .2078072
#3	36.66878	k .1775074	k 4.812401	2.089041	k 3.066655	k .2076431

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-01 Acquired: 1/27/2025 18:30:12 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	sF 360.9821	kF 168.7950	k 3.375686	.3358744	.3658211	.0208091
Stddev	10.8475	.4162	.005105	.0013353	.0022616	.0007197
%RSD	3.004987	.2465702	.1512394	.3975524	.6182261	3.458616
#1	s 355.2243	k 168.4479	k 3.370437	.3343631	.3682397	.0214690
#2	s 354.2277	k 168.6806	k 3.380635	.3363659	.3637588	.0209168
#3	s 373.4945	k 169.2564	k 3.375986	.3368943	.3654650	.0200417

Elem	Sr4077
Units	ppm
Avg	.7737799
Stddev	.0029965
%RSD	.3872574
#1	.7745113
#2	.7763431
#3	.7704854

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	^ *****	72997.45	11572.09	1980.348	3908.024
Stddev	-----	235.54	22.59	7.986	3.886
%RSD	-----	.3226630	.1952053	.4032500	.0994401
#1	^ -----	73149.45	11580.55	1982.592	3911.668
#2	^ -----	72726.13	11546.49	1971.480	3908.471
#3	^ -----	73116.76	11589.22	1986.971	3903.934

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-02 Acquired: 1/27/2025 18:34:26 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ1 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1107924	-.029082	2.885827	.0308061	.0608309	43.42664
Stddev	.0017403	.001474	.025662	.0032888	.0017955	.37201
%RSD	1.570754	5.069672	.8892402	10.67571	2.951622	.8566388
#1	.1090809	-.030426	2.857671	.0273377	.0598692	43.00126
#2	.1125600	-.027505	2.891907	.0338796	.0597212	43.58758
#3	.1107363	-.029317	2.907902	.0312010	.0629024	43.69108

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.2877065	.0042921	.0076725	31.55529	26.31424	F 11.91319
Stddev	.0024256	.0000481	.0001404	.13028	.10626	.11788
%RSD	.8430794	1.120507	1.829248	.4128597	.4038021	.9894947
#1	.2851991	.0042735	.0076672	31.40765	26.20328	11.78292
#2	.2878793	.0042560	.0075349	31.60417	26.41507	11.94412
#3	.2900410	.0043466	.0078154	31.65407	26.32438	12.01251

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.266639	120.1486	.8712623	18.52408	F 11.50748	.0011576
Stddev	.008941	.7345	.0024140	.02487	.11504	.0001034
%RSD	.7058598	.6113147	.2770701	.1342677	.9997098	8.928771
#1	1.276635	119.3151	.8689481	18.49599	11.38010	.0011312
#2	1.259405	120.4295	.8710735	18.54331	11.53853	.0010700
#3	1.263878	120.7011	.8737651	18.53292	11.60381	.0012716

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	31.55221	.2653342	1.947634	9.463292	F 11.93254	.6557734
Stddev	.09093	.0019155	.007655	.116930	.12694	.0027071
%RSD	.2881936	.7219141	.3930438	1.235612	1.063772	.4128043
#1	31.63906	.2634159	1.953521	9.332048	11.78762	.6526932
#2	31.55988	.2672469	1.950400	9.501461	11.98602	.6568525
#3	31.45769	.2653399	1.938980	9.556368	12.02399	.6577744

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-02 Acquired: 1/27/2025 18:34:26 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ1 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.754979	F 105.4346	5.082301	.0911807	1.067668	.0710895
Stddev	.016167	.7817	.027982	.0010387	.002903	.0007556
%RSD	.9211860	.7413850	.5505850	1.139178	.2719345	1.062858
#1	1.736718	104.5507	5.114596	.0903003	1.071020	.0702217
#2	1.760753	105.7179	5.065242	.0923263	1.066054	.0714452
#3	1.767467	106.0351	5.067067	.0909156	1.065930	.0716015

Elem	Sr4077
Units	ppm
Avg	.4135445
Stddev	.0027549
%RSD	.6661708
#1	.4104992
#2	.4142708
#3	.4158636

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3403.305	79807.50	12109.42	2597.378	4172.774
Stddev	31.233	62.65	93.93	6.364	40.952
%RSD	.9177173	.0785035	.7756857	.2450057	.9814118
#1	3436.000	79878.08	12002.84	2594.072	4217.260
#2	3400.138	79785.97	12145.32	2593.347	4164.416
#3	3373.776	79758.45	12180.12	2604.714	4136.645

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-03 Acquired: 1/27/2025 18:38:28 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ2 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0828945	-.004345	1.567960	.0281109	.0213732	37.11711
Stddev	.0043395	.001055	.005914	.0012601	.0010590	.32680
%RSD	5.235001	24.27128	.3771557	4.482618	4.954738	.8804617
#1	.0829448	-.003398	1.574217	.0288413	.0212350	36.75390
#2	.0872086	-.005481	1.562462	.0288356	.0224945	37.21004
#3	.0785300	-.004156	1.567203	.0266559	.0203901	37.38737

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.3236039	.0072655	.0152435	16.79408	1.845119	F 8.528199
Stddev	.0037358	.0001004	.0001576	.14261	.004878	.036148
%RSD	1.154428	1.381651	1.033693	.8491620	.2643797	.4238648
#1	.3193097	.0073711	.0154164	16.63639	1.839948	8.566598
#2	.3253956	.0071713	.0151081	16.83186	1.849640	8.494828
#3	.3261063	.0072541	.0152059	16.91400	1.845768	8.523172

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.188620	99.28287	.5477526	9.304021	F 5.133687	.0024866
Stddev	.003884	.75718	.0033695	.057084	.022117	.0002989
%RSD	.3267594	.7626453	.6151461	.6135390	.4308284	12.01900
#1	1.191763	98.52040	.5438663	9.246613	5.157583	.0027981
#2	1.184278	99.29357	.5495344	9.360775	5.113934	.0024595
#3	1.189818	100.0346	.5498571	9.304676	5.129544	.0022022

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	21.31914	.1535716	2.286873	2.813644	2.844984	.5091452
Stddev	.29200	.0016856	.027820	.097168	.015830	.0029872
%RSD	1.369673	1.097565	1.216499	3.453464	.5564237	.5867038
#1	21.55573	.1555132	2.254812	2.734597	2.860855	.5060994
#2	21.40890	.1524833	2.304641	2.784210	2.829195	.5092661
#3	20.99280	.1527184	2.301167	2.922127	2.844902	.5120701

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-03 Acquired: 1/27/2025 18:38:28 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ2 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1316058	F 60.40851	2.361144	.0784245	.6172808	.0332066
Stddev	.0006639	.28906	.013884	.0004956	.0032524	.0002601
%RSD	.5044885	.4785018	.5880169	.6319248	.5268864	.7832934
#1	.1323682	60.71560	2.376854	.0784259	.6191893	.0330609
#2	.1311546	60.14171	2.350519	.0779283	.6135254	.0330519
#3	.1312947	60.36821	2.356060	.0789194	.6191276	.0335068

Elem	Sr4077
Units	ppm
Avg	.1975145
Stddev	.0020596
%RSD	1.042748
#1	.1951621
#2	.1983879
#3	.1989934

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3861.479	82584.64	12858.22	2675.659	4205.128
Stddev	10.310	249.09	130.40	19.236	16.151
%RSD	.2669847	.3016121	1.014135	.7189407	.3840774
#1	3850.861	82861.16	12707.93	2697.736	4189.167
#2	3871.450	82514.90	12925.43	2666.742	4221.462
#3	3862.124	82377.86	12941.30	2662.500	4204.754

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-04 Acquired: 1/27/2025 18:42:21 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ3 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0513198**	**-.000629**	**.5237729**	**.0194253**	**.0124175**	**35.65171**
Stddev	.0002776	.000603	.0041839	.0054014	.0017374	.10008
%RSD	.5408730	95.80961	.7988036	27.80586	13.99186	.2807132
#1	.0516150	.000023	.5261460	.0147329	.0106559	35.71672
#2	.0510641	-.000744	.5262308	.0253298	.0124669	35.70194
#3	.0512804	-.001166	.5189420	.0182133	.0141298	35.53646

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1136273**	**.0022595**	**.0026221**	**14.58903**	**.2201465**	**1.500838**
Stddev	.0006834	.0000327	.0000880	.03482	.0004002	.004444
%RSD	.6014270	1.448304	3.356305	.2386980	.1817928	.2961277
#1	.1129396	.0022858	.0025690	14.61255	.2197552	1.504223
#2	.1136360	.0022698	.0025736	14.60551	.2205551	1.502485
#3	.1143063	.0022229	.0027237	14.54903	.2201293	1.495805

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1737731**	**109.1590**	**.4931003**	**9.769327**	**.6503931**	**.0008161**
Stddev	.0013167	.2896	.0009593	.040347	.0020698	.0007576
%RSD	.7577109	.2652566	.1945500	.4129951	.3182427	92.82906
#1	.1730721	109.3049	.4931101	9.759104	.6515292	.0008702
#2	.1729553	109.3465	.4940546	9.813801	.6516460	.0015451
#3	.1752920	108.8255	.4921360	9.735074	.6480040	.0000329

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**19.23713**	**.1136370**	**.3775964**	**4.387295**	**1.692565**	**.5406279**
Stddev	.31362	.0010663	.0060613	.051739	.006254	.0009302
%RSD	1.630281	.9383219	1.605240	1.179285	.3694915	.1720684
#1	18.89062	.1124472	.3801262	4.428484	1.696661	.5402514
#2	19.50151	.1139576	.3706800	4.329224	1.695668	.5416874
#3	19.31927	.1145062	.3819831	4.404177	1.685366	.5399449

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-04 Acquired: 1/27/2025 18:42:21 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ3 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0395593	F 79.21304	4.326668	.0229890	.9192270	.0533192
Stddev	.0005081	.25685	.016214	.0011175	.0032224	.0007147
%RSD	1.284500	.3242515	.3747551	4.861258	.3505602	1.340347
#1	.0401364	79.44878	4.338209	.0233090	.9179835	.0526144
#2	.0391791	79.25102	4.308130	.0217463	.9168116	.0532999
#3	.0393623	78.93931	4.333664	.0239116	.9228859	.0540433

Elem	Sr4077
Units	ppm
Avg	.1252882
Stddev	.0001004
%RSD	.0801186
#1	.1253914
#2	.1251908
#3	.1252825

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3716.909	78004.70	12200.24	2526.186	4317.000
Stddev	3.333	85.43	24.70	4.112	8.229
%RSD	.0896641	.1095133	.2024704	.1627581	.1906156
#1	3717.645	77982.20	12204.86	2521.449	4314.059
#2	3713.269	77932.77	12222.31	2528.279	4310.646
#3	3719.812	78099.12	12173.56	2528.829	4326.295

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-05 Acquired: 1/27/2025 18:46:18 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ4 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0887587	-.003815	1.256959	.0354469	.0203947	74.63712
Stddev	.0007121	.002862	.002521	.0023605	.0009010	.11897
%RSD	.8022455	75.02293	.2005629	6.659274	4.417598	.1593932
#1	.0885262	-.001301	1.259207	.0331248	.0206197	74.52924
#2	.0895580	-.006929	1.257438	.0353720	.0211619	74.76471
#3	.0881920	-.003213	1.254233	.0378440	.0194026	74.61743

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.2613228	.0066585	.0106948	22.29805	4.467221	F 5.539451
Stddev	.0009596	.0000694	.0000421	.06419	.006754	.006676
%RSD	.3671993	1.042575	.3934527	.2878868	.1511993	.1205225
#1	.2603182	.0067105	.0106491	22.23430	4.474725	5.542457
#2	.2622299	.0066854	.0107034	22.36267	4.465312	5.544095
#3	.2614202	.0065797	.0107320	22.29717	4.461627	5.531800

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5673546	176.8981	1.363929	30.31978	4.299666	.0025893
Stddev	.0030938	.3648	.003202	.14447	.006265	.0000930
%RSD	.5453058	.2062156	.2347744	.4764992	.1457118	3.593048
#1	.5700791	176.5004	1.360610	30.19258	4.301939	.0024865
#2	.5639912	177.2172	1.367000	30.28990	4.304477	.0026677
#3	.5679934	176.9766	1.364175	30.47686	4.292581	.0026136

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	45.33569	.2029770	2.028322	17.08317	8.100535	.8591426
Stddev	.29208	.0022968	.012421	.03695	.016852	.0019689
%RSD	.6442507	1.131542	.6123702	.2163046	.2080390	.2291667
#1	45.67292	.2003311	2.013980	17.04053	8.115342	.8569879
#2	45.16379	.2041438	2.035553	17.10311	8.104067	.8608478
#3	45.17034	.2044561	2.035434	17.10587	8.082197	.8595922

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-05 Acquired: 1/27/2025 18:46:18 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ4 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.3978152	F 121.8718	5.933357	.0537031	1.537713	.1303187
Stddev	.0007691	.2516	.035397	.0008963	.007751	.0010375
%RSD	.1933378	.2064842	.5965704	1.669037	.5040552	.7961386
#1	.3974968	122.0991	5.966914	.0537624	1.546539	.1308607
#2	.3972563	121.9151	5.896370	.0527786	1.534582	.1309729
#3	.3986924	121.6014	5.936786	.0545683	1.532016	.1291224

Elem	Sr4077
Units	ppm
Avg	.2420323
Stddev	.0005141
%RSD	.2124197
#1	.2414815
#2	.2424995
#3	.2421158

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3907.762	84254.98	13356.31	2701.572	4103.706
Stddev	10.196	72.49	42.84	5.677	2.705
%RSD	.2609268	.0860420	.3207368	.2101339	.0659150
#1	3918.206	84338.19	13316.62	2708.099	4106.829
#2	3907.247	84205.42	13401.73	2697.780	4102.146
#3	3897.833	84221.35	13350.59	2698.838	4102.142

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-06 Acquired: 1/27/2025 18:50:12 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ5 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0758936**	**-.001625**	**.6278153**	**.0263370**	**.0212763**	**66.94854**
Stddev	.0016367	.002706	.0018563	.0036617	.0025127	.35037
%RSD	2.156622	166.4602	.2956676	13.90322	11.80970	.5233429
#1	.0754000	-.000433	.6256744	.0222337	.0241261	66.75774
#2	.0745605	.000279	.6289758	.0275055	.0193796	67.35290
#3	.0777203	-.004723	.6287956	.0292718	.0203234	66.73498

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2335204**	**.0050290**	**.0057691**	**12.08603**	**10.72783**	**3.313764**
Stddev	.0011446	.0000315	.0000628	.05035	.01388	.004510
%RSD	.4901358	.6269093	1.089241	.4165680	.1293960	.1361042
#1	.2329008	.0050645	.0057082	12.03638	10.71194	3.317409
#2	.2348412	.0050042	.0057654	12.13704	10.73759	3.308720
#3	.2328192	.0050183	.0058337	12.08467	10.73397	3.315163

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4254242**	**140.8663**	**1.181699**	**28.04811**	**3.049012**	**.0024285**
Stddev	.0023754	.6492	.002807	.07000	.002601	.0003627
%RSD	.5583659	.4608816	.2375662	.2495776	.0852969	14.93592
#1	.4275602	140.4035	1.180106	27.99312	3.046564	.0020204
#2	.4258464	141.6084	1.184940	28.12691	3.048731	.0027141
#3	.4228659	140.5869	1.180051	28.02430	3.051742	.0025510

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**43.36818**	**.1982497**	**1.202322**	**15.04062**	**3.986184**	**.6879979**
Stddev	.26469	.0028034	.007570	.09411	.006360	.0017970
%RSD	.6103430	1.414073	.6295914	.6257077	.1595498	.2611967
#1	43.62252	.1950230	1.194382	14.96563	3.992684	.6862402
#2	43.38781	.1996390	1.203126	15.14622	3.979975	.6898318
#3	43.09422	.2000872	1.209458	15.01000	3.985893	.6879216

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-06 Acquired: 1/27/2025 18:50:12 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ5 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.3549858	F 87.68603	6.651267	.0358445	1.389649	.1160669
Stddev	.0011761	.06225	.035652	.0004993	.005818	.0002786
%RSD	.3313179	.0709923	.5360168	1.393079	.4186861	.2399947
#1	.3563177	87.69479	6.670719	.0362262	1.393242	.1160304
#2	.3540900	87.61987	6.672963	.0360278	1.392770	.1158084
#3	.3545498	87.74344	6.610121	.0352794	1.382936	.1163619

Elem	Sr4077
Units	ppm
Avg	.2344730
Stddev	.0007621
%RSD	.3250118
#1	.2337570
#2	.2352740
#3	.2343880

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3677.307	81613.01	12961.46	2639.032	4111.323
Stddev	7.681	193.77	55.70	12.274	2.926
%RSD	.2088666	.2374204	.4297090	.4650814	.0711694
#1	3675.023	81743.44	12906.92	2653.142	4112.666
#2	3671.028	81390.36	12959.21	2633.129	4107.966
#3	3685.871	81705.23	13018.25	2630.825	4113.336

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-07 Acquired: 1/27/2025 18:54:06 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ6 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0160958	-.001158	.2745051	.0097443	.0045347	28.97688
Stddev	.0024044	.001497	.0015219	.0021515	.0009838	.14580
%RSD	14.93806	129.2583	.5544122	22.08002	21.69417	.5031488
#1	.0154435	.000526	.2751680	.0118921	.0038285	28.95353
#2	.0140848	-.001663	.2727642	.0075890	.0041172	28.84416
#3	.0187590	-.002338	.2755832	.0097519	.0056583	29.13294

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.3099365	.0214913	.0092636	30.42619	.0915794	.1703208
Stddev	.0008669	.0001238	.0001147	.14954	.0000973	.0005823
%RSD	.2796935	.5758313	1.237970	.4914734	.1062642	.3418634
#1	.3100586	.0213704	.0093300	30.48986	.0916015	.1705626
#2	.3090151	.0216178	.0091312	30.25535	.0914729	.1696565
#3	.3107359	.0214857	.0093296	30.53334	.0916637	.1707431

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1753573	51.50031	1.085514	14.61912	.2456831	.0003314
Stddev	.0004585	.26098	.006890	.06058	.0006307	.0001290
%RSD	.2614548	.5067447	.6347637	.4144023	.2567246	38.92772
#1	.1756491	51.56146	1.090492	14.67468	.2462978	.0002211
#2	.1748289	51.21419	1.077649	14.55453	.2450375	.0002997
#3	.1755940	51.72528	1.088400	14.62815	.2457141	.0004732

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	48.64287	.0569178	.4519639	5.467896	6.042413	.2529071
Stddev	.12353	.0004758	.0022605	.029247	.017002	.0012609
%RSD	.2539465	.8359001	.5001450	.5348868	.2813851	.4985556
#1	48.63009	.0564963	.4522977	5.468482	6.061728	.2531911
#2	48.52622	.0568236	.4495550	5.438361	6.035799	.2515284
#3	48.77228	.0574337	.4540389	5.496846	6.029710	.2540018

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-07 Acquired: 1/27/2025 18:54:06 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ6 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0044542	F 19.01717	5.331130	.0437626	.2652369	.0192900
Stddev	.0003441	.03688	.012284	.0001407	.0006031	.0006201
%RSD	7.726131	.1939549	.2304277	.3214582	.2273821	3.214742
#1	.0048417	19.05955	5.339045	.0439178	.2645478	.0198178
#2	.0043368	18.99227	5.316978	.0437264	.2654942	.0186071
#3	.0041841	18.99970	5.337367	.0436435	.2656687	.0194452

Elem	Sr4077
Units	ppm
Avg	.3169615
Stddev	.0019789
%RSD	.6243481
#1	.3167210
#2	.3151138
#3	.3190497

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4873.225	104875.4	16585.51	3384.625	4125.338
Stddev	9.385	229.8	56.28	11.553	5.028
%RSD	.1925880	.2190792	.3393342	.3413390	.1218742
#1	4868.161	104627.3	16548.86	3375.258	4120.433
#2	4867.459	105080.9	16557.35	3397.535	4125.100
#3	4884.055	104917.9	16650.31	3381.083	4130.480

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-08 Acquired: 1/27/2025 18:58:02 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0762684**	**.0014393**	**.7580748**	**.0253209**	**.0059362**	**25.63936**
Stddev	.0003441	.0019059	.0011665	.0013653	.0008527	.12040
%RSD	.4511400	132.4246	.1538710	5.391856	14.36538	.4695900
#1	.0762097	.0031943	.7589986	.0238890	.0050179	25.77780
#2	.0759575	-.000588	.7567640	.0254657	.0067031	25.58118
#3	.0766381	.001712	.7584617	.0266080	.0060875	25.55909

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.5175466**	**.0176600**	**.0075058**	**16.24432**	**.1707346**	**.2458559**
Stddev	.0043935	.0000587	.0000808	.05212	.0005790	.0003321
%RSD	.8489126	.3322518	1.076404	.3208623	.3391086	.1350824
#1	.5225101	.0175943	.0075757	16.30390	.1712429	.2457112
#2	.5159734	.0176787	.0074173	16.22187	.1708566	.2462358
#3	.5141563	.0177071	.0075244	16.20718	.1701044	.2456207

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2430461**	**51.17148**	**.3841331**	**11.66616**	**.2569313**	**.0002890**
Stddev	.0034915	.25146	.0042861	.05242	.0006564	.0000772
%RSD	1.436556	.4914081	1.115778	.4493729	.2554651	26.70928
#1	.2463117	51.46150	.3889742	11.71533	.2563661	.0003243
#2	.2434610	51.01429	.3808218	11.67216	.2567767	.0003422
#3	.2393658	51.03864	.3826034	11.61100	.2576512	.0002005

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**35.52005**	**.0858408**	**.5413282**	**5.259314**	**4.930691**	**.2647862**
Stddev	.26413	.0013324	.0051231	.055584	.003098	.0013080
%RSD	.7436166	1.552186	.9463965	1.056868	.0628361	.4939699
#1	35.57500	.0870979	.5470885	5.306339	4.927504	.2661400
#2	35.75239	.0844441	.5396141	5.273631	4.933693	.2635294
#3	35.23277	.0859805	.5372818	5.197972	4.930875	.2646891

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-08 Acquired: 1/27/2025 18:58:02 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0133872	F 41.57838	4.463615	.0190624	.7151061	.0185252
Stddev	.0002723	.04867	.015891	.0009659	.0037486	.0010561
%RSD	2.034186	.1170488	.3560074	5.066846	.5242041	5.700845
#1	.0135658	41.52270	4.474700	.0194581	.7183365	.0196899
#2	.0130738	41.59964	4.470737	.0197675	.7159861	.0182559
#3	.0135220	41.61280	4.445410	.0179615	.7109958	.0176299

Elem	Sr4077
Units	ppm
Avg	.3102727
Stddev	.0023469
%RSD	.7564062
#1	.3129150
#2	.3094729
#3	.3084303

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4299.088	91831.87	14424.83	2956.707	4243.047
Stddev	9.293	198.02	29.94	6.038	3.422
%RSD	.2161527	.2156326	.2075544	.2042146	.0806404
#1	4306.754	91612.45	14457.89	2950.047	4245.702
#2	4301.757	91997.29	14417.05	2958.251	4244.254
#3	4288.753	91885.87	14399.55	2961.823	4239.186

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-09 Acquired: 1/27/2025 19:01:57 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0769253**	**.0034966**	**.7559648**	**.0260618**	**.0054233**	**25.82483**
Stddev	.0017997	.0013330	.0027344	.0022606	.0008029	.16673
%RSD	2.339519	38.12312	.3617148	8.673925	14.80505	.6456195
#1	.0752774	.0019875	.7577560	.0271328	.0048627	25.66399
#2	.0766527	.0045135	.7528173	.0234647	.0063431	25.99688
#3	.0788457	.0039889	.7573210	.0275878	.0050641	25.81362

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.5188818**	**.0175681**	**.0075353**	**16.22423**	**.1699403**	**.2459365**
Stddev	.0030683	.0000584	.0000648	.05521	.0001582	.0003033
%RSD	.5913275	.3321896	.8604947	.3403214	.0931097	.1233061
#1	.5162157	.0175712	.0074900	16.19398	.1700372	.2457608
#2	.5222356	.0175082	.0076096	16.28796	.1697577	.2457621
#3	.5181942	.0176248	.0075064	16.19075	.1700259	.2462867

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2345918**	**51.19346**	**.3845146**	**11.69990**	**.2573014**	**.0004577**
Stddev	.0022899	.25175	.0003344	.05657	.0002623	.0001119
%RSD	.9761364	.4917557	.0869709	.4834659	.1019328	24.45034
#1	.2340509	50.91144	.3849002	11.69141	.2575070	.0004957
#2	.2371038	51.39548	.3843400	11.76023	.2570060	.0005458
#3	.2326208	51.27348	.3843037	11.64806	.2573912	.0003318

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**35.51939**	**.0857176**	**.5396046**	**5.271787**	**4.909200**	**.2650126**
Stddev	.30735	.0006170	.0026315	.024207	.016950	.0014732
%RSD	.8653016	.7198190	.4876634	.4591744	.3452654	.5559102
#1	35.31229	.0854441	.5374666	5.247901	4.901627	.2634214
#2	35.87253	.0852847	.5425434	5.296302	4.897357	.2663293
#3	35.37335	.0864241	.5388037	5.271156	4.928616	.2652871

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-09 Acquired: 1/27/2025 19:01:57 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7D Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0132973	F 41.50570	5.006735	.0194143	.7288295	.0189314
Stddev	.0001172	.12780	.025866	.0001986	.0055872	.0004779
%RSD	.8816883	.3079102	.5166260	1.022833	.7666006	2.524584
#1	.0131745	41.47584	4.978330	.0192383	.7239565	.0183803
#2	.0133095	41.39547	5.028934	.0196296	.7349276	.0192325
#3	.0134080	41.64578	5.012940	.0193751	.7276043	.0191814

Elem	Sr4077
Units	ppm
Avg	.3106060
Stddev	.0021805
%RSD	.7020182
#1	.3087406
#2	.3130032
#3	.3100741

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4297.715	91895.71	14543.53	2975.262	4245.104
Stddev	22.746	121.79	76.07	11.557	17.798
%RSD	.5292672	.1325313	.5230617	.3884292	.4192660
#1	4301.877	91766.15	14484.19	2963.846	4246.356
#2	4318.093	92007.87	14629.29	2974.987	4262.243
#3	4273.175	91913.10	14517.12	2986.954	4226.712

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-08LX5 Acquired: 1/27/2025 19:05:53 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0183215	.0016233	.1562835	.0066361	.0021017	5.813757	.1135360
Stddev	.0016658	.0012309	.0016812	.0012581	.0007304	.004477	.0010928
%RSD	9.092208	75.82618	1.075719	18.95800	34.75314	.0770033	.9624681
#1	.0173967	.0006640	.1563557	.0074854	.0029397	5.816756	.1122743
#2	.0173234	.0030113	.1545674	.0072321	.0017649	5.815905	.1141563
#3	.0202446	.0011947	.1579274	.0051908	.0016004	5.808611	.1141775

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0043476	.0014586	3.709881	.0404108	.0493884	.0591074	11.75691
Stddev	.0000625	.0000938	.012976	.0002464	.0001076	.0007665	.02499
%RSD	1.436414	6.433259	.3497700	.6097962	.2178565	1.296833	.2125856
#1	.0043659	.0015576	3.711430	.0404217	.0495123	.0582236	11.73073
#2	.0042780	.0013710	3.696200	.0406516	.0493191	.0595919	11.78052
#3	.0043988	.0014471	3.722013	.0401591	.0493338	.0595065	11.75949

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0877011	2.638854	.0516309	-.000127	8.343853	.0202908	.1239131
Stddev	.0001750	.012127	.0001960	.000304	.250434	.0012497	.0018135
%RSD	.1994819	.4595699	.3796430	239.2859	3.001417	6.159139	1.463541
#1	.0875192	2.650525	.0516110	.000087	8.238250	.0214558	.1259047
#2	.0878682	2.639721	.0518362	-.000475	8.629792	.0204457	.1234778
#3	.0877159	2.626317	.0514457	.000007	8.163517	.0189708	.1223569

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.072871	.9993895	.0600495	.0031898	8.473208	1.135413	.0044953
Stddev	.020834	.0050438	.0002485	.0001371	.008380	.000924	.0003773
%RSD	1.941883	.5046902	.4137929	4.298296	.0988996	.0813666	8.393869
#1	1.066986	.9937930	.0600688	.0030322	8.464069	1.134637	.0044307
#2	1.055613	1.000791	.0597919	.0032555	8.475024	1.136435	.0041545
#3	1.096015	1.003584	.0602878	.0032818	8.480531	1.135168	.0049008

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-08LX5 Acquired: 1/27/2025 19:05:53 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7L Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.1713136	.0041739	.0687818
Stddev	.0010617	.0006062	.0001455
%RSD	.6197319	14.52420	.2115321
#1	.1723141	.0037401	.0689498
#2	.1701998	.0039149	.0686965
#3	.1714269	.0048665	.0686990

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3810.103	81769.80	12166.22	2648.438	4466.002
Stddev	10.242	14.44	13.11	16.093	11.707
%RSD	.2688141	.0176611	.1077614	.6076312	.2621373
#1	3799.695	81753.40	12173.96	2638.202	4452.903
#2	3810.445	81775.37	12173.62	2640.125	4469.660
#3	3820.170	81780.63	12151.08	2666.987	4475.444

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-10 Acquired: 1/27/2025 19:09:55 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7S Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1339277	.1026208	.7745042	.1661957	.1455581	28.41242
Stddev	.0005221	.0007588	.0021186	.0003630	.0012662	.01854
%RSD	.3898556	.7393905	.2735373	.2184179	.8698824	.0652699
#1	.1342806	.1034471	.7754324	.1657783	.1441555	28.42170
#2	.1333280	.1024601	.7760002	.1663714	.1466167	28.42450
#3	.1341747	.1019553	.7720799	.1664375	.1459023	28.39107

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	3.637436	.0950733	.1017736	16.25911	.5183211	1.191218
Stddev	.013423	.0006535	.0000187	.03734	.0025162	.001130
%RSD	.3690368	.6873190	.0183867	.2296858	.4854481	.0948541
#1	3.632190	.0948465	.1017729	16.23597	.5183533	1.191915
#2	3.652690	.0945634	.1017927	16.23917	.5157890	1.191824
#3	3.627428	.0958099	.1017553	16.30219	.5208210	1.189914

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.6428840	51.92037	1.161244	11.59006	1.210144	.0591598
Stddev	.0008985	.03235	.002554	.07743	.001199	.0001947
%RSD	.1397567	.0622995	.2199118	.6680842	.0990585	.3290638
#1	.6438478	51.89672	1.158306	11.55135	1.210680	.0593709
#2	.6427345	51.90717	1.162927	11.53962	1.210981	.0589874
#3	.6420696	51.95723	1.162499	11.67921	1.208771	.0591212

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	37.12641	.9004768	1.288618	5.173423	4.876510	.2687201
Stddev	.11082	.0024242	.006814	.017620	.015382	.0002880
%RSD	.2984939	.2692109	.5287502	.3405900	.3154389	.1071928
#1	36.99854	.9032042	1.281188	5.165830	4.858784	.2685739
#2	37.19464	.8996586	1.294575	5.193566	4.886359	.2690520
#3	37.18604	.8985676	1.290091	5.160871	4.884385	.2685346

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-10 Acquired: 1/27/2025 19:09:55 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7S Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0126365	F 40.32393	5.901444	.0193608	.7599771	.0191091
Stddev	.0006480	.04079	.043884	.0006275	.0024225	.0007701
%RSD	5.128317	.1011680	.7436075	3.241307	.3187579	4.030094
#1	.0119129	40.28034	5.850959	.0193019	.7614311	.0182484
#2	.0128332	40.36118	5.922914	.0187648	.7571806	.0193456
#3	.0131634	40.33028	5.930459	.0200157	.7613196	.0197332

Elem	Sr4077
Units	ppm
Avg	.3072861
Stddev	.0009980
%RSD	.3247906
#1	.3071294
#2	.3083533
#3	.3063757

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4389.354	92517.36	14270.50	3044.232	4333.650
Stddev	2.706	608.22	100.87	21.438	.575
%RSD	.0616425	.6574097	.7068162	.7042109	.0132676
#1	4392.124	92848.01	14316.63	3065.448	4334.288
#2	4386.718	92888.64	14340.05	3044.670	4333.490
#3	4389.222	91815.44	14154.81	3022.579	4333.172

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-11 Acquired: 1/27/2025 19:13:47 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0B00 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1371115	-.007159	.9798147	.0604072	.0324829	26.87135
Stddev	.0033768	.001783	.0024698	.0044332	.0023147	.15295
%RSD	2.462828	24.90229	.2520722	7.338834	7.125984	.5691854
#1	.1407689	-.009010	.9806871	.0602477	.0324011	27.03226
#2	.1364533	-.007013	.9770270	.0649180	.0302102	26.85393
#3	.1341122	-.005454	.9817299	.0560559	.0348375	26.72786

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.7460745	.0041471	.0255657	37.97886	.1383036	.0706457
Stddev	.0054043	.0000761	.0000943	.11119	.0003427	.0001186
%RSD	.7243703	1.834464	.3687755	.2927631	.2477607	.1678524
#1	.7518600	.0041157	.0256054	38.10275	.1385910	.0707770
#2	.7452072	.0042338	.0254580	37.94606	.1379244	.0705463
#3	.7411562	.0040917	.0256336	37.88775	.1383954	.0706140

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.4005731	359.4077	1.228077	23.65972	.2272666	-.000793
Stddev	.0027952	1.4378	.002976	.13693	.0006168	.000662
%RSD	.6978016	.4000588	.2423409	.5787484	.2713881	83.42702
#1	.3999063	360.9631	1.230855	23.80759	.2279713	-.000136
#2	.4036415	359.1329	1.228440	23.63427	.2268248	-.001459
#3	.3981716	358.1271	1.224936	23.53731	.2270037	-.000784

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	38.41468	.1215893	4.436435	6.627691	F 19.34846	1.578505
Stddev	.27939	.0012165	.015546	.072078	.03699	.008465
%RSD	.7273124	1.000511	.3504130	1.087531	.1911824	.5362975
#1	38.73615	.1213478	4.454057	6.702382	19.37959	1.587826
#2	38.27751	.1205117	4.430583	6.622146	19.35822	1.576397
#3	38.23039	.1229085	4.424664	6.558545	19.30757	1.571293

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-11 Acquired: 1/27/2025 19:13:47 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0B00 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0136625	F 74.48428	4.926083	3.228632	.7755144	.0360083
Stddev	.0002207	.10799	.003575	.002861	.0043932	.0010525
%RSD	1.615343	.1449831	.0725773	.0886161	.5664944	2.922964
#1	.0139128	74.60180	4.926127	3.227735	.7759490	.0372227
#2	.0134958	74.46164	4.922486	3.226327	.7796742	.0353599
#3	.0135788	74.38941	4.929636	3.231834	.7709200	.0354423

Elem	Sr4077
Units	ppm
Avg	.3096480
Stddev	.0019452
%RSD	.6282128
#1	.3117635
#2	.3092441
#3	.3079364

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3706.723	80214.10	12354.02	2611.569	4112.473
Stddev	7.030	94.78	29.21	4.703	4.347
%RSD	.1896587	.1181621	.2364489	.1800807	.1057007
#1	3714.629	80108.69	12386.46	2606.182	4107.681
#2	3701.173	80241.28	12345.81	2613.673	4113.576
#3	3704.368	80292.32	12329.80	2614.853	4116.163

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCV023 Acquired: 1/27/2025 19:21:58 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV023 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.008648**	**4.621067**	**24.30442**	**4.836545**	**4.887723**	**403.1535**
Stddev	.015598	.031475	.06413	.019075	.021906	3.2345
%RSD	.3114301	.6811128	.2638621	.3943887	.4481851	.8023036
#1	4.993762	4.592299	24.25520	4.817788	4.870404	400.7363
#2	5.007309	4.616218	24.28111	4.835926	4.880416	406.8278
#3	5.024872	4.654685	24.37694	4.855923	4.912348	401.8962

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**9.925218**	**.4788448**	**2.420897**	**405.8619**	**15.34153**	**2.418212**
Stddev	.163891	.0015954	.007264	1.3479	.05483	.006523
%RSD	1.651258	.3331801	.3000573	.3321087	.3574173	.2697247
#1	9.736040	.4771928	2.414577	404.8210	15.29878	2.413479
#2	10.01544	.4803769	2.419280	407.3845	15.40335	2.415505
#3	10.02417	.4789647	2.428833	405.3803	15.32247	2.425652

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**14.45309**	**407.7298**	**14.80126**	**398.7629**	**2.415123**	**1.254635**
Stddev	.02856	.7187	.03126	.4072	.006429	.001621
%RSD	.1975909	.1762768	.2112248	.1021050	.2661829	.1292059
#1	14.48529	408.2175	14.83732	399.1403	2.410601	1.256356
#2	14.43081	408.0674	14.78478	398.8169	2.412286	1.254413
#3	14.44317	406.9044	14.78169	398.3314	2.422482	1.253137

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**377.2276**	**2.390490**	**15.06274**	**154.6102**	**4.943449**	F **5.837398**
Stddev	1.2773	.005794	.05540	.3519	.015648	.001737
%RSD	.3385919	.2423909	.3677641	.2275777	.3165407	.0297514
#1	378.5058	2.396589	15.08724	154.9100	4.925919	5.838011
#2	375.9513	2.385057	15.10167	154.6978	4.956008	5.835439
#3	377.2258	2.389825	14.99932	154.2228	4.948419	5.838746

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCV023 Acquired: 1/27/2025 19:21:58 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV023 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**4.792162**	**4.890443**	F **2.518286**	**4.891494**	**4.833492**	**5.075464**
Stddev	.021531	.003443	.003883	.007883	.006526	.019360
%RSD	.4492898	.0704117	.1541949	.1611537	.1350224	.3814455
#1	4.769884	4.886916	2.522477	4.885724	4.839958	5.097580
#2	4.793742	4.890619	2.514811	4.888282	4.826907	5.067227
#3	4.812859	4.893796	2.517571	4.900476	4.833610	5.061584

Elem	Sr4077
Units	ppm
Avg	**4.695748**
Stddev	.039090
%RSD	.8324467
#1	4.705760
#2	4.652626
#3	4.728858

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2893.928**	**63732.11**	**10662.11**	**2048.358**	**3336.536**
Stddev	9.374	192.38	28.73	12.921	7.934
%RSD	.3239248	.3018511	.2694833	.6308126	.2378009
#1	2901.086	63840.10	10691.36	2047.267	3338.315
#2	2897.382	63510.00	10633.92	2036.017	3343.430
#3	2883.317	63846.22	10661.04	2061.790	3327.863

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCB023 Acquired: 1/27/2025 19:26:16 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB023 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.001181**	**.0006702**	**.0022601**	**-.000047**	**-.000924**	**.0108340**	**-.000231**
Stddev	.001676	.0009652	.0006161	.000581	.001336	.0059688	.000665
%RSD	141.8848	144.0126	27.26032	1244.158	144.4599	55.09291	288.1232
#1	-.001970	-.000311	.0015743	.000374	-.001860	.0113365	-.000280
#2	-.002317	.000703	.0027670	.000196	-.001518	.0165357	-.000870
#3	.000744	.001619	.0024388	-.000710	.000605	.0046299	.000458

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0000446**	**.0000444**	**.0064767**	**.0004219**	**-.000251**	**-.000828**	**.0165488**
Stddev	.0000260	.0001009	.0085163	.0002064	.000140	.001304	.0058505
%RSD	58.29272	227.0753	131.4909	48.92167	55.80852	157.4397	35.35283
#1	.0000700	.0000689	.0007217	.0003322	-.000141	-.000743	.0135583
#2	.0000456	-.000066	.0024486	.0002755	-.000408	.000431	.0127981
#3	.0000181	.000131	.0162598	.0006580	-.000203	-.002172	.0232901

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0001883**	**-.001827**	**-.000154**	**-.000262**	**.2779442**	**-.000544**	**.0008709**
Stddev	.0000940	.010191	.000307	.000271	.4246571	.001064	.0014574
%RSD	49.91652	557.7130	199.5250	103.5411	152.7850	195.6227	167.3473
#1	.0002043	-.005142	-.000475	-.000474	-.107335	.000683	.0024685
#2	.0002733	-.009948	.000135	.000043	.207899	-.001107	.0005297
#3	.0000873	.009608	-.000121	-.000354	.733269	-.001207	-.000386

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0812839**	**.0006881**	**.0053732**	**.0006957**	**.0073695**	**-.001187**	**.0007498**
Stddev	.0595517	.0013600	.0005885	.0003965	.0030854	.000712	.0005698
%RSD	73.26387	197.6434	10.95346	56.99160	41.86748	59.97173	75.99646
#1	.0507496	.0001777	.0059371	.0003669	.0103224	-.001505	.0013722
#2	.1499097	.0022295	.0047627	.0005843	.0041667	-.001685	.0006235
#3	.0431923	-.000343	.0054198	.0011361	.0076195	-.000372	.0002538

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCB023 Acquired: 1/27/2025 19:26:16 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB023 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0011127	.0001217	.0001065
Stddev	.0006691	.0004483	.0000619
%RSD	60.13703	368.2657	58.06954
#1	.0015244	-.000381	.0001025
#2	.0003406	.000481	.0000468
#3	.0014731	.000266	.0001703

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3714.578	76897.24	11513.22	2536.835	4685.209
Stddev	2.806	225.48	49.09	17.471	1.730
%RSD	.0755477	.2932185	.4263627	.6886962	.0369331
#1	3714.691	76981.56	11536.67	2524.439	4687.183
#2	3717.326	76641.76	11546.19	2529.249	4683.955
#3	3711.717	77068.40	11456.81	2556.817	4684.490

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-12 Acquired: 1/27/2025 19:30:26 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0B01 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0481784**	**.0001711**	**.4414277**	**.0162768**	**.0095664**	**47.48957**
Stddev	.0015515	.0028367	.0052274	.0016489	.0007393	.28046
%RSD	3.220302	1658.153	1.184200	10.13054	7.727591	.5905789
#1	.0487045	.0029154	.4353916	.0180842	.0091402	47.80597
#2	.0493985	.0003476	.4444499	.0158914	.0091390	47.39115
#3	.0464323	-.002750	.4444415	.0148546	.0104200	47.27157

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2283234**	**.0026150**	**.0046276**	**7.044954**	**.2454005**	**.0733015**
Stddev	.0018475	.0000143	.0001358	.035080	.0012304	.0011477
%RSD	.8091725	.5483212	2.934788	.4979445	.5013624	1.565776
#1	.2302813	.0026244	.0044915	7.067083	.2466800	.0719829
#2	.2280782	.0026220	.0046283	7.063272	.2452955	.0740765
#3	.2266108	.0025985	.0047631	7.004507	.2442260	.0738450

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.3810478**	**92.77312**	**.4424163**	**13.60289**	**.1201436**	**.0021654**
Stddev	.0021223	.31404	.0029401	.06869	.0010853	.0002874
%RSD	.5569621	.3385039	.6645615	.5049917	.9033661	13.27329
#1	.3822765	93.12485	.4457496	13.66109	.1188918	.0024660
#2	.3822697	92.67365	.4413076	13.62045	.1207177	.0021368
#3	.3785972	92.52086	.4401917	13.52712	.1208214	.0018933

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**44.38362**	**.1537935**	**.8084750**	**7.374062**	**2.563812**	**.4561118**
Stddev	.15450	.0014903	.0049510	.053506	.031765	.0012017
%RSD	.3480921	.9690104	.6123918	.7255997	1.238977	.2634767
#1	44.32550	.1520926	.8122138	7.426948	2.527207	.4573712
#2	44.55875	.1544183	.8103510	7.375280	2.580087	.4559870
#3	44.26662	.1548697	.8028601	7.319957	2.584141	.4549774

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1151-12 Acquired: 1/27/2025 19:30:26 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0B01 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0187871	F 62.05840	5.243198	.0261074	.8123913	.0660628
Stddev	.0002450	.80515	.017791	.0016757	.0007545	.0016896
%RSD	1.304301	1.297401	.3393165	6.418428	.0928746	2.557632
#1	.0185912	61.13642	5.246664	.0247638	.8117282	.0677864
#2	.0187083	62.41579	5.259000	.0255734	.8132122	.0659927
#3	.0190619	62.62298	5.223929	.0279850	.8122334	.0644093

Elem	Sr4077
Units	ppm
Avg	.1300828
Stddev	.0012795
%RSD	.9836061
#1	.1313735
#2	.1300601
#3	.1288148

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3730.302	79256.60	12367.48	2600.274	4198.203
Stddev	43.358	146.27	38.70	6.294	49.581
%RSD	1.162327	.1845480	.3129358	.2420669	1.181015
#1	3779.364	79088.28	12410.87	2605.489	4253.171
#2	3714.405	79328.70	12355.06	2602.052	4184.583
#3	3697.135	79352.81	12336.51	2593.282	4156.855

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-01 Acquired: 1/27/2025 19:34:22 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2946 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1042699	-.128049	5.508688	.1690843	.1851631	68.79401
Stddev	.0037504	.003811	.012274	.0110686	.0048023	.39139
%RSD	3.596822	2.976031	.2228044	6.546204	2.593569	.5689372
#1	.1077011	-.124239	5.502457	.1677601	.1815522	69.24580
#2	.1048423	-.131861	5.500780	.1807555	.1833239	68.57832
#3	.1002661	-.128047	5.522827	.1587374	.1906132	68.55790

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.7791559	.0047180	.0911256	677.2669	4.848385	.1388398
Stddev	.0039225	.0003337	.0004646	2.6763	.005011	.0007624
%RSD	.5034248	7.072574	.5098592	.3951614	.1033565	.5491052
#1	.7836829	.0043458	.0911756	675.3081	4.853986	.1385539
#2	.7767695	.0048177	.0906381	676.1763	4.846844	.1397038
#3	.7770152	.0049905	.0915632	680.3163	4.844326	.1382617

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5131712	F 1998.852	F 75.56418	169.1272	2.189279	^ *****
Stddev	.0073478	13.100	.42186	.4345	.001411	-----
%RSD	1.431831	.6553534	.5582758	.2568861	.0644404	-----
#1	.5083219	1986.084	75.42738	169.4845	2.187811	^ -----
#2	.5095667	2012.260	76.03746	169.2536	2.189402	^ -----
#3	.5216252	1998.211	75.22770	168.6436	2.190625	^ -----

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.800338	.5094739	15.70207	7.118252	7.612564	8.337842
Stddev	.412073	.0027775	.06932	.042111	.017976	.056806
%RSD	22.88867	.5451719	.4414425	.5915941	.2361363	.6813015
#1	1.559147	.5086149	15.73225	7.146568	7.596877	8.285168
#2	2.276144	.5072273	15.75119	7.069859	7.608637	8.398031
#3	1.565723	.5125794	15.62278	7.138328	7.632180	8.330325

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-01 Acquired: 1/27/2025 19:34:22 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2946 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0971056	F 11.99948	9.507232	.1100535	4.178698	.1402231
Stddev	.0005909	.00962	.021608	.0011026	.005831	.0004385
%RSD	.6085168	.0801575	.2272805	1.001898	.1395367	.3127227
#1	.0964664	11.98865	9.487661	.1109137	4.173356	.1405902
#2	.0976320	12.00276	9.530421	.1104363	4.184918	.1397375
#3	.0972185	12.00703	9.503614	.1088105	4.177819	.1403417

Elem	Sr4077
Units	ppm
Avg	.6783806
Stddev	.0042597
%RSD	.6279196
#1	.6830886
#2	.6772598
#3	.6747933

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2993.173	67276.99	10844.95	2063.405	3458.375
Stddev	10.005	100.90	49.84	8.586	6.319
%RSD	.3342743	.1499830	.4595752	.4161109	.1827040
#1	2992.119	67223.59	10900.13	2059.234	3453.367
#2	3003.664	67214.00	10803.20	2057.702	3465.474
#3	2983.736	67393.37	10831.53	2073.280	3456.284

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-02 Acquired: 1/27/2025 19:38:38 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0746377	-.019411	.9659339	.0552717	.0462035	80.69071
Stddev	.0041640	.006090	.0011769	.0065508	.0017436	.75654
%RSD	5.578904	31.37407	.1218442	11.85203	3.773694	.9375797
#1	.0698296	-.025314	.9645757	.0605889	.0481813	81.15866
#2	.0770268	-.013149	.9666525	.0479538	.0448884	79.81789
#3	.0770566	-.019771	.9665736	.0572723	.0455409	81.09557

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.6574066	.0038659	.0193801	F 888.8159	5.372557	.1395831
Stddev	.0060449	.0000342	.0000468	3.5987	.027685	.0010423
%RSD	.9195073	.8852256	.2416483	.4048904	.5152961	.7467113
#1	.6621622	.0038567	.0194067	886.2616	5.380052	.1385633
#2	.6506040	.0038373	.0193261	887.2545	5.341897	.1395395
#3	.6594537	.0039038	.0194077	892.9316	5.395723	.1406465

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.2664803	489.5933	22.44953	216.7917	2.819015	-.002660
Stddev	.0035586	2.0576	.17177	1.4597	.001983	.000680
%RSD	1.335408	.4202713	.7651325	.6733084	.0703374	25.56424
#1	.2682367	489.4280	22.55911	217.8371	2.818422	-.002778
#2	.2688192	487.6232	22.25157	215.1240	2.817397	-.001928
#3	.2623850	491.7285	22.53792	217.4139	2.821227	-.003273

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.9485598	.2742583	2.660203	11.70779	5.400723	2.165908
Stddev	.2480010	.0005586	.016272	.17444	.022970	.010482
%RSD	26.14500	.2036815	.6116943	1.489935	.4253216	.4839405
#1	.6855989	.2748497	2.672985	11.79339	5.412910	2.165555
#2	.9818407	.2741857	2.641885	11.50709	5.374228	2.155607
#3	1.178240	.2737395	2.665739	11.82289	5.415033	2.176562

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-02 Acquired: 1/27/2025 19:38:38 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0980913	7.120568	6.392913	.0297586	1.776980	.1670473
Stddev	.0004708	.028442	.028664	.0009162	.006395	.0015550
%RSD	.4799404	.3994309	.4483762	3.078830	.3598827	.9308491
#1	.0981142	7.122833	6.371534	.0301299	1.783682	.1677550
#2	.0976094	7.091062	6.425485	.0304308	1.776311	.1652644
#3	.0985501	7.147810	6.381719	.0287150	1.770945	.1681225

Elem	Sr4077
Units	ppm
Avg	1.185499
Stddev	.002826
%RSD	.2384020
#1	1.182490
#2	1.185910
#3	1.188098

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3259.482	72510.08	11757.33	2319.022	3405.213
Stddev	5.643	421.63	45.08	10.935	3.857
%RSD	.1731313	.5814722	.3833982	.4715508	.1132543
#1	3260.247	72314.96	11770.36	2324.782	3401.526
#2	3264.703	72993.92	11707.18	2325.873	3409.220
#3	3253.495	72221.35	11794.47	2306.410	3404.893

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-03 Acquired: 1/27/2025 19:42:55 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0769327	-.020059	.9686592	.0548029	.0462518	81.68234
Stddev	.0037242	.000774	.0043947	.0021400	.0022148	.33272
%RSD	4.840912	3.859237	.4536935	3.904941	4.788570	.4073360
#1	.0797049	-.020923	.9680526	.0524610	.0487239	82.05507
#2	.0783937	-.019428	.9645993	.0552910	.0455832	81.41531
#3	.0726994	-.019827	.9733257	.0566567	.0444484	81.57664

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.6740935	.0038298	.0196740	F 895.8859	5.360172	.1397466
Stddev	.0030297	.0001559	.0000898	5.5837	.012592	.0003760
%RSD	.4494519	4.071562	.4562306	.6232631	.2349268	.2690542
#1	.6774047	.0038619	.0195715	901.8276	5.368412	.1393154
#2	.6714601	.0039671	.0197385	895.0829	5.366427	.1400062
#3	.6734157	.0036603	.0197122	890.7471	5.345676	.1399181

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.2740179	493.7014	22.82466	220.0438	2.826918	.0001274
Stddev	.0030252	1.3701	.07257	.1923	.003396	.0012297
%RSD	1.104028	.2775258	.3179380	.0873783	.1201211	965.3388
#1	.2715808	495.0599	22.90843	220.2656	2.823022	.0000110
#2	.2730692	492.3199	22.78088	219.9408	2.828485	-.001040
#3	.2774038	493.7244	22.78467	219.9250	2.829247	.001411

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.7356500	.2810744	2.728869	11.76513	5.410554	2.180721
Stddev	.1182567	.0022924	.005954	.03565	.015637	.007281
%RSD	16.07513	.8155796	.2181680	.3030165	.2890101	.3338597
#1	.7012322	.2835127	2.733166	11.80505	5.394652	2.188019
#2	.8672975	.2789631	2.722073	11.75385	5.411097	2.173458
#3	.6384202	.2807472	2.731367	11.73648	5.425912	2.180685

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-03 Acquired: 1/27/2025 19:42:55 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947D Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0982520	7.122397	6.560362	.0304705	1.828748	.1719432
Stddev	.0001389	.009543	.038056	.0004873	.015411	.0022100
%RSD	.1414065	.1339820	.5800959	1.599290	.8427212	1.285325
#1	.0980945	7.116597	6.588005	.0304214	1.836887	.1743799
#2	.0983040	7.117184	6.516957	.0300095	1.810974	.1700682
#3	.0983574	7.133411	6.576124	.0309805	1.838384	.1713815

Elem	Sr4077
Units	ppm
Avg	1.205794
Stddev	.012726
%RSD	1.055429
#1	1.201805
#2	1.220037
#3	1.195540

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3262.477	73848.84	11850.54	2320.521	3404.496
Stddev	2.685	297.41	24.27	8.136	3.603
%RSD	.0823037	.4027260	.2048190	.3506166	.1058365
#1	3261.046	73691.28	11844.31	2323.369	3408.129
#2	3260.810	73663.35	11877.32	2311.343	3404.435
#3	3265.574	74191.87	11830.00	2326.850	3400.923

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-02LX5 Acquired: 1/27/2025 19:47:14 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0174166	-.001518	.2072335	.0188841	.0081968	16.87573	.1422591
Stddev	.0010509	.001315	.0009951	.0018594	.0020189	.10704	.0007300
%RSD	6.033841	86.65222	.4801851	9.846405	24.63000	.6342771	.5131326
#1	.0167299	-.002903	.2080553	.0170868	.0089697	16.85027	.1429242
#2	.0168935	-.000286	.2075180	.0208000	.0097150	16.99321	.1423750
#3	.0186263	-.001364	.2061271	.0187656	.0059057	16.78373	.1414781

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0008057	.0032437	199.8521	1.242110	.0283770	.0557774	112.4404
Stddev	.0000691	.0001113	1.1903	.002266	.0005792	.0019775	.4690
%RSD	8.576109	3.430485	.5956012	.1824640	2.041061	3.545368	.4171390
#1	.0008854	.0033434	199.4207	1.242514	.0280221	.0577580	112.3135
#2	.0007684	.0031237	201.1980	1.244147	.0280636	.0538030	112.9598
#3	.0007632	.0032640	198.9376	1.239668	.0290454	.0557712	112.0478

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	5.084091	47.13093	.5981617	.0007790	-.220285	.0635057	.5701035
Stddev	.039066	.36333	.0046819	.0003898	.101023	.0009757	.0052029
%RSD	.7683942	.7708941	.7827130	50.03782	45.86042	1.536386	.9126302
#1	5.080053	46.90692	.5959785	.0003298	-.143893	.0638579	.5743101
#2	5.125020	47.55014	.5949701	.0009789	-.334828	.0624028	.5717149
#3	5.047202	46.93574	.6035364	.0010282	-.182133	.0642564	.5642856

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	2.407741	1.062993	.5002345	.0213576	1.388442	1.433677	.0033651
Stddev	.068251	.009125	.0018122	.0005682	.007950	.007528	.0008082
%RSD	2.834634	.8584655	.3622787	2.660483	.5725837	.5251018	24.01716
#1	2.441931	1.058908	.5000832	.0207893	1.384429	1.427108	.0030470
#2	2.452140	1.056624	.5021177	.0219258	1.383299	1.441892	.0027644
#3	2.329153	1.073448	.4985027	.0213578	1.397599	1.432031	.0042840

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-02LX5 Acquired: 1/27/2025 19:47:14 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947L Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.4093648	.0341158	.2580134
Stddev	.0015905	.0012977	.0019378
%RSD	.3885238	3.803710	.7510441
#1	.4075413	.0326478	.2580711
#2	.4100869	.0345898	.2599217
#3	.4104661	.0351098	.2560474

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3440.546	73469.75	11460.23	2395.716	3970.580
Stddev	19.747	126.18	48.40	15.112	24.098
%RSD	.5739413	.1717498	.4223660	.6307951	.6069146
#1	3448.550	73535.07	11477.14	2380.823	3984.004
#2	3455.034	73324.29	11497.90	2395.286	3984.977
#3	3418.054	73549.88	11405.63	2411.038	3942.760

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-04 Acquired: 1/27/2025 19:51:15 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947S Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1495834**	**.0765470**	**1.007403**	**.2318924**	**.2235862**	**87.24203**
Stddev	.0025554	.0031341	.002446	.0043844	.0027983	.18425
%RSD	1.708379	4.094324	.2428012	1.890716	1.251547	.2111884
#1	.1481458	.0731718	1.008030	.2351829	.2219368	87.03916
#2	.1525339	.0771037	1.009475	.2335792	.2220046	87.28801
#3	.1480705	.0793654	1.004705	.2269151	.2268171	87.39894

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**4.459812**	**.0927290**	**.1162155**	F **922.6688**	**5.781490**	**1.117685**
Stddev	.007087	.0003921	.0001622	9.6686	.019853	.001224
%RSD	.1589042	.4228047	.1395929	1.047897	.3433958	.1095318
#1	4.453563	.0923730	.1160284	915.6053	5.763372	1.116426
#2	4.467512	.0926647	.1163166	918.7130	5.802713	1.117757
#3	4.458362	.0931492	.1163016	933.6880	5.778386	1.118871

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.7332237**	**507.6303**	**24.39963**	**225.9886**	**3.787356**	**.0749165**
Stddev	.0040919	2.9329	.10799	1.1721	.003084	.0002904
%RSD	.5580644	.5777711	.4426037	.5186532	.0814378	.3876967
#1	.7373134	504.2613	24.27940	224.6352	3.784638	.0747093
#2	.7291296	509.0152	24.48841	226.6637	3.790708	.0747916
#3	.7332282	509.6143	24.43107	226.6669	3.786722	.0752485

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.045496**	**1.172618**	**3.684265**	**12.14729**	**5.440300**	**2.254478**
Stddev	.136178	.004738	.014293	.03203	.021248	.013061
%RSD	13.02518	.4040369	.3879567	.2636940	.3905602	.5793507
#1	.992382	1.167573	3.669200	12.17721	5.419769	2.239535
#2	.943880	1.173307	3.685958	12.11350	5.438931	2.260177
#3	1.200227	1.176973	3.697636	12.15117	5.462198	2.263721

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1163-04 Acquired: 1/27/2025 19:51:15 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947S Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0973091	7.099963	6.745373	.0317424	1.835852	.1768968
Stddev	.0005985	.021262	.029127	.0004488	.007990	.0012034
%RSD	.6151021	.2994639	.4318095	1.414048	.4352344	.6802875
#1	.0979862	7.091087	6.711748	.0313373	1.826738	.1755421
#2	.0970907	7.084577	6.762817	.0322250	1.841654	.1778421
#3	.0968505	7.124225	6.761553	.0316650	1.839163	.1773062

Elem	Sr4077
Units	ppm
Avg	1.244777
Stddev	.020664
%RSD	1.660043
#1	1.241539
#2	1.266869
#3	1.225923

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3241.192	71511.28	11793.21	2296.346	3382.917
Stddev	10.866	246.24	56.89	9.334	6.554
%RSD	.3352535	.3443403	.4824065	.4064618	.1937410
#1	3228.651	71793.80	11858.88	2306.666	3375.424
#2	3247.810	71397.77	11758.86	2293.875	3385.739
#3	3247.115	71342.27	11761.88	2288.496	3387.587

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166229BL Acquired: 1/27/2025 19:55:31 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: PBS229 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0001881**	**.0003755**	**.0001183**	**-.000523**	**-.000747**	**-.000492**	**-.000430**
Stddev	.0025802	.0006974	.0005484	.002403	.000627	.006221	.000080
%RSD	1371.744	185.7212	463.4718	459.4435	83.82581	1264.986	18.65943
#1	.0031673	-.000213	.0007027	-.000698	-.000050	-.000755	-.000401
#2	-.001272	.001146	-.000385	.001963	-.001262	-.006577	-.000369
#3	-.001331	.000194	.000037	-.002834	-.000931	.005857	-.000521

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000027**	**.0000000**	**.0233346**	**.0002740**	**.0000098**	**-.000569**	**.0126157**
Stddev	.000046	.0000626	.0043313	.0001810	.0000245	.001179	.0044588
%RSD	168.5023	129641.6	18.56155	66.04262	249.4866	207.1788	35.34331
#1	.000001	-.000022	.0267812	.0002897	-.000015	.000279	.0173531
#2	-.000002	-.000049	.0247498	.0000857	.000010	-.000071	.0119930
#3	-.000080	.000071	.0184728	.0004466	.000034	-.001915	.0085010

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0001508**	**-.001698**	**-.000160**	**-.000264**	**-.038518**	**-.001491**	**-.000396**
Stddev	.0004460	.001444	.000265	.000033	.228331	.000804	.001373
%RSD	295.7732	85.06451	165.3280	12.33654	592.7983	53.91140	346.3883
#1	.0003034	-.000032	-.000450	-.000281	.188129	-.000936	.001187
#2	-.000351	-.002465	.000069	-.000227	-.035185	-.001124	-.001122
#3	.000500	-.002596	-.000100	-.000285	-.268497	-.002413	-.001254

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0273456**	**.0007643**	**-.000510**	**.0001229**	**.0054703**	**-.001300**	**.0008880**
Stddev	.0105567	.0007988	.000733	.0002392	.0033868	.002614	.0005240
%RSD	38.60468	104.5186	143.8371	194.5714	61.91249	201.1134	59.01413
#1	.0155092	.0007941	.000301	.0003587	.0015784	.001647	.0004755
#2	.0357874	-.000049	-.000705	-.000120	.0077478	-.002205	.0007108
#3	.0307402	.001548	-.001125	.000130	.0070848	-.003342	.0014776

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166229BL Acquired: 1/27/2025 19:55:31 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: PBS229 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0002879	.0004256	.0000350
Stddev	.0006652	.0009986	.0000094
%RSD	231.0377	234.6316	26.87478
#1	.0005116	-.000235	.0000408
#2	-.000460	-.000063	.0000401
#3	.000812	.001574	.0000242

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3709.536	77676.81	11394.35	2608.484	4625.422
Stddev	8.727	183.39	45.94	13.031	14.900
%RSD	.2352672	.2360927	.4031970	.4995730	.3221316
#1	3717.673	77471.30	11343.00	2594.008	4641.382
#2	3710.617	77823.79	11408.49	2619.279	4623.005
#3	3700.319	77735.33	11431.55	2612.165	4611.878

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166229BS Acquired: 1/27/2025 19:59:40 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LCS229 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0179848	.0518663	.0200718	.0618388	.1088943	.3571723	.3633301
Stddev	.0021039	.0021825	.0014761	.0022516	.0007154	.0013084	.0023086
%RSD	11.69842	4.207925	7.354272	3.640997	.6569492	.3663194	.6353971
#1	.0204008	.0519109	.0211681	.0638191	.1096534	.3566327	.3608737
#2	.0165557	.0496619	.0183934	.0593897	.1082327	.3562200	.3636614
#3	.0169980	.0540262	.0206541	.0623075	.1087967	.3586642	.3654551

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0104307	.0100545	9.646732	.0215484	.0986767	.0527097	.2031249
Stddev	.0000957	.0001288	.031182	.0002924	.0002610	.0017378	.0082256
%RSD	.9174859	1.280547	.3232433	1.357077	.2645461	3.296851	4.049545
#1	.0105165	.0099221	9.610779	.0218621	.0988221	.0525354	.1936356
#2	.0104482	.0100621	9.663016	.0212833	.0983754	.0545281	.2082254
#3	.0103275	.0101793	9.666402	.0214997	.0988327	.0510657	.2075136

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0295266	8.612928	.0807217	.0189191	9.645124	.1048541	.1134494
Stddev	.0000507	.055468	.0002700	.0001694	.508876	.0002580	.0027823
%RSD	.1718125	.6440090	.3344506	.8952537	5.275994	.2460686	2.452457
#1	.0294939	8.572230	.0809877	.0189659	10.22504	.1050592	.1106268
#2	.0295009	8.590446	.0804479	.0187312	9.27313	.1045644	.1135318
#3	.0295851	8.676108	.0807294	.0190601	9.43721	.1049388	.1161896

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	8.981851	.0199527	.0004314	.0203661	.1739621	.4510150	.0149630
Stddev	.031527	.0003722	.0001064	.0002495	.0042588	.0040506	.0001191
%RSD	.3510033	1.865204	24.65961	1.224872	2.448090	.8981149	.7959055
#1	8.949354	.0199384	.0003306	.0201568	.1719420	.4550244	.0149974
#2	9.012308	.0195879	.0004209	.0202994	.1710894	.4510964	.0148305
#3	8.983892	.0203318	.0005426	.0206421	.1788550	.4469243	.0150611

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166229BS Acquired: 1/27/2025 19:59:40 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LCS229 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.2043864	.0270219	.1722661
Stddev	.0005837	.0016253	.0009699
%RSD	.2856128	6.014619	.5630270
#1	.2037369	.0260070	.1711537
#2	.2048674	.0288965	.1727098
#3	.2045548	.0261624	.1729348

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3602.603	74551.84	11133.97	2469.331	4434.404
Stddev	8.442	89.22	44.38	5.477	3.207
%RSD	.2343434	.1196803	.3985814	.2217855	.0723227
#1	3601.412	74636.54	11085.45	2475.046	4434.890
#2	3611.578	74458.69	11143.95	2468.818	4437.341
#3	3594.820	74560.28	11172.51	2464.129	4430.982

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-01 Acquired: 1/27/2025 20:03:45 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH96 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0939114**	**-.007087**	**.2126002**	**.0469527**	**.0279553**	**139.5381**	**.9934291**
Stddev	.0014514	.003064	.0028809	.0016710	.0026824	.3238	.0043867
%RSD	1.545514	43.23326	1.355069	3.558963	9.595261	.2320161	.4415674
#1	.0952122	-.005392	.2133905	.0475999	.0298439	139.9026	.9975043
#2	.0941764	-.005244	.2150035	.0482033	.0291372	139.4277	.9939967
#3	.0923458	-.010623	.2094067	.0450548	.0248850	139.2840	.9887863

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0081183**	**.0072572**	**112.9316**	**.4666094**	**.1889078**	**.5420835**	**350.8989**
Stddev	.0002099	.0002697	.1235	.0004189	.0001327	.0030814	.4366
%RSD	2.586027	3.716879	.1093546	.0897684	.0702209	.5684280	.1244261
#1	.0078956	.0071532	113.0255	.4669460	.1888018	.5399950	351.4021
#2	.0083126	.0070549	112.9776	.4667420	.1888651	.5406331	350.6744
#3	.0081467	.0075634	112.7917	.4661403	.1890566	.5456225	350.6203

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**7.192808**	**104.9848**	**.4330188**	**-.002102**	**1.010145**	**.4233502**	**.7894297**
Stddev	.021191	.0562	.0004601	.000143	.162153	.0019855	.0045063
%RSD	.2946118	.0535205	.1062588	6.803843	16.05243	.4690007	.5708339
#1	7.209684	104.9439	.4325348	-.001937	.920119	.4240729	.7912348
#2	7.199716	104.9616	.4330712	-.002175	.912979	.4211046	.7843007
#3	7.169026	105.0489	.4334505	-.002194	1.197338	.4248731	.7927537

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**3.586414**	**5.013382**	**1.481858**	**.0001876**	**.3080043**	**2.319673**	**.0035308**
Stddev	.029772	.017915	.001899	.0002925	.0010130	.025119	.0006613
%RSD	.8301413	.3573468	.1281533	155.9071	.3288899	1.082874	18.72847
#1	3.562934	5.005431	1.484031	.0002316	.3087802	2.343918	.0041188
#2	3.619901	5.000818	1.481023	-.000124	.3068583	2.321339	.0036586
#3	3.576409	5.033896	1.480519	.000456	.3083745	2.293762	.0028150

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-01 Acquired: 1/27/2025 20:03:45 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH96 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.3805651	.4488544	.5384410
Stddev	.0097996	.0033543	.0023246
%RSD	2.575010	.7472996	.4317268
#1	.3759565	.4503167	.5408706
#2	.3918194	.4512293	.5382143
#3	.3739194	.4450172	.5362380

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3899.445	82135.02	13002.26	2647.602	3988.436
Stddev	8.460	61.18	31.14	5.317	12.051
%RSD	.2169435	.0744872	.2395071	.2008390	.3021465
#1	3905.893	82150.98	13037.25	2645.455	3998.114
#2	3902.577	82067.44	12991.94	2653.658	3992.257
#3	3889.867	82186.63	12977.59	2643.695	3974.938

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-02 Acquired: 1/27/2025 20:07:39 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH97 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1063080	-.004502	.2035325	.0474489	.0248018	132.0917	1.149320
Stddev	.0039802	.001587	.0008110	.0014847	.0013912	.8056	.005969
%RSD	3.743976	35.26044	.3984748	3.129122	5.609285	.6098499	.5193246
#1	.1043687	-.002762	.2030343	.0481833	.0240318	132.3906	1.152937
#2	.1108861	-.005871	.2030948	.0457401	.0264078	131.1794	1.142431
#3	.1036692	-.004872	.2044683	.0484234	.0239659	132.7050	1.152593

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0076825	.0067364	47.09101	.4356010	.1655132	.3240630	332.0648
Stddev	.0001915	.0001359	.08271	.0007000	.0005179	.0009690	1.3548
%RSD	2.492319	2.017321	.1756357	.1606990	.3128837	.2990185	.4079939
#1	.0075565	.0065819	47.16604	.4348397	.1655801	.3234222	332.6232
#2	.0079029	.0067903	47.00232	.4357464	.1649651	.3251777	330.5200
#3	.0075882	.0068372	47.10466	.4362168	.1659943	.3235889	333.0511

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	6.143999	99.41224	.4206847	.0006737	1.113874	.4168549	.7656497
Stddev	.011640	.30369	.0001176	.0008745	.071990	.0043577	.0044412
%RSD	.1894581	.3054851	.0279521	129.8000	6.463061	1.045367	.5800627
#1	6.149830	99.45664	.4206050	.0010892	1.184680	.4142865	.7706167
#2	6.130596	99.08880	.4208197	-.000331	1.040755	.4218863	.7642714
#3	6.151571	99.69129	.4206293	.001263	1.116186	.4143919	.7620610

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	2.863813	4.388760	1.402132	.0064825	.1484923	1.941055	.0033111
Stddev	.058601	.006686	.008512	.0000674	.0025865	.008080	.0014359
%RSD	2.046271	.1523476	.6070697	1.039959	1.741806	.4162708	43.36512
#1	2.896129	4.381061	1.406111	.0064179	.1514772	1.950253	.0018675
#2	2.796168	4.393109	1.392359	.0065524	.1470870	1.935101	.0047390
#3	2.899141	4.392110	1.407925	.0064772	.1469127	1.937811	.0033267

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-02 Acquired: 1/27/2025 20:07:39 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH97 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.3444037	.4506745	.2290210
Stddev	.0064798	.0021335	.0013465
%RSD	1.881439	.4734108	.5879265
#1	.3387263	.4513593	.2300296
#2	.3514629	.4482827	.2274920
#3	.3430219	.4523816	.2295414

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3877.615	82816.60	13127.37	2672.575	3968.838
Stddev	6.988	165.00	79.59	11.635	6.798
%RSD	.1802166	.1992379	.6062797	.4353594	.1712963
#1	3878.777	82849.93	13171.49	2659.151	3972.397
#2	3883.950	82962.39	13035.50	2679.771	3973.118
#3	3870.119	82637.48	13175.13	2678.802	3960.999

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-03 Acquired: 1/27/2025 20:11:34 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH98 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0594570	-.003708	.2380946	.0267865	.0133480	101.5299	.7967120
Stddev	.0008368	.003560	.0025419	.0003679	.0008646	.2765	.0036240
%RSD	1.407342	96.01095	1.067600	1.373383	6.477365	.2723283	.4548685
#1	.0596380	-.006248	.2406733	.0263849	.0140699	101.8399	.7990136
#2	.0585446	.000361	.2380194	.0271072	.0135842	101.3088	.7925346
#3	.0601886	-.005238	.2355912	.0268673	.0123898	101.4409	.7985878

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0087271	.0045086	40.98472	.2463832	.1656370	.2234585	186.8172
Stddev	.0000630	.0001001	.09173	.0005894	.0003974	.0007466	.3254
%RSD	.7214360	2.221162	.2238266	.2392125	.2399149	.3341210	.1741958
#1	.0087248	.0046198	41.08918	.2470500	.1656759	.2236669	187.1904
#2	.0086653	.0044255	40.91729	.2461679	.1652216	.2226298	186.6681
#3	.0087912	.0044806	40.94768	.2459317	.1660135	.2240787	186.5930

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	6.747136	60.11387	.3164648	.0005056	.5653445	.2387217	.8302923
Stddev	.018757	.08855	.0006663	.0003579	.1348592	.0010299	.0060355
%RSD	.2779949	.1473006	.2105451	70.77386	23.85434	.4314140	.7269153
#1	6.767416	60.15727	.3169144	.0001759	.4913474	.2378992	.8310624
#2	6.730411	60.17234	.3167806	.0004549	.7210036	.2398768	.8239087
#3	6.743581	60.01199	.3156993	.0008862	.4836826	.2383891	.8359058

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	8.395146	3.832188	.8020200	.0088022	1.905789	2.229716	.0063336
Stddev	.060974	.005102	.0020178	.0002398	.001080	.003593	.0002727
%RSD	.7263059	.1331368	.2515898	2.724616	.0566700	.1611384	4.305059
#1	8.457646	3.833584	.8043474	.0089002	1.905034	2.232406	.0066199
#2	8.391969	3.836446	.8009505	.0089775	1.905307	2.231107	.0060770
#3	8.335822	3.826533	.8007621	.0085289	1.907026	2.225636	.0063037

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-03 Acquired: 1/27/2025 20:11:34 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH98 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	1.380112	.2271257	.3842739
Stddev	.007726	.0011715	.0020802
%RSD	.5597799	.5157868	.5413397
#1	1.380029	.2284568	.3861546
#2	1.372429	.2262517	.3820395
#3	1.387879	.2266685	.3846276

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3941.084	83682.83	13338.77	2718.058	4006.944
Stddev	2.508	257.83	39.85	10.604	3.775
%RSD	.0636464	.3080995	.2987283	.3901373	.0942109
#1	3941.218	83568.01	13377.85	2730.276	4006.885
#2	3943.522	83502.35	13298.20	2711.261	4010.748
#3	3938.510	83978.12	13340.26	2712.636	4003.199

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-04 Acquired: 1/27/2025 20:15:32 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH99 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0200799	-.003410	.1864659	.0131714	.0061540	55.91947	.8393970
Stddev	.0013885	.001402	.0016753	.0025770	.0007546	.14242	.0038415
%RSD	6.914796	41.10621	.8984516	19.56491	12.26139	.2546824	.4576516
#1	.0214045	-.002659	.1883493	.0161451	.0066640	56.07792	.8429282
#2	.0201998	-.002545	.1851418	.0117772	.0065108	55.87833	.8399563
#3	.0186353	-.005028	.1859066	.0115919	.0052872	55.80215	.8353065

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0055423	.0018921	147.2953	.0965768	.0684555	.0679303	83.02641
Stddev	.0000290	.0000410	.5264	.0009186	.0002392	.0009924	.26297
%RSD	.5232477	2.165026	.3574036	.9511137	.3493600	1.460897	.3167308
#1	.0055252	.0019369	147.8789	.0975640	.0681990	.0670540	83.32795
#2	.0055758	.0018827	147.1510	.0964193	.0686723	.0677290	82.90668
#3	.0055260	.0018566	146.8561	.0957472	.0684953	.0690079	82.84462

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	7.150481	34.03924	.1207095	.0004693	.2941158	.1190171	.4421685
Stddev	.033512	.19853	.0007431	.0003329	.3674811	.0010665	.0017260
%RSD	.4686670	.5832291	.6156285	70.92752	124.9443	.8960971	.3903577
#1	7.184339	34.25436	.1200378	.0000850	.0686388	.1178810	.4441616
#2	7.149779	34.00028	.1215078	.0006668	.7181620	.1199967	.4411722
#3	7.117326	33.86309	.1205828	.0006561	.0955468	.1191735	.4411718

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	5.639639	4.302573	.3649393	.0026066	1.781936	3.422079	.0005869
Stddev	.072916	.020418	.0010369	.0001379	.002415	.034215	.0009045
%RSD	1.292911	.4745447	.2841159	5.289489	.1355153	.9998402	154.1159
#1	5.626843	4.325378	.3660846	.0024618	1.782906	3.405678	-.000450
#2	5.718106	4.296348	.3640645	.0026218	1.783715	3.461408	.001216
#3	5.573969	4.285992	.3646687	.0027363	1.779187	3.399153	.000995

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-04 Acquired: 1/27/2025 20:15:32 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH99 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.7930383	.1068352	.5293027
Stddev	.0068633	.0003017	.0024677
%RSD	.8654462	.2824318	.4662264
#1	.7923718	.1066732	.5316953
#2	.7865326	.1071833	.5294467
#3	.8002106	.1066490	.5267661

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3799.680	79659.95	12783.23	2590.756	4119.045
Stddev	13.967	311.57	32.88	12.701	9.555
%RSD	.3675837	.3911297	.2572097	.4902273	.2319799
#1	3814.400	79307.51	12753.99	2585.475	4129.502
#2	3786.613	79898.77	12818.82	2605.246	4110.769
#3	3798.027	79773.57	12776.88	2581.548	4116.865

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-05 Acquired: 1/27/2025 20:19:31 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH99D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0214750**	**-.001906**	**.1871264**	**.0136115**	**.0058315**	**54.41837**	**.8204843**
Stddev	.0013443	.003811	.0021391	.0023561	.0009519	.22932	.0052871
%RSD	6.259838	199.9709	1.143122	17.30929	16.32268	.4213998	.6443892
#1	.0201114	.002473	.1875073	.0162750	.0049182	54.18834	.8151576
#2	.0227992	-.003714	.1848224	.0127592	.0068177	54.41982	.8205643
#3	.0215145	-.004477	.1890494	.0118001	.0057586	54.64697	.8257310

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0055745**	**.0019698**	**144.3511**	**.0950647**	**.0686529**	**.0645843**	**81.09108**
Stddev	.0000567	.0000682	.5375	.0004614	.0002757	.0011098	.31476
%RSD	1.017911	3.461587	.3723478	.4853638	.4016051	1.718444	.3881619
#1	.0056225	.0020484	143.7456	.0948492	.0686754	.0641282	80.74509
#2	.0055890	.0019335	144.5363	.0955944	.0683666	.0637751	81.16764
#3	.0055119	.0019274	144.7716	.0947505	.0689166	.0658495	81.36050

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**7.003062**	**33.43994**	**.1215487**	**.0000087**	**.0301603**	**.1176644**	**.4220595**
Stddev	.033428	.02896	.0008217	.0000191	.2169931	.0002649	.0012409
%RSD	.4773370	.0866145	.6760314	219.2796	719.4656	.2251466	.2940169
#1	6.964692	33.41242	.1210293	.0000118	.2393445	.1175273	.4206331
#2	7.018611	33.47016	.1211207	.0000260	-.193878	.1174961	.4226555
#3	7.025884	33.43723	.1224960	-.000012	.045015	.1179698	.4228900

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.478146**	**4.371864**	**.3555199**	**.0026078**	**1.767936**	**3.104365**	**.0016692**
Stddev	.053286	.004786	.0017434	.0003444	.008051	.008290	.0002879
%RSD	.9727088	.1094760	.4903948	13.20702	.4553733	.2670353	17.24900
#1	5.416943	4.370814	.3540012	.0026134	1.773669	3.103049	.0019921
#2	5.514231	4.367690	.3551348	.0029494	1.758732	3.096812	.0014393
#3	5.503265	4.377088	.3574237	.0022606	1.771407	3.113234	.0015760

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-05 Acquired: 1/27/2025 20:19:31 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH99D Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.7664225	.1028728	.5198540
Stddev	.0071368	.0006150	.0027635
%RSD	.9311861	.5978408	.5315884
#1	.7654608	.1021909	.5170288
#2	.7739914	.1030420	.5199816
#3	.7598153	.1033855	.5225514

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3788.391	80151.47	12757.78	2622.871	4091.609
Stddev	3.784	185.08	46.83	19.229	4.811
%RSD	.0998820	.2309081	.3670826	.7331442	.1175740
#1	3790.426	80318.53	12721.18	2643.515	4089.452
#2	3790.722	79952.52	12741.60	2605.468	4097.121
#3	3784.025	80183.37	12810.55	2619.630	4088.255

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-04LX5 Acquired: 1/27/2025 20:23:30 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH99L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0044017	.0004999	.0404138	.0032396	.0023464	11.55055	.1702938
Stddev	.0024275	.0019843	.0003094	.0033350	.0006806	.05646	.0005079
%RSD	55.14859	396.9492	.7655965	102.9443	29.00492	.4888450	.2982367
#1	.0071436	-.001790	.0401903	.0021157	.0028591	11.48640	.1701165
#2	.0035349	.001587	.0407669	.0069914	.0015742	11.57252	.1698984
#3	.0025266	.001703	.0402841	.0006118	.0026057	11.59272	.1708666

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0013148	.0003715	30.81668	.0212997	.0141050	.0155549	17.72045
Stddev	.0000259	.0000495	.10594	.0002378	.0001962	.0022654	.04974
%RSD	1.969356	13.33845	.3437617	1.116221	1.391300	14.56380	.2807074
#1	.0013139	.0003293	30.70077	.0214561	.0138931	.0174242	17.66855
#2	.0013412	.0004260	30.84077	.0214170	.0142804	.0130356	17.76770
#3	.0012894	.0003590	30.90849	.0210262	.0141416	.0162050	17.72511

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.507300	7.164983	.0246753	-.000340	.0297654	.0266201	.0907285
Stddev	.007126	.041250	.0003037	.000103	.3339627	.0016384	.0013110
%RSD	.4727887	.5757126	1.230750	30.37185	1121.984	6.154639	1.445010
#1	1.499351	7.146169	.0243690	-.000221	-.241317	.0285089	.0896204
#2	1.509430	7.212285	.0249763	-.000398	-.072216	.0255825	.0903893
#3	1.513118	7.136494	.0246805	-.000401	.402829	.0257690	.0921758

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.9951917	.8946960	.0761962	.0006104	.3569637	.8780260	-.000905
Stddev	.0577366	.0051510	.0003671	.0001553	.0067324	.0067852	.000478
%RSD	5.801557	.5757290	.4817851	25.44573	1.886009	.7727730	52.75014
#1	.9652647	.8888097	.0765739	.0007894	.3509958	.8788042	-.000790
#2	1.061748	.8983783	.0758407	.0005106	.3642619	.8843884	-.000496
#3	.958562	.8969000	.0761740	.0005313	.3556335	.8708852	-.001430

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-04LX5 Acquired: 1/27/2025 20:23:30 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH99L Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.1829571	.0213310	.1081228
Stddev	.0101935	.0009267	.0004856
%RSD	5.571548	4.344147	.4491532
#1	.1805421	.0202933	.1076314
#2	.1741879	.0220758	.1081347
#3	.1941413	.0216238	.1086024

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3705.624	77572.86	11822.02	2572.496	4406.004
Stddev	20.879	202.72	37.69	7.414	26.443
%RSD	.5634383	.2613234	.3188240	.2881981	.6001540
#1	3716.212	77632.53	11805.97	2580.159	4425.623
#2	3681.573	77739.04	11865.08	2571.970	4375.933
#3	3719.089	77347.00	11795.00	2565.359	4416.457

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-06 Acquired: 1/27/2025 20:27:34 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH99S Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0899921**	**.1029019**	**.2222142**	**.1716790**	**.1670819**	**55.33943**	**4.111116**
Stddev	.0024293	.0014119	.0010663	.0014594	.0013427	.25019	.033286
%RSD	2.699512	1.372102	.4798541	.8500790	.8036401	.4521026	.8096564
#1	.0872776	.1013194	.2233104	.1719182	.1660412	55.53385	4.138407
#2	.0907365	.1040325	.2221517	.1701147	.1666069	55.42728	4.120908
#3	.0919620	.1033539	.2211806	.1730040	.1685975	55.05717	4.074032

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0952755**	**.0976600**	**138.2772**	**.4843646**	**1.026207**	**.4815202**	**79.20228**
Stddev	.0003951	.0002924	.4628	.0021418	.005296	.0007477	.29854
%RSD	.4146723	.2994509	.3347220	.4421810	.5161045	.1552746	.3769321
#1	.0948883	.0974263	138.7837	.4866192	1.024630	.4814990	79.47936
#2	.0952601	.0975658	138.1716	.4823572	1.021879	.4822783	79.24136
#3	.0956780	.0979880	137.8762	.4841174	1.032113	.4807834	78.88613

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**7.546714**	**31.88036**	**1.085608**	**.0669837**	**.4819015**	**.9945234**	**1.220042**
Stddev	.037353	.12206	.003683	.0004617	.1494627	.0029840	.014274
%RSD	.4949620	.3828700	.3392728	.6893148	31.01521	.3000394	1.169985
#1	7.589203	32.02037	1.082815	.0674045	.3101657	.9935298	1.234337
#2	7.531899	31.82434	1.084227	.0670569	.5825758	.9921631	1.205788
#3	7.519042	31.79636	1.089782	.0664898	.5529629	.9978775	1.220000

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.246308**	**4.342501**	**.3471174**	**.0018698**	**1.769392**	**3.235231**	**.0010390**
Stddev	.040934	.015612	.0009476	.0002762	.005132	.042184	.0000813
%RSD	.7802477	.3595129	.2729896	14.77157	.2900497	1.303898	7.823071
#1	5.286098	4.336581	.3467948	.0019006	1.766614	3.191939	.0011157
#2	5.204318	4.330715	.3463732	.0021293	1.766248	3.237543	.0009538
#3	5.248507	4.360207	.3481842	.0015795	1.775314	3.276212	.0010475

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: Q1181-06 Acquired: 1/27/2025 20:27:34 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MBHH99S Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.7706772	.0977038	.4950986
Stddev	.0127470	.0011335	.0029403
%RSD	1.653998	1.160169	.5938713
#1	.7842561	.0988136	.4977517
#2	.7688066	.0965480	.4956066
#3	.7589688	.0977498	.4919374

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3788.788	80377.49	12365.87	2639.589	4099.287
Stddev	11.996	351.91	39.15	24.219	14.279
%RSD	.3166259	.4378235	.3165804	.9175349	.3483313
#1	3801.748	79983.95	12354.14	2612.843	4110.681
#2	3786.543	80661.92	12409.54	2660.037	4103.911
#3	3778.073	80486.61	12333.93	2645.886	4083.269

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166278BL Acquired: 1/27/2025 20:31:30 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: PBS278 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0012988**	**.0002190**	**.0005759**	**.0000414**	**.0003639**	**.0044383**	**-.001360**
Stddev	.0025974	.0022736	.0008252	.0024378	.0000829	.0073238	.000445
%RSD	199.9804	1038.440	143.2915	5889.716	22.78144	165.0150	32.69385
#1	.0032622	-.002081	-.000230	.0004526	.0003744	-.003334	-.001853
#2	.0022806	.000273	.000538	.0022474	.0004410	.011210	-.000991
#3	-.001646	.002465	.001419	-.002576	.0002762	.005439	-.001234

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000036**	**.0000516**	**.0235692**	**-.000023**	**-.000100**	**.0009972**	**.0039454**
Stddev	.000037	.0000690	.0061138	.000224	.000213	.0003674	.0032069
%RSD	104.9527	133.8850	25.93963	985.2124	213.7480	36.84031	81.28111
#1	-.000078	.0001313	.0165309	.000236	.000146	.0014147	.0029875
#2	-.000008	.0000117	.0266145	-.000168	-.000239	.0008540	.0013267
#3	-.000021	.0000117	.0275622	-.000136	-.000206	.0007230	.0075222

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0000801**	**-.013044**	**.0001658**	**-.000601**	**-.068652**	**-.000856**	**.0005117**
Stddev	.0000381	.012329	.0003246	.000132	.360422	.001407	.0020379
%RSD	47.55842	94.52364	195.7685	21.92832	524.9982	164.2799	398.2226
#1	.0001184	-.001032	.0000541	-.000539	.181572	-.000839	.0028512
#2	.0000422	-.025667	-.000088	-.000512	-.481765	-.002272	-.000439
#3	.0000797	-.012432	.000531	-.000753	.094237	.000542	-.000877

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.102158**	**.0011182**	**-.002287**	**.0001755**	**.0016498**	**-.001315**	**.0005183**
Stddev	.038492	.0008618	.000488	.0002576	.0014916	.001897	.0006660
%RSD	37.67880	77.06558	21.32549	146.7731	90.40923	144.2330	128.4996
#1	-.131684	.0009092	-.002834	-.000102	.0032170	-.002318	.0005271
#2	-.116167	.0020653	-.002127	.000407	.0002475	-.002501	-.000152
#3	-.058624	.0003802	-.001899	.000221	.0014849	.000873	.001180

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166278BL Acquired: 1/27/2025 20:31:30 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: PBS278 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0008854	-.001743	.0000130
Stddev	.0003735	.000862	.0000559
%RSD	42.17847	49.42000	430.0408
#1	.0004814	-.000854	.0000147
#2	.0009570	-.002574	-.000044
#3	.0012180	-.001802	.000068

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3631.268	76657.22	11363.13	2553.599	4523.716
Stddev	11.035	149.68	30.53	15.020	12.231
%RSD	.3038793	.1952636	.2686873	.5881793	.2703785
#1	3618.623	76733.80	11367.03	2568.055	4511.404
#2	3636.229	76753.12	11391.52	2538.073	4523.881
#3	3638.952	76484.74	11330.83	2554.668	4535.864

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166278BS Acquired: 1/27/2025 20:35:40 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LCS278 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0167677	.0492326	.0195535	.0612261	.1037857	.3528574	.3596474
Stddev	.0008345	.0019809	.0005598	.0022080	.0025335	.0059500	.0009985
%RSD	4.976590	4.023601	2.862694	3.606301	2.441070	1.686241	.2776436
#1	.0160635	.0471271	.0198503	.0588367	.1010820	.3463056	.3588110
#2	.0176894	.0510594	.0189079	.0631912	.1061050	.3579245	.3607529
#3	.0165503	.0495114	.0199024	.0616504	.1041701	.3543422	.3593784

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0100736	.0097591	9.465035	.0209935	.0950681	.0508109	.1992053
Stddev	.0000659	.0000565	.022543	.0002234	.0003669	.0021315	.0021106
%RSD	.6545693	.5785026	.2381713	1.063966	.3859473	4.195049	1.059525
#1	.0100960	.0097890	9.440112	.0210550	.0954433	.0517012	.1968088
#2	.0099993	.0096940	9.484003	.0207458	.0947101	.0483785	.2007874
#3	.0101253	.0097943	9.470989	.0211797	.0950509	.0523530	.2000197

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0287277	8.394785	.0778532	.0180817	9.449476	.1013330	.1135556
Stddev	.0003086	.012120	.0004035	.0002458	.136997	.0022575	.0018569
%RSD	1.074158	.1443715	.5182528	1.359358	1.449788	2.227760	1.635250
#1	.0286709	8.407221	.0782768	.0180705	9.352919	.0999447	.1154356
#2	.0284515	8.394127	.0774735	.0178417	9.389239	.1039378	.1135083
#3	.0290607	8.383008	.0778091	.0183329	9.606271	.1001165	.1117227

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	8.685582	.0187011	-.000747	.0195775	.1671118	.4435634	.0144614
Stddev	.053948	.0007526	.000027	.0000533	.0017234	.0016769	.0004121
%RSD	.6211220	4.024458	3.643148	.2723364	1.031296	.3780538	2.849808
#1	8.635573	.0194616	-.000723	.0195161	.1661664	.4419970	.0147589
#2	8.742753	.0179567	-.000776	.0196115	.1691010	.4453324	.0139910
#3	8.678421	.0186849	-.000741	.0196050	.1660679	.4433608	.0146344

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: PB166278BS Acquired: 1/27/2025 20:35:40 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LCS278 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.1994975	.0257060	.1697550
Stddev	.0008590	.0006529	.0004187
%RSD	.4305805	2.539795	.2466218
#1	.2004688	.0256599	.1692907
#2	.1991863	.0250774	.1698702
#3	.1988376	.0263808	.1701039

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3709.215	76167.45	11466.33	2548.483	4547.343
Stddev	2.107	85.74	42.48	11.827	4.262
%RSD	.0568024	.1125712	.3704865	.4640809	.0937176
#1	3711.578	76079.75	11417.54	2535.395	4552.250
#2	3708.536	76251.09	11495.08	2558.403	4544.566
#3	3707.531	76171.50	11486.39	2551.652	4545.214

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCV024 Acquired: 1/27/2025 20:44:03 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV024 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.076451**	**4.685918**	**24.76731**	**4.914249**	**4.936508**	**400.1258**
Stddev	.030768	.031603	.13527	.029925	.035886	1.7042
%RSD	.6060935	.6744262	.5461584	.6089411	.7269583	.4259152
#1	5.054146	4.710115	24.66438	4.896726	4.918710	402.0537
#2	5.063654	4.650163	24.71703	4.897218	4.912999	398.8201
#3	5.111552	4.697476	24.92051	4.948802	4.977814	399.5038

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**9.984770**	**.4855554**	**2.468897**	**405.9339**	**15.33360**	**2.460881**
Stddev	.122482	.0034054	.011609	3.5691	.12956	.013213
%RSD	1.226687	.7013306	.4702232	.8792412	.8449713	.5369305
#1	9.881803	.4873351	2.459914	409.5868	15.41144	2.450790
#2	10.12022	.4877022	2.464771	405.7599	15.40532	2.456017
#3	9.95229	.4816290	2.482006	402.4548	15.18403	2.475837

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**14.84520**	**406.1306**	**14.96897**	**397.1613**	**2.462122**	**1.263065**
Stddev	.02304	.8537	.01599	1.0297	.013639	.008887
%RSD	.1552215	.2102142	.1068465	.2592541	.5539557	.7036178
#1	14.85074	406.4945	14.98197	397.5772	2.451999	1.266562
#2	14.81989	406.7421	14.97382	397.9181	2.456736	1.269671
#3	14.86496	405.1552	14.95111	395.9888	2.477632	1.252961

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**388.8349**	**2.438639**	**15.16706**	**154.4543**	**5.125846**	F **5.916366**
Stddev	.7748	.009256	.14159	.0703	.023479	.026864
%RSD	.1992496	.3795432	.9335607	.0455445	.4580494	.4540608
#1	388.8777	2.434409	15.28408	154.4845	5.117491	5.934209
#2	388.0396	2.449254	15.20744	154.5045	5.107687	5.929420
#3	389.5874	2.432254	15.00966	154.3739	5.152360	5.885470

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCV024 Acquired: 1/27/2025 20:44:03 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV024 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**4.834668**	**5.074521**	F **2.578418**	**4.993157**	**4.941555**	**5.099075**
Stddev	.031099	.020785	.010400	.014581	.000627	.002098
%RSD	.6432498	.4095902	.4033530	.2920147	.0126851	.0411525
#1	4.819729	5.066613	2.573714	4.985304	4.940867	5.097736
#2	4.813856	5.058850	2.571201	4.984186	4.942093	5.097997
#3	4.870417	5.098099	2.590339	5.009981	4.941705	5.101494

Elem	Sr4077
Units	ppm
Avg	**4.687316**
Stddev	.021346
%RSD	.4554086
#1	4.708483
#2	4.687672
#3	4.665794

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2861.665**	**63981.97**	**10565.10**	**2072.351**	**3275.021**
Stddev	20.354	347.22	44.80	26.999	18.815
%RSD	.7112683	.5426873	.4240677	1.302841	.5745114
#1	2870.650	63743.49	10530.30	2051.867	3285.968
#2	2875.981	63822.08	10549.35	2062.238	3285.800
#3	2838.365	64380.33	10615.65	2102.947	3253.295

Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCB024 Acquired: 1/27/2025 20:48:21 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB024 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0005800**	**.0005237**	**.0004773**	**-.000555**	**-.001292**	**.0114248**	**-.000369**
Stddev	.0008395	.0024446	.0015971	.001252	.000290	.0055928	.001253
%RSD	144.7409	466.8335	334.6316	225.5996	22.48211	48.95302	339.1541
#1	.0002489	.0030402	.0013170	-.000579	-.000963	.0061966	-.000961
#2	.0015346	-.001842	.0014792	.000709	-.001514	.0107559	-.001217
#3	-.000043	.000373	-.001364	-.001795	-.001399	.0173220	.001070

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000030**	**.0000245**	**.0158822**	**.0003444**	**.0000086**	**.0008209**	**.0113484**
Stddev	.000043	.0000369	.0029244	.0002122	.0000669	.0015629	.0028616
%RSD	144.7245	150.6772	18.41286	61.61799	777.9529	190.3746	25.21584
#1	-.000011	-.000000	.0150048	.0003634	-.000018	.0021171	.0142357
#2	-.000079	.000067	.0134970	.0001233	-.000041	-.000915	.0085132
#3	.000001	.000007	.0191448	.0005465	.000085	.001260	.0112965

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0004439**	**.0052577**	**.0003115**	**-.000222**	**.0959274**	**-.000223**	**.0001042**
Stddev	.0003422	.0042966	.0004405	.000191	.0827206	.001188	.0015063
%RSD	77.08602	81.71879	141.4052	86.04998	86.23248	531.7375	1445.734
#1	.0002765	.0023399	.0000521	-.000266	.0657090	.000377	.0016370
#2	.0008377	.0032418	.0008201	-.000387	.0325647	-.001592	.0000496
#3	.0002177	.0101916	.0000623	-.000013	.1895084	.000545	-.001374

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0938435**	**.0009977**	**.0049214**	**.0004466**	**.0014058**	**-.000571**	**.0002274**
Stddev	.0588181	.0013153	.0004843	.0001312	.0022905	.002964	.0008831
%RSD	62.67680	131.8294	9.840509	29.36983	162.9337	519.3730	388.4396
#1	.0358391	.0023999	.0047939	.0003520	.0026681	-.000725	-.000114
#2	.0922487	.0008017	.0045137	.0003915	.0027875	-.003454	.001230
#3	.1534429	-.000209	.0054567	.0005963	-.001238	.002468	-.000434


Reviewed By:kareem
On:1/28/2025 12:16:01 PM
Inst Id :P4

Sample Name: CCB024 Acquired: 1/27/2025 20:48:21 Type: Unk
Method: EPA SFAM01.0(v56) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB024 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0007615	-.000557	.0001559
Stddev	.0002630	.000543	.0000360
%RSD	34.54342	97.45740	23.06478
#1	.0006288	.000068	.0001973
#2	.0005912	-.000907	.0001330
#3	.0010645	-.000834	.0001373

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3652.915	76761.84	11342.60	2549.070	4557.907
Stddev	4.694	165.34	37.99	8.929	10.809
%RSD	.1285024	.2153883	.3349265	.3502730	.2371466
#1	3648.222	76578.93	11353.30	2542.153	4545.460
#2	3657.610	76900.66	11374.10	2559.149	4564.930
#3	3652.912	76805.93	11300.41	2545.908	4563.330

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




As 189.042 {479}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000123	Re-Slope:	1.000000
A1 (Gain):	0.057645	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999906	Status:	OK.
Std Error of Est:	0.000013		
Predicted MDL:	0.002522		
Predicted MQL:	0.008406		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00012	.000	1
S1	.01000	.00913	-.001	-8.70	.00040	.000	1
S3	2.5000	2.4565	-.043	-1.74	.14123	.001	1
S4	5.0000	5.0301	.030	.602	.28933	.000	1
S5	10.000	10.065	.065	.651	.57906	.003	1
S2	1.2500	1.1991	-.051	-4.07	.06887	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Tl 190.856 {477}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000069	Re-Slope:	1.000000
A1 (Gain):	0.046951	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999327	Status:	OK.
Std Error of Est:	0.000045		
Predicted MDL:	0.002553		
Predicted MQL:	0.008511		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00007	.000	1
S1	.02500	.02626	.001	5.03	.00125	.000	1
S3	2.5000	2.6125	.112	4.50	.12046	.001	1
S4	5.0000	5.1484	.148	2.97	.23725	.004	1
S5	10.000	9.6688	-.331	-3.31	.44496	.004	1
S2	1.2500	1.3190	.069	5.52	.06087	.001	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Pb 220.353 {453}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000254	Re-Slope:	1.000000
A1 (Gain):	0.221033	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999830	Status:	OK.
Std Error of Est:	0.000153		
Predicted MDL:	0.001381		
Predicted MQL:	0.004603		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00025	.000	1
S1	.01000	.01016	.000	1.60	.00198	.000	1
S3	12.500	12.604	.104	.831	2.7833	.007	1
S4	25.000	25.682	.682	2.73	5.6717	.008	1
S5	50.000	49.216	-.784	-1.57	10.869	.037	1
S2	6.2500	6.2481	-.002	-.030	1.3796	.003	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Se 196.090 {472}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000277	Re-Slope:	1.000000
A1 (Gain):	0.055715	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999980	Status:	OK.
Std Error of Est:	0.000011		
Predicted MDL:	0.003226		
Predicted MQL:	0.010752		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00028	.000	1
S1	.03500	.03419	-.001	-2.30	.00218	.000	1
S3	2.5000	2.4952	-.005	-.192	.13801	.001	1
S4	5.0000	5.0433	.043	.865	.27869	.001	1
S5	10.000	9.9822	-.018	-.178	.55130	.002	1
S2	1.2500	1.2302	-.020	-1.59	.06817	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Sb 206.833 {463}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000093	Re-Slope:	1.000000
A1 (Gain):	0.133233	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999913	Status:	OK.
Std Error of Est:	0.000073		
Predicted MDL:	0.001635		
Predicted MQL:	0.005451		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00009	.000	1
S1	.06000	.05865	-.001	-2.26	.00789	.000	1
S3	2.5000	2.4518	-.048	-1.93	.33119	.001	1
S4	5.0000	5.0402	.040	.804	.68050	.002	1
S5	10.000	10.056	.056	.564	1.3577	.006	1
S2	1.2500	1.2030	-.047	-3.76	.16259	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Al 396.152 { 85}

Date of Fit:	1/28/2025 18:27:03	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000104	Re-Slope:	1.000000
A1 (Gain):	0.012388	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998919	Status:	OK.
Std Error of Est:	0.000358		
Predicted MDL:	0.007305		
Predicted MQL:	0.024351		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00008	.000	.000	.00010	.000	1
S1	.20000	.16973	-.030	-15.1	.00221	.000	1
S3	77.500	71.899	-5.60	-7.23	.89191	.004	1
S4	155.00	148.78	-6.22	-4.02	1.8454	.006	1
S5	310.00	295.25	-14.8	-4.76	3.6621	.042	1
S2	38.750	34.592	-4.16	-10.7	.42919	.001	1
S6	800.00	830.80	30.8	3.85	10.292	.052	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Ba 493.409 { 68}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.004840	Re-Slope:	1.000000
A1 (Gain):	0.418269	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999895	Status:	OK.
Std Error of Est:	0.000643		
Predicted MDL:	0.000772		
Predicted MQL:	0.002574		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00003	.000	.000	.00485	.001	1
S1	.20000	.17814	-.022	-10.9	.07935	.000	1
S3	5.0000	4.9289	-.071	-1.42	2.0664	.020	1
S4	10.000	10.021	.021	.210	4.1963	.041	1
S5	20.000	20.161	.161	.804	8.4375	.044	1
S2	2.5000	2.4112	-.089	-3.55	1.0134	.005	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Be 234.861 {144}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000337	Re-Slope:	1.000000
A1 (Gain):	4.174532	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999841	Status:	OK.
Std Error of Est:	0.000279		
Predicted MDL:	0.000073		
Predicted MQL:	0.000245		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00034	.000	1
S1	.00500	.00538	.000	7.70	.02212	.000	1
S3	.25000	.25048	.000	.193	1.0406	.006	1
S4	.50000	.51140	.011	2.28	2.1251	.010	1
S5	1.0000	.98475	-.015	-1.52	4.0918	.016	1
S2	.12500	.12798	.003	2.39	.53158	.002	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Cd 214.438 {457}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000010	Re-Slope:	1.000000
A1 (Gain):	2.445788	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999714	Status:	OK.
Std Error of Est:	0.000491		
Predicted MDL:	0.000079		
Predicted MQL:	0.000262		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00001	.000	1
S1	.00500	.00498	-.000	-.355	.01218	.000	1
S3	1.2500	1.2722	.022	1.78	3.1176	.009	1
S4	2.5000	2.5821	.082	3.28	6.3272	.012	1
S5	5.0000	4.8931	-.107	-2.14	11.992	.041	1
S2	.62500	.62769	.003	.430	1.5382	.004	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Ca 373.690 { 90}

Date of Fit:	1/28/2025 18:27:03	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000075	Re-Slope:	1.000000
A1 (Gain):	0.008083	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999688	Status:	OK.
Std Error of Est:	0.000705		
Predicted MDL:	0.008730		
Predicted MQL:	0.029099		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00072	.001	.000	.00008	.000	1
S2	62.500	60.143	-2.36	-3.77	.48620	.001	1
S3	125.00	122.84	-2.16	-1.73	.99295	.003	1
S4	250.00	250.36	.360	.144	2.0237	.007	1
S5	500.00	485.05	-15.0	-2.99	3.9207	.002	1
S1	5.0000	4.5741	-.426	-8.52	.03705	.000	1
S6	800.00	819.54	19.5	2.44	6.6243	.033	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Cr 267.716 {126}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000005	Re-Slope:	1.000000
A1 (Gain):	0.147559	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999132	Status:	OK.
Std Error of Est:	0.000182		
Predicted MDL:	0.000409		
Predicted MQL:	0.001362		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00001	.000	1
S1	.01000	.01077	.001	7.68	.00158	.000	1
S3	7.7500	8.1000	.350	4.52	1.1955	.004	1
S4	15.500	16.121	.621	4.00	2.3793	.003	1
S5	31.000	29.797	-1.20	-3.88	4.3980	.021	1
S2	3.8750	4.1061	.231	5.96	.60603	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Co 228.616 {448}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000026	Re-Slope:	1.000000
A1 (Gain):	0.813681	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999863	Status:	OK.
Std Error of Est:	0.000359		
Predicted MDL:	0.000260		
Predicted MQL:	0.000867		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00003	.000	1
S1	.05000	.04917	-.001	-1.66	.04019	.000	1
S3	1.2500	1.2602	.010	.818	1.0293	.002	1
S4	2.5000	2.5612	.061	2.45	2.0918	.003	1
S5	5.0000	4.9291	-.071	-1.42	4.0262	.015	1
S2	.62500	.62523	.000	.037	.51070	.001	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Cu 324.754 {104}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.003050	Re-Slope:	1.000000
A1 (Gain):	0.143032	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999951	Status:	OK.
Std Error of Est:	0.000065		
Predicted MDL:	0.002277		
Predicted MQL:	0.007591		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00305	.000	1
S1	.02500	.02759	.003	10.4	.00700	.000	1
S3	7.5000	7.3368	-.163	-2.18	1.0523	.005	1
S4	15.000	15.069	.069	.459	2.1582	.005	1
S5	30.000	30.144	.144	.480	4.3142	.023	1
S2	3.7500	3.6978	-.052	-1.39	.53190	.001	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Fe 259.837 {130}

Date of Fit:	1/28/2025 18:27:03	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.005002	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999916	Status:	OK.
Std Error of Est:	0.000028		
Predicted MDL:	0.006015		
Predicted MQL:	0.020050		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00000	.000	1
S1	.10000	.09914	-.001	-.860	.00049	.000	1
S3	75.000	76.060	1.06	1.41	.38008	.001	1
S4	150.00	151.95	1.95	1.30	.75932	.004	1
S5	300.00	292.91	-7.09	-2.36	1.4636	.004	1
S2	37.500	37.527	.027	.072	.18752	.001	1
S6	800.00	804.05	4.05	.506	4.0219	.039	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Mn 257.610 {131}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000016	Re-Slope:	1.000000
A1 (Gain):	0.080983	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999880	Status:	OK.
Std Error of Est:	0.000045		
Predicted MDL:	0.000358		
Predicted MQL:	0.001193		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00002	.000	1
S1	.01500	.01477	-.000	-1.54	.00118	.000	1
S3	7.5000	7.5445	.045	.594	.61055	.002	1
S4	15.000	15.356	.356	2.37	1.2427	.004	1
S5	30.000	29.632	-.368	-1.23	2.3980	.017	1
S2	3.7500	3.7181	-.032	-.852	.30087	.001	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Mg 279.079 {121}

Date of Fit:	1/28/2025 18:27:03	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000022	Re-Slope:	1.000000
A1 (Gain):	0.002167	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999287	Status:	OK.
Std Error of Est:	0.000286		
Predicted MDL:	0.017002		
Predicted MQL:	0.056672		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00160	.002	.000	-.00002	.000	1
S2	62.500	57.390	-5.11	-8.18	.12433	.000	1
S3	125.00	118.40	-6.60	-5.28	.25651	.001	1
S4	250.00	245.62	-4.38	-1.75	.53217	.002	1
S5	500.00	486.84	-13.2	-2.63	1.0548	.004	1
S1	5.0000	4.1006	-.899	-18.0	.00886	.000	1
S6	800.00	830.16	30.2	3.77	1.7987	.002	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Ni 231.604 {446}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000227	Re-Slope:	1.000000
A1 (Gain):	0.577224	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999784	Status:	OK.
Std Error of Est:	0.000286		
Predicted MDL:	0.000410		
Predicted MQL:	0.001367		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00023	.000	1
S1	.04000	.04014	.000	.353	.02297	.000	1
S3	1.2500	1.2726	.023	1.81	.73602	.002	1
S4	2.5000	2.5667	.067	2.67	1.4847	.001	1
S5	5.0000	4.9041	-.096	-1.92	2.8373	.010	1
S2	.62500	.63150	.007	1.04	.36514	.001	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Ag 328.068 {103}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000386	Re-Slope:	1.000000
A1 (Gain):	0.268393	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999802	Status:	OK.
Std Error of Est:	0.000043		
Predicted MDL:	0.000364		
Predicted MQL:	0.001213		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00039	.000	1
S1	.01000	.00976	-.000	-2.44	.00221	.000	1
S3	.62500	.60310	-.022	-3.50	.15557	.000	1
S4	1.2500	1.2573	.007	.587	.32525	.000	1
S5	2.5000	2.5284	.028	1.14	.65458	.000	1
S2	.31250	.29890	-.014	-4.35	.07688	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Na 818.326 { 41}

Date of Fit:	1/28/2025 18:27:03	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.002217	Re-Slope:	1.000000
A1 (Gain):	0.002593	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999234	Status:	OK.
Std Error of Est:	0.000314		
Predicted MDL:	0.366559		
Predicted MQL:	1.221865		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00142	.001	.000	-.00221	.001	1
S2	37.500	34.893	-2.61	-6.95	.08825	.000	1
S3	75.000	70.222	-4.78	-6.37	.17986	.001	1
S4	150.00	143.08	-6.92	-4.61	.36876	.001	1
S5	300.00	288.95	-11.1	-3.68	.74697	.004	1
S1	5.0000	4.5014	-.499	-9.97	.00945	.000	1
S6	800.00	825.86	25.9	3.23	2.1391	.005	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




V 292.402 {115}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear
Weighting:	1/Conc		

A0 (Offset):	0.000020	Re-Slope:	1.000000
A1 (Gain):	0.152090	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999797	Status:	OK.
Std Error of Est:	0.000077		
Predicted MDL:	0.001839		
Predicted MQL:	0.006131		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00002	.000	1
S1	.05000	.05088	.001	1.76	.00774	.000	1
S3	1.2500	1.2665	.016	1.32	.18152	.000	1
S4	2.5000	2.5582	.058	2.33	.36685	.001	1
S5	5.0000	4.9118	-.088	-1.76	.70258	.003	1
S2	.62500	.63768	.013	2.03	.09145	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Zn 213.856 {158}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000507	Re-Slope:	1.000000
A1 (Gain):	0.284548	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999940	Status:	OK.
Std Error of Est:	0.000223		
Predicted MDL:	0.001677		
Predicted MQL:	0.005591		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00051	.000	1
S1	.06000	.05542	-.005	-7.63	.01638	.000	1
S3	7.5000	7.4493	-.051	-.676	2.1282	.012	1
S4	15.000	15.098	.098	.655	4.3128	.016	1
S5	30.000	30.096	.096	.321	8.5965	.014	1
S2	3.7500	3.6107	-.139	-3.71	1.0320	.002	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




K 769.896 { 44}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.005394	Re-Slope:	1.000000
A1 (Gain):	0.003621	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999639	Status:	OK.
Std Error of Est:	0.000201		
Predicted MDL:	0.046730		
Predicted MQL:	0.155767		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00106	.001	.000	.00540	.000	1
S2	37.500	34.899	-2.60	-6.94	.13175	.000	1
S3	75.000	72.733	-2.27	-3.02	.26873	.001	1
S4	150.00	151.46	1.46	.971	.55376	.002	1
S5	300.00	304.09	4.09	1.36	1.1064	.001	1
S1	5.0000	4.3258	-.674	-13.5	.02106	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




P 177.495 {490}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.001129	Re-Slope:	1.000000
A1 (Gain):	0.045986	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999577	Status:	OK.
Std Error of Est:	0.000022		
Predicted MDL:	0.002209		
Predicted MQL:	0.007364		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00113	.000	1
S1	.01000	.00840	-.002	-16.0	-.00075	.000	1
S3	2.5000	2.3979	-.102	-4.09	.10832	.001	1
S4	5.0000	5.0701	.070	1.40	.23038	.001	1
S5	10.000	10.136	.136	1.36	.46170	.002	1
S2	1.2500	1.1476	-.102	-8.19	.05124	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




B 249.678 {135}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.001154	Re-Slope:	1.000000
A1 (Gain):	0.422524	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998747	Status:	OK.
Std Error of Est:	0.000303		
Predicted MDL:	0.000767		
Predicted MQL:	0.002556		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00116	.000	1
S1	.01000	.00005	-.010	-99.5	.00096	.000	1
S3	2.5000	2.5868	.087	3.47	.93874	.002	1
S4	5.0000	5.1692	.169	3.38	1.8745	.008	1
S5	10.000	9.6753	-.325	-3.25	3.4677	.009	1
S2	1.2500	1.3298	.080	6.38	.48533	.003	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Mo 202.030 {467}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000139	Re-Slope:	1.000000
A1 (Gain):	0.536349	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999811	Status:	OK.
Std Error of Est:	0.000175		
Predicted MDL:	0.000357		
Predicted MQL:	0.001189		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00014	.000	1
S1	.01000	.01078	.001	7.82	.00592	.000	1
S3	2.5000	2.5467	.047	1.87	1.3661	.004	1
S4	5.0000	5.1015	.102	2.03	2.7363	.006	1
S5	10.000	9.8189	-.181	-1.81	5.2665	.020	1
S2	1.2500	1.2820	.032	2.56	.68776	.002	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




S 182.034 {485}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000106	Re-Slope:	1.000000
A1 (Gain):	0.026841	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999359	Status:	OK.
Std Error of Est:	0.000051		
Predicted MDL:	0.003826		
Predicted MQL:	0.012752		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00003	.000	.000	.00011	.000	1
S1	.10000	.08501	-.015	-15.0	.00239	.000	1
S3	2.5000	2.3816	-.118	-4.74	.06412	.000	1
S4	5.0000	5.0423	.042	.846	.13562	.000	1
S5	10.000	10.211	.211	2.11	.27453	.001	1
S2	1.2500	1.1297	-.120	-9.62	.03047	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Si 251.611 {134}

Date of Fit:	1/28/2025 18:22:38	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000557	Re-Slope:	1.000000
A1 (Gain):	0.038508	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.972785	Status:	OK.
Std Error of Est:	0.000489		
Predicted MDL:	0.004864		
Predicted MQL:	0.016213		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00032	-.000	.000	.00054	.000	1
S1	.10000	.42682	.327	327.	.01699	.000	1
S3	2.5000	2.4303	-.070	-2.79	.09443	.000	1
S4	5.0000	4.9673	-.033	-.653	.19242	.001	1
S5	10.000	9.8052	-.195	-1.95	.37929	.002	1
S2	1.2500	1.2211	-.029	-2.31	.04772	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Sn 189.989 {478}

Date of Fit:	1/28/2025 18:22:39	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000162	Re-Slope:	1.000000
A1 (Gain):	0.146916	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999794	Status:	OK.
Std Error of Est:	0.000042		
Predicted MDL:	0.000799		
Predicted MQL:	0.002662		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00016	.000	1
S1	.00700	.00715	.000	2.07	.00117	.000	1
S3	2.5000	2.5344	.034	1.38	.37137	.001	1
S4	5.0000	5.1435	.144	2.87	.75355	.002	1
S5	10.000	9.8246	-.175	-1.75	1.4390	.005	1
S2	1.2500	1.2473	-.003	-.213	.18285	.001	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Ti 336.121 {100}

Date of Fit:	1/28/2025 18:22:39	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.002092	Re-Slope:	1.000000
A1 (Gain):	0.435919	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999860	Status:	OK.
Std Error of Est:	0.000388		
Predicted MDL:	0.000857		
Predicted MQL:	0.002857		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	.00209	.000	1
S1	.10000	.10223	.002	2.23	.04665	.000	1
S3	2.5000	2.5257	.026	1.03	1.1031	.005	1
S4	5.0000	5.0947	.095	1.89	2.2230	.004	1
S5	10.000	9.8458	-.154	-1.54	4.2940	.014	1
S2	1.2500	1.2816	.032	2.52	.56074	.001	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Li 670.784 { 50}

Date of Fit:	1/28/2025 18:22:39	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000705	Re-Slope:	1.000000
A1 (Gain):	0.144540	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999544	Status:	OK.
Std Error of Est:	0.000090		
Predicted MDL:	0.001169		
Predicted MQL:	0.003896		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00071	.000	1
S5	10.000	10.216	.216	2.16	1.4774	.002	1
S4	5.0000	4.9900	-.010	-.201	.72195	.003	1
S3	2.5000	2.3936	-.106	-4.26	.34668	.002	1
S1	.01500	.01339	-.002	-10.7	.00264	.000	1
S2	1.2500	1.1517	-.098	-7.86	.16718	.000	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Sr 407.771 { 83}

Date of Fit:	1/28/2025 18:22:39	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000058	Re-Slope:	1.000000
A1 (Gain):	1.436114	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999935	Status:	OK.
Std Error of Est:	0.000869		
Predicted MDL:	0.000063		
Predicted MQL:	0.000209		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00007	.000	1
S1	.10000	.09068	-.009	-9.32	.13029	.001	1
S3	2.5000	2.4864	-.014	-.544	3.5708	.009	1
S4	5.0000	5.0743	.074	1.49	7.2873	.027	1
S5	10.000	9.9679	-.032	-.321	14.315	.154	1
S2	1.2500	1.2308	-.019	-1.54	1.7676	.005	1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4




Y 224.306 {450}*

Date of Fit:	1/28/2025 17:56:48	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.000000	Status:	Warning Zero Gain
Std Error of Est:	0.000000		
Predicted MDL:	n/a		
Predicted MQL:	n/a		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



Y 360.073 { 94}*


Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

A2 (Curvature):	0.000000						
n (Exponent):	1.000000						
Correlation:	0.000000			Status:	Warning	Zero Gain	
Std Error of Est:	0.000000						
Predicted MDL:	n/a						
Predicted MQL:	n/a						

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis




Y 371.030 { 91}*

Date of Fit:	<not fit>		Type of Fit:	Linear	Weighting:	1/Conc	
A0 (Offset):		0.000000		Re-Slope:	1.000000		
A1 (Gain):		0.000000		Y-int:	0.000000		
A2 (Curvature):		0.000000					
n (Exponent):		1.000000					
Correlation:		0.000000		Status:	Warning	Zero Gain	
Std Error of Est:		0.000000					
Predicted MDL:		n/a					
Predicted MQL:		n/a					

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis


Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4



Y 224.306 {150}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):	0.000000		Re-Slope:	1.000000	
A1 (Gain):	0.000000		Y-int:	0.000000	
A2 (Curvature):	0.000000				
n (Exponent):	1.000000				
Correlation:	0.000000		Status:	Warning	Zero Gain
Std Error of Est:	0.000000				
Predicted MDL:	n/a				
Predicted MQL:	n/a				

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



In 230.606 {446}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):	0.000000		Re-Slope:	1.000000	
A1 (Gain):	0.000000		Y-int:	0.000000	

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

A2 (Curvature):		0.000000					
n (Exponent):		1.000000					
Correlation:		0.000000		Status:	Warning	Zero Gain	
Std Error of Est:		0.000000					
Predicted MDL:		n/a					
Predicted MQL:		n/a					

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S0 Acquired: 1/28/2025 17:57:32 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00012**	**.00007**	**-.00025**	**.00028**	**.00009**	**.00010**	**.00485**	**-.00034**
Stddev	.00005	.00005	.00029	.00016	.00021	.00006	.00053	.00031
%RSD	42.311	78.909	112.80	58.690	223.32	53.853	10.943	90.942
#1	-.00009	.00004	-.00023	.00028	-.00006	.00013	.00536	.00002
#2	-.00018	.00003	-.00055	.00044	.00001	.00014	.00430	-.00049
#3	-.00010	.00013	.00002	.00012	.00033	.00004	.00489	-.00055

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00001**	**.00008**	**-.00001**	**.00003**	**.00305**	**.00000**	**-.00002**	**-.00002**
Stddev	.00008	.00000	.00001	.00022	.00024	.00003	.00002	.00004
%RSD	812.84	6.1856	251.14	846.03	8.0125	11648.	127.01	208.65
#1	-.00002	.00009	.00001	-.00021	.00331	-.00003	-.00000	-.00004
#2	.00007	.00008	-.00002	.00022	.00300	.00003	-.00000	-.00004
#3	-.00009	.00008	-.00001	.00007	.00283	-.00000	-.00004	.00003

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00023**	**-.00039**	**-.00221**	**.00002**	**.00051**	**.00540**	**-.00113**	**.00116**
Stddev	.00024	.00010	.00140	.00012	.00032	.00022	.00004	.00011
%RSD	103.47	26.273	63.400	583.89	63.480	4.0243	3.6183	9.3318
#1	-.00048	-.00047	-.00281	.00011	.00081	.00564	-.00109	.00107
#2	-.00020	-.00027	-.00061	-.00011	.00055	.00534	-.00112	.00113
#3	-.00001	-.00042	-.00322	.00006	.00017	.00521	-.00117	.00128

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00014**	**.00011**	**.00054**	**.00016**	**.00209**	**.00071**	**.00007**
Stddev	.00005	.00003	.00007	.00006	.00037	.00008	.00008
%RSD	35.639	28.266	13.131	38.810	17.481	11.336	112.35
#1	.00013	.00014	.00056	.00009	.00171	.00076	-.00002
#2	.00009	.00009	.00061	.00022	.00243	.00074	.00011
#3	.00019	.00009	.00047	.00017	.00213	.00061	.00013

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S0 Acquired: 1/28/2025 17:57:32 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3666.6	79491.	11506.	2579.7	4657.4
Stddev	19.5	206.	55.	6.1	13.3
%RSD	.53205	.25917	.47422	.23555	.28528
#1	3686.4	79266.	11458.	2580.9	4672.0
#2	3665.9	79534.	11565.	2585.2	4654.2
#3	3647.4	79671.	11494.	2573.2	4646.0

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S1 Acquired: 1/28/2025 18:01:45 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00040**	**.00125**	**.00198**	**.00218**	**.00789**	**.00221**	**.07935**	**.02212**
Stddev	.00014	.00015	.00026	.00026	.00017	.00003	.00048	.00026
%RSD	35.702	11.938	13.216	12.000	2.1006	1.5700	.60970	1.1552
#1	.00028	.00109	.00181	.00190	.00808	.00223	.07990	.02204
#2	.00037	.00128	.00228	.00242	.00777	.00223	.07899	.02240
#3	.00056	.00139	.00184	.00222	.00783	.00217	.07916	.02191

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.01218**	**.03705**	**.00158**	**.04019**	**.00700**	**.00049**	**.00118**	**.00886**
Stddev	.00010	.00016	.00000	.00016	.00006	.00001	.00002	.00005
%RSD	.81855	.42651	.24742	.40914	.89192	2.7317	1.8521	.60879
#1	.01209	.03723	.00158	.04001	.00706	.00048	.00117	.00881
#2	.01217	.03693	.00158	.04032	.00700	.00048	.00120	.00887
#3	.01229	.03698	.00159	.04025	.00693	.00050	.00116	.00891

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.02297**	**.00221**	**.00945**	**.00774**	**.01638**	**.02106**	**-.00075**	**.00096**
Stddev	.00026	.00009	.00027	.00008	.00018	.00013	.00004	.00007
%RSD	1.1466	4.1129	2.8138	1.0660	1.1162	.62685	5.5919	7.4352
#1	.02316	.00231	.00975	.00779	.01657	.02091	-.00071	.00095
#2	.02308	.00213	.00924	.00765	.01637	.02117	-.00074	.00104
#3	.02267	.00221	.00937	.00779	.01620	.02108	-.00079	.00089

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00592**	**.00239**	**.01699**	**.00117**	**.04665**	**.00264**	**.13029**
Stddev	.00012	.00005	.00011	.00003	.00032	.00005	.00098
%RSD	2.1060	2.0926	.64618	2.4235	.69324	1.9151	.74965
#1	.00597	.00244	.01704	.00115	.04683	.00264	.13129
#2	.00602	.00237	.01687	.00120	.04628	.00259	.13025
#3	.00578	.00235	.01707	.00115	.04685	.00269	.12933

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S1 Acquired: 1/28/2025 18:01:45 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3676.6	79568.	11629.	2560.0	4590.8
Stddev	6.9	182.	29.	12.1	6.6
%RSD	.18706	.22852	.25202	.47366	.14343
#1	3682.9	79462.	11660.	2573.9	4595.4
#2	3669.3	79464.	11603.	2551.7	4583.3
#3	3677.6	79778.	11623.	2554.5	4593.8

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S2 Acquired: 1/28/2025 18:05:59 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.06887**	**.06087**	**1.3796**	**.06817**	**.16259**	**.42919**	**1.0134**	**.53158**
Stddev	.00025	.00058	.0031	.00015	.00033	.00063	.0052	.00234
%RSD	.36781	.94658	.22785	.22442	.20603	.14688	.51553	.44080
#1	.06860	.06095	1.3771	.06809	.16243	.42855	1.0120	.53395
#2	.06910	.06025	1.3786	.06835	.16237	.42921	1.0090	.53154
#3	.06892	.06140	1.3831	.06808	.16298	.42981	1.0192	.52926

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**1.5382**	**.48620**	**.60603**	**.51070**	**.53190**	**.18752**	**.30087**	**.12433**
Stddev	.0044	.00143	.00037	.00145	.00140	.00065	.00125	.00044
%RSD	.28527	.29330	.06093	.28423	.26374	.34752	.41453	.35641
#1	1.5351	.48502	.60646	.50990	.53286	.18687	.29996	.12397
#2	1.5362	.48579	.60581	.50982	.53029	.18752	.30037	.12419
#3	1.5432	.48779	.60583	.51237	.53256	.18818	.30229	.12482

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.36514**	**.07688**	**.08825**	**.09145**	**1.0320**	**.13175**	**.05124**	**.48533**
Stddev	.00101	.00010	.00035	.00008	.0018	.00043	.00010	.00320
%RSD	.27754	.13449	.39375	.08512	.16989	.32402	.19377	.65876
#1	.36448	.07682	.08864	.09139	1.0306	.13126	.05119	.48847
#2	.36463	.07700	.08798	.09142	1.0314	.13203	.05117	.48546
#3	.36630	.07682	.08814	.09153	1.0339	.13197	.05135	.48208

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.68776**	**.03047**	**.04772**	**.18285**	**.56074**	**.16718**	**1.7676**
Stddev	.00176	.00004	.00023	.00089	.00078	.00044	.0051
%RSD	.25519	.13487	.48011	.48833	.13856	.26428	.29020
#1	.68604	.03043	.04751	.18213	.56085	.16722	1.7631
#2	.68770	.03052	.04769	.18257	.55992	.16672	1.7665
#3	.68955	.03047	.04797	.18385	.56147	.16760	1.7732

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S2 Acquired: 1/28/2025 18:05:59 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3500.4	74522.	11596.	2407.1	4089.3
Stddev	5.5	180.	20.	4.3	11.6
%RSD	.15807	.24199	.17084	.18040	.28397
#1	3506.0	74609.	11579.	2403.6	4093.8
#2	3500.2	74643.	11590.	2411.9	4097.9
#3	3494.9	74315.	11618.	2405.7	4076.1

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S3 Acquired: 1/28/2025 18:09:58 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.14123	.12046	2.7833	.13801	.33119	.89191	2.0664	1.0406
Stddev	.00053	.00129	.0075	.00092	.00106	.00367	.0201	.0056
%RSD	.37423	1.0673	.26881	.67006	.32013	.41195	.97466	.54221
#1	.14074	.12006	2.7868	.13727	.33077	.88874	2.0432	1.0441
#2	.14116	.11942	2.7747	.13771	.33041	.89104	2.0774	1.0436
#3	.14179	.12190	2.7884	.13905	.33240	.89594	2.0787	1.0341

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3.1176	.99295	1.1955	1.0293	1.0523	.38008	.61055	.25651
Stddev	.0094	.00271	.0043	.0021	.0052	.00144	.00223	.00077
%RSD	.30146	.27250	.36140	.20826	.49116	.37872	.36606	.30164
#1	3.1205	.99121	1.1944	1.0292	1.0561	.37929	.60989	.25601
#2	3.1071	.99157	1.2003	1.0272	1.0465	.37921	.60871	.25613
#3	3.1253	.99606	1.1919	1.0315	1.0545	.38174	.61304	.25740

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.73602	.15557	.17986	.18152	2.1282	.26873	.10832	.93874
Stddev	.00223	.00015	.00052	.00012	.0121	.00123	.00051	.00199
%RSD	.30270	.09393	.29131	.06355	.56735	.45673	.46674	.21154
#1	.73543	.15549	.18043	.18165	2.1363	.26765	.10817	.94024
#2	.73414	.15548	.17972	.18144	2.1143	.26848	.10790	.93951
#3	.73848	.15574	.17941	.18147	2.1340	.27007	.10888	.93649

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.3661	.06412	.09443	.37137	1.1031	.34668	3.5708
Stddev	.0043	.00029	.00020	.00108	.0054	.00165	.0088
%RSD	.31202	.45204	.21154	.29009	.48877	.47456	.24720
#1	1.3645	.06380	.09456	.37152	1.1048	.34542	3.5652
#2	1.3628	.06417	.09420	.37023	1.0971	.34606	3.5662
#3	1.3709	.06438	.09453	.37237	1.1075	.34854	3.5810

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S3 Acquired: 1/28/2025 18:09:58 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3370.5	72565.	11622.	2309.4	3841.5
Stddev	7.1	188.	42.	7.8	10.3
%RSD	.21161	.25857	.35815	.33713	.26810
#1	3372.4	72732.	11593.	2300.5	3843.8
#2	3376.5	72362.	11604.	2314.6	3850.5
#3	3362.6	72601.	11670.	2313.2	3830.2

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S4 Acquired: 1/28/2025 18:14:02 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.28933	.23725	5.6717	.27869	.68050	1.8454	4.1963	2.1251
Stddev	.00039	.00377	.0080	.00061	.00218	.0060	.0415	.0096
%RSD	.13638	1.5889	.14024	.22038	.32078	.32653	.98870	.45148
#1	.28937	.23352	5.6745	.27813	.68029	1.8523	4.2368	2.1151
#2	.28891	.23719	5.6627	.27860	.67843	1.8413	4.1982	2.1261
#3	.28970	.24106	5.6779	.27935	.68278	1.8426	4.1539	2.1342

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	6.3272	2.0237	2.3793	2.0918	2.1582	.75932	1.2427	.53217
Stddev	.0122	.0073	.0033	.0027	.0052	.00351	.0044	.00227
%RSD	.19321	.35879	.13895	.13166	.23929	.46257	.35290	.42702
#1	6.3208	2.0321	2.3815	2.0923	2.1610	.76321	1.2478	.53479
#2	6.3196	2.0188	2.3755	2.0888	2.1522	.75836	1.2398	.53075
#3	6.3413	2.0202	2.3809	2.0943	2.1613	.75638	1.2406	.53097

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.4847	.32525	.36876	.36685	4.3128	.55376	.23038	1.8745
Stddev	.0014	.00026	.00119	.00110	.0161	.00199	.00125	.0081
%RSD	.09076	.08024	.32357	.29943	.37247	.36026	.54124	.43132
#1	1.4857	.32528	.36856	.36806	4.3298	.55603	.22941	1.8652
#2	1.4832	.32550	.36768	.36590	4.3106	.55228	.22995	1.8782
#3	1.4853	.32498	.37004	.36660	4.2979	.55296	.23179	1.8801

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2.7363	.13562	.19242	.75355	2.2230	.72195	7.2873
Stddev	.0063	.00033	.00107	.00220	.0044	.00289	.0266
%RSD	.23098	.24276	.55381	.29212	.19717	.40003	.36501
#1	2.7326	.13527	.19202	.75114	2.2274	.72517	7.3029
#2	2.7328	.13567	.19161	.75405	2.2186	.71957	7.3024
#3	2.7436	.13592	.19363	.75545	2.2229	.72112	7.2566

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S4 Acquired: 1/28/2025 18:14:02 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3160.3	68691.	11098.	2198.7	3516.8
Stddev	3.6	205.	33.	7.8	3.9
%RSD	.11365	.29794	.30033	.35634	.10997
#1	3159.8	68480.	11107.	2190.5	3517.1
#2	3164.1	68889.	11125.	2199.5	3520.6
#3	3156.9	68705.	11061.	2206.1	3512.8

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S5 Acquired: 1/28/2025 18:18:04 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.57906	.44496	10.869	.55130	1.3577	3.6621	8.4375	4.0918
Stddev	.00287	.00396	.037	.00198	.0057	.0419	.0442	.0159
%RSD	.49517	.88908	.34408	.35935	.42271	1.1454	.52408	.38758
#1	.57754	.44416	10.839	.55027	1.3535	3.6505	8.4715	4.0814
#2	.57727	.44146	10.856	.55004	1.3554	3.6272	8.4533	4.1100
#3	.58236	.44925	10.911	.55358	1.3643	3.7086	8.3875	4.0839

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	11.992	3.9207	4.3980	4.0262	4.3142	1.4636	2.3980	1.0548
Stddev	.041	.0024	.0213	.0150	.0227	.0038	.0167	.0036
%RSD	.34468	.06228	.48429	.37193	.52723	.26096	.69815	.34162
#1	11.961	3.9216	4.3737	4.0128	4.2924	1.4603	2.3904	1.0517
#2	11.975	3.9225	4.4132	4.0235	4.3378	1.4628	2.3864	1.0539
#3	12.039	3.9179	4.4071	4.0424	4.3124	1.4678	2.4172	1.0588

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2.8373	.65458	.74697	.70258	8.5965	1.1064	.46170	3.4677
Stddev	.0095	.00046	.00450	.00330	.0141	.0015	.00161	.0090
%RSD	.33586	.07041	.60215	.47025	.16453	.13289	.34842	.25832
#1	2.8296	.65419	.74346	.70056	8.6095	1.1057	.46087	3.4670
#2	2.8343	.65446	.75204	.70639	8.5986	1.1053	.46068	3.4769
#3	2.8480	.65508	.74539	.70078	8.5814	1.1080	.46356	3.4591

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	5.2665	.27453	.37929	1.4390	4.2940	1.4774	14.315
Stddev	.0202	.00122	.00208	.0054	.0143	.0024	.154
%RSD	.38297	.44491	.54939	.37330	.33333	.16054	1.0725
#1	5.2522	.27394	.37777	1.4359	4.2852	1.4746	14.140
#2	5.2578	.27372	.38167	1.4359	4.3106	1.4787	14.428
#3	5.2896	.27594	.37844	1.4452	4.2864	1.4788	14.377

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S5 Acquired: 1/28/2025 18:18:04 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2934.5	66171.	10916.	2091.6	3230.4
Stddev	8.9	175.	48.	9.2	9.1
%RSD	.30396	.26395	.44090	.44173	.28179
#1	2941.6	66372.	10941.	2082.9	3236.8
#2	2937.4	66063.	10860.	2090.6	3234.4
#3	2924.5	66076.	10946.	2101.3	3220.0

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: S6 Acquired: 1/28/2025 18:22:39 Type: Cal
Method: EPA SFAM01.0(v58) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S06 Custom ID2: Custom ID3:
Comment:

Elem	Al3961	Ca3736	Fe2598	Mg2790	Na8183
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**10.292**	**6.6243**	**4.0219**	**1.7987**	**2.1391**
Stddev	.052	.0329	.0386	.0023	.0048
%RSD	.50141	.49712	.96023	.12547	.22539
#1	10.234	6.6044	3.9841	1.7973	2.1371
#2	10.307	6.6623	4.0205	1.7975	2.1356
#3	10.334	6.6062	4.0613	1.8013	2.1446

Int. Std.	Y_3600	Y_3710
Units	Cts/S	Cts/S
Avg	**60500.**	**10419.**
Stddev	116.	58.
%RSD	.19131	.55384
#1	60542.	10412.
#2	60588.	10480.
#3	60369.	10366.

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: ICV004 Acquired: 1/28/2025 19:08:21 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICV004 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.024072**	**1.080656**	**.9815387**	**.9901187**	**1.052336**	**2.454092**
Stddev	.002816	.017991	.0026185	.0073205	.004353	.016395
%RSD	.2749579	1.664859	.2667783	.7393523	.4136151	.6680699
#1	1.021157	1.067994	.9795567	.9834615	1.050054	2.438892
#2	1.024282	1.072725	.9805521	.9889362	1.049599	2.471465
#3	1.026777	1.101251	.9845072	.9979584	1.057355	2.451919

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.5627036**	**.5030200**	**.4920648**	**10.07143**	**.5475218**	**.4958866**
Stddev	.0027988	.0030089	.0017023	.02899	.0010018	.0010390
%RSD	.4973785	.5981653	.3459396	.2878105	.1829618	.2095336
#1	.5603289	.5057926	.4912732	10.04159	.5478532	.4953172
#2	.5657893	.5034469	.4909024	10.09948	.5483159	.4952567
#3	.5619924	.4998204	.4940186	10.07322	.5463964	.4970859

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4966123**	**9.576807**	**.5699108**	**6.035969**	**.5045477**	**.2289889**
Stddev	.0038909	.046879	.0038233	.016695	.0019185	.0002036
%RSD	.7834804	.4895081	.6708540	.2765993	.3802494	.0888963
#1	.4960086	9.522813	.5658833	6.022862	.5044961	.2288219
#2	.5007698	9.607149	.5734904	6.054766	.5026555	.2292157
#3	.4930586	9.600459	.5703586	6.030280	.5064916	.2289292

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**10.27528**	**.4987958**	**.9583374**	**9.582529**	**5.121295**	F **.0150007**
Stddev	.33611	.0025752	.0032669	.057136	.027320	.0009024
%RSD	3.271030	.5162804	.3408914	.5962523	.5334656	6.015566
#1	10.34105	.4993099	.9546471	9.557184	5.111495	.0150904
#2	9.91115	.5010752	.9608598	9.542449	5.100226	.0140568
#3	10.57364	.4960024	.9595053	9.647953	5.152164	.0158549

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: ICV004 Acquired: 1/28/2025 19:08:21 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICV004 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F -.000409	F .0042013	F .0011405	F .0004284	F -.000379	4.960938
Stddev	.000347	.0010380	.0024441	.0005214	.000607	.021586
%RSD	84.83578	24.70679	214.3035	121.7039	160.2407	.4351186
#1	-.000155	.0053818	.0002670	.0006561	-.000289	4.936463
#2	-.000805	.0037907	.0039013	-.000168	-.001026	4.977261
#3	-.000268	.0034314	-.000747	.000797	.000178	4.969090

Elem	Sr4077
Units	ppm
Avg	F 5.749802
Stddev	.072098
%RSD	1.253917
#1	5.666704
#2	5.786972
#3	5.795730

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3601.369	77743.63	11749.69	2518.855	4370.579
Stddev	4.200	233.96	91.22	8.689	5.629
%RSD	.1166199	.3009415	.7763724	.3449484	.1288007
#1	3604.863	77652.95	11675.63	2510.167	4375.129
#2	3602.535	77568.59	11721.85	2527.544	4372.325
#3	3596.709	78009.36	11851.59	2518.855	4364.284

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: ICB004 Acquired: 1/28/2025 19:12:24 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICB004 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.001037**	**-.000310**	**.0001953**	**.0004497**	**.0008429**	**-.005442**	**-.000054**
Stddev	.001175	.000947	.0016006	.0008182	.0011130	.004174	.000553
%RSD	113.3000	305.5002	819.5513	181.9386	132.0505	76.70182	1031.516
#1	-.000678	-.001301	.0007556	-.000480	-.000298	-.009501	.000192
#2	-.002349	.000587	.0014404	.000769	.001926	-.005666	-.000687
#3	-.000084	-.000216	-.001610	.001060	.000900	-.001161	.000334

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0000000**	**.0000330**	**.0007337**	**.0001013**	**-.000043**	**.0012971**	**.0038621**
Stddev	.0000317	.0000583	.0015360	.0002227	.000082	.0004690	.0017554
%RSD	88162.90	176.7051	209.3464	219.8600	187.8018	36.15962	45.45240
#1	-.000035	.0000725	.0024556	.0000549	-.000126	.0009279	.0022486
#2	.000026	.0000605	.0002410	-.000095	.000037	.0018249	.0057314
#3	.000009	-.000034	-.000495	.000344	-.000042	.0011385	.0036065

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0001542**	**-.010209**	**-.000218**	**.0000320**	**-.032329**	**-.000149**	**.0002471**
Stddev	.0003528	.017599	.000408	.0002081	.276009	.002512	.0028320
%RSD	228.8774	172.3968	187.6664	650.0631	853.7476	1690.742	1146.131
#1	.0002289	-.030155	-.000477	-.000106	.276983	.000934	-.000780
#2	.0004637	.003132	-.000429	.000271	-.120463	.001641	.003449
#3	-.000230	-.003603	.000253	-.000069	-.253507	-.003021	-.001928

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0074191**	**-.000588**	**.0005080**	**-.000106**	**.0015043**	**.0015780**	**.0002664**
Stddev	.0242765	.001755	.0002954	.000129	.0034996	.0015981	.0006070
%RSD	327.2141	298.6133	58.13617	121.3110	232.6467	101.2788	227.8113
#1	.0227279	-.001097	.0002057	-.000132	.0039782	.0028209	.0007051
#2	.0201014	.001366	.0007958	.000034	-.002500	.0021377	.0005205
#3	-.020572	-.002032	.0005226	-.000220	.003034	-.000225	-.000426

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: ICB004 Acquired: 1/28/2025 19:12:24 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICB004 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0002668	.0003494	.0000680
Stddev	.0006123	.0004222	.0000590
%RSD	229.4667	120.8557	86.79928
#1	.0008245	.0004349	.0001362
#2	.0003645	-.000109	.0000363
#3	-.000388	.000722	.0000316

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3671.244	79741.36	11699.87	2550.914	4687.856
Stddev	2.581	99.32	39.27	7.773	7.498
%RSD	.0702918	.1245556	.3356546	.3046995	.1599368
#1	3668.295	79765.82	11707.29	2559.660	4681.074
#2	3672.350	79632.09	11734.90	2544.795	4695.907
#3	3673.088	79826.16	11657.42	2548.289	4686.586

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: ICSA004 Acquired: 1/28/2025 19:29:00 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSA004 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0017704**	**-.002500**	**.0036714**	**.0129850**	**.0049714**	**221.5081**
Stddev	.0035874	.003660	.0020899	.0009780	.0029588	1.4691
%RSD	202.6352	146.4048	56.92415	7.531863	59.51747	.6632342
#1	-.000201	.001128	.0015874	.0129574	.0016447	219.8127
#2	-.000399	-.006192	.0057671	.0120211	.0059603	222.3053
#3	.005911	-.002436	.0036596	.0139765	.0073090	222.4063

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0060213**	**-.000490**	**.0007857**	**233.6179**	**.0600327**	**.0008597**
Stddev	.0002571	.000065	.0001404	1.8097	.0003536	.0003236
%RSD	4.269739	13.21399	17.86802	.7746254	.5889934	37.64158
#1	.0058389	-.000415	.0008233	231.7889	.0596249	.0010111
#2	.0059097	-.000518	.0009034	233.6573	.0602205	.0004882
#3	.0063154	-.000535	.0006303	235.4076	.0602528	.0010799

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.001608**	**97.35675**	**.0188906**	**228.9408**	**.0023882**	**-.001542**
Stddev	.001860	.76480	.0001758	1.9741	.0004680	.000494
%RSD	115.6623	.7855676	.9307195	.8622889	19.59577	32.04019
#1	-.002536	96.55301	.0189462	226.9489	.0027738	-.002106
#2	.000533	97.44173	.0186937	228.9769	.0018675	-.001336
#3	-.002820	98.07551	.0190319	230.8967	.0025234	-.001184

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.321340**	**-.005598**	**-.006593**	**-.072375**	**.0031917**	F **.1375005**
Stddev	.416916	.001562	.001087	.016214	.0034195	.0054265
%RSD	129.7427	27.90014	16.48461	22.40203	107.1400	3.946559
#1	-.506939	-.003795	-.006248	-.059586	.0007905	.1314191
#2	.156145	-.006452	-.007810	-.090611	.0071068	.1392336
#3	-.613228	-.006545	-.005720	-.066929	.0016777	.1418487

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: ICSA004 Acquired: 1/28/2025 19:29:00 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSA004 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000649**	**.0255624**	**.0047724**	**-.003439**	**-.001973**	**.0042078**
Stddev	.000707	.0004087	.0015749	.001113	.000431	.0004693
%RSD	109.0771	1.598940	32.99986	32.37247	21.84313	11.15247
#1	-.000125	.0256363	.0037022	-.003999	-.001487	.0036841
#2	-.000367	.0259291	.0040342	-.002157	-.002126	.0045900
#3	-.001453	.0251217	.0065808	-.004162	-.002307	.0043494

Elem	Sr4077
Units	ppm
Avg	**.0976591**
Stddev	.0006434
%RSD	.6588367
#1	.0969463
#2	.0978342
#3	.0981969

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3248.292**	**70236.97**	**11267.08**	**2258.367**	**3705.150**
Stddev	11.295	412.54	49.05	8.462	5.299
%RSD	.3477131	.5873602	.4352952	.3747096	.1430135
#1	3247.993	70622.63	11214.30	2267.509	3702.067
#2	3259.734	70286.31	11275.69	2256.785	3711.269
#3	3237.151	69801.98	11311.25	2250.807	3702.115

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: ICSAB004 Acquired: 1/28/2025 19:33:14 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSAB004 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0984752**	**.1072255**	**.0536597**	**.0656287**	**.5929165**	**223.1824**
Stddev	.0029852	.0009894	.0005770	.0053840	.0013292	2.3654
%RSD	3.031383	.9227303	1.075223	8.203790	.2241743	1.059833
#1	.1011677	.1073922	.0535994	.0608889	.5919598	225.4878
#2	.0952651	.1081210	.0531153	.0714826	.5944342	223.2980
#3	.0989928	.1061634	.0542645	.0645144	.5923555	220.7613

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4982733**	**.5174900**	**1.013980**	**237.5935**	**.6108018**	**.5125355**
Stddev	.0012214	.0020423	.000844	1.0781	.0029668	.0007996
%RSD	.2451354	.3946557	.0832322	.4537731	.4857283	.1560172
#1	.4987483	.5159934	1.013006	238.6091	.6138452	.5118172
#2	.4968857	.5198166	1.014469	236.4621	.6079180	.5133971
#3	.4991859	.5166599	1.014465	237.7091	.6106423	.5123921

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4931073**	**98.54347**	**.5185856**	**232.4035**	**1.024002**	**.2019991**
Stddev	.0033599	.36492	.0015719	1.1830	.001561	.0005527
%RSD	.6813632	.3703115	.3031191	.5090314	.1524817	.2736112
#1	.4941519	98.86321	.5196438	233.6874	1.022222	.2015335
#2	.4958209	98.14593	.5167793	231.3577	1.025140	.2018538
#3	.4893493	98.62127	.5193336	232.1654	1.024645	.2026099

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.562431**	**.4917839**	**.9649070**	**-.240257**	**.0061078**	F **.1323241**
Stddev	.319505	.0024779	.0024072	.048050	.0021330	.0039637
%RSD	56.80781	.5038595	.2494734	19.99932	34.92309	2.995462
#1	-.841750	.4946000	.9672342	-.197607	.0076552	.1350299
#2	-.631504	.4899378	.9650597	-.292315	.0069936	.1277743
#3	-.214040	.4908137	.9624270	-.230850	.0036746	.1341680

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: ICSAB004 Acquired: 1/28/2025 19:33:14 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSAB004 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000946	.0214703	.0018220	-.004186	-.003214	.0045713
Stddev	.000213	.0027344	.0007225	.001444	.000258	.0004014
%RSD	22.55359	12.73552	39.65152	34.50771	8.034094	8.780004
#1	-.000700	.0187727	.0018252	-.002681	-.003433	.0049526
#2	-.001070	.0242399	.0010980	-.004315	-.003280	.0046090
#3	-.001069	.0213982	.0025429	-.005561	-.002929	.0041525

Elem	Sr4077
Units	ppm
Avg	.0986244
Stddev	.0003287
%RSD	.3333314
#1	.0987391
#2	.0982536
#3	.0988804

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3274.309	70267.09	11201.28	2279.465	3714.032
Stddev	7.441	237.49	38.57	6.907	4.905
%RSD	.2272637	.3379823	.3443161	.3029964	.1320650
#1	3269.066	69993.20	11209.55	2272.461	3715.672
#2	3282.826	70415.96	11159.25	2279.665	3717.907
#3	3271.036	70392.10	11235.04	2286.270	3708.517

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: CCV025 Acquired: 1/28/2025 19:37:18 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV025 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.118387**	**5.034869**	**25.59717**	**5.229792**	**5.249854**	**407.4405**
Stddev	.020649	.043953	.03798	.020641	.025647	.9915
%RSD	.4034223	.8729691	.1483789	.3946767	.4885191	.2433485
#1	5.108573	5.069821	25.57737	5.240854	5.236209	407.9164
#2	5.104475	4.985524	25.57318	5.205978	5.233913	406.3008
#3	5.142112	5.049261	25.64096	5.242544	5.279438	408.1043

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**10.76587**	**.5394792**	**2.625318**	**416.8475**	**16.38113**	**2.629880**
Stddev	.19483	.0016130	.004659	1.3311	.04356	.005863
%RSD	1.809729	.2989970	.1774484	.3193332	.2658977	.2229547
#1	10.58485	.5400304	2.629760	415.7126	16.40446	2.627776
#2	10.97207	.5376628	2.620469	416.5171	16.33088	2.625359
#3	10.74069	.5407443	2.625723	418.3127	16.40806	2.636505

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**16.19001**	**414.9626**	**16.24688**	**414.9139**	**2.619255**	**1.365174**
Stddev	.04347	.8136	.04025	.3680	.004748	.000305
%RSD	.2684750	.1960759	.2477604	.0886959	.1812603	.0223282
#1	16.23867	415.6266	16.27887	415.0088	2.615819	1.365428
#2	16.17633	415.2063	16.26008	415.2252	2.617274	1.365257
#3	16.15503	414.0550	16.20168	414.5078	2.624672	1.364836

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**428.0150**	**2.645803**	**16.07317**	**161.4269**	**5.357741**	F **5.628883**
Stddev	1.3217	.006953	.03898	.2729	.015766	.006153
%RSD	.3087928	.2627923	.2425247	.1690855	.2942698	.1093146
#1	429.3596	2.646561	16.03053	161.6887	5.358964	5.635399
#2	426.7175	2.638501	16.08199	161.4481	5.341398	5.623172
#3	427.9677	2.652345	16.10698	161.1441	5.372859	5.628078

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: CCV025 Acquired: 1/28/2025 19:37:18 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV025 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.200077**	**5.291973**	F **7.594269**	**5.220972**	**5.323204**	**5.374206**
Stddev	.015630	.011864	.016534	.006257	.019727	.015080
%RSD	.3005708	.2241914	.2177167	.1198358	.3705766	.2806021
#1	5.197406	5.297007	7.606397	5.224988	5.345434	5.385308
#2	5.185954	5.278422	7.600974	5.213763	5.307786	5.380272
#3	5.216870	5.300491	7.575436	5.224165	5.316392	5.357037

Elem	Sr4077
Units	ppm
Avg	F **5.619974**
Stddev	.018621
%RSD	.3313308
#1	5.609255
#2	5.641475
#3	5.609192

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3000.040**	**65428.63**	**10603.61**	**2095.602**	**3274.195**
Stddev	8.626	86.18	39.60	12.496	4.601
%RSD	.2875258	.1317173	.3734622	.5963108	.1405286
#1	3005.682	65392.43	10590.57	2104.617	3277.834
#2	3004.328	65527.01	10648.09	2100.852	3275.728
#3	2990.111	65366.46	10572.18	2081.337	3269.023

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: CCB025 Acquired: 1/28/2025 19:41:37 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB025 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0019137**	**-.000083**	**.0006243**	**.0007240**	**-.000469**	**.0037900**	**-.000454**
Stddev	.0008079	.001221	.0008699	.0012439	.000801	.0065336	.000863
%RSD	42.21798	1468.010	139.3375	171.8009	170.7863	172.3897	190.1486
#1	.0028380	-.001476	.0012698	-.000368	-.000254	-.003579	-.000294
#2	.0015608	.000426	-.000365	.000461	-.001356	.006073	-.001385
#3	.0013422	.000800	.000968	.002078	.000202	.008875	.000318

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0000139**	**-.000018**	**.0010109**	**.0001979**	**-.000092**	**.0021652**	**.0098070**
Stddev	.0000967	.000057	.0030830	.0001717	.000177	.0009150	.0034248
%RSD	697.4076	319.7116	304.9882	86.72548	193.1154	42.25730	34.92139
#1	-.000004	-.000042	.0044394	.0001958	-.000147	.0021446	.0099104
#2	-.000073	-.000059	.0001266	.0003706	-.000235	.0030904	.0131789
#3	.000118	.000048	-.001533	.0000274	.000106	.0012608	.0063318

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0002781**	**-.007657**	**-.000101**	**-.000081**	**-.038172**	**.0004309**	**-.000520**
Stddev	.0000488	.013290	.000130	.000118	.064028	.0028684	.001052
%RSD	17.56015	173.5656	128.5273	145.9789	167.7325	665.6527	202.1730
#1	.0002271	-.017348	-.000031	-.000000	-.029417	-.002494	-.001730
#2	.0002830	.007493	-.000251	-.000216	.021027	.003239	-.000014
#3	.0003244	-.013117	-.000021	-.000026	-.106127	.000548	.000183

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0046217**	**.0006761**	**.0037635**	**-.000013**	**-.000449**	**.0036685**	**.0001907**
Stddev	.0305312	.0013036	.0008744	.000309	.000498	.0036933	.0008775
%RSD	660.6060	192.8165	23.23467	2443.360	111.0329	100.6767	460.0838
#1	-.023561	.0019547	.0034935	.000121	.000125	.0079309	.0005808
#2	.037056	-.000651	.0030559	.000207	-.000777	.0014187	.0008055
#3	.000370	.000725	.0047411	-.000366	-.000694	.0016558	-.000814

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: CCB025 Acquired: 1/28/2025 19:41:37 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB025 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0001849	-.000352	.0000605
Stddev	.0004669	.001454	.0000711
%RSD	252.5298	412.7705	117.5467
#1	-.000307	.001299	.0001417
#2	.000239	-.000913	.0000088
#3	.000623	-.001443	.0000311

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3734.858	79917.57	11577.30	2580.528	4769.529
Stddev	8.371	175.54	105.71	14.315	11.384
%RSD	.2241264	.2196532	.9131062	.5547177	.2386876
#1	3742.094	79851.96	11505.07	2578.144	4780.085
#2	3736.789	80116.47	11698.63	2595.885	4771.037
#3	3725.690	79784.29	11528.19	2567.555	4757.466

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1136-02 Acquired: 1/28/2025 19:45:45 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0147780**	**.0069812**	**.0068284**	**-.003376**	**-.001624**	**33.81171**
Stddev	.0005629	.0008576	.0006384	.000902	.000872	.17705
%RSD	3.809333	12.28377	9.349771	26.70711	53.72408	.5236490
#1	.0142164	.0071950	.0061497	-.004294	-.002397	33.62962
#2	.0147754	.0060369	.0074170	-.003341	-.000678	33.82224
#3	.0153422	.0077115	.0069183	-.002492	-.001796	33.98326

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0410467**	**.0028413**	**.0016578**	**53.08451**	**.0332094**	**.1134061**
Stddev	.0003308	.0000433	.0000322	.11781	.0001827	.0006442
%RSD	.8059867	1.524955	1.940036	.2219258	.5500661	.5680038
#1	.0409200	.0028815	.0016693	52.94848	.0329989	.1127534
#2	.0407980	.0027954	.0016827	53.15215	.0333274	.1134235
#3	.0414222	.0028469	.0016215	53.15291	.0333018	.1140414

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1250833**	**13.09764**	**2.442305**	**24.74865**	**.1068792**	**-.002578**
Stddev	.0011669	.05456	.006388	.06552	.0002217	.000098
%RSD	.9328981	.4165267	.2615703	.2647573	.2074056	3.820053
#1	.1237421	13.03512	2.434951	24.67354	.1071243	-.002494
#2	.1256420	13.13561	2.446487	24.79408	.1066927	-.002686
#3	.1258659	13.12218	2.445475	24.77833	.1068206	-.002553

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**2.479239**	**.0247641**	**.5181907**	**12.91934**	**.5906014**	**.2939675**
Stddev	.108049	.0002136	.0028850	.07600	.0035165	.0001100
%RSD	4.358155	.8625757	.5567504	.5882696	.5954147	.0374341
#1	2.409450	.0246002	.5207099	12.84025	.5873207	.2938497
#2	2.424570	.0246864	.5188190	12.92595	.5901697	.2939851
#3	2.603698	.0250057	.5150434	12.99182	.5943139	.2940677

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1136-02 Acquired: 1/28/2025 19:45:45 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0001113	F 325.3368	F 22.74824	-.001405	.0134576	.0249069
Stddev	.0000381	.3611	.05435	.000787	.0003290	.0001612
%RSD	34.23355	.1109790	.2388983	56.04197	2.445005	.6472893
#1	.0000891	325.5031	22.80922	-.002119	.0130974	.0248633
#2	.0000895	324.9225	22.73057	-.001535	.0135330	.0250855
#3	.0001553	325.5847	22.70493	-.000561	.0137424	.0247720

Elem	Sr4077
Units	ppm
Avg	.2973897
Stddev	.0017260
%RSD	.5803752
#1	.2956431
#2	.2974318
#3	.2990943

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7553.949	164353.0	24800.55	5250.213	4243.696
Stddev	30.305	334.7	76.25	21.444	14.717
%RSD	.4011777	.2036189	.3074727	.4084340	.3468083
#1	7584.121	164674.1	24752.70	5236.826	4255.065
#2	7554.213	164006.3	24760.46	5238.867	4248.951
#3	7523.513	164378.7	24888.49	5274.946	4227.073

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1136-03 Acquired: 1/28/2025 19:49:44 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0151549**	**.0065648**	**.0074004**	**-.004706**	**-.001385**	**34.72050**
Stddev	.0005877	.0009288	.0012188	.001143	.000603	.23862
%RSD	3.877934	14.14767	16.46952	24.29916	43.57525	.6872476
#1	.0144764	.0064606	.0062159	-.003765	-.002047	34.47433
#2	.0155056	.0056925	.0086508	-.004374	-.000866	34.95077
#3	.0154827	.0075413	.0073346	-.005979	-.001241	34.73638

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0425579**	**.0028050**	**.0015834**	**54.54164**	**.0333956**	**.1130793**
Stddev	.0004030	.0000554	.0001409	.23334	.0001359	.0005026
%RSD	.9470137	1.974231	8.895324	.4278146	.4069237	.4444969
#1	.0421952	.0028592	.0016924	54.28491	.0332987	.1133262
#2	.0429918	.0028071	.0016334	54.74080	.0333372	.1125009
#3	.0424869	.0027486	.0014244	54.59922	.0335509	.1134107

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1273432**	**13.42806**	**2.520961**	**25.50848**	**.1067633**	**-.002570**
Stddev	.0002995	.08941	.011886	.08916	.0007250	.000151
%RSD	.2352132	.6658636	.4715029	.3495343	.6790816	5.864099
#1	.1276313	13.33208	2.507857	25.42134	.1066232	-.002454
#2	.1270334	13.50900	2.531049	25.59953	.1061186	-.002740
#3	.1273649	13.44310	2.523978	25.50456	.1075482	-.002515

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**2.542568**	**.0249352**	**.5288804**	**13.21984**	**.5820108**	**.2940947**
Stddev	.041329	.0005237	.0031533	.09524	.0045604	.0013867
%RSD	1.625502	2.100306	.5962237	.7203980	.7835567	.4715205
#1	2.525063	.0248900	.5252461	13.13256	.5780340	.2954643
#2	2.512872	.0244356	.5308917	13.32142	.5810099	.2926915
#3	2.589769	.0254801	.5305032	13.20555	.5869885	.2941284

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1136-03 Acquired: 1/28/2025 19:49:44 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7D Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0000420	F 320.3798	F 23.09086	-.002541	.0136097	.0260836
Stddev	.0001253	.1553	.03674	.000670	.0006286	.0001740
%RSD	297.8778	.0484885	.1591002	26.34812	4.618481	.6669719
#1	-.000058	320.4137	23.13288	-.002561	.0143279	.0260483
#2	.000183	320.2103	23.06481	-.001862	.0133420	.0262726
#3	.000002	320.5155	23.07489	-.003201	.0131594	.0259300

Elem	Sr4077
Units	ppm
Avg	.3071698
Stddev	.0025483
%RSD	.8295891
#1	.3043469
#2	.3093003
#3	.3078623

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7603.134	161980.4	24877.08	5200.427	4260.381
Stddev	30.353	107.4	166.00	4.146	11.448
%RSD	.3992185	.0662842	.6672679	.0797152	.2686985
#1	7637.278	161961.1	24706.58	5198.282	4271.882
#2	7592.915	162096.1	25038.18	5205.205	4260.273
#3	7579.209	161884.0	24886.49	5197.793	4248.988

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1136-02LX5 Acquired: 1/28/2025 19:53:42 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0061676**	**.0031680**	**.0026969**	**-.002109**	**-.000624**	**11.77968**
Stddev	.0018760	.0001571	.0010787	.001471	.000490	.12082
%RSD	30.41712	4.957291	39.99864	69.73279	78.47322	1.025684
#1	.0083335	.0029942	.0021448	-.002876	-.000065	11.72811
#2	.0050534	.0032997	.0039400	-.000413	-.000978	11.91774
#3	.0051159	.0032101	.0020060	-.003038	-.000828	11.69321

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0162199**	**.0009920**	**.0002471**	**18.81616**	**.0118016**	**.0227751**
Stddev	.0006541	.0000255	.0000665	.09421	.0002899	.0000347
%RSD	4.032672	2.573051	26.92489	.5006862	2.456890	.1524458
#1	.0164583	.0009681	.0001822	18.73599	.0114787	.0227418
#2	.0154800	.0010189	.0003151	18.91992	.0120397	.0227722
#3	.0167213	.0009890	.0002438	18.79255	.0118865	.0228111

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0468268**	**4.718418**	**.8897972**	**8.660730**	**.0218343**	**-.000856**
Stddev	.0012120	.026330	.0052829	.028672	.0004246	.000064
%RSD	2.588181	.5580280	.5937155	.3310597	1.944672	7.449954
#1	.0454421	4.710181	.8856573	8.630719	.0213785	-.000911
#2	.0476949	4.747882	.8957471	8.663628	.0219056	-.000871
#3	.0473432	4.697191	.8879870	8.687843	.0222187	-.000786

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.7568630**	**.0091844**	**.1799570**	**4.301281**	**.1154171**	**.1065679**
Stddev	.3122256	.0009987	.0022527	.044758	.0009630	.0009183
%RSD	41.25259	10.87433	1.251796	1.040570	.8343615	.8616986
#1	1.097422	.0084628	.1774526	4.274533	.1143424	.1075552
#2	.689049	.0103242	.1818179	4.352952	.1157074	.1057393
#3	.484117	.0087660	.1806006	4.276358	.1162016	.1064093

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1136-02LX5 Acquired: 1/28/2025 19:53:42 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7L Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000057	F 65.49333	8.229046	-.000948	.0056128	.0088958
Stddev	.000192	.18024	.029320	.000072	.0005797	.0008041
%RSD	333.6048	.2752023	.3563017	7.563344	10.32865	9.038934
#1	.000065	65.38461	8.225209	-.001028	.0050435	.0082660
#2	-.000278	65.39399	8.201833	-.000929	.0055925	.0086199
#3	.000041	65.70138	8.260095	-.000889	.0062024	.0098015

Elem	Sr4077
Units	ppm
Avg	.1045974
Stddev	.0013171
%RSD	1.259252
#1	.1039208
#2	.1061153
#3	.1037560

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4484.515	95841.91	14255.51	3114.470	4480.574
Stddev	11.733	185.84	166.92	8.228	4.751
%RSD	.2616315	.1939025	1.170905	.2641715	.1060408
#1	4488.300	95989.34	14214.23	3123.854	4484.120
#2	4493.889	95903.23	14439.20	3108.497	4482.427
#3	4471.357	95633.16	14113.11	3111.058	4475.176

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1136-04 Acquired: 1/28/2025 19:57:45 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7S Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0352516**	**.0580033**	**.0286544**	**.0465898**	**.0453682**	**35.98168**
Stddev	.0006978	.0022432	.0015008	.0014407	.0012720	.29796
%RSD	1.979550	3.867300	5.237533	3.092219	2.803615	.8280977
#1	.0344578	.0561194	.0297511	.0469845	.0441495	35.64532
#2	.0355285	.0574057	.0269440	.0477920	.0452676	36.08720
#3	.0357685	.0604847	.0292681	.0449930	.0466874	36.21253

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.9615274**	**.0277737**	**.0534311**	**55.32377**	**.1380373**	**.6239273**
Stddev	.0133308	.0003701	.0003113	.25439	.0004053	.0015238
%RSD	1.386416	1.332573	.5826921	.4598212	.2936436	.2442213
#1	.9461881	.0281956	.0536852	55.03900	.1384510	.6239536
#2	.9680840	.0276214	.0530838	55.40375	.1380199	.6223906
#3	.9703102	.0275040	.0535242	55.52856	.1376409	.6254378

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2529781**	**14.03462**	**2.845161**	**25.78346**	**.6242395**	**.0159009**
Stddev	.0017735	.09398	.018888	.04968	.0015137	.0001040
%RSD	.7010513	.6696481	.6638782	.1926661	.2424857	.6539159
#1	.2509336	13.93288	2.823499	25.72767	.6253267	.0157853
#2	.2541020	14.05278	2.853793	25.82290	.6225107	.0159868
#3	.2538986	14.11820	2.858191	25.79980	.6248811	.0159307

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**2.583270**	**.2691659**	**.7781836**	**13.12044**	**.6031810**	**.2936667**
Stddev	.146648	.0004904	.0080359	.15455	.0045107	.0015613
%RSD	5.676856	.1821967	1.032643	1.177931	.7478183	.5316709
#1	2.521964	.2692604	.7749202	12.94806	.6032870	.2954591
#2	2.750623	.2686352	.7873378	13.16662	.5986183	.2929388
#3	2.477222	.2696022	.7722928	13.24664	.6076378	.2926023

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1136-04 Acquired: 1/28/2025 19:57:45 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7S Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000119**	F **330.8813**	F **23.79579**	**-.002187**	**.0131760**	**.0272457**
Stddev	.000251	.9827	.05948	.000498	.0002075	.0006184
%RSD	210.1684	.2969918	.2499688	22.76488	1.574871	2.269516
#1	-.000139	330.7629	23.85558	-.001852	.0132741	.0268345
#2	.000141	329.9632	23.79519	-.002759	.0133162	.0279568
#3	-.000360	331.9178	23.73662	-.001950	.0129376	.0269458

Elem	Sr4077
Units	ppm
Avg	**.3134672**
Stddev	.0038646
%RSD	1.232866
#1	.3090467
#2	.3151480
#3	.3162067

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**7461.474**	**162949.5**	**25001.48**	**5243.595**	**4165.726**
Stddev	29.489	21.8	215.57	15.488	18.613
%RSD	.3952190	.0133964	.8622255	.2953718	.4468062
#1	7490.847	162968.1	24756.50	5242.024	4176.746
#2	7461.706	162955.1	25085.80	5228.952	4176.197
#3	7431.870	162925.5	25162.15	5259.808	4144.236

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-01 Acquired: 1/28/2025 20:01:39 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.7739310	-.716565	2.149432	.4322301	5.496121	14.20943
Stddev	.0035123	.024018	.006217	.0080677	.028317	.03526
%RSD	.4538203	3.351868	.2892275	1.866527	.5152117	.2481247
#1	.7772865	-.731958	2.155764	.4319829	5.522180	14.24865
#2	.7702806	-.728848	2.143337	.4242889	5.465988	14.18038
#3	.7742260	-.688889	2.149195	.4404186	5.500197	14.19925

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.3811330	.0414587	.0118606	87.07797	F 322.2298	F 117.7215
Stddev	.0009213	.0002367	.0000572	.31534	.6719	.6667
%RSD	.2417324	.5709142	.4821676	.3621399	.2085031	.5662966
#1	.3821920	.0414573	.0118215	87.43886	322.0563	117.0907
#2	.3806909	.0412228	.0118341	86.93950	322.9714	117.6548
#3	.3805160	.0416961	.0119262	86.85556	321.6617	118.4190

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	3.327391	138.1456	2.253830	12.64228	F 98.25901	.0086273
Stddev	.005291	.3976	.001731	.09338	.64036	.0001617
%RSD	.1590252	.2877838	.0768099	.7386368	.6517055	1.874047
#1	3.325254	138.6046	2.255422	12.70343	97.94289	.0086609
#2	3.333417	137.9189	2.251987	12.68861	97.83818	.0084514
#3	3.323503	137.9132	2.254081	12.53479	98.99596	.0087695

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	36.46556	1.830980	5.068877	2.172824	3.131673	1.001341
Stddev	.51616	.015232	.077075	.022853	.009992	.003178
%RSD	1.415483	.8319140	1.520563	1.051743	.3190543	.3173434
#1	36.10901	1.821054	5.140054	2.184262	3.141927	1.003477
#2	37.05745	1.823370	5.079560	2.146511	3.121966	.997689
#3	36.23021	1.848518	4.987018	2.187700	3.131125	1.002857

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-01 Acquired: 1/28/2025 20:01:39 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F 97.59689	F 173.3436	7.123264	.3403215	.3812290	.0202916
Stddev	.29849	.7823	.005615	.0003477	.0023210	.0021982
%RSD	.3058441	.4513058	.0788234	.1021684	.6088218	10.83286
#1	97.58978	174.2354	7.125565	.3404131	.3827502	.0215395
#2	97.30202	172.7735	7.127363	.3399372	.3823792	.0177535
#3	97.89888	173.0217	7.116864	.3406142	.3785575	.0215817

Elem	Sr4077
Units	ppm
Avg	.8446854
Stddev	.0011904
%RSD	.1409254
#1	.8449794
#2	.8433756
#3	.8457013

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1920.251	74057.51	11657.61	1883.154	3827.234
Stddev	9.187	250.50	51.77	26.643	8.736
%RSD	.4784460	.3382563	.4440741	1.414784	.2282464
#1	1926.063	73852.76	11642.53	1856.095	3822.722
#2	1925.031	73982.95	11615.06	1884.006	3837.303
#3	1909.659	74336.83	11715.25	1909.360	3821.677

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-01DLX10 Acquired: 1/28/2025 20:05:56 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0691838**	**-.104911**	**.2144700**	**.0285724**	**.1133862**	**1.366862**
Stddev	.0012502	.001935	.0014015	.0017878	.0107617	.022601
%RSD	1.807009	1.843973	.6534884	6.257093	9.491225	1.653495
#1	.0685296	-.105248	.2153976	.0289781	.1015707	1.391978
#2	.0683964	-.106655	.2128578	.0266167	.1159607	1.360443
#3	.0706253	-.102831	.2151547	.0301226	.1226272	1.348164

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0320396**	**.0020597**	**.0009941**	**8.186777**	F **50.23631**	F **12.33794**
Stddev	.0002185	.0000868	.0000369	.075931	.68669	.05699
%RSD	.6820676	4.213724	3.716089	.9274800	1.366921	.4619167
#1	.0322884	.0019781	.0010356	8.274040	51.02710	12.29736
#2	.0318789	.0021509	.0009817	8.150519	49.89118	12.31336
#3	.0319515	.0020503	.0009649	8.135772	49.79064	12.40310

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.3272525**	**13.14004**	**.2105533**	**1.183044**	F **10.42881**	**.0006670**
Stddev	.0017364	.09286	.0026093	.004264	.04736	.0001196
%RSD	.5305839	.7067005	1.239267	.3604313	.4540825	17.92507
#1	.3287016	13.24589	.2135221	1.186912	10.39731	.0005616
#2	.3253279	13.10195	.2095140	1.183749	10.40585	.0006425
#3	.3277279	13.07229	.2086238	1.178471	10.48326	.0007969

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**3.486633**	**.2137508**	**.3497255**	**-.000594**	**.2881732**	**.0898802**
Stddev	.196833	.0053095	.0043454	.017243	.0026707	.0005731
%RSD	5.645361	2.483952	1.242503	2904.001	.9267749	.6376514
#1	3.701307	.2198744	.3547412	.018680	.2888652	.0893104
#2	3.314646	.2109459	.3473351	-.005905	.2852246	.0904566
#3	3.443947	.2104320	.3471001	-.014557	.2904298	.0898736

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-01DLX10 Acquired: 1/28/2025 20:05:56 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	6.510186	F 16.48000	.7541040	.0338500	.0407980	.0005958
Stddev	.016428	.03936	.0118915	.0006330	.0009102	.0004652
%RSD	.2523422	.2388137	1.576905	1.870118	2.231040	78.08553
#1	6.502099	16.46046	.7495817	.0332929	.0416232	.0000942
#2	6.499369	16.45423	.7675932	.0337188	.0398217	.0006802
#3	6.529089	16.52530	.7451370	.0345384	.0409493	.0010131

Elem	Sr4077
Units	ppm
Avg	.0740663
Stddev	.0008596
%RSD	1.160606
#1	.0750531
#2	.0736655
#3	.0734802

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3538.139	79071.80	11108.09	2520.067	4554.664
Stddev	8.437	551.26	16.86	20.027	16.118
%RSD	.2384578	.6971698	.1518164	.7947132	.3538863
#1	3541.457	78440.53	11104.49	2500.305	4561.943
#2	3544.412	79316.57	11093.33	2540.350	4565.859
#3	3528.547	79458.29	11126.47	2519.546	4536.190

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-02DLX2 Acquired: 1/28/2025 20:10:02 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ1 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0531038	-.033761	1.463034	.0241722	.0249779	22.08972
Stddev	.0005366	.001760	.001379	.0011329	.0023079	.13158
%RSD	1.010550	5.214489	.0942640	4.686681	9.239530	.5956843
#1	.0536197	-.033115	1.462909	.0228660	.0234415	22.22495
#2	.0531432	-.032415	1.461722	.0247634	.0276318	21.96212
#3	.0525486	-.035754	1.464472	.0248872	.0238606	22.08208

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1564410	.0023648	.0035690	16.58536	14.07433	F 6.016998
Stddev	.0010180	.0000624	.0000433	.06548	.05607	.005384
%RSD	.6507068	2.636843	1.213865	.3948021	.3983968	.0894815
#1	.1573978	.0024310	.0035192	16.65429	14.13477	6.023210
#2	.1565540	.0023072	.0035906	16.52399	14.02401	6.013674
#3	.1553712	.0023562	.0035973	16.57781	14.06422	6.014110

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.7019743	62.35863	.4799384	9.681554	F 5.837373	.0002468
Stddev	.0082688	.24005	.0032749	.029665	.003823	.0002581
%RSD	1.177931	.3849510	.6823610	.3064115	.0654995	104.5782
#1	.7114678	62.60340	.4837198	9.714710	5.841787	.0002612
#2	.6981092	62.12359	.4780705	9.657523	5.835238	-.000018
#3	.6963458	62.34889	.4780248	9.672428	5.835093	.000497

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	17.56608	.1479695	1.039820	4.857974	5.894674	.1743887
Stddev	.33622	.0025779	.005177	.026026	.007719	.0003808
%RSD	1.914025	1.742147	.4978632	.5357444	.1309479	.2183885
#1	17.84280	.1509058	1.044068	4.872905	5.888362	.1747650
#2	17.19190	.1469238	1.034054	4.873095	5.903280	.1740035
#3	17.66355	.1460787	1.041339	4.827921	5.892381	.1743976

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-02DLX2 Acquired: 1/28/2025 20:10:02 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ1 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.8897201	F 53.10561	6.344822	.0448655	.5879901	.0366947
Stddev	.0008922	.04646	.048376	.0002194	.0040206	.0021783
%RSD	.1002808	.0874910	.7624444	.4891273	.6837876	5.936372
#1	.8907445	53.08586	6.396958	.0448816	.5923709	.0361125
#2	.8893030	53.15868	6.336121	.0450764	.5844687	.0348666
#3	.8891129	53.07228	6.301388	.0446384	.5871306	.0391050

Elem	Sr4077
Units	ppm
Avg	.2354466
Stddev	.0014453
%RSD	.6138585
#1	.2371073
#2	.2347596
#3	.2344730

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3698.859	82563.65	12228.19	2612.282	4347.870
Stddev	7.485	87.37	48.21	5.791	7.073
%RSD	.2023639	.1058169	.3942133	.2216710	.1626775
#1	3691.463	82467.18	12172.83	2612.427	4340.231
#2	3698.682	82637.45	12260.89	2606.420	4349.185
#3	3706.430	82586.32	12250.85	2617.999	4354.193

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-03DLX2 Acquired: 1/28/2025 20:13:56 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ2 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0438953	-.005719	.8073661	.0201898	.0106556	18.71914
Stddev	.0025156	.003309	.0024370	.0017763	.0007415	.08134
%RSD	5.730798	57.86289	.3018473	8.797887	6.958579	.4345432
#1	.0419987	-.003416	.8066493	.0201042	.0112601	18.75787
#2	.0467489	-.009511	.8100811	.0220073	.0108786	18.62567
#3	.0429384	-.004230	.8053679	.0184579	.0098283	18.77389

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1800270	.0045485	.0078113	8.827675	1.001663	4.394044
Stddev	.0014404	.0000610	.0000708	.042474	.004208	.006398
%RSD	.8000724	1.340287	.9061321	.4811454	.4201404	.1456102
#1	.1816387	.0045603	.0078682	8.871296	1.003958	4.386869
#2	.1788654	.0044824	.0078335	8.786449	.996806	4.399156
#3	.1795769	.0046026	.0077320	8.825279	1.004225	4.396107

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.6521810	50.44420	.2985998	4.778823	2.657837	.0002101
Stddev	.0048732	.18519	.0024551	.047723	.005221	.0001519
%RSD	.7472118	.3671204	.8222028	.9986319	.1964555	72.30113
#1	.6577922	50.53820	.3003150	4.756179	2.652140	.0002052
#2	.6497411	50.23086	.2957874	4.746637	2.662395	.0000607
#3	.6490097	50.56353	.2996969	4.833652	2.658976	.0003644

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	11.76120	.0848923	1.179939	1.458695	1.432556	.1209167
Stddev	.44268	.0004447	.011236	.044914	.004679	.0023038
%RSD	3.763902	.5238566	.9522701	3.079065	.3266337	1.905252
#1	12.15383	.0845089	1.192279	1.467621	1.436657	.1225765
#2	11.28143	.0853799	1.170298	1.409988	1.433553	.1182865
#3	11.84835	.0847882	1.177241	1.498476	1.427459	.1218870

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-03DLX2 Acquired: 1/28/2025 20:13:56 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ2 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0756595	F 30.99597	4.831500	.0387335	.3580009	.0156858
Stddev	.0000803	.06689	.017326	.0002571	.0016084	.0003325
%RSD	.1061012	.2157968	.3586050	.6637665	.4492641	2.119636
#1	.0756245	30.95805	4.851274	.0385874	.3594736	.0159721
#2	.0756027	31.07321	4.824246	.0385827	.3562846	.0157641
#3	.0757514	30.95667	4.818981	.0390303	.3582446	.0153212

Elem	Sr4077
Units	ppm
Avg	.1138087
Stddev	.0012632
%RSD	1.109966
#1	.1150778
#2	.1125514
#3	.1137969

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3842.257	84027.18	12402.84	2720.963	4393.871
Stddev	2.988	312.09	8.00	19.726	3.760
%RSD	.0777547	.3714183	.0645318	.7249587	.0855715
#1	3845.589	83774.36	12401.25	2708.820	4390.694
#2	3841.367	84375.99	12395.75	2743.724	4392.898
#3	3839.816	83931.18	12411.52	2710.347	4398.022

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-05DLX2 Acquired: 1/28/2025 20:17:52 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ4 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0476604**	**-.009210**	**.6583301**	**.0263107**	**.0100935**	**38.13962**
Stddev	.0023137	.001360	.0014053	.0032861	.0005422	.24829
%RSD	4.854577	14.76801	.2134674	12.48943	5.371251	.6510035
#1	.0460670	-.008816	.6571019	.0298113	.0099624	37.85415
#2	.0503142	-.008090	.6580259	.0232925	.0096289	38.25941
#3	.0465998	-.010723	.6598627	.0258282	.0106892	38.30531

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1443100**	**.0042391**	**.0052857**	**12.19573**	**2.475532**	**2.885098**
Stddev	.0003154	.0001658	.0000630	.03285	.011424	.002210
%RSD	.2185418	3.912365	1.192394	.2693281	.4614665	.0766047
#1	.1440256	.0043646	.0052896	12.15944	2.486683	2.883583
#2	.1442551	.0043015	.0053467	12.22343	2.476060	2.884077
#3	.1446492	.0040510	.0052209	12.20432	2.463853	2.887634

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.3257633**	**92.81062**	**.7711747**	**16.04857**	**2.253386**	**-.000788**
Stddev	.0011677	.35251	.0042075	.08226	.003656	.000355
%RSD	.3584484	.3798135	.5456013	.5125673	.1622581	45.08749
#1	.3261540	92.48775	.7664007	16.03064	2.252030	-.000741
#2	.3244504	93.18671	.7727804	16.13831	2.250601	-.000458
#3	.3266856	92.75739	.7743429	15.97675	2.257526	-.001164

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**26.41560**	**.1167141**	**1.085776**	**8.914875**	**4.186017**	**.1970575**
Stddev	.21922	.0005494	.002836	.050710	.008800	.0031192
%RSD	.8298815	.4707277	.2611973	.5688234	.2102120	1.582877
#1	26.39400	.1171477	1.088089	8.857358	4.184980	.1934582
#2	26.64481	.1160963	1.086628	8.953141	4.177782	.1989711
#3	26.20797	.1168984	1.082612	8.934125	4.195290	.1987432

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-05DLX2 Acquired: 1/28/2025 20:17:52 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ4 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.2275975	F 63.62164	7.396390	.0268989	.8851391	.0685070
Stddev	.0004777	.10097	.007000	.0005036	.0002347	.0011679
%RSD	.2098811	.1586989	.0946473	1.872301	.0265127	1.704720
#1	.2272814	63.66675	7.392498	.0274781	.8850450	.0679304
#2	.2281470	63.50598	7.404472	.0265646	.8849661	.0677396
#3	.2273641	63.69219	7.392200	.0266539	.8854062	.0698510

Elem	Sr4077
Units	ppm
Avg	.1397384
Stddev	.0012866
%RSD	.9207065
#1	.1383029
#2	.1401246
#3	.1407876

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3814.393	83522.17	12605.55	2682.667	4222.762
Stddev	9.738	318.81	110.06	15.071	2.541
%RSD	.2553065	.3817011	.8730695	.5618005	.0601834
#1	3805.398	83273.37	12498.28	2671.992	4221.359
#2	3813.046	83411.61	12600.16	2676.103	4221.232
#3	3824.735	83881.54	12718.19	2699.907	4225.696

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-08A Acquired: 1/28/2025 20:21:46 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7A Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1949449**	**-.003761**	**.7496662**	**.0829757**	**.1200381**	**25.23052**
Stddev	.0014885	.002120	.0030219	.0017451	.0015173	.07042
%RSD	.7635221	56.37487	.4030945	2.103093	1.264052	.2791076
#1	.1941451	-.002643	.7496154	.0833420	.1190635	25.21139
#2	.1940273	-.002433	.7466701	.0810766	.1217863	25.17164
#3	.1966623	-.006206	.7527132	.0845085	.1192644	25.30853

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.5391496**	**.0491461**	**.0075753**	**16.15049**	**.1753735**	**.2491670**
Stddev	.0025519	.0001917	.0000485	.01183	.0005001	.0006389
%RSD	.4733173	.3900664	.6402186	.0732764	.2851483	.2564266
#1	.5410663	.0491262	.0075902	16.16292	.1759369	.2492271
#2	.5362530	.0493471	.0076146	16.13936	.1749823	.2485002
#3	.5401296	.0489652	.0075211	16.14919	.1752012	.2497738

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2906829**	**50.37873**	**.4652300**	**11.62153**	**.2592022**	**.0160628**
Stddev	.0012265	.16370	.0018432	.06709	.0007480	.0000733
%RSD	.4219216	.3249424	.3961862	.5773258	.2885628	.4559957
#1	.2898281	50.30415	.4668514	11.58921	.2600579	.0160254
#2	.2920881	50.26560	.4632253	11.57671	.2588758	.0160158
#3	.2901325	50.56644	.4656133	11.69867	.2586728	.0161472

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**37.36189**	**.0916937**	**.6211781**	**5.323312**	**4.841460**	**.1287036**
Stddev	.11605	.0008865	.0014063	.004782	.018835	.0008289
%RSD	.3106189	.9667550	.2263912	.0898256	.3890271	.6440382
#1	37.38872	.0923035	.6195688	5.318698	4.862588	.1294059
#2	37.46217	.0921008	.6221706	5.328245	4.835359	.1277893
#3	37.23477	.0906768	.6217948	5.322991	4.826432	.1289157

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1151-08A Acquired: 1/28/2025 20:21:46 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7A Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0152061	F 40.84521	F 11.92122	.0183772	.7661361	.0195291
Stddev	.0001130	.07386	.02784	.0005404	.0011429	.0001329
%RSD	.7432649	.1808306	.2335014	2.940831	.1491725	.6803819
#1	.0152167	40.93047	11.89980	.0181020	.7666529	.0196697
#2	.0153134	40.80060	11.95269	.0180298	.7669294	.0195120
#3	.0150882	40.80457	11.91119	.0189999	.7648262	.0194056

Elem	Sr4077
Units	ppm
Avg	.3462089
Stddev	.0009050
%RSD	.2613965
#1	.3468668
#2	.3451769
#3	.3465831

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4385.193	94860.55	14511.94	3052.110	4316.853
Stddev	8.964	288.57	64.01	9.354	10.419
%RSD	.2044142	.3042003	.4410787	.3064704	.2413649
#1	4389.665	95181.81	14559.02	3060.149	4318.801
#2	4391.042	94776.47	14439.06	3054.337	4326.160
#3	4374.873	94623.35	14537.74	3041.843	4305.596

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-01DLX5 Acquired: 1/28/2025 20:25:42 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2946 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0230190	-.047586	1.309760	.0980263	.0372681	14.19844	.1738094
Stddev	.0016104	.000220	.031057	.0010932	.0014023	.08228	.0007509
%RSD	6.996082	.4619502	2.371232	1.115241	3.762814	.5794953	.4320230
#1	.0235769	-.047344	1.331752	.0986858	.0359340	14.28626	.1746437
#2	.0212038	-.047773	1.323296	.0986288	.0387299	14.18594	.1731877
#3	.0242763	-.047642	1.274232	.0967644	.0371405	14.12313	.1735968

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0009132	.0161275	155.9550	1.181418	.0301001	.1186301	494.7593
Stddev	.0001492	.0005826	.7576	.000792	.0004508	.0033496	4.2539
%RSD	16.34249	3.612235	.4857715	.0670600	1.497546	2.823596	.8597877
#1	.0010157	.0167117	156.7475	1.182315	.0305900	.1216389	494.8640
#2	.0007420	.0161240	155.8794	1.181126	.0300075	.1192306	498.9599
#3	.0009818	.0155466	155.2380	1.180813	.0297028	.1150208	490.4540

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	18.65143	38.28223	.5233839	-.007940	.5326866	.1250715	3.406324
Stddev	.08154	.25673	.0106535	.001118	.1700040	.0030591	.012940
%RSD	.4371733	.6706220	2.035508	14.08303	31.91445	2.445895	.3798734
#1	18.73958	38.57202	.5312077	-.008596	.7254277	.1283960	3.421155
#2	18.63602	38.19147	.5276932	-.006649	.4685574	.1244433	3.400473
#3	18.57870	38.08322	.5112507	-.008576	.4040746	.1223753	3.397343

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.440664	1.679022	.6901996	.0235503	2.660885	5.142029	.0213792
Stddev	.012175	.031440	.0205112	.0006905	.054368	.020320	.0012110
%RSD	.8451208	1.872537	2.971779	2.932214	2.043228	.3951651	5.664510
#1	1.446741	1.701600	.6816942	.0242316	2.699753	5.165098	.0219141
#2	1.448605	1.692354	.7135953	.0235685	2.684145	5.126784	.0222308
#3	1.426647	1.643113	.6753093	.0228508	2.598756	5.134206	.0199929

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-01DLX5 Acquired: 1/28/2025 20:25:42 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2946 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	1.018527	.0285799	.1608051
Stddev	.005442	.0013579	.0006703
%RSD	.5342844	4.751063	.4168600
#1	1.024703	.0298630	.1613852
#2	1.016440	.0287189	.1609589
#3	1.014438	.0271580	.1600713

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3437.864	74996.78	11417.65	2412.145	4019.364
Stddev	32.017	172.60	36.45	15.419	44.282
%RSD	.9313034	.2301484	.3192314	.6392122	1.101706
#1	3422.299	74913.16	11403.23	2396.724	3993.605
#2	3416.606	75195.27	11459.11	2427.561	3993.992
#3	3474.688	74881.91	11390.63	2412.150	4070.496

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-02DLX2 Acquired: 1/28/2025 20:29:47 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0403037	-.032461	.5069621	.0478654	.0247878	41.08907	.3561706
Stddev	.0026909	.002274	.0041895	.0022519	.0013282	.19527	.0026343
%RSD	6.676600	7.005807	.8263900	4.704631	5.358439	.4752261	.7396253
#1	.0416575	-.034979	.5103590	.0493002	.0253360	41.30379	.3590946
#2	.0420488	-.030556	.5022808	.0490261	.0232732	41.04130	.3554348
#3	.0372047	-.031848	.5082466	.0452700	.0257543	40.92212	.3539825

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0024489	.0089594	481.4991	3.024579	.0731610	.1488691	264.1960
Stddev	.0001824	.0002546	1.7471	.008909	.0004879	.0011563	1.4113
%RSD	7.447361	2.841874	.3628536	.2945676	.6668773	.7767358	.5342025
#1	.0023461	.0090473	482.1057	3.034261	.0727804	.1476065	265.6654
#2	.0026595	.0086725	479.5296	3.022751	.0729915	.1498766	264.0715
#3	.0023412	.0091584	482.8621	3.016726	.0737110	.1491240	262.8510

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	12.59126	115.2031	1.497198	-.002987	.3001402	.1600487	1.416878
Stddev	.06578	.5681	.002685	.000289	.3505880	.0028128	.021753
%RSD	.5224519	.4931469	.1793664	9.664389	116.8081	1.757448	1.535242
#1	12.65275	115.7257	1.495431	-.002689	.0898909	.1616668	1.437744
#2	12.59914	115.2852	1.495875	-.003265	.1056679	.1568008	1.418555
#3	12.52190	114.5984	1.500288	-.003007	.7048619	.1616785	1.394336

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	6.101774	2.735378	.4138411	.0562970	3.599746	8.031717	.0135489
Stddev	.023218	.005487	.0098435	.0001897	.005082	.007336	.0006469
%RSD	.3805142	.2005787	2.378582	.3369988	.1411843	.0913416	4.774377
#1	6.088045	2.729615	.4242260	.0562356	3.594334	8.039047	.0142824
#2	6.128581	2.735981	.4126499	.0561455	3.600486	8.031729	.0133042
#3	6.088695	2.740539	.4046473	.0565098	3.604418	8.024375	.0130600

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-02DLX2 Acquired: 1/28/2025 20:29:47 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	1.033336	.0862604	.6899371
Stddev	.001050	.0006515	.0046921
%RSD	.1016290	.7553252	.6800727
#1	1.033762	.0862390	.6948795
#2	1.034106	.0869224	.6893882
#3	1.032140	.0856198	.6855436

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3345.478	73711.18	11428.16	2350.171	3629.687
Stddev	2.480	148.13	31.27	11.138	4.389
%RSD	.0741448	.2009579	.2736441	.4739405	.1209119
#1	3346.301	73554.93	11463.90	2339.512	3632.285
#2	3347.443	73729.04	11405.83	2349.268	3632.155
#3	3342.691	73849.56	11414.76	2361.734	3624.619

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-03DLX2 Acquired: 1/28/2025 20:33:51 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0386066**	**-.033218**	**.5086281**	**.0472124**	**.0212862**	**41.43400**	**.3566515**
Stddev	.0028514	.001823	.0067464	.0016413	.0016786	.29555	.0036323
%RSD	7.385871	5.488982	1.326394	3.476460	7.885651	.7132936	1.018457
#1	.0397706	-.035233	.5106084	.0489540	.0227769	41.75170	.3607788
#2	.0353573	-.032739	.5141627	.0469892	.0194680	41.38310	.3539415
#3	.0406920	-.031683	.5011131	.0456942	.0216136	41.16722	.3552341

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0024464**	**.0089774**	**480.0761**	**3.035264**	**.0738443**	**.1503277**	**265.3192**
Stddev	.0001170	.0001366	2.8523	.001829	.0007696	.0011757	.9023
%RSD	4.783307	1.521851	.5941308	.0602578	1.042261	.7821216	.3400729
#1	.0025641	.0091274	477.7530	3.034835	.0747129	.1509344	266.3301
#2	.0024449	.0088601	479.2157	3.033688	.0735727	.1510762	265.0319
#3	.0023301	.0089447	483.2595	3.037270	.0732472	.1489726	264.5955

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**12.58472**	**115.1058**	**1.501591**	**-.003351**	**.4122832**	**.1567608**	**1.418735**
Stddev	.05787	.0830	.004600	.000221	.3215259	.0032186	.003429
%RSD	.4598243	.0720862	.3063106	6.597506	77.98665	2.053179	.2416731
#1	12.65027	115.1640	1.506156	-.003112	.4076438	.1531583	1.421928
#2	12.54071	115.1427	1.501660	-.003393	.0931021	.1577707	1.415111
#3	12.56319	115.0108	1.496957	-.003548	.7361037	.1593533	1.419164

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**6.184163**	**2.745271**	**.4217970**	**.0557916**	**3.604923**	**7.899746**	**.0133288**
Stddev	.025541	.005220	.0096674	.0008949	.015901	.023777	.0003966
%RSD	.4130007	.1901615	2.291946	1.603938	.4411011	.3009887	2.975441
#1	6.212912	2.750238	.4311794	.0567901	3.622080	7.914619	.0134018
#2	6.164093	2.745746	.4223437	.0550621	3.602009	7.872323	.0136839
#3	6.175483	2.739830	.4118678	.0555227	3.590680	7.912296	.0129008

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-03DLX2 Acquired: 1/28/2025 20:33:51 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947D Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	1.021377	.0868608	.6948646
Stddev	.003745	.0003421	.0054560
%RSD	.3666353	.3938454	.7851888
#1	1.017718	.0868233	.7010909
#2	1.021212	.0872201	.6925834
#3	1.025202	.0865390	.6909194

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3369.342	73774.13	11619.09	2361.807	3657.179
Stddev	9.569	59.79	80.09	9.660	10.706
%RSD	.2840091	.0810477	.6893141	.4089906	.2927308
#1	3363.086	73810.02	11702.81	2372.948	3644.949
#2	3380.357	73807.26	11611.26	2355.781	3664.856
#3	3364.582	73705.10	11543.20	2356.690	3661.732

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-02LDLX10 Acquired: 1/28/2025 20:37:54 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0087897**	**-.005105**	**.1026936**	**.0079043**	**.0047753**	**8.205280**	**.0724852**
Stddev	.0013124	.003048	.0020356	.0010623	.0005800	.036765	.0007170
%RSD	14.93123	59.70222	1.982161	13.43935	12.14567	.4480709	.9892235
#1	.0102560	-.008456	.1003569	.0089677	.0054402	8.247731	.0733096
#2	.0077253	-.002499	.1040818	.0068431	.0043738	8.183720	.0720065
#3	.0083877	-.004360	.1036420	.0079022	.0045118	8.184389	.0721394

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0005796**	**.0015630**	**96.30148**	**.6431030**	**.0142420**	**.0321526**	**54.57928**
Stddev	.0001014	.0000269	.40359	.0040439	.0002695	.0016025	.26139
%RSD	17.49114	1.719264	.4190951	.6288096	1.892159	4.984055	.4789104
#1	.0004750	.0015391	96.73357	.6463632	.0140219	.0332492	54.84605
#2	.0005864	.0015577	95.93424	.6385778	.0141615	.0303136	54.32363
#3	.0006775	.0015921	96.23662	.6443680	.0145425	.0328952	54.56816

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**2.566455**	**22.95223**	**.3018716**	**-.000522**	**.3248051**	**.0325990**	**.2786759**
Stddev	.017842	.13565	.0013718	.000106	.3019873	.0008032	.0043662
%RSD	.6952034	.5910169	.4544443	20.20587	92.97494	2.463750	1.566758
#1	2.586883	23.08547	.3011961	-.000414	.3222277	.0316794	.2835563
#2	2.553928	22.81429	.3009684	-.000527	.6280729	.0331630	.2751402
#3	2.558553	22.95692	.3034502	-.000625	.0241147	.0329545	.2773312

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.317548**	**.5174337**	**.0827702**	**.0121671**	**.6712766**	**2.080761**	**.0007252**
Stddev	.013993	.0041232	.0009883	.0002718	.0018356	.006357	.0006106
%RSD	1.062066	.7968512	1.194083	2.234015	.2734456	.3055156	84.20487
#1	1.322253	.5174859	.0827771	.0124383	.6708975	2.082153	.0000964
#2	1.301808	.5132847	.0817784	.0118947	.6696603	2.073823	.0007633
#3	1.328582	.5215306	.0837550	.0121683	.6732722	2.086307	.0013158

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-02LDLX10 Acquired: 1/28/2025 20:37:54 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947L Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.2255726	.0163205	.1356746
Stddev	.0014577	.0009253	.0009984
%RSD	.6462300	5.669685	.7358423
#1	.2265620	.0157433	.1368200
#2	.2238986	.0158304	.1352148
#3	.2262573	.0173878	.1349891

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3534.507	76894.71	11463.01	2502.023	4168.583
Stddev	16.487	491.38	47.12	19.267	15.345
%RSD	.4664497	.6390301	.4111016	.7700646	.3681075
#1	3546.941	76465.18	11417.61	2494.577	4177.759
#2	3540.774	77430.54	11511.68	2523.901	4177.122
#3	3515.806	76788.42	11459.73	2487.589	4150.868

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-04DLX2 Acquired: 1/28/2025 20:41:56 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947S Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0787062**	**.0247368**	**.5202568**	**.1350289**	**.1169472**	**40.31779**	**2.124153**
Stddev	.0040167	.0029729	.0024322	.0075419	.0023534	.31296	.028094
%RSD	5.103435	12.01824	.4674947	5.585422	2.012386	.7762254	1.322585
#1	.0793181	.0281523	.5174725	.1264427	.1149369	40.21975	2.107844
#2	.0744186	.0227311	.5213313	.1380612	.1163689	40.66803	2.156592
#3	.0823818	.0233269	.5219668	.1405826	.1195359	40.06559	2.108021

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0533874**	**.0605024**	**447.2305**	**3.153374**	**.5840974**	**.3775835**	**248.9420**
Stddev	.0004212	.0000746	1.3130	.009641	.0005619	.0015378	1.4918
%RSD	.7889582	.1233392	.2935952	.3057355	.0961995	.4072803	.5992568
#1	.0535001	.0605808	448.2774	3.160329	.5837930	.3765099	248.5897
#2	.0529213	.0604323	447.6568	3.157424	.5837534	.3793453	250.5785
#3	.0537408	.0604942	445.7572	3.142368	.5847458	.3768955	247.6580

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**12.14268**	**107.5454**	**1.984073**	**.0322783**	**.6198362**	**.6311057**	**1.773477**
Stddev	.11071	.5111	.001579	.0003052	.3053886	.0036424	.018483
%RSD	.9117039	.4752406	.0795632	.9455060	49.26924	.5771446	1.042212
#1	12.08372	107.5305	1.982895	.0319422	.3033388	.6342852	1.774611
#2	12.27038	108.0638	1.983458	.0325381	.6434215	.6271316	1.791368
#3	12.07393	107.0419	1.985867	.0323546	.9127484	.6319002	1.754453

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.821773**	**2.698849**	**.3275075**	**.0549246**	**3.549640**	**7.756334**	**.0132753**
Stddev	.093494	.003739	.0159618	.0004335	.005883	.010565	.0012137
%RSD	1.605939	.1385432	4.873710	.7893626	.1657343	.1362072	9.142399
#1	5.800307	2.695566	.3252407	.0544859	3.543339	7.748983	.0120848
#2	5.924133	2.698062	.3444816	.0553528	3.550591	7.751577	.0132300
#3	5.740879	2.702919	.3128004	.0549350	3.554989	7.768441	.0145109

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1163-04DLX2 Acquired: 1/28/2025 20:41:56 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947S Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.9904305	.0804534	.6438386
Stddev	.0019354	.0016171	.0082105
%RSD	.1954122	2.009922	1.275241
#1	.9894615	.0788576	.6397412
#2	.9891710	.0820909	.6532914
#3	.9926590	.0804117	.6384831

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3370.506	75077.42	11346.62	2399.035	3666.878
Stddev	5.881	226.04	77.15	11.671	1.821
%RSD	.1744824	.3010723	.6799552	.4864986	.0496704
#1	3373.495	75059.64	11299.02	2395.700	3668.760
#2	3374.292	74860.79	11435.63	2389.394	3666.751
#3	3363.731	75311.82	11305.20	2412.011	3665.124

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: PB166236TB Acquired: 1/28/2025 20:45:57 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LEB236 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0034162**	**-.001305**	**.0012528**	**-.005142**	**.0017185**	**.0015383**
Stddev	.0029545	.002547	.0015908	.003043	.0005653	.0060217
%RSD	86.48503	195.2425	126.9817	59.17487	32.89726	391.4439
#1	.0066587	-.004027	.0000481	-.006862	.0011302	-.005343
#2	.0008766	-.000909	.0030560	-.006934	.0022576	.005845
#3	.0027131	.001022	.0006541	-.001629	.0017676	.004112

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000445**	**.0000409**	**-.000031**	**.0245543**	**.0014614**	**-.000222**
Stddev	.001504	.0000275	.000064	.0043022	.0003745	.000210
%RSD	338.3499	67.35844	209.8025	17.52115	25.62610	94.48398
#1	.001125	.0000712	.000040	.0267084	.0012123	-.000102
#2	-.000584	.0000174	-.000084	.0196006	.0018921	-.000464
#3	-.001874	.0000340	-.000048	.0273540	.0012799	-.000100

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0009754**	**.0188736**	**.0022195**	**-.005432**	**.0030301**	**-.000052**
Stddev	.0009402	.0026379	.0002038	.011680	.0004192	.000086
%RSD	96.39365	13.97648	9.181102	215.0088	13.83466	166.6399
#1	.0004730	.0161173	.0022930	-.018066	.0025460	-.000142
#2	.0003931	.0213744	.0019892	-.003203	.0032699	-.000042
#3	.0020600	.0191291	.0023763	.004972	.0032743	.000029

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F **1548.497**	**.0010279**	**.0001312**	**-.734294**	**.0044747**	**-.001177**
Stddev	4.398	.0002861	.0021070	.021165	.0015878	.000579
%RSD	.2840319	27.82968	1605.476	2.882406	35.48293	49.21174
#1	1550.754	.0013419	.0023974	-.744772	.0027522	-.001104
#2	1543.428	.0009598	-.001769	-.748178	.0058797	-.001789
#3	1551.309	.0007821	-.000235	-.709934	.0047923	-.000638

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: PB166236TB Acquired: 1/28/2025 20:45:57 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LEB236 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0004436	.0612303	.0065380	.0030259	.0008663	-.002505
Stddev	.0001903	.0010561	.0036972	.0011527	.0007796	.000906
%RSD	42.91121	1.724853	56.55028	38.09220	89.99264	36.17559
#1	.0005621	.0612999	.0107943	.0028214	.0013882	-.003070
#2	.0005446	.0601411	.0046964	.0042672	.0012404	-.001460
#3	.0002240	.0622499	.0041232	.0019893	-.000030	-.002985

Elem	Sr4077
Units	ppm
Avg	.0000187
Stddev	.0000561
%RSD	300.5285
#1	.0000331
#2	.0000662
#3	-.000043

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3161.834	68105.06	11576.92	2235.126	3540.568
Stddev	5.447	318.20	59.88	13.742	9.877
%RSD	.1722785	.4672126	.5172008	.6148116	.2789781
#1	3156.303	67995.61	11516.55	2233.297	3539.395
#2	3167.193	67856.04	11577.91	2222.389	3550.980
#3	3162.005	68463.54	11636.29	2249.690	3531.330

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1164-01 Acquired: 1/28/2025 20:50:07 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2946 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0037419	-.004480	.0012597	-.012131	.0075687	.2393526
Stddev	.0034073	.003850	.0014660	.001334	.0014747	.0090095
%RSD	91.05931	85.93106	116.3756	10.99248	19.48408	3.764123
#1	.0059037	-.008076	.0022568	-.011485	.0058691	.2299406
#2	-.000186	-.000418	-.000424	-.011244	.0083285	.2478969
#3	.005508	-.004948	.001946	-.013665	.0085086	.2402202

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.6397138	.0003699	-.000147	493.5365	-.000479	.0008173
Stddev	.0029006	.0000454	.000150	.9155	.000313	.0002049
%RSD	.4534232	12.27759	102.1092	.1854887	65.37456	25.06767
#1	.6388062	.0004044	-.000209	494.5559	-.000177	.0006224
#2	.6429597	.0003184	.000024	492.7844	-.000803	.0007986
#3	.6373755	.0003869	-.000256	493.2694	-.000458	.0010308

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0057725	.1154094	2.995863	107.2681	.0286472	-.000104
Stddev	.0015745	.0108563	.018597	.2316	.0009622	.000049
%RSD	27.27585	9.406782	.6207602	.2159108	3.358789	47.45147
#1	.0043321	.1037721	2.998180	107.1017	.0284877	-.000142
#2	.0074535	.1171921	3.013193	107.5326	.0296792	-.000048
#3	.0055319	.1252640	2.976216	107.1699	.0277748	-.000122

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F 1499.906	.0037018	.1778136	10.50945	.0340612	1.755119
Stddev	3.365	.0022635	.0017235	.05856	.0031261	.011270
%RSD	.2243620	61.14558	.9692825	.5571709	9.177799	.6421029
#1	1503.266	.0062948	.1768425	10.53673	.0355663	1.755206
#2	1496.535	.0021214	.1798036	10.54939	.0361499	1.743806
#3	1499.917	.0026891	.1767948	10.44223	.0304673	1.766345

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1164-01 Acquired: 1/28/2025 20:50:07 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2946 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0840907	F 46.51507	F 12.60843	-.001712	-.013637	.0720131
Stddev	.0005042	.07180	.06997	.000451	.000475	.0010537
%RSD	.5995383	.1543568	.5549265	26.35404	3.480931	1.463165
#1	.0846129	46.58261	12.67323	-.001355	-.013336	.0732209
#2	.0840524	46.52293	12.53424	-.002219	-.013392	.0715368
#3	.0836068	46.43966	12.61783	-.001563	-.014185	.0712817

Elem	Sr4077
Units	ppm
Avg	1.295930
Stddev	.009101
%RSD	.7022422
#1	1.295113
#2	1.305411
#3	1.287265

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2947.244	64221.11	10860.59	2064.217	3253.594
Stddev	18.220	82.96	63.11	4.558	12.448
%RSD	.6181997	.1291741	.5811000	.2207938	.3825965
#1	2963.351	64224.72	10839.51	2069.436	3265.736
#2	2950.910	64136.40	10931.54	2062.191	3254.185
#3	2927.469	64302.19	10810.72	2061.023	3240.861

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1164-02 Acquired: 1/28/2025 20:54:17 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0033605	-.009051	.0045824	-.013287	.0064193	.2320891
Stddev	.0028305	.004631	.0009976	.001971	.0005988	.0111587
%RSD	84.22724	51.16537	21.77091	14.83253	9.327980	4.807919
#1	.0007751	-.013498	.0035445	-.011423	.0057299	.2448212
#2	.0029217	-.009401	.0046684	-.015349	.0067183	.2240097
#3	.0063847	-.004255	.0055342	-.013088	.0068097	.2274363

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.547137	.0003536	.0011411	643.5712	-.000533	.0058147
Stddev	.004866	.0000724	.0000264	4.9249	.000206	.0002107
%RSD	.3145382	20.48520	2.312310	.7652497	38.68146	3.623958
#1	1.550113	.0003506	.0011646	638.2034	-.000362	.0060228
#2	1.549778	.0002827	.0011125	644.6288	-.000762	.0058199
#3	1.541521	.0004274	.0011463	647.8815	-.000474	.0056015

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0076493	.0249122	4.216201	32.84333	.0200378	-.000252
Stddev	.0013022	.0058288	.006077	.09152	.0003191	.000146
%RSD	17.02418	23.39746	.1441346	.2786584	1.592276	57.95884
#1	.0065836	.0199594	4.219168	32.87599	.0197133	-.000389
#2	.0072634	.0313355	4.209211	32.73996	.0200492	-.000269
#3	.0091009	.0234418	4.220225	32.91405	.0203511	-.000098

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F 1579.502	.0006041	.4959351	5.893291	.0057672	.2326500
Stddev	2.007	.0004281	.0026044	.043578	.0020022	.0009275
%RSD	.1270528	70.87425	.5251556	.7394494	34.71700	.3986481
#1	1578.827	.0007719	.4947128	5.854757	.0066424	.2316122
#2	1581.760	.0009229	.4989259	5.884532	.0034764	.2329403
#3	1577.920	.0001175	.4941666	5.940582	.0071829	.2333976

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1164-02 Acquired: 1/28/2025 20:54:17 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0143075**	**9.410834**	**5.671311**	**-.001081**	**-.017341**	**.0199932**
Stddev	.0003250	.010833	.006872	.000763	.000529	.0002894
%RSD	2.271303	.1151128	.1211751	70.61127	3.050512	1.447545
#1	.0144449	9.405307	5.665746	-.001166	-.017193	.0196663
#2	.0139364	9.423316	5.669194	-.001798	-.017928	.0200966
#3	.0145412	9.403879	5.678992	-.000279	-.016902	.0202167

Elem	Sr4077
Units	ppm
Avg	**1.678255**
Stddev	.012545
%RSD	.7475265
#1	1.664270
#2	1.681974
#3	1.688520

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2934.932**	**64447.47**	**10997.12**	**2056.365**	**3224.473**
Stddev	13.456	250.58	77.06	5.130	4.029
%RSD	.4584827	.3888086	.7006880	.2494569	.1249607
#1	2945.583	64660.16	11080.57	2055.562	3228.508
#2	2939.404	64511.00	10982.10	2061.850	3224.461
#3	2919.809	64171.24	10928.67	2051.685	3220.449

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1164-03 Acquired: 1/28/2025 20:58:36 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0044190**	**-.007085**	**.0036007**	**-.015777**	**.0049826**	**.1855270**
Stddev	.0014153	.003226	.0012592	.003447	.0023969	.0088042
%RSD	32.02731	45.53103	34.96944	21.84865	48.10513	4.745528
#1	.0060408	-.006149	.0028205	-.016768	.0032141	.1901591
#2	.0037823	-.004431	.0029284	-.018620	.0077106	.1910482
#3	.0034340	-.010676	.0050534	-.011943	.0040231	.1753737

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.537721**	**.0004008**	**.0012710**	**645.8310**	**-.000746**	**.0054126**
Stddev	.010936	.0000320	.0000899	5.6178	.000300	.0001802
%RSD	.7112103	7.986111	7.074774	.8698591	40.15130	3.329635
#1	1.542067	.0004372	.0012809	647.4589	-.000945	.0055695
#2	1.545816	.0003885	.0013555	650.4552	-.000891	.0052157
#3	1.525279	.0003768	.0011765	639.5790	-.000402	.0054526

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0081681**	**.0270567**	**4.178425**	**32.89643**	**.0197110**	**.0001233**
Stddev	.0013431	.0005190	.023928	.18262	.0002846	.0001993
%RSD	16.44283	1.918213	.5726587	.5551502	1.443974	161.5740
#1	.0078928	.0276404	4.188406	33.04183	.0195445	-.000023
#2	.0096275	.0268827	4.195746	32.95601	.0200396	.000043
#3	.0069840	.0266471	4.151122	32.69146	.0195488	.000350

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F **1555.984**	**.0011058**	**.4876108**	**5.904053**	**.0037652**	**.2335010**
Stddev	6.501	.0012551	.0036813	.076089	.0027940	.0006100
%RSD	.4178328	113.5105	.7549694	1.288765	74.20572	.2612384
#1	1555.451	-.000014	.4909323	5.858258	.0069429	.2327967
#2	1562.736	.002462	.4882476	5.991887	.0026587	.2338555
#3	1549.766	.000869	.4836527	5.862015	.0016939	.2338509

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1164-03 Acquired: 1/28/2025 20:58:36 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947D Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0145421	9.250952	5.608536	-.000834	-.016602	.0204262
Stddev	.0005391	.035314	.013838	.001034	.000758	.0001004
%RSD	3.707020	.3817314	.2467396	123.9182	4.568124	.4917038
#1	.0150982	9.231555	5.608458	-.000575	-.017282	.0203988
#2	.0145063	9.229588	5.622413	.000045	-.016741	.0205374
#3	.0140218	9.291713	5.594737	-.001973	-.015784	.0203422

Elem	Sr4077
Units	ppm
Avg	1.680247
Stddev	.002578
%RSD	.1534362
#1	1.677396
#2	1.682415
#3	1.680930

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2944.364	63971.96	10940.04	2052.588	3239.890
Stddev	5.044	192.38	41.02	4.177	7.396
%RSD	.1713095	.3007208	.3749335	.2035063	.2282845
#1	2947.641	64046.71	10987.40	2057.190	3246.695
#2	2946.896	63753.43	10915.76	2051.537	3240.956
#3	2938.556	64115.75	10916.97	2049.036	3232.019

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1164-02LX5 Acquired: 1/28/2025 21:02:57 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000356**	**-.002539**	**.0004949**	**-.001093**	**.0020542**	**.1014241**	**.2889304**
Stddev	.002248	.001905	.0019249	.002491	.0016698	.0037488	.0022533
%RSD	631.6418	75.02849	388.9243	227.9870	81.28779	3.696193	.7798658
#1	.001737	-.002568	-.000881	-.002193	.0039822	.1055546	.2870837
#2	-.002732	-.004428	-.000329	.001759	.0011130	.0982372	.2914411
#3	-.000073	-.000619	.002695	-.002844	.0010675	.1004806	.2882666

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0001373**	**.0002183**	**125.3094**	**-.000696**	**.0010845**	**.0022028**	**.0121470**
Stddev	.0000066	.0000234	.7218	.000585	.0003842	.0031688	.0023687
%RSD	4.791281	10.73689	.5760205	84.11614	35.42478	143.8521	19.50009
#1	.0001352	.0002454	124.5577	-.000620	.0014380	.0046773	.0096790
#2	.0001446	.0002039	125.9970	-.000152	.0011400	.0032999	.0123601
#3	.0001319	.0002057	125.3735	-.001316	.0006756	-.001369	.0144019

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.8355517**	**6.421307**	**.0038410**	**-.000254**	**304.9486**	**.0006154**	**.0932079**
Stddev	.0049003	.061254	.0001382	.000360	.7996	.0009772	.0012269
%RSD	.5864737	.9539151	3.597965	141.7735	.2622027	158.7906	1.316327
#1	.8299818	6.357796	.0036825	-.000308	305.6061	-.000485	.0917916
#2	.8391997	6.426103	.0039367	.000130	304.0585	.001383	.0938871
#3	.8374737	6.480022	.0039036	-.000584	305.1812	.000948	.0939451

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.442577**	**-.000345**	**.0534189**	**.0034510**	**1.784056**	**1.158560**	**-.002103**
Stddev	.031839	.002551	.0002529	.0001073	.007683	.010847	.000461
%RSD	2.207120	738.4832	.4733699	3.109942	.4306465	.9362227	21.93099
#1	1.454723	.001339	.0531834	.0033508	1.785499	1.147332	-.002375
#2	1.406452	-.003280	.0536862	.0035643	1.790915	1.159369	-.002365
#3	1.466555	.000904	.0533872	.0034380	1.775754	1.168980	-.001571

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: Q1164-02LX5 Acquired: 1/28/2025 21:02:57 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ME2947L Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	-.002804	.0063017	.3153138
Stddev	.000225	.0022182	.0017648
%RSD	8.017739	35.20017	.5597079
#1	-.003054	.0047867	.3134394
#2	-.002740	.0052706	.3169435
#3	-.002619	.0088478	.3155585

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3311.605	70714.70	11115.44	2308.809	3777.856
Stddev	20.099	319.82	26.98	11.452	17.580
%RSD	.6069178	.4522692	.2427432	.4960226	.4653444
#1	3292.737	71014.96	11086.57	2321.968	3763.329
#2	3309.334	70378.38	11140.02	2303.360	3772.840
#3	3332.742	70750.76	11119.72	2301.098	3797.398

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: CCV026 Acquired: 1/28/2025 21:11:22 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV026 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.023703**	**4.934285**	**25.09389**	**5.014920**	**5.034738**	**394.2481**	**10.16543**
Stddev	.019684	.002738	.10439	.023929	.008752	2.7346	.14722
%RSD	.3918185	.0554979	.4160162	.4771552	.1738243	.6936117	1.448288
#1	5.016457	4.936674	25.09557	4.996901	5.024777	396.1329	10.32069
#2	5.008669	4.931296	24.98866	5.005790	5.038240	395.4996	10.14777
#3	5.045983	4.934884	25.19743	5.042070	5.041196	391.1117	10.02784

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.5169747**	**2.569112**	**404.8855**	**16.02950**	**2.539182**	**15.37745**	**403.1055**
Stddev	.0006204	.009893	1.3169	.04711	.007886	.06610	.7670
%RSD	.1200033	.3850867	.3252484	.2938746	.3105737	.4298716	.1902663
#1	.5162894	2.573345	405.3657	16.07462	2.539468	15.33381	403.8802
#2	.5171367	2.557807	405.8949	16.03325	2.531157	15.34504	403.0896
#3	.5174980	2.576186	403.3959	15.98063	2.546921	15.45350	402.3465

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**15.51538**	**404.6799**	**2.538579**	**1.295772**	**401.9557**	**2.541147**	**15.35078**
Stddev	.00863	.6635	.007363	.000533	1.6626	.012825	.03323
%RSD	.0556214	.1639625	.2900485	.0410973	.4136241	.5046914	.2164903
#1	15.50635	405.0629	2.539739	1.295228	400.6766	2.526852	15.33852
#2	15.51624	405.0630	2.530705	1.295794	401.3553	2.544946	15.32543
#3	15.52355	403.9137	2.545294	1.296293	403.8350	2.551643	15.38840

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**154.1346**	**5.152559**	**5.372881**	**5.001973**	**5.098785**	**5.086739**	**5.089266**
Stddev	.4466	.016513	.007289	.008320	.017288	.025022	.018722
%RSD	.2897782	.3204826	.1356587	.1663250	.3390665	.4919155	.3678685
#1	154.4283	5.141081	5.366218	4.996750	5.101179	5.081286	5.089874
#2	154.3550	5.145112	5.371760	4.997601	5.080425	5.064892	5.070248
#3	153.6206	5.171484	5.380666	5.011567	5.114752	5.114038	5.107677

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: CCV026 Acquired: 1/28/2025 21:11:22 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV026 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	**5.106333**	**5.091577**	**5.129190**
Stddev	.019890	.008277	.031465
%RSD	.3895240	.1625531	.6134407
#1	5.104513	5.096143	5.098922
#2	5.087416	5.096565	5.161728
#3	5.127071	5.082023	5.126918

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2962.050**	**64226.63**	**10435.84**	**2065.735**	**3235.015**
Stddev	4.183	109.31	25.14	3.077	5.293
%RSD	.1412139	.1702017	.2409014	.1489674	.1636201
#1	2963.793	64149.98	10451.11	2062.334	3235.976
#2	2965.080	64178.10	10449.59	2068.327	3239.761
#3	2957.278	64351.81	10406.82	2066.543	3229.306

Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: CCB026 Acquired: 1/28/2025 21:15:41 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB026 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0004193**	**.0012068**	**.0003768**	**-.000263**	**.0014297**	**-.000965**	**.0024448**
Stddev	.0019895	.0013685	.0004773	.003273	.0006000	.004195	.0003251
%RSD	474.4641	113.3993	126.6658	1246.397	41.96540	434.7720	13.29877
#1	-.001559	-.000004	.0001907	.002698	.0009436	.003863	.0027537
#2	.000397	.000933	.0000206	.000291	.0021002	-.003031	.0021056
#3	.002420	.002692	.0009192	-.003777	.0012453	-.003726	.0024750

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0000208**	**.0000251**	**-.000773**	**.0004269**	**-.000080**	**.0005824**	**.0102342**
Stddev	.0000704	.0000304	.008492	.0002678	.000146	.0029438	.0008317
%RSD	339.3935	121.0209	1098.979	62.73970	183.1964	505.4508	8.126859
#1	-.000060	.0000595	-.005224	.0001177	-.000240	.0001366	.0102531
#2	.000072	.0000017	.009019	.0005890	.000047	.0037236	.0093932
#3	.000050	.0000142	-.006113	.0005738	-.000046	-.002113	.0110563

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0003332**	**-.002756**	**-.000055**	**.0001068**	**-.163498**	**-.000430**	**-.001476**
Stddev	.0003167	.013613	.000234	.0002562	.044618	.000273	.000775
%RSD	95.04921	493.9991	429.3990	239.9098	27.28946	63.66042	52.51427
#1	.0000455	-.017957	.000212	-.000187	-.115472	-.000617	-.002041
#2	.0002816	.001380	-.000146	.000282	-.171360	-.000116	-.001794
#3	.0006725	.008310	-.000229	.000226	-.203662	-.000556	-.000592

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.5122053**	**-.001845**	**.0063849**	**.0005480**	**.0038144**	**.0035680**	**.0005891**
Stddev	.0458323	.002497	.0009083	.0000577	.0034153	.0051286	.0003919
%RSD	8.948028	135.3049	14.22581	10.53744	89.53833	143.7417	66.52026
#1	.4613688	-.004728	.0073935	.0005734	.0005632	.0050979	.0009497
#2	.5248825	-.000404	.0056314	.0004819	.0073730	-.002152	.0001721
#3	.5503646	-.000403	.0061298	.0005886	.0035069	.007758	.0006455


Reviewed By:Jaswal
On:1/30/2025 7:27:43 AM
Inst Id :P4

Sample Name: CCB026 Acquired: 1/28/2025 21:15:41 Type: Unk
Method: EPA SFAM01.0(v58) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB026 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0011509	.0022069	.0000761
Stddev	.0008144	.0005904	.0000474
%RSD	70.76521	26.75294	62.26168
#1	.0020762	.0015295	.0000392
#2	.0008334	.0024791	.0001295
#3	.0005430	.0026121	.0000596

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3678.363	78247.57	11031.94	2597.717	4602.640
Stddev	5.617	277.49	83.50	8.657	6.791
%RSD	.1527025	.3546280	.7569286	.3332414	.1475466
#1	3678.621	78133.91	10938.10	2591.659	4595.119
#2	3672.622	78044.95	11098.06	2593.861	4604.476
#3	3683.847	78563.84	11059.66	2607.632	4608.324

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




As 189.042 {479}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000171	Re-Slope:	1.000000
A1 (Gain):	0.062425	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999707	Status:	OK.
Std Error of Est:	0.000025		
Predicted MDL:	0.002576		
Predicted MQL:	0.008587		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00017	.000	1
S1	.01000	.01046	.000	4.56	.00048	.000	1
S3	2.5000	2.4129	-.087	-3.48	.15018	.000	1
S4	5.0000	4.9336	-.066	-1.33	.30725	.002	1
S5	10.000	10.210	.210	2.10	.63609	.003	1
S2	1.2500	1.1928	-.057	-4.58	.07415	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Tl 190.856 {477}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000061	Re-Slope:	1.000000
A1 (Gain):	0.067165	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999450	Status:	OK.
Std Error of Est:	0.000058		
Predicted MDL:	0.002078		
Predicted MQL:	0.006927		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00006	.000	1
S1	.02500	.02731	.002	9.22	.00182	.000	1
S3	2.5000	2.6224	.122	4.90	.17295	.000	1
S4	5.0000	5.0971	.097	1.94	.33591	.003	1
S5	10.000	9.7122	-.288	-2.88	.63940	.006	1
S2	1.2500	1.3161	.066	5.29	.08683	.001	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Pb 220.353 {453}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000268	Re-Slope:	1.000000
A1 (Gain):	0.245554	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999972	Status:	OK.
Std Error of Est:	0.000069		
Predicted MDL:	0.001446		
Predicted MQL:	0.004821		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00027	.000	1
S1	.01000	.01087	.001	8.73	.00239	.000	1
S3	12.500	12.579	.079	.634	3.0860	.008	1
S4	25.000	25.256	.256	1.02	6.1962	.024	1
S5	50.000	49.680	-.320	-.641	12.188	.047	1
S2	6.2500	6.2345	-.016	-.248	1.5293	.002	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Se 196.090 {472}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000278	Re-Slope:	1.000000
A1 (Gain):	0.062328	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999874	Status:	OK.
Std Error of Est:	0.000031		
Predicted MDL:	0.003213		
Predicted MQL:	0.010709		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00028	.000	1
S1	.03500	.03683	.002	5.22	.00257	.000	1
S3	2.5000	2.4419	-.058	-2.32	.15104	.000	1
S4	5.0000	4.9549	-.045	-.902	.30623	.002	1
S5	10.000	10.136	.136	1.36	.62626	.003	1
S2	1.2500	1.2157	-.034	-2.74	.07533	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Sb 206.833 {463}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000285	Re-Slope:	1.000000
A1 (Gain):	0.139842	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999688	Status:	OK.
Std Error of Est:	0.000145		
Predicted MDL:	0.001732		
Predicted MQL:	0.005773		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00029	.000	1
S1	.06000	.05659	-.003	-5.69	.00818	.000	1
S3	2.5000	2.4105	-.089	-3.58	.34204	.000	1
S4	5.0000	4.9352	-.065	-1.30	.69977	.005	1
S5	10.000	10.219	.219	2.19	1.4480	.006	1
S2	1.2500	1.1887	-.061	-4.91	.16884	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Al 396.152 { 85}

Date of Fit:	1/29/2025 15:25:32	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000001	Re-Slope:	1.000000
A1 (Gain):	0.013178	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998301	Status:	OK.
Std Error of Est:	0.000478		
Predicted MDL:	0.008023		
Predicted MQL:	0.026745		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00007	.000	.000	.00000	.000	1
S1	.20000	.18271	-.017	-8.65	.00241	.000	1
S3	77.500	69.709	-7.79	-10.1	.91985	.006	1
S4	155.00	145.63	-9.37	-6.04	1.9216	.007	1
S5	310.00	292.21	-17.8	-5.74	3.8556	.023	1
S2	38.750	34.675	-4.08	-10.5	.45755	.001	1
S6	800.00	839.09	39.1	4.89	11.058	.022	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Ba 493.409 { 68}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.007599	Re-Slope:	1.000000
A1 (Gain):	0.432340	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999844	Status:	OK.
Std Error of Est:	0.000812		
Predicted MDL:	0.000862		
Predicted MQL:	0.002872		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00002	.000	.000	.00761	.000	1
S1	.20000	.18421	-.016	-7.89	.08724	.001	1
S3	5.0000	4.9281	-.072	-1.44	2.1382	.022	1
S4	10.000	10.279	.279	2.79	4.4517	.009	1
S5	20.000	19.842	-.158	-.792	8.5860	.039	1
S2	2.5000	2.4669	-.033	-1.33	1.0741	.006	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Be 234.861 {144}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000107	Re-Slope:	1.000000
A1 (Gain):	3.669692	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999939	Status:	OK.
Std Error of Est:	0.000152		
Predicted MDL:	0.000074		
Predicted MQL:	0.000246		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00011	.000	1
S1	.00500	.00535	.000	6.96	.01971	.000	1
S3	.25000	.25551	.006	2.20	.93362	.007	1
S4	.50000	.50117	.001	.235	1.8310	.006	1
S5	1.0000	.99173	-.008	-.827	3.6229	.019	1
S2	.12500	.12624	.001	.991	.46130	.002	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Cd 214.438 {457}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000036	Re-Slope:	1.000000
A1 (Gain):	2.765445	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999858	Status:	OK.
Std Error of Est:	0.000392		
Predicted MDL:	0.000081		
Predicted MQL:	0.000270		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00004	.000	1
S1	.00500	.00507	.000	1.33	.01398	.000	1
S3	1.2500	1.2783	.028	2.26	3.5417	.009	1
S4	2.5000	2.5443	.044	1.77	7.0497	.023	1
S5	5.0000	4.9222	-.078	-1.56	13.640	.060	1
S2	.62500	.63019	.005	.830	1.7461	.004	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Ca 373.690 { 90}

Date of Fit:	1/29/2025 15:25:32	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000036	Re-Slope:	1.000000
A1 (Gain):	0.008713	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999323	Status:	OK.
Std Error of Est:	0.001120		
Predicted MDL:	0.009431		
Predicted MQL:	0.031436		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00066	.001	.000	.00004	.000	1
S2	62.500	60.899	-1.60	-2.56	.53066	.001	1
S3	125.00	121.06	-3.94	-3.15	1.0548	.005	1
S4	250.00	248.35	-1.65	-.659	2.1640	.003	1
S5	500.00	477.32	-22.7	-4.54	4.1591	.018	1
S1	5.0000	4.6958	-.304	-6.08	.04095	.000	1
S6	800.00	830.18	30.2	3.77	7.2336	.028	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Cr 267.716 {126}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000003	Re-Slope:	1.000000
A1 (Gain):	0.165298	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999471	Status:	OK.
Std Error of Est:	0.000159		
Predicted MDL:	0.000424		
Predicted MQL:	0.001415		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00000	.000	1
S1	.01000	.01094	.001	9.37	.00181	.000	1
S3	7.7500	8.0960	.346	4.46	1.3386	.003	1
S4	15.500	15.813	.313	2.02	2.6144	.002	1
S5	31.000	30.107	-.893	-2.88	4.9779	.012	1
S2	3.8750	4.1084	.233	6.02	.67926	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Co 228.616 {448}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000044	Re-Slope:	1.000000
A1 (Gain):	0.906070	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999978	Status:	OK.
Std Error of Est:	0.000161		
Predicted MDL:	0.000271		
Predicted MQL:	0.000904		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00004	.000	1
S1	.05000	.04963	-.000	-.734	.04519	.000	1
S3	1.2500	1.2573	.007	.586	1.1436	.002	1
S4	2.5000	2.5224	.022	.896	2.2941	.008	1
S5	5.0000	4.9706	-.029	-.588	4.5210	.016	1
S2	.62500	.62503	.000	.005	.56852	.001	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Cu 324.754 {104}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.002340	Re-Slope:	1.000000
A1 (Gain):	0.116027	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999803	Status:	OK.
Std Error of Est:	0.000106		
Predicted MDL:	0.002477		
Predicted MQL:	0.008258		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00234	.000	1
S1	.02500	.02879	.004	15.2	.00568	.000	1
S3	7.5000	7.3837	-.116	-1.55	.85896	.002	1
S4	15.000	15.483	.483	3.22	1.7986	.008	1
S5	30.000	29.646	-.354	-1.18	3.4418	.013	1
S2	3.7500	3.7333	-.017	-.445	.43546	.001	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Fe 259.837 {130}

Date of Fit:	1/29/2025 15:25:32	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000019	Re-Slope:	1.000000
A1 (Gain):	0.005384	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999682	Status:	OK.
Std Error of Est:	0.000059		
Predicted MDL:	0.006447		
Predicted MQL:	0.021492		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00002	.000	1
S1	.10000	.09550	-.005	-4.50	.00052	.000	1
S3	75.000	73.770	-1.23	-1.64	.39682	.002	1
S4	150.00	148.66	-1.34	-.894	.79964	.002	1
S5	300.00	287.22	-12.8	-4.26	1.5449	.004	1
S2	37.500	37.601	.101	.269	.20227	.001	1
S6	800.00	815.23	15.2	1.90	4.3895	.022	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Mn 257.610 {131}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000015	Re-Slope:	1.000000
A1 (Gain):	0.088416	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999671	Status:	OK.
Std Error of Est:	0.000081		
Predicted MDL:	0.000378		
Predicted MQL:	0.001260		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00001	.000	1
S1	.01500	.01505	.000	.342	.00132	.000	1
S3	7.5000	7.4919	-.008	-.109	.66193	.003	1
S4	15.000	15.606	.606	4.04	1.3789	.003	1
S5	30.000	29.389	-.611	-2.04	2.5966	.004	1
S2	3.7500	3.7632	.013	.351	.33248	.001	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Mg 279.079 {121}

Date of Fit:	1/29/2025 15:25:32	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000078	Re-Slope:	1.000000
A1 (Gain):	0.002358	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998805	Status:	OK.
Std Error of Est:	0.000403		
Predicted MDL:	0.018182		
Predicted MQL:	0.060606		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00156	.002	.000	-.00007	.000	1
S2	62.500	57.949	-4.55	-7.28	.13659	.000	1
S3	125.00	116.79	-8.21	-6.57	.27536	.001	1
S4	250.00	243.92	-6.08	-2.43	.57519	.001	1
S5	500.00	478.56	-21.4	-4.29	1.1285	.001	1
S1	5.0000	4.2103	-.790	-15.8	.00985	.000	1
S6	800.00	841.07	41.1	5.13	1.9835	.006	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Ni 231.604 {446}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000412	Re-Slope:	1.000000
A1 (Gain):	0.647071	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999936	Status:	OK.
Std Error of Est:	0.000175		
Predicted MDL:	0.000425		
Predicted MQL:	0.001417		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00041	.000	1
S1	.04000	.04078	.001	1.95	.02600	.000	1
S3	1.2500	1.2689	.019	1.51	.82257	.000	1
S4	2.5000	2.5267	.027	1.07	1.6383	.005	1
S5	5.0000	4.9471	-.053	-1.06	3.2083	.014	1
S2	.62500	.63145	.006	1.03	.40912	.002	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Ag 328.068 {103}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000494	Re-Slope:	1.000000
A1 (Gain):	0.290281	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999794	Status:	OK.
Std Error of Est:	0.000048		
Predicted MDL:	0.000392		
Predicted MQL:	0.001308		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00049	.000	1
S1	.01000	.00962	-.000	-3.75	.00228	.000	1
S3	.62500	.60732	-.018	-2.83	.16941	.000	1
S4	1.2500	1.2390	-.011	-.884	.34636	.000	1
S5	2.5000	2.5416	.042	1.66	.71171	.001	1
S2	.31250	.30001	-.012	-4.00	.08340	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Na 818.326 { 41}

Date of Fit:	1/29/2025 15:25:32	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.002389	Re-Slope:	1.000000
A1 (Gain):	0.002132	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998933	Status:	OK.
Std Error of Est:	0.000305		
Predicted MDL:	0.395543		
Predicted MQL:	1.318476		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00104	.001	.000	-.00239	.000	1
S2	37.500	35.352	-2.15	-5.73	.07299	.001	1
S3	75.000	70.557	-4.44	-5.92	.14805	.000	1
S4	150.00	149.26	-.739	-.492	.31585	.003	1
S5	300.00	278.88	-21.1	-7.04	.59220	.003	1
S1	5.0000	4.7423	-.258	-5.15	.00772	.000	1
S6	800.00	828.71	28.7	3.59	1.7645	.008	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




V 292.402 {115}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000020	Re-Slope:	1.000000
A1 (Gain):	0.128001	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999676	Status:	OK.
Std Error of Est:	0.000082		
Predicted MDL:	0.001952		
Predicted MQL:	0.006507		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	-.00002	.000	1
S1	.05000	.05469	.005	9.38	.00697	.000	1
S3	1.2500	1.2729	.023	1.83	.15355	.000	1
S4	2.5000	2.5643	.064	2.57	.30950	.001	1
S5	5.0000	4.8902	-.110	-2.20	.58850	.002	1
S2	.62500	.64274	.018	2.84	.07757	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Zn 213.856 {158}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000335	Re-Slope:	1.000000
A1 (Gain):	0.294981	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999877	Status:	OK.
Std Error of Est:	0.000331		
Predicted MDL:	0.001811		
Predicted MQL:	0.006037		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00034	.000	1
S1	.06000	.05955	-.000	-.755	.01800	.001	1
S3	7.5000	7.2935	-.206	-2.75	2.1601	.013	1
S4	15.000	15.306	.306	2.04	4.5319	.022	1
S5	30.000	29.990	-.010	-.035	8.8800	.010	1
S2	3.7500	3.6615	-.088	-2.36	1.0846	.008	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




K 769.896 { 44}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.005329	Re-Slope:	1.000000
A1 (Gain):	0.003761	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999540	Status:	OK.
Std Error of Est:	0.000235		
Predicted MDL:	0.051932		
Predicted MQL:	0.173108		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00100	.001	.000	.00533	.000	1
S2	37.500	35.461	-2.04	-5.44	.13870	.000	1
S3	75.000	71.693	-3.31	-4.41	.27496	.002	1
S4	150.00	148.54	-1.46	-.974	.56398	.002	1
S5	300.00	307.39	7.39	2.46	1.1614	.004	1
S1	5.0000	4.4149	-.585	-11.7	.02193	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




P 177.495 {490}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000991	Re-Slope:	1.000000
A1 (Gain):	0.052233	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999655	Status:	OK.
Std Error of Est:	0.000023		
Predicted MDL:	0.002199		
Predicted MQL:	0.007330		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00099	.000	1
S1	.01000	.00755	-.002	-24.5	-.00060	.000	1
S3	2.5000	2.4212	-.079	-3.15	.12454	.000	1
S4	5.0000	5.0272	.027	.545	.25973	.001	1
S5	10.000	10.150	.150	1.50	.52542	.001	1
S2	1.2500	1.1545	-.096	-7.64	.05884	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




B 249.678 {135}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.001600	Re-Slope:	1.000000
A1 (Gain):	0.372525	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999082	Status:	OK.
Std Error of Est:	0.000228		
Predicted MDL:	0.000777		
Predicted MQL:	0.002591		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00160	.000	1
S1	.01000	.00049	-.010	-95.1	.00159	.000	1
S3	2.5000	2.6216	.122	4.86	.84122	.007	1
S4	5.0000	5.0810	.081	1.62	1.6204	.007	1
S5	10.000	9.7509	-.249	-2.49	3.0861	.017	1
S2	1.2500	1.3070	.057	4.56	.42001	.001	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Mo 202.030 {467}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000115	Re-Slope:	1.000000
A1 (Gain):	0.760384	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999984	Status:	OK.
Std Error of Est:	0.000071		
Predicted MDL:	0.000295		
Predicted MQL:	0.000983		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00011	.000	1
S1	.01000	.01068	.001	6.84	.00824	.000	1
S3	2.5000	2.5126	.013	.503	1.9106	.005	1
S4	5.0000	5.0150	.015	.299	3.8134	.015	1
S5	10.000	9.9548	-.045	-.452	7.5696	.035	1
S2	1.2500	1.2669	.017	1.36	.96348	.002	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




S 182.034 {485}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000006	Re-Slope:	1.000000
A1 (Gain):	0.030301	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999255	Status:	OK.
Std Error of Est:	0.000062		
Predicted MDL:	0.003933		
Predicted MQL:	0.013110		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00002	.000	.000	.00001	.000	1
S1	.10000	.09074	-.009	-9.26	.00275	.000	1
S3	2.5000	2.3755	-.125	-4.98	.07208	.000	1
S4	5.0000	4.9724	-.028	-.553	.15087	.001	1
S5	10.000	10.287	.287	2.87	.31211	.001	1
S2	1.2500	1.1240	-.126	-10.1	.03411	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Si 251.611 {134}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000419	Re-Slope:	1.000000
A1 (Gain):	0.032536	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.970444	Status:	OK.
Std Error of Est:	0.000431		
Predicted MDL:	0.005091		
Predicted MQL:	0.016971		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00033	-.000	.000	.00041	.000	1
S1	.10000	.44026	.340	340.	.01474	.000	1
S3	2.5000	2.4446	-.055	-2.21	.08020	.000	1
S4	5.0000	5.0719	.072	1.44	.16593	.000	1
S5	10.000	9.6724	-.328	-3.28	.31610	.002	1
S2	1.2500	1.2217	-.028	-2.27	.04029	.000	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Sn 189.989 {478}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000282	Re-Slope:	1.000000
A1 (Gain):	0.165950	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999933	Status:	OK.
Std Error of Est:	0.000027		
Predicted MDL:	0.000819		
Predicted MQL:	0.002731		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00028	.000	1
S1	.00700	.00653	-.000	-6.74	.00131	.000	1
S3	2.5000	2.5341	.034	1.36	.41952	.001	1
S4	5.0000	5.0708	.071	1.42	.83921	.004	1
S5	10.000	9.9006	-.099	-.994	1.6381	.008	1
S2	1.2500	1.2450	-.005	-.402	.20624	.001	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Ti 336.121 {100}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.001904	Re-Slope:	1.000000
A1 (Gain):	0.361555	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999714	Status:	OK.
Std Error of Est:	0.000460		
Predicted MDL:	0.000919		
Predicted MQL:	0.003064		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	.00190	.000	1
S1	.10000	.10400	.004	4.00	.03951	.000	1
S3	2.5000	2.5381	.038	1.52	.91957	.002	1
S4	5.0000	5.1422	.142	2.84	1.8611	.008	1
S5	10.000	9.7787	-.221	-2.21	3.5374	.012	1
S2	1.2500	1.2870	.037	2.96	.46724	.001	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Li 670.784 { 50}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000400	Re-Slope:	1.000000
A1 (Gain):	0.145489	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999614	Status:	OK.
Std Error of Est:	0.000083		
Predicted MDL:	0.001347		
Predicted MQL:	0.004489		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00040	.000	1
S5	10.000	10.111	.111	1.11	1.4714	.005	1
S4	5.0000	5.0962	.096	1.92	.74184	.003	1
S3	2.5000	2.3647	-.135	-5.41	.34443	.003	1
S1	.01500	.01355	-.001	-9.65	.00237	.000	1
S2	1.2500	1.1796	-.070	-5.63	.17202	.001	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Sr 407.771 { 83}

Date of Fit:	1/29/2025 15:21:06	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000111	Re-Slope:	1.000000
A1 (Gain):	1.463766	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999919	Status:	OK.
Std Error of Est:	0.000993		
Predicted MDL:	0.000072		
Predicted MQL:	0.000238		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00012	.000	1
S1	.10000	.09422	-.006	-5.78	.13803	.001	1
S3	2.5000	2.4788	-.021	-.849	3.6285	.017	1
S4	5.0000	5.0925	.093	1.85	7.4544	.030	1
S5	10.000	9.9191	-.081	-.809	14.519	.094	1
S2	1.2500	1.2654	.015	1.23	1.8523	.008	1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4




Y 224.306 {450}*

Date of Fit:	1/29/2025 14:43:41	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.000000	Status:	Warning Zero Gain
Std Error of Est:	0.000000		
Predicted MDL:	n/a		
Predicted MQL:	n/a		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



Y 360.073 { 94}*


Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

A2 (Curvature):	0.000000					
n (Exponent):	1.000000					
Correlation:	0.000000		Status:	Warning	Zero Gain	
Std Error of Est:	0.000000					
Predicted MDL:	n/a					
Predicted MQL:	n/a					

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis




Y 371.030 { 91}*

Date of Fit:	<not fit>		Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):		0.000000		Re-Slope:	1.000000	
A1 (Gain):		0.000000		Y-int:	0.000000	
A2 (Curvature):		0.000000				
n (Exponent):		1.000000				
Correlation:		0.000000		Status:	Warning	Zero Gain
Std Error of Est:		0.000000				
Predicted MDL:		n/a				
Predicted MQL:		n/a				

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis


Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4



Y 224.306 {150}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):	0.000000		Re-Slope:	1.000000	
A1 (Gain):	0.000000		Y-int:	0.000000	
A2 (Curvature):	0.000000				
n (Exponent):	1.000000				
Correlation:	0.000000		Status:	Warning	Zero Gain
Std Error of Est:	0.000000				
Predicted MDL:	n/a				
Predicted MQL:	n/a				

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



In 230.606 {446}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):	0.000000		Re-Slope:	1.000000	
A1 (Gain):	0.000000		Y-int:	0.000000	

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

A2 (Curvature):		0.000000					
n (Exponent):		1.000000					
Correlation:		0.000000		Status:	Warning	Zero Gain	
Std Error of Est:		0.000000					
Predicted MDL:		n/a					
Predicted MQL:		n/a					

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S0 Acquired: 1/29/2025 14:56:12 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00017**	**.00006**	**-.00027**	**.00028**	**.00029**	**.00000**	**.00761**	**.00011**
Stddev	.00007	.00005	.00010	.00015	.00006	.00006	.00033	.00003
%RSD	41.217	84.285	36.550	55.700	21.255	2834.7	4.3132	30.545
#1	-.00021	.00009	-.00037	.00037	.00030	-.00003	.00772	.00012
#2	-.00021	.00009	-.00018	.00037	.00034	.00007	.00724	.00013
#3	-.00009	.00000	-.00025	.00010	.00022	-.00004	.00786	.00007

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00004**	**.00004**	**-.00000**	**.00004**	**.00234**	**.00002**	**-.00001**	**-.00007**
Stddev	.00003	.00004	.00002	.00020	.00031	.00001	.00002	.00001
%RSD	90.199	91.978	483.43	454.40	13.063	40.802	109.66	19.356
#1	-.00006	.00006	-.00002	.00018	.00265	.00002	.00000	-.00006
#2	-.00000	.00007	.00001	.00014	.00233	.00001	-.00003	-.00007
#3	-.00004	-.00000	.00000	-.00018	.00204	.00003	-.00002	-.00009

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00041**	**-.00049**	**-.00239**	**-.00002**	**.00034**	**.00533**	**-.00099**	**.00160**
Stddev	.00017	.00002	.00043	.00018	.00028	.00000	.00008	.00015
%RSD	42.163	4.8886	18.020	870.57	82.440	.00654	8.4921	9.1553
#1	-.00058	-.00051	-.00195	-.00013	.00046	.00533	-.00109	.00158
#2	-.00023	-.00051	-.00281	-.00012	.00002	.00533	-.00095	.00176
#3	-.00043	-.00047	-.00239	.00019	.00053	.00533	-.00094	.00147

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00011**	**.00001**	**.00041**	**.00028**	**.00190**	**.00040**	**.00012**
Stddev	.00017	.00016	.00004	.00003	.00028	.00013	.00006
%RSD	147.91	2320.6	9.0902	10.948	14.895	32.698	50.886
#1	-.00002	-.00017	.00039	.00030	.00192	.00044	.00006
#2	.00006	.00006	.00045	.00030	.00161	.00051	.00011
#3	.00031	.00013	.00038	.00025	.00217	.00026	.00018

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S0 Acquired: 1/29/2025 14:56:12 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3343.6	69827.	13258.	2338.9	4051.8
Stddev	25.1	2197.	109.	86.0	29.7
%RSD	.75178	3.1458	.82415	3.6779	.73222
#1	3352.8	67304.	13348.	2241.0	4064.7
#2	3363.0	70864.	13288.	2373.1	4072.9
#3	3315.2	71313.	13136.	2402.5	4017.9

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S1 Acquired: 1/29/2025 15:00:28 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00048**	**.00182**	**.00239**	**.00257**	**.00818**	**.00241**	**.08724**	**.01971**
Stddev	.00019	.00006	.00010	.00020	.00007	.00009	.00102	.00022
%RSD	38.611	3.3558	4.2021	7.7950	.80053	3.6535	1.1744	1.0963
#1	.00027	.00189	.00235	.00234	.00816	.00232	.08609	.01946
#2	.00061	.00181	.00231	.00263	.00826	.00242	.08757	.01983
#3	.00057	.00177	.00250	.00273	.00813	.00250	.08806	.01984

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.01398**	**.04095**	**.00181**	**.04519**	**.00568**	**.00052**	**.00132**	**.00985**
Stddev	.00011	.00032	.00006	.00026	.00041	.00002	.00000	.00009
%RSD	.75118	.77427	3.5146	.57052	7.2164	4.3711	.09298	.89940
#1	.01388	.04061	.00178	.04540	.00564	.00050	.00131	.00975
#2	.01399	.04101	.00188	.04490	.00611	.00053	.00132	.00990
#3	.01409	.04123	.00176	.04527	.00529	.00054	.00132	.00991

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.02600**	**.00228**	**.00772**	**.00697**	**.01800**	**.02193**	**-.00060**	**.00159**
Stddev	.00031	.00008	.00050	.00020	.00068	.00020	.00006	.00021
%RSD	1.1911	3.3892	6.4102	2.9147	3.7756	.89278	9.3858	13.438
#1	.02633	.00222	.00732	.00717	.01879	.02192	-.00060	.00136
#2	.02598	.00237	.00758	.00698	.01759	.02214	-.00054	.00164
#3	.02571	.00226	.00827	.00676	.01763	.02175	-.00066	.00177

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00824**	**.00275**	**.01474**	**.00131**	**.03951**	**.00237**	**.13803**
Stddev	.00016	.00001	.00026	.00010	.00024	.00006	.00138
%RSD	1.9621	.52399	1.7816	7.8587	.61200	2.7396	1.0013
#1	.00841	.00274	.01502	.00122	.03975	.00236	.13657
#2	.00809	.00276	.01471	.00143	.03950	.00244	.13820
#3	.00822	.00276	.01450	.00129	.03927	.00231	.13932

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S1 Acquired: 1/29/2025 15:00:28 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3304.0**	**69989.**	**13082.**	**2337.6**	**3957.6**
Stddev	1.1	129.	132.	8.4	2.3
%RSD	.03434	.18414	1.0070	.36092	.05752
#1	3303.7	70073.	12955.	2344.3	3955.3
#2	3305.3	70054.	13072.	2340.3	3959.8
#3	3303.1	69841.	13218.	2328.1	3957.7

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S2 Acquired: 1/29/2025 15:04:43 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.07415	.08683	1.5293	.07533	.16884	.45755	1.0741	.46130
Stddev	.00016	.00054	.0017	.00038	.00024	.00146	.0057	.00202
%RSD	.21176	.62320	.10969	.49999	.14481	.31956	.53460	.43816
#1	.07430	.08647	1.5280	.07538	.16858	.45601	1.0680	.46241
#2	.07399	.08745	1.5289	.07494	.16890	.45773	1.0749	.46252
#3	.07415	.08657	1.5312	.07568	.16906	.45892	1.0794	.45897

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.7461	.53066	.67926	.56852	.43546	.20227	.33248	.13659
Stddev	.0036	.00141	.00036	.00112	.00122	.00081	.00130	.00040
%RSD	.20607	.26556	.05361	.19639	.27931	.40246	.39170	.29632
#1	1.7421	.52906	.67895	.56730	.43506	.20144	.33122	.13613
#2	1.7475	.53124	.67966	.56876	.43683	.20232	.33241	.13674
#3	1.7489	.53169	.67917	.56949	.43450	.20306	.33382	.13689

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.40912	.08340	.07299	.07757	1.0846	.13870	.05884	.42001
Stddev	.00182	.00018	.00095	.00010	.0083	.00033	.00005	.00061
%RSD	.44571	.21613	1.2960	.12663	.76794	.23605	.09312	.14534
#1	.40704	.08358	.07406	.07752	1.0750	.13837	.05882	.42043
#2	.40993	.08339	.07260	.07751	1.0903	.13870	.05880	.42029
#3	.41041	.08322	.07230	.07769	1.0884	.13902	.05891	.41931

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.96348	.03411	.04029	.20624	.46724	.17202	1.8523
Stddev	.00192	.00027	.00013	.00061	.00140	.00087	.0078
%RSD	.19944	.78002	.32056	.29760	.29875	.50322	.42338
#1	.96151	.03437	.04016	.20553	.46600	.17121	1.8450
#2	.96358	.03384	.04030	.20661	.46875	.17192	1.8515
#3	.96535	.03414	.04041	.20658	.46696	.17293	1.8606

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S2 Acquired: 1/29/2025 15:04:43 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3203.8	66626.	13210.	2232.1	3628.8
Stddev	1.0	40.	69.	9.5	5.1
%RSD	.03155	.06048	.51886	.42703	.14154
#1	3204.5	66655.	13168.	2235.3	3634.3
#2	3204.2	66580.	13173.	2221.3	3624.2
#3	3202.6	66643.	13289.	2239.5	3627.9

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S3 Acquired: 1/29/2025 15:08:39 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.15018	.17295	3.0860	.15104	.34204	.91985	2.1382	.93362
Stddev	.00026	.00034	.0076	.00039	.00048	.00564	.0217	.00694
%RSD	.17462	.19691	.24619	.25790	.13986	.61292	1.0149	.74382
#1	.15027	.17330	3.0908	.15061	.34199	.92430	2.1565	.92994
#2	.14988	.17262	3.0773	.15136	.34159	.92175	2.1440	.92929
#3	.15038	.17292	3.0901	.15115	.34255	.91351	2.1142	.94163

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3.5417	1.0548	1.3386	1.1436	.85896	.39682	.66193	.27536
Stddev	.0091	.0051	.0029	.0021	.00189	.00182	.00348	.00082
%RSD	.25706	.48743	.22006	.18603	.21956	.45786	.52519	.29633
#1	3.5438	1.0593	1.3417	1.1440	.86113	.39849	.66439	.27592
#2	3.5318	1.0560	1.3359	1.1413	.85805	.39707	.66344	.27574
#3	3.5496	1.0492	1.3380	1.1454	.85770	.39489	.65795	.27443

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.82257	.16941	.14805	.15355	2.1601	.27496	.12454	.84122
Stddev	.00044	.00021	.00048	.00034	.0129	.00157	.00021	.00742
%RSD	.05302	.12196	.32579	.22114	.59784	.57170	.17065	.88184
#1	.82283	.16937	.14810	.15389	2.1666	.27628	.12430	.83878
#2	.82280	.16963	.14754	.15321	2.1685	.27538	.12471	.83533
#3	.82206	.16922	.14850	.15355	2.1453	.27322	.12461	.84956

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.9106	.07208	.08020	.41952	.91957	.34443	3.6285
Stddev	.0046	.00022	.00021	.00065	.00218	.00320	.0168
%RSD	.23932	.31187	.26698	.15491	.23660	.92845	.46261
#1	1.9102	.07196	.07997	.41951	.92196	.34706	3.6475
#2	1.9063	.07194	.08023	.41888	.91770	.34536	3.6220
#3	1.9154	.07234	.08040	.42018	.91905	.34087	3.6159

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S3 Acquired: 1/29/2025 15:08:39 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3093.8**	**65077.**	**12911.**	**2185.2**	**3420.0**
Stddev	6.5	60.	84.	2.8	1.8
%RSD	.21163	.09216	.65340	.12940	.05360
#1	3098.2	65017.	12956.	2187.9	3421.7
#2	3096.8	65077.	12964.	2182.3	3420.0
#3	3086.2	65137.	12814.	2185.6	3418.1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S4 Acquired: 1/29/2025 15:12:36 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.30725	.33591	6.1962	.30623	.69977	1.9216	4.4517	1.8310
Stddev	.00197	.00257	.0239	.00175	.00450	.0071	.0088	.0065
%RSD	.64176	.76562	.38637	.57105	.64316	.37038	.19862	.35386
#1	.30587	.33535	6.1888	.30498	.69543	1.9178	4.4595	1.8297
#2	.30638	.33367	6.1769	.30549	.69947	1.9298	4.4533	1.8253
#3	.30951	.33872	6.2230	.30823	.70441	1.9172	4.4421	1.8380

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7.0497	2.1640	2.6144	2.2941	1.7986	.79964	1.3789	.57519
Stddev	.0228	.0031	.0024	.0077	.0079	.00219	.0029	.00099
%RSD	.32412	.14243	.09257	.33792	.43802	.27350	.20846	.17143
#1	7.0474	2.1629	2.6119	2.2900	1.8068	.79798	1.3808	.57477
#2	7.0281	2.1675	2.6167	2.2893	1.7911	.80212	1.3803	.57631
#3	7.0736	2.1616	2.6147	2.3031	1.7979	.79882	1.3756	.57448

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.6383	.34636	.31585	.30950	4.5319	.56398	.25973	1.6204
Stddev	.0048	.00023	.00285	.00081	.0224	.00153	.00087	.0070
%RSD	.29402	.06740	.90291	.26195	.49512	.27055	.33684	.43138
#1	1.6374	.34626	.31887	.31008	4.5552	.56335	.25969	1.6256
#2	1.6341	.34663	.31320	.30857	4.5302	.56571	.25888	1.6125
#3	1.6436	.34620	.31549	.30984	4.5104	.56286	.26062	1.6232

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3.8134	.15087	.16593	.83921	1.8611	.74184	7.4544
Stddev	.0155	.00054	.00044	.00383	.0082	.00261	.0299
%RSD	.40535	.35989	.26614	.45602	.44177	.35236	.40089
#1	3.8044	.15049	.16639	.83786	1.8673	.74240	7.4219
#2	3.8046	.15061	.16587	.83624	1.8518	.74413	7.4807
#3	3.8313	.15149	.16551	.84353	1.8641	.73899	7.4606

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S4 Acquired: 1/29/2025 15:12:36 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2910.8	62779.	12719.	2087.3	3166.3
Stddev	6.8	119.	60.	3.8	4.6
%RSD	.23497	.18937	.47487	.18155	.14498
#1	2917.5	62915.	12711.	2083.0	3168.0
#2	2911.1	62698.	12783.	2088.8	3169.8
#3	2903.8	62722.	12663.	2090.1	3161.1

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S5 Acquired: 1/29/2025 15:16:38 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.63609**	**.63940**	**12.188**	**.62626**	**1.4480**	**3.8556**	**8.5860**	**3.6229**
Stddev	.00279	.00600	.047	.00264	.0057	.0227	.0387	.0189
%RSD	.43819	.93794	.38749	.42103	.39622	.58992	.45094	.52172
#1	.63463	.63355	12.172	.62396	1.4449	3.8294	8.6290	3.6089
#2	.63433	.63910	12.151	.62568	1.4445	3.8676	8.5539	3.6154
#3	.63930	.64554	12.242	.62914	1.4546	3.8699	8.5750	3.6444

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**13.640**	**4.1591**	**4.9779**	**4.5210**	**3.4418**	**1.5449**	**2.5966**	**1.1285**
Stddev	.060	.0184	.0117	.0163	.0133	.0045	.0037	.0014
%RSD	.43985	.44137	.23503	.35964	.38617	.28926	.14407	.12029
#1	13.615	4.1415	4.9760	4.5145	3.4303	1.5495	2.5947	1.1299
#2	13.596	4.1781	4.9905	4.5090	3.4387	1.5447	2.6009	1.1286
#3	13.708	4.1575	4.9673	4.5395	3.4563	1.5405	2.5941	1.1272

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3.2083**	**.71171**	**.59220**	**.58850**	**8.8800**	**1.1614**	**.52542**	**3.0861**
Stddev	.0138	.00061	.00339	.00158	.0096	.0044	.00135	.0168
%RSD	.42950	.08509	.57187	.26810	.10761	.37563	.25671	.54269
#1	3.2051	.71237	.58886	.58756	8.8707	1.1661	.52612	3.0713
#2	3.1964	.71117	.59212	.58762	8.8795	1.1607	.52387	3.0826
#3	3.2234	.71159	.59563	.59032	8.8898	1.1574	.52628	3.1043

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**7.5696**	**.31211**	**.31610**	**1.6381**	**3.5374**	**1.4714**	**14.519**
Stddev	.0353	.00108	.00168	.0079	.0121	.0046	.094
%RSD	.46628	.34543	.52995	.48358	.34280	.31472	.64565
#1	7.5452	.31178	.31463	1.6374	3.5318	1.4756	14.576
#2	7.5536	.31123	.31574	1.6306	3.5291	1.4722	14.411
#3	7.6101	.31331	.31793	1.6464	3.5513	1.4665	14.570

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S5 Acquired: 1/29/2025 15:16:38 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2628.7	59032.	12208.	1910.3	2859.1
Stddev	10.1	22.	72.	3.1	11.2
%RSD	.38465	.03651	.59286	.16315	.39149
#1	2635.2	59052.	12266.	1910.5	2865.0
#2	2633.8	59036.	12231.	1913.3	2866.1
#3	2617.1	59009.	12127.	1907.1	2846.2

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: S6 Acquired: 1/29/2025 15:21:07 Type: Cal
Method: EPA SFAM01.0(v59) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S06 Custom ID2: Custom ID3:
Comment:

Elem	Al3961	Ca3736	Fe2598	Mg2790	Na8183
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**11.058**	**7.2336**	**4.3895**	**1.9835**	**1.7645**
Stddev	.022	.0278	.0220	.0058	.0085
%RSD	.19895	.38421	.50066	.29055	.47942
#1	11.057	7.2098	4.3695	1.9773	1.7713
#2	11.080	7.2269	4.3861	1.9843	1.7550
#3	11.036	7.2641	4.4130	1.9888	1.7672

Int. Std.	Y_3600	Y_3710
Units	Cts/S	Cts/S
Avg	**54428.**	**12060.**
Stddev	167.	33.
%RSD	.30660	.27646
#1	54600.	12086.
#2	54417.	12071.
#3	54267.	12022.

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: ICV005 Acquired: 1/29/2025 15:31:10 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICV005 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.9990606**	**1.030469**	**.9580774**	**.9667031**	**1.001295**	**2.351126**
Stddev	.0056953	.015157	.0026986	.0058509	.002675	.013824
%RSD	.5700686	1.470855	.2816683	.6052408	.2671288	.5879655
#1	.9931768	1.016518	.9566313	.9619182	.998407	2.366601
#2	.9994582	1.028293	.9564101	.9649650	1.001790	2.346782
#3	1.004547	1.046596	.9611909	.9732261	1.003687	2.339997

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.5624476**	**.4942479**	**.4877198**	**10.05475**	**.5347769**	**.4888557**
Stddev	.0047080	.0010559	.0016726	.07615	.0026056	.0017389
%RSD	.8370527	.2136484	.3429412	.7573965	.4872352	.3557094
#1	.5669708	.4935556	.4864727	10.13007	.5372316	.4869830
#2	.5627976	.4937249	.4870662	10.05638	.5350562	.4891647
#3	.5575744	.4954633	.4896205	9.97779	.5320428	.4904194

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4756728**	**9.288009**	**.5515622**	**5.781006**	**.4931815**	**.2258069**
Stddev	.0016367	.065925	.0033645	.020225	.0006043	.0013151
%RSD	.3440858	.7097891	.6099988	.3498502	.1225252	.5824196
#1	.4738989	9.350894	.5544574	5.773981	.4927347	.2266075
#2	.4771244	9.293719	.5523581	5.803807	.4929407	.2265241
#3	.4759951	9.219415	.5478711	5.765231	.4938690	.2242890

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**10.30212**	**.4966874**	**.9336785**	**9.526703**	**5.082850**	F **.0233640**
Stddev	.20224	.0032236	.0025832	.083659	.022333	.0010429
%RSD	1.963078	.6490204	.2766645	.8781557	.4393753	4.463836
#1	10.14584	.5004097	.9308458	9.620429	5.068428	.0236183
#2	10.53054	.4948236	.9342860	9.500102	5.071547	.0242563
#3	10.22999	.4948289	.9359038	9.459579	5.108575	.0222175

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: ICV005 Acquired: 1/29/2025 15:31:10 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICV005 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F -.000211	4.816161	F .0079037	5.398317	F -.001064	4.922811
Stddev	.000108	.015554	.0045135	.023326	.000471	.037764
%RSD	51.00861	.3229611	57.10653	.4320922	44.24065	.7671158
#1	-.000172	4.803261	.0027166	5.379514	-.000526	4.952277
#2	-.000333	4.811789	.0109362	5.391018	-.001400	4.935916
#3	-.000129	4.833434	.0100582	5.424419	-.001266	4.880241

Elem	Sr4077
Units	ppm
Avg	F 5.811753
Stddev	.103623
%RSD	1.782987
#1	5.920689
#2	5.714421
#3	5.800150

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3325.136	70529.07	13423.03	2381.597	3871.476
Stddev	7.221	327.79	15.82	2.196	4.040
%RSD	.2171694	.4647642	.1178380	.0921933	.1043572
#1	3326.349	70187.88	13427.61	2383.466	3872.239
#2	3331.673	70557.76	13436.06	2379.179	3875.080
#3	3317.385	70841.59	13405.43	2382.145	3867.109

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: ICB005 Acquired: 1/29/2025 15:35:11 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICB005 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0008439**	**-.000321**	**.0007344**	**-.002516**	**-.000155**	**-.001415**	**.0000541**
Stddev	.0021898	.000949	.0011468	.004210	.000290	.003860	.0000561
%RSD	259.4984	295.3362	156.1652	167.3286	186.8017	272.8565	103.6724
#1	.0033594	-.001214	.0013350	-.007281	-.000319	-.004886	.0000638
#2	-.000636	-.000425	.0014562	.000701	.000180	-.002100	.0001048
#3	-.000192	.000675	-.000588	-.000969	-.000327	.002742	-.000006

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000047**	**.0000237**	**.0106732**	**.0000867**	**-.000103**	**.0001253**	**-.003270**
Stddev	.000011	.0001170	.0047677	.0002905	.000109	.0024832	.003818
%RSD	23.67226	494.0466	44.66952	335.2024	105.7496	1982.395	116.7501
#1	-.000034	.0001487	.0160818	-.000242	-.000228	-.002585	-.005274
#2	-.000054	.0000053	.0088584	.000310	-.000062	.000668	-.005670
#3	-.000052	-.000083	.0070795	.000191	-.000021	.002292	.001133

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000021**	**-.006895**	**.0001273**	**-.000167**	**-.144052**	**.0000414**	**.0005785**
Stddev	.000356	.010181	.0005169	.000292	.230842	.0014554	.0008267
%RSD	1714.575	147.6590	405.9518	174.3023	160.2497	3515.988	142.8943
#1	-.000429	-.011799	-.000418	-.000476	.035190	-.000545	-.000331
#2	.000231	-.013695	.000611	-.000130	-.404531	-.001029	.000783
#3	.000135	.004810	.000189	.000104	-.062814	.001699	.001284

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0525499**	**-.000401**	**.0030494**	**-.000082**	**.0054814**	**.0023781**	**-.000119**
Stddev	.0211642	.001618	.0001381	.000321	.0019289	.0054834	.000608
%RSD	40.27452	403.8744	4.528450	392.1341	35.18943	230.5779	512.1881
#1	.0761911	-.001458	.0031523	-.000001	.0054477	-.003186	.000047
#2	.0353680	-.001207	.0031033	.000191	.0074269	.002544	-.000792
#3	.0460906	.001463	.0028925	-.000435	.0035696	.007777	.000389

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: ICB005 Acquired: 1/29/2025 15:35:11 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICB005 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0004056	-.000064	.0000905
Stddev	.0011269	.000188	.0000491
%RSD	277.8177	293.0287	54.22499
#1	-.000670	.000137	.0001469
#2	.001578	-.000236	.0000579
#3	.000309	-.000093	.0000666

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3393.712	72569.04	13440.39	2418.402	4126.671
Stddev	7.678	293.71	110.96	16.819	6.816
%RSD	.2262274	.4047375	.8255761	.6954544	.1651643
#1	3402.459	72235.83	13364.41	2401.373	4128.472
#2	3388.089	72790.39	13389.04	2418.831	4119.135
#3	3390.587	72680.91	13567.73	2435.003	4132.405

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: ICSA005 Acquired: 1/29/2025 15:41:14 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSA005 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0057793**	**.0031054**	**.0035286**	**.0240222**	**.0066356**	**224.9548**
Stddev	.0027539	.0023666	.0001792	.0061843	.0004721	3.1704
%RSD	47.65011	76.21014	5.079024	25.74399	7.114860	1.409346
#1	.0034595	.0017694	.0033464	.0299022	.0067706	228.2456
#2	.0088227	.0058379	.0037047	.0175730	.0061106	221.9203
#3	.0050557	.0017089	.0035346	.0245914	.0070254	224.6985

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0064678**	**-.000596**	**-.000158**	**238.0932**	**.0608726**	**.0010856**
Stddev	.0010750	.000043	.000043	1.9821	.0002750	.0002135
%RSD	16.62037	7.227137	27.43365	.8324992	.4518249	19.66436
#1	.0071888	-.000601	-.000156	238.8002	.0607802	.0010241
#2	.0069822	-.000551	-.000116	235.8545	.0611819	.0009096
#3	.0052322	-.000636	-.000203	239.6249	.0606556	.0013231

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.004185**	**98.33179**	**.0186281**	**232.7414**	**.0026951**	**-.002328**
Stddev	.002299	.70391	.0003500	1.6901	.0002697	.000147
%RSD	54.93401	.7158497	1.878767	.7261843	10.00791	6.310000
#1	-.006718	98.54928	.0188776	233.1784	.0027974	-.002159
#2	-.002231	97.54480	.0182280	230.8757	.0028988	-.002427
#3	-.003606	98.90129	.0187786	234.1701	.0023892	-.002397

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.163871**	**-.004008**	**-.008741**	**-.075078**	**.0009837**	F **.1988006**
Stddev	.306160	.003157	.002605	.034602	.0013667	.0045377
%RSD	186.8298	78.76847	29.80048	46.08866	138.9333	2.282531
#1	.094452	-.001884	-.005780	-.113895	.0025555	.2001760
#2	-.502044	-.002504	-.010681	-.047468	.0003207	.1937344
#3	-.084022	-.007635	-.009761	-.063870	.0000750	.2024915

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: ICSA005 Acquired: 1/29/2025 15:41:14 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSA005 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0000526	.0214723	.0056031	-.004040	-.002501	.0055373
Stddev	.0006628	.0019963	.0030023	.001631	.000569	.0001267
%RSD	1261.067	9.297170	53.58390	40.36887	22.74598	2.288362
#1	.0008146	.0208924	.0071832	-.005146	-.002144	.0055050
#2	-.000390	.0198301	.0074853	-.002167	-.002202	.0056770
#3	-.000267	.0236943	.0021406	-.004806	-.003157	.0054298

Elem	Sr4077
Units	ppm
Avg	F .1014649
Stddev	.0010411
%RSD	1.026091
#1	.1019634
#2	.1002683
#3	.1021631

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2981.033	63412.18	13041.63	2108.384	3300.914
Stddev	1.969	161.98	55.73	4.605	1.900
%RSD	.0660349	.2554350	.4273333	.2184351	.0575587
#1	2979.978	63405.38	13092.11	2103.990	3302.091
#2	2979.817	63577.45	12981.82	2107.987	3301.929
#3	2983.304	63253.71	13050.94	2113.175	3298.722

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: ICSAB005 Acquired: 1/29/2025 15:45:28 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSAB005 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0961105**	**.0997608**	**.0534378**	**.0691383**	**.5769237**	**221.9573**
Stddev	.0022726	.0008657	.0019882	.0028731	.0034307	1.4036
%RSD	2.364599	.8678192	3.720643	4.155518	.5946521	.6323901
#1	.0938583	.1007538	.0545979	.0676908	.5789263	223.5775
#2	.0960702	.0993645	.0545735	.0724473	.5729624	221.1106
#3	.0984031	.0991642	.0511420	.0672770	.5788825	221.1838

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4952464**	**.5064060**	**.9837477**	**233.8816**	**.5995154**	**.4987010**
Stddev	.0034023	.0005514	.0020330	.8585	.0004185	.0008707
%RSD	.6869919	.1088958	.2066597	.3670596	.0697983	.1745897
#1	.4981722	.5060239	.9822796	234.8630	.5992888	.4987744
#2	.4915129	.5061559	.9828953	233.2698	.5999982	.4977960
#3	.4960540	.5070382	.9860681	233.5120	.5992591	.4995327

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4850098**	**96.74679**	**.5081471**	**228.2457**	**.9955795**	**.1992657**
Stddev	.0009009	.32068	.0030906	.7513	.0010581	.0003182
%RSD	.1857529	.3314584	.6082092	.3291826	.1062760	.1596633
#1	.4843089	97.11487	.5107776	228.9942	.9952975	.1995533
#2	.4860259	96.59765	.5047433	228.2513	.9967500	.1989239
#3	.4846945	96.52784	.5089206	227.4915	.9946911	.1993198

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.130691**	**.4848134**	**.9584420**	**-.275210**	**.0060727**	F **.1807588**
Stddev	.171914	.0022309	.0047669	.053868	.0024190	.0010988
%RSD	131.5423	.4601478	.4973539	19.57339	39.83416	.6078650
#1	-.308529	.4860035	.9557177	-.217855	.0080725	.1819961
#2	.034613	.4822399	.9556620	-.283042	.0067618	.1798969
#3	-.118157	.4861970	.9639462	-.324733	.0033840	.1803835

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: ICSAB005 Acquired: 1/29/2025 15:45:28 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSAB005 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000099	.0248077	-.000068	-.003963	-.004674	.0042103
Stddev	.000627	.0037848	.006270	.000501	.000673	.0008301
%RSD	630.7351	15.25666	9259.927	12.64200	14.38889	19.71552
#1	.000071	.0290348	.007042	-.004401	-.004782	.0032518
#2	.000425	.0217331	-.002436	-.004072	-.005286	.0046959
#3	-.000793	.0236552	-.004808	-.003417	-.003954	.0046831

Elem	Sr4077
Units	ppm
Avg	.0989680
Stddev	.0009041
%RSD	.9135033
#1	.0994054
#2	.0979284
#3	.0995702

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3060.931	63560.55	12878.77	2126.991	3399.128
Stddev	4.259	175.46	10.38	6.364	.790
%RSD	.1391425	.2760515	.0806227	.2991949	.0232280
#1	3056.719	63358.31	12866.85	2122.762	3399.403
#2	3060.839	63651.19	12883.57	2123.901	3398.237
#3	3065.236	63672.16	12885.88	2134.310	3399.742

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: CCV028 Acquired: 1/29/2025 15:49:33 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV028 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.106231**	**4.965000**	**25.16854**	**5.143835**	**5.199633**	**405.4101**
Stddev	.010631	.018986	.03707	.012946	.009543	2.4661
%RSD	.2082056	.3823904	.1472779	.2516889	.1835362	.6082890
#1	5.100450	4.958127	25.14548	5.136843	5.189592	407.8203
#2	5.099742	4.950407	25.14884	5.135889	5.200722	405.5181
#3	5.118500	4.986465	25.21130	5.158775	5.208585	402.8918

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**10.96322**	**.5162241**	**2.555079**	**413.1468**	**15.97342**	**2.560251**
Stddev	.04592	.0037606	.002704	2.9092	.01044	.001207
%RSD	.4188510	.7284796	.1058365	.7041452	.0653500	.0471285
#1	10.91069	.5205648	2.552817	410.3555	15.96209	2.559181
#2	10.98318	.5139480	2.554345	416.1610	15.98265	2.560014
#3	10.99578	.5141596	2.558074	412.9240	15.97552	2.561559

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**15.81434**	**408.8166**	**15.97336**	**409.4044**	**2.552075**	**1.334014**
Stddev	.06592	2.0364	.07254	1.5681	.004292	.002457
%RSD	.4168624	.4981311	.4541116	.3830212	.1681779	.1842081
#1	15.78600	406.4705	15.89142	407.5968	2.548284	1.335790
#2	15.76732	410.1271	15.99928	410.3993	2.551207	1.335043
#3	15.88969	409.8522	16.02937	410.2171	2.556735	1.331210

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**413.6875**	**2.580286**	**16.04027**	**163.7206**	**5.142794**	F **5.572764**
Stddev	1.7070	.004600	.04001	1.0645	.029720	.024418
%RSD	.4126215	.1782628	.2494656	.6501640	.5778934	.4381713
#1	413.5458	2.584060	16.01520	162.4936	5.118302	5.600787
#2	412.0559	2.575163	16.01920	164.2728	5.134222	5.561452
#3	415.4609	2.581635	16.08642	164.3956	5.175858	5.556054

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: CCV028 Acquired: 1/29/2025 15:49:33 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV028 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.079681**	**5.189158**	F **6.514212**	**5.093894**	**5.200003**	**5.453585**
Stddev	.011658	.004821	.031187	.011251	.010499	.049589
%RSD	.2294998	.0929026	.4787575	.2208815	.2019104	.9092995
#1	5.069662	5.185065	6.539903	5.089401	5.189865	5.397660
#2	5.076905	5.187936	6.479512	5.085583	5.199314	5.470897
#3	5.092476	5.194472	6.523220	5.106698	5.210830	5.492198

Elem	Sr4077
Units	ppm
Avg	F **5.626155**
Stddev	.053139
%RSD	.9445042
#1	5.620416
#2	5.681931
#3	5.576118

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2765.010**	**59820.67**	**12488.23**	**1964.820**	**2975.489**
Stddev	10.066	116.39	76.25	2.988	7.762
%RSD	.3640601	.1945701	.6105773	.1520658	.2608737
#1	2776.293	59878.95	12402.70	1961.371	2984.088
#2	2761.786	59686.65	12512.92	1966.447	2973.378
#3	2756.950	59896.40	12549.08	1966.641	2969.000

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: CCB028 Acquired: 1/29/2025 15:53:51 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB028 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0021815**	**.0018599**	**.0007598**	**.0014983**	**-.000514**	**.0093605**	**.0005395**
Stddev	.0015411	.0014459	.0012506	.0020784	.002103	.0044132	.0001797
%RSD	70.64563	77.73949	164.5853	138.7185	408.9715	47.14682	33.30148
#1	.0008758	.0034347	.0022035	.0036248	-.000164	.0045335	.0004947
#2	.0017872	.0015528	.0000632	.0013983	.001392	.0131887	.0003865
#3	.0038815	.0005923	.0000127	-.000528	-.002770	.0103594	.0007373

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000049**	**.0000394**	**.0122853**	**.0001827**	**.0000156**	**-.001537**	**.0076877**
Stddev	.000054	.0000379	.0068434	.0002331	.0002706	.000535	.0034188
%RSD	110.6052	95.96721	55.70414	127.5489	1737.221	34.78844	44.47054
#1	-.000015	.0000483	.0056074	.0002769	-.000166	-.001048	.0092253
#2	-.000111	-.000002	.0192831	-.000083	-.000114	-.002108	.0037701
#3	-.000021	.000072	.0119655	.000354	.000327	-.001455	.0100677

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0001270**	**.0188466**	**-.000175**	**.0000214**	**.0299063**	**.0011106**	**.0000325**
Stddev	.0002549	.0078177	.000296	.0001196	.2377015	.0006864	.0006413
%RSD	200.6651	41.48047	169.2967	559.3378	794.8215	61.80556	1971.023
#1	-.000148	.0208362	-.000278	.0001489	-.197814	.0016400	-.000373
#2	.000173	.0254773	-.000406	.0000035	.276467	.0003351	-.000301
#3	.000356	.0102264	.000159	-.000088	.011066	.0013568	.000772

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0942873**	**-.001280**	**.0054925**	**.0000876**	**.0059609**	**.0014401**	**-.000191**
Stddev	.0278586	.000792	.0003645	.0001493	.0037390	.0038794	.000380
%RSD	29.54654	61.85363	6.636351	170.4256	62.72598	269.3851	198.8116
#1	.1020913	-.002075	.0053288	.0002389	.0039164	.0059191	.000015
#2	.1174116	-.001273	.0052384	.0000836	.0036899	-.000741	-.000629
#3	.0633589	-.000492	.0059101	-.000060	.0102763	-.000858	.000041

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: CCB028 Acquired: 1/29/2025 15:53:51 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB028 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0008864	.0007086	.0000882
Stddev	.0003290	.0009410	.0000880
%RSD	37.11425	132.8057	99.76392
#1	.0011328	.0001854	-.000013
#2	.0005128	.0017950	.000129
#3	.0010134	.0001454	.000149

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3378.218	72622.83	13529.11	2431.064	4091.355
Stddev	6.574	274.68	88.17	5.183	2.454
%RSD	.1946130	.3782274	.6516734	.2131896	.0599864
#1	3373.962	72703.06	13585.01	2436.862	4089.090
#2	3385.790	72848.46	13427.48	2429.451	4093.963
#3	3374.902	72316.97	13574.86	2426.880	4091.012

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1136-02 Acquired: 1/29/2025 15:58:00 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0153133	.0029970	.0050894	-.004850	-.002604	31.07541
Stddev	.0008638	.0017222	.0012616	.000060	.000248	.10745
%RSD	5.640586	57.46476	24.78902	1.230892	9.521662	.3457558
#1	.0161779	.0010444	.0051716	-.004783	-.002715	31.08915
#2	.0153117	.0042999	.0063079	-.004869	-.002778	30.96175
#3	.0144504	.0036466	.0037887	-.004898	-.002320	31.17532

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0376117	.0025540	.0015093	51.17705	.0297309	.1126255
Stddev	.0005110	.0000205	.0001048	.07150	.0000738	.0003275
%RSD	1.358590	.8022116	6.946504	.1397019	.2481043	.2907949
#1	.0381876	.0025642	.0016170	51.23373	.0296666	.1129624
#2	.0374347	.0025304	.0014075	51.09673	.0297146	.1123083
#3	.0372127	.0025674	.0015034	51.20069	.0298114	.1126057

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1197466	11.58207	2.282116	23.18116	.1059449	-.002937
Stddev	.0007050	.02877	.005575	.04572	.0003199	.000158
%RSD	.5887161	.2484325	.2442992	.1972140	.3019291	5.393663
#1	.1193918	11.57855	2.287318	23.20380	.1055756	-.002796
#2	.1192895	11.55522	2.276231	23.12854	.1061287	-.002907
#3	.1205585	11.61244	2.282800	23.21113	.1061305	-.003108

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	2.760222	.0243054	.5084607	12.91822	.6329755	.2887731
Stddev	.152769	.0003075	.0030588	.03776	.0045437	.0010080
%RSD	5.534660	1.265106	.6015760	.2922817	.7178296	.3490448
#1	2.715903	.0239516	.5089764	12.93361	.6381013	.2886267
#2	2.930250	.0245082	.5051768	12.87520	.6294430	.2898463
#3	2.634512	.0244564	.5112288	12.94586	.6313823	.2878465

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1136-02 Acquired: 1/29/2025 15:58:00 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0000959	F 327.8339	F 21.18949	-.002491	.0109164	.0249730
Stddev	.0001848	.2513	.03463	.000242	.0001648	.0003093
%RSD	192.7179	.0766552	.1634198	9.713579	1.509276	1.238672
#1	.0001423	328.0892	21.22934	-.002574	.0110841	.0249078
#2	.0002531	327.5868	21.17240	-.002680	.0107548	.0253097
#3	-.000108	327.8259	21.16673	-.002218	.0109101	.0247014

Elem	Sr4077
Units	ppm
Avg	.2956309
Stddev	.0011462
%RSD	.3877199
#1	.2968437
#2	.2945655
#3	.2954835

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7298.725	157105.9	30320.25	5243.303	3738.736
Stddev	21.600	483.2	68.46	24.317	9.181
%RSD	.2959405	.3075347	.2257933	.4637800	.2455701
#1	7318.782	157255.4	30387.55	5264.027	3745.154
#2	7301.535	157496.7	30322.50	5249.350	3742.834
#3	7275.857	156565.7	30250.69	5216.533	3728.219

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1136-03 Acquired: 1/29/2025 16:01:59 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0149272**	**.0032718**	**.0070963**	**-.003786**	**-.002895**	**31.30768**
Stddev	.0009618	.0015072	.0019157	.000605	.000462	.14055
%RSD	6.443632	46.06613	26.99612	15.98667	15.95944	.4489219
#1	.0144294	.0015348	.0067492	-.003798	-.003168	31.17539
#2	.0160359	.0042336	.0091618	-.003175	-.003156	31.29242
#3	.0143162	.0040469	.0053778	-.004386	-.002362	31.45524

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0364753**	**.0025335**	**.0015179**	**50.81248**	**.0295408**	**.1117600**
Stddev	.0010216	.0000216	.0000825	.08176	.0001014	.0003118
%RSD	2.800825	.8520933	5.434208	.1609079	.3434048	.2790062
#1	.0355097	.0025573	.0014910	50.74527	.0296577	.1117868
#2	.0363713	.0025152	.0016105	50.78866	.0294883	.1114357
#3	.0375449	.0025280	.0014522	50.90350	.0294764	.1120576

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1189654**	**11.59444**	**2.251447**	**22.90463**	**.1052959**	**-.002762**
Stddev	.0015697	.04338	.004841	.03677	.0005193	.000085
%RSD	1.319434	.3741176	.2150268	.1605567	.4931894	3.074794
#1	.1174930	11.56680	2.246257	22.93887	.1050470	-.002751
#2	.1187863	11.57209	2.252243	22.86576	.1049478	-.002852
#3	.1206169	11.64444	2.255841	22.90928	.1058928	-.002683

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**2.848472**	**.0242785**	**.5118017**	**13.08315**	**.6237633**	**.2879888**
Stddev	.074559	.0015884	.0025901	.06596	.0030243	.0011064
%RSD	2.617510	6.542573	.5060828	.5041934	.4848414	.3841724
#1	2.815819	.0252612	.5121112	13.02814	.6271609	.2889830
#2	2.795809	.0224460	.5090707	13.06504	.6213655	.2881864
#3	2.933786	.0251285	.5142232	13.15628	.6227636	.2867969

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1136-03 Acquired: 1/29/2025 16:01:59 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7D Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0003053	F 326.7778	F 20.83910	-.002469	.0109334	.0251447
Stddev	.0000675	.6466	.07977	.001901	.0001683	.0003497
%RSD	22.11984	.1978731	.3827689	77.00483	1.539126	1.390761
#1	.0002705	326.4483	20.91744	-.000331	.0110220	.0249111
#2	.0002623	326.3624	20.84188	-.003106	.0110389	.0255468
#3	.0003832	327.5228	20.75798	-.003970	.0107393	.0249762

Elem	Sr4077
Units	ppm
Avg	.2952264
Stddev	.0015225
%RSD	.5156879
#1	.2936512
#2	.2953380
#3	.2966899

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7197.481	156152.3	30316.68	5122.422	3715.663
Stddev	36.309	325.9	159.93	13.121	22.096
%RSD	.5044623	.2086812	.5275394	.2561576	.5946698
#1	7234.744	156399.5	30221.48	5134.005	3738.077
#2	7195.489	155783.0	30227.24	5108.172	3715.013
#3	7162.209	156274.2	30501.32	5125.091	3693.899

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1136-02LX5 Acquired: 1/29/2025 16:05:57 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0061721**	**.0013295**	**.0038430**	**-.002684**	**-.000690**	**11.10259**
Stddev	.0006695	.0003954	.0014811	.001827	.000437	.04356
%RSD	10.84813	29.74264	38.53986	68.04523	63.39449	.3922986
#1	.0069044	.0016513	.0034357	-.000766	-.001058	11.09307
#2	.0055912	.0008881	.0026082	-.004403	-.000206	11.06459
#3	.0060206	.0014491	.0054852	-.002884	-.000806	11.15012

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0119751**	**.0009296**	**.0004155**	**18.25253**	**.0116935**	**.0227015**
Stddev	.0007946	.0000064	.0000623	.04910	.0002355	.0001950
%RSD	6.635218	.6913535	15.00337	.2690193	2.013568	.8587945
#1	.0117074	.0009339	.0003974	18.22891	.0115317	.0228370
#2	.0128689	.0009328	.0003642	18.21970	.0119636	.0227895
#3	.0113490	.0009223	.0004849	18.30898	.0115852	.0224781

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0446559**	**4.242455**	**.8238035**	**8.166453**	**.0215420**	**-.000996**
Stddev	.0018919	.019698	.0048790	.020418	.0000995	.000128
%RSD	4.236591	.4643127	.5922527	.2500280	.4617918	12.89933
#1	.0466005	4.230366	.8213893	8.148675	.0214383	-.000948
#2	.0445456	4.231815	.8206023	8.161932	.0215512	-.000898
#3	.0428215	4.265185	.8294189	8.188754	.0216366	-.001141

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.046580**	**.0091656**	**.1801557**	**4.475365**	**.1364607**	**.1090021**
Stddev	.155505	.0009035	.0021409	.002441	.0009777	.0005437
%RSD	14.85844	9.857839	1.188335	.0545429	.7164661	.4987660
#1	.883211	.0084397	.1776895	4.475961	.1367621	.1096289
#2	1.063728	.0088796	.1815352	4.472681	.1353678	.1087179
#3	1.192800	.0101775	.1812425	4.477453	.1372523	.1086594

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1136-02LX5 Acquired: 1/29/2025 16:05:57 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7L Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0004150	F 65.46945	7.650868	-.001098	.0045245	.0091357
Stddev	.0002212	.19812	.009348	.000158	.0006532	.0002352
%RSD	53.30526	.3026197	.1221822	14.37452	14.43676	2.574038
#1	.0006705	65.57182	7.650619	-.001048	.0046697	.0091668
#2	.0002888	65.24108	7.660338	-.000971	.0050929	.0088865
#3	.0002858	65.59544	7.641647	-.001274	.0038109	.0093537

Elem	Sr4077
Units	ppm
Avg	.1053583
Stddev	.0004823
%RSD	.4577392
#1	.1051716
#2	.1049972
#3	.1059060

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4192.431	89840.93	16965.68	2967.726	3995.087
Stddev	3.990	186.88	118.67	6.688	7.268
%RSD	.0951708	.2080155	.6994732	.2253432	.1819133
#1	4190.027	89852.77	16930.43	2975.425	3986.966
#2	4197.037	89648.41	16868.64	2963.364	4000.979
#3	4190.229	90021.62	17097.99	2964.388	3997.315

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1136-04 Acquired: 1/29/2025 16:09:59 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7S Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0503951	.0788905	.0528370	.0878469	.0852065	33.69555
Stddev	.0020990	.0033333	.0005532	.0015460	.0012385	.13352
%RSD	4.165072	4.225251	1.046969	1.759871	1.453570	.3962497
#1	.0509426	.0754483	.0522556	.0892855	.0841948	33.54860
#2	.0521662	.0791202	.0533568	.0862122	.0848369	33.72861
#3	.0480766	.0821031	.0528987	.0880429	.0865877	33.80943

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.786568	.0478759	.1012649	52.60154	.2222327	1.081557
Stddev	.013017	.0001202	.0007390	.18485	.0006263	.005445
%RSD	.7285971	.2510283	.7297388	.3514224	.2818266	.5034723
#1	1.771738	.0479500	.1008581	52.39379	.2215115	1.078779
#2	1.796104	.0479404	.1008187	52.66296	.2226400	1.078061
#3	1.791860	.0477372	.1021179	52.74786	.2225466	1.087832

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.3451935	12.81183	2.794195	23.79175	1.085772	.0319151
Stddev	.0029502	.03023	.012826	.05095	.004212	.0001450
%RSD	.8546506	.2359310	.4590310	.2141391	.3879615	.4543657
#1	.3431578	12.77943	2.779614	23.73412	1.082909	.0317798
#2	.3438458	12.81680	2.799237	23.81034	1.083799	.0320682
#3	.3485768	12.83927	2.803735	23.83080	1.090609	.0318971

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	2.856198	.4676936	.9527194	13.34606	.6743956	.2857381
Stddev	.022757	.0006586	.0089259	.06035	.0052642	.0006667
%RSD	.7967443	.1408244	.9368852	.4522016	.7805743	.2333327
#1	2.879033	.4680049	.9426588	13.29855	.6731765	.2862509
#2	2.856041	.4681388	.9596885	13.41396	.6698479	.2859790
#3	2.833521	.4669370	.9558109	13.32566	.6801623	.2849844

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1136-04 Acquired: 1/29/2025 16:09:59 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8F7S Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0006431	F 314.0590	F 21.18055	-.000418	.0104394	.0268924
Stddev	.0001279	1.1677	.03381	.001539	.0000316	.0003294
%RSD	19.88574	.3718147	.1596080	368.4065	.3030824	1.224809
#1	.0006101	313.4582	21.16184	-.000520	.0104257	.0265673
#2	.0005349	313.3140	21.21957	.001170	.0104168	.0272259
#3	.0007842	315.4048	21.16023	-.001903	.0104755	.0268841

Elem	Sr4077
Units	ppm
Avg	.3089301
Stddev	.0018101
%RSD	.5859130
#1	.3068559
#2	.3101898
#3	.3097446

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7354.686	155649.6	30987.77	5177.977	3815.781
Stddev	27.974	588.6	31.97	27.038	21.359
%RSD	.3803505	.3781564	.1031750	.5221789	.5597462
#1	7386.862	156274.3	30987.09	5208.907	3836.598
#2	7341.058	155569.1	31020.08	5166.200	3816.826
#3	7336.138	155105.3	30956.15	5158.825	3793.919

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1151-01DLX20 Acquired: 1/29/2025 16:13:53 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0317233**	**.0187045**	**.1073728**	**.0132739**	**.0490555**	**.7271002**
Stddev	.0005279	.0003207	.0009819	.0021647	.0026300	.0081165
%RSD	1.664013	1.714738	.9144672	16.30763	5.361205	1.116286
#1	.0320988	.0187048	.1074132	.0142570	.0470749	.7185702
#2	.0319514	.0190251	.1063713	.0107921	.0480520	.7347279
#3	.0311198	.0183837	.1083338	.0147725	.0520394	.7280024

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0160429**	**.0008033**	**.0003438**	**4.292522**	**25.61671**	F **6.133567**
Stddev	.0001850	.0000815	.0000623	.018369	.08224	.023482
%RSD	1.153119	10.14729	18.12453	.4279361	.3210401	.3828408
#1	.0160358	.0007656	.0002829	4.273792	25.65887	6.124181
#2	.0158616	.0007475	.0003410	4.310508	25.52194	6.116230
#3	.0162314	.0008969	.0004074	4.293265	25.66932	6.160290

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1667054**	**6.800204**	**.1110795**	**.6277432**	F **5.186416**	**.0003535**
Stddev	.0017333	.047832	.0008056	.0130387	.017616	.0002216
%RSD	1.039722	.7033941	.7252033	2.077078	.3396648	62.69897
#1	.1653690	6.765114	.1103948	.6211309	5.179465	.0006082
#2	.1686638	6.854687	.1108766	.6427633	5.173336	.0002481
#3	.1660833	6.780810	.1119671	.6193354	5.206448	.0002043

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.941499**	**.1137196**	**.1873524**	**.0050285**	**.1364766**	**.0502275**
Stddev	.205327	.0016990	.0033557	.0372403	.0011344	.0007821
%RSD	10.57572	1.494004	1.791090	740.5798	.8312144	1.557149
#1	1.897932	.1138181	.1849497	.0337766	.1351923	.0510228
#2	2.165113	.1119735	.1911864	-.037040	.1368956	.0494593
#3	1.761451	.1153672	.1859212	.018349	.1373419	.0502005

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1151-01DLX20 Acquired: 1/29/2025 16:13:53 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**3.177277**	**8.135086**	**.4162888**	**.0161244**	**.0198408**	**-.000002**
Stddev	.012342	.024440	.0050137	.0001724	.0004357	.000137
%RSD	.3884370	.3004303	1.204378	1.069250	2.196207	6809.203
#1	3.172255	8.128730	.4154840	.0162942	.0193721	.000156
#2	3.168238	8.114452	.4117262	.0159495	.0202335	-.000090
#3	3.191338	8.162077	.4216563	.0161295	.0199169	-.000073

Elem	Sr4077
Units	ppm
Avg	**.0408825**
Stddev	.0001139
%RSD	.2786286
#1	.0407904
#2	.0410099
#3	.0408472

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3339.428**	**71791.36**	**13491.01**	**2379.898**	**4156.673**
Stddev	8.951	72.42	72.00	11.548	11.110
%RSD	.2680448	.1008758	.5336683	.4852203	.2672833
#1	3331.002	71742.53	13421.37	2383.876	4147.402
#2	3348.825	71756.99	13565.15	2366.887	4168.988
#3	3338.456	71874.57	13486.51	2388.930	4153.629

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1151-02DLX5 Acquired: 1/29/2025 16:18:01 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ1 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0224758**	**-.000810**	**.5971860**	**.0115847**	**.0081355**	**9.462948**
Stddev	.0024467	.001575	.0020974	.0021431	.0021699	.030229
%RSD	10.88596	194.4647	.3512099	18.49981	26.67218	.3194482
#1	.0197104	.000129	.5980643	.0115201	.0101001	9.466875
#2	.0233577	-.002628	.5947922	.0094746	.0058064	9.491022
#3	.0243593	.000070	.5987014	.0137595	.0084998	9.430948

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0661240**	**.0009110**	**.0011463**	**7.093154**	**5.905280**	**2.425917**
Stddev	.0006479	.0000286	.0000241	.020439	.004827	.003968
%RSD	.9798166	3.135135	2.103216	.2881494	.0817374	.1635766
#1	.0653866	.0009216	.0011708	7.070211	5.901729	2.425022
#2	.0666019	.0008787	.0011453	7.109416	5.903336	2.422473
#3	.0663835	.0009327	.0011227	7.099837	5.910776	2.430256

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2892964**	**26.62786**	**.2033433**	**4.166160**	**2.371819**	**-.000252**
Stddev	.0006401	.08223	.0009601	.014595	.003918	.000181
%RSD	.2212603	.3088037	.4721664	.3503179	.1651734	71.78642
#1	.2885799	26.59233	.2022484	4.159261	2.372627	-.000191
#2	.2898116	26.72187	.2040418	4.156294	2.367561	-.000456
#3	.2894978	26.56936	.2037396	4.182926	2.375270	-.000110

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**7.196632**	**.0610559**	**.4401800**	**2.097294**	**2.377979**	**.0898778**
Stddev	.240318	.0015574	.0010872	.012758	.007362	.0009760
%RSD	3.339312	2.550789	.2469952	.6082864	.3095696	1.085962
#1	7.273524	.0624930	.4394549	2.097933	2.375897	.0904604
#2	7.389094	.0612736	.4396549	2.109719	2.371883	.0904219
#3	6.927278	.0594011	.4414301	2.084228	2.386158	.0887509

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1151-02DLX5 Acquired: 1/29/2025 16:18:01 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ1 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.3606916	F 21.85227	2.844516	.0176235	.2410962	.0168747
Stddev	.0008366	.05251	.011298	.0005364	.0011921	.0005481
%RSD	.2319455	.2402844	.3971755	3.043693	.4944378	3.247767
#1	.3615035	21.84000	2.835545	.0171122	.2411807	.0168306
#2	.3607390	21.80698	2.840799	.0175764	.2398642	.0163501
#3	.3598323	21.90982	2.857204	.0181819	.2422438	.0174435

Elem	Sr4077
Units	ppm
Avg	.1014745
Stddev	.0005048
%RSD	.4974959
#1	.1012602
#2	.1020511
#3	.1011122

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3349.137	71796.13	14046.30	2373.854	3944.941
Stddev	6.522	272.26	102.58	14.119	6.412
%RSD	.1947416	.3792176	.7302711	.5947864	.1625474
#1	3341.699	71524.57	13976.93	2362.578	3945.068
#2	3351.833	72069.09	14164.13	2389.690	3951.290
#3	3353.879	71794.74	13997.84	2369.294	3938.467

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-01 Acquired: 1/29/2025 16:21:56 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C9 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1345382	-.010367	.1231950	.0403097	.0098205	73.13456	1.798778
Stddev	.0013687	.000558	.0013984	.0029662	.0008761	.50057	.010019
%RSD	1.017311	5.377754	1.135068	7.358495	8.921597	.6844480	.5570061
#1	.1360255	-.010070	.1236131	.0370828	.0107771	73.66754	1.805782
#2	.1342573	-.010021	.1243365	.0409287	.0090571	73.06177	1.803251
#3	.1333317	-.011010	.1216352	.0429175	.0096272	72.67437	1.787302

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0026583	.0017184	22.27083	.1952257	.1653853	.2239371	173.2333
Stddev	.0000451	.0000459	.19102	.0024537	.0015786	.0015289	1.3082
%RSD	1.697215	2.671079	.8576924	1.256853	.9545085	.6827404	.7551608
#1	.0026840	.0016717	22.48630	.1980584	.1671895	.2256148	174.7433
#2	.0026846	.0017634	22.20389	.1938607	.1647078	.2226223	172.4440
#3	.0026062	.0017201	22.12229	.1937580	.1642585	.2235742	172.5125

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	8.440970	38.65893	.3214922	-.000022	.2511353	.1862940	.4268455
Stddev	.063989	.38102	.0024806	.000099	.2107686	.0007294	.0040460
%RSD	.7580805	.9855839	.7715939	438.7883	83.92630	.3915492	.9478836
#1	8.510926	39.08995	.3239007	.000090	.2005117	.1856736	.4299225
#2	8.426590	38.36702	.3216308	-.000092	.0702886	.1870976	.4283516
#3	8.385394	38.51982	.3189453	-.000066	.4826056	.1861110	.4222625

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.036655	1.779237	.3342442	.0079744	.1837722	1.662993	.0010931
Stddev	.019587	.015803	.0041147	.0003961	.0030388	.010012	.0009043
%RSD	1.889447	.8881622	1.231036	4.967571	1.653568	.6020750	82.73204
#1	1.059092	1.794920	.3386280	.0079648	.1872687	1.657749	.0000709
#2	1.027902	1.779471	.3304657	.0083753	.1822798	1.656692	.0014195
#3	1.022970	1.763318	.3336388	.0075832	.1817682	1.674539	.0017889

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-01 Acquired: 1/29/2025 16:21:56 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C9 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.6816669	.0711779	.2264513
Stddev	.0018240	.0009501	.0015161
%RSD	.2675822	1.334788	.6695165
#1	.6795918	.0710901	.2278055
#2	.6823927	.0721689	.2267349
#3	.6830164	.0702748	.2248133

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3474.073	74041.19	14909.50	2451.886	3811.544
Stddev	21.052	739.89	65.86	29.961	24.593
%RSD	.6059685	.9993002	.4417128	1.221953	.6452164
#1	3452.066	73189.53	14838.27	2419.098	3785.040
#2	3476.134	74408.21	14968.18	2458.722	3815.966
#3	3494.018	74525.82	14922.05	2477.838	3833.625

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1151-01DLX40 Acquired: 1/29/2025 16:25:56 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0187640	.0109963	.0560347	.0092146	.0211938	.4041072	.0090349
Stddev	.0004042	.0016361	.0012381	.0027796	.0012099	.0033516	.0006644
%RSD	2.153985	14.87901	2.209583	30.16553	5.708592	.8293723	7.353784
#1	.0183222	.0123765	.0571743	.0073133	.0212683	.4032520	.0090659
#2	.0191151	.0091889	.0547173	.0079258	.0199484	.4012661	.0083555
#3	.0188547	.0114233	.0562126	.0124047	.0223647	.4078035	.0096832

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0003664	.0001103	2.330600	13.53656	3.145471	.0891927	3.714706
Stddev	.0000721	.0000537	.005931	.06103	.011125	.0023206	.014884
%RSD	19.68381	48.72896	.2544785	.4508573	.3536910	2.601769	.4006658
#1	.0003479	.0001111	2.330699	13.46889	3.149227	.0918664	3.713616
#2	.0003054	.0000562	2.336481	13.55339	3.132954	.0880092	3.730105
#3	.0004460	.0001636	2.324621	13.58742	3.154232	.0877024	3.700398

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0608194	.3501130	2.673387	.0003170	1.030325	.0600911	.1017161
Stddev	.0003767	.0065209	.009986	.0001786	.267136	.0012291	.0006484
%RSD	.6193150	1.862516	.3735502	56.34592	25.92739	2.045394	.6374662
#1	.0612364	.3498135	2.678408	.0003394	1.148080	.0587265	.1024408
#2	.0607179	.3567786	2.661887	.0004833	.724542	.0604354	.1011908
#3	.0605038	.3437471	2.679867	.0001282	1.218352	.0611112	.1015167

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0383791	.0677831	.0256588	1.621930	4.160503	.2168949	.0080175
Stddev	.0370318	.0006292	.0004953	.002120	.026184	.0008647	.0007108
%RSD	96.48958	.9281890	1.930387	.1307360	.6293404	.3986843	8.865129
#1	.0379783	.0674987	.0254993	1.623450	4.187748	.2176663	.0086469
#2	.0015493	.0673464	.0252629	1.619508	4.135529	.2170583	.0081588
#3	.0756097	.0685043	.0262143	1.622832	4.158232	.2159602	.0072466

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1151-01DLX40 Acquired: 1/29/2025 16:25:56 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ0 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0105669	.0004129	.0222259
Stddev	.0003084	.0005358	.0001163
%RSD	2.918777	129.7745	.5233569
#1	.0109172	.0006745	.0222352
#2	.0103363	.0007675	.0223373
#3	.0104470	-.000203	.0221052

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3381.928	71088.64	13894.46	2349.035	4183.440
Stddev	9.629	240.63	20.84	16.889	14.724
%RSD	.2847127	.3384891	.1499736	.7189895	.3519672
#1	3370.863	71356.25	13916.71	2342.476	4169.907
#2	3386.526	70890.10	13891.26	2336.410	4199.120
#3	3388.397	71019.59	13875.41	2368.220	4181.293

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-02 Acquired: 1/29/2025 16:29:56 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C9D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1332916**	**-.008115**	**.1241497**	**.0390520**	**.0104564**	**73.31936**	**1.815188**
Stddev	.0022437	.003194	.0020063	.0026989	.0015296	.13492	.003306
%RSD	1.683272	39.36173	1.616031	6.911054	14.62833	.1840165	.1821311
#1	.1316711	-.004829	.1262752	.0418528	.0087586	73.35870	1.817508
#2	.1323513	-.008305	.1238852	.0364681	.0117271	73.43023	1.816653
#3	.1358524	-.011209	.1222888	.0388352	.0108834	73.16914	1.811402

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0026891**	**.0017957**	**22.39426**	**.1948245**	**.1655866**	**.2269862**	**173.7950**
Stddev	.0001535	.0000573	.06063	.0005559	.0009019	.0015656	.4200
%RSD	5.708195	3.193321	.2707388	.2853225	.5446574	.6897116	.2416801
#1	.0027382	.0018549	22.43003	.1952290	.1665949	.2252458	173.8842
#2	.0028120	.0017404	22.42851	.1941906	.1648567	.2282797	174.1633
#3	.0025170	.0017919	22.32426	.1950538	.1653083	.2274331	173.3375

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**8.547086**	**39.02682**	**.3210292**	**.0000818**	**-.021327**	**.1925470**	**.4237105**
Stddev	.018885	.07396	.0013079	.0003503	.165116	.0019752	.0037276
%RSD	.2209565	.1895234	.4074192	428.0148	774.1982	1.025822	.8797611
#1	8.544439	39.07596	.3224795	.0001676	-.183422	.1943838	.4232525
#2	8.567155	39.06274	.3199390	.0003813	-.027214	.1904577	.4276459
#3	8.529663	38.94175	.3206691	-.000303	.146653	.1927996	.4202330

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.038283**	**1.793097**	**.3356644**	**.0085572**	**.1819520**	**1.881504**	**.0008747**
Stddev	.015807	.007598	.0023185	.0001743	.0034081	.017314	.0006804
%RSD	1.522410	.4237169	.6907053	2.036676	1.873073	.9202142	77.78547
#1	1.050367	1.797864	.3382919	.0085774	.1821039	1.865954	.0012053
#2	1.044087	1.784336	.3347953	.0083737	.1784705	1.900161	.0013268
#3	1.020394	1.797092	.3339061	.0087205	.1852816	1.878397	.0000922

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-02 Acquired: 1/29/2025 16:29:56 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C9D Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.6911790	.0723408	.2272967
Stddev	.0008851	.0005012	.0003243
%RSD	.1280508	.6927918	.1426642
#1	.6921987	.0725685	.2269232
#2	.6906097	.0726878	.2275053
#3	.6907286	.0717663	.2274618

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3497.706	74078.34	14765.81	2491.224	3819.523
Stddev	9.312	220.51	48.65	8.570	10.019
%RSD	.2662400	.2976685	.3294990	.3440216	.2623000
#1	3487.084	74078.68	14804.52	2491.671	3808.983
#2	3504.470	73857.66	14711.19	2482.439	3828.922
#3	3501.562	74298.68	14781.72	2499.562	3820.664

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-01LX5 Acquired: 1/29/2025 16:33:55 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C9L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0279216	-.000110	.0261435	.0065358	.0010576	15.08716	.3639199
Stddev	.0002771	.002720	.0005407	.0036036	.0008637	.01812	.0010852
%RSD	.9924418	2471.147	2.068169	55.13619	81.66438	.1200781	.2982016
#1	.0276386	.002730	.0260613	.0041233	.0001171	15.09504	.3627905
#2	.0281924	-.002693	.0256486	.0048059	.0018151	15.06644	.3640144
#3	.0279339	-.000367	.0267206	.0106782	.0012406	15.10000	.3649547

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0005779	.0002057	4.653275	.0420364	.0333367	.0488310	36.44546
Stddev	.0000310	.0000233	.021649	.0001666	.0002551	.0014570	.07372
%RSD	5.362842	11.33144	.4652403	.3962448	.7652469	2.983708	.2022632
#1	.0005919	.0001909	4.632043	.0418802	.0336035	.0487312	36.50610
#2	.0005994	.0002326	4.675318	.0420172	.0333113	.0474265	36.46687
#3	.0005424	.0001937	4.652463	.0422117	.0330952	.0503353	36.36341

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.761334	8.019258	.0656501	-.000500	.0326023	.0437304	.0862960
Stddev	.002824	.036007	.0000984	.000410	.2736923	.0010148	.0009154
%RSD	.1603167	.4490008	.1499041	82.04253	839.4875	2.320548	1.060706
#1	1.758134	7.987159	.0657231	-.000526	-.099770	.0445519	.0861383
#2	1.763476	8.058193	.0655382	-.000078	-.149739	.0440433	.0872800
#3	1.762391	8.012423	.0656888	-.000897	.347315	.0425961	.0854698

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1995205	.3576457	.0630225	.0018730	.0430623	.7778326	-.000241
Stddev	.0034329	.0016931	.0006494	.0001855	.0044145	.0028200	.000837
%RSD	1.720562	.4734081	1.030421	9.903475	10.25135	.3625475	347.0602
#1	.1974933	.3565762	.0623347	.0016860	.0481529	.7749590	.000269
#2	.2034841	.3567631	.0631076	.0020569	.0402895	.7805958	-.001207
#3	.1975842	.3595978	.0636251	.0018762	.0407444	.7779430	.000214

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-01LX5 Acquired: 1/29/2025 16:33:55 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C9L Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.1472591	.0148808	.0466970
Stddev	.0002732	.0010703	.0001165
%RSD	.1855379	7.192142	.2493707
#1	.1473897	.0140609	.0465939
#2	.1474425	.0144900	.0468233
#3	.1469451	.0160916	.0466738

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3478.687	72252.00	13844.90	2442.941	4084.368
Stddev	5.406	259.66	71.78	14.891	6.106
%RSD	.1554021	.3593872	.5184823	.6095590	.1494912
#1	3472.473	72446.43	13880.73	2444.690	4077.865
#2	3481.282	71957.12	13762.25	2427.252	4085.259
#3	3482.306	72352.46	13891.70	2456.880	4089.979

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-03 Acquired: 1/29/2025 16:38:00 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C9S Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1989204	.0721886	.1586515	.2090398	.1820507	75.13967	5.519214
Stddev	.0012356	.0020713	.0014387	.0039625	.0022335	.42569	.088679
%RSD	.6211361	2.869326	.9068333	1.895588	1.226875	.5665296	1.606729
#1	.1976060	.0698360	.1601376	.2114475	.1827368	75.03786	5.543283
#2	.2000580	.0729914	.1572654	.2112054	.1795546	75.60704	5.420986
#3	.1990973	.0737383	.1585514	.2044663	.1838607	74.77412	5.593375

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0933429	.0981251	21.87760	.6036258	1.119101	.6882171	171.6394
Stddev	.0004915	.0010430	.03871	.0026362	.010214	.0039767	.4100
%RSD	.5265741	1.062885	.1769366	.4367203	.9127070	.5778318	.2388546
#1	.0938591	.0991475	21.91326	.6065531	1.128486	.6872993	171.8532
#2	.0928805	.0970627	21.88312	.6028848	1.108222	.6925725	171.8983
#3	.0932891	.0981651	21.83643	.6014394	1.120596	.6847795	171.1667

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	9.269824	37.92954	1.274786	.0707116	.2919342	1.142171	1.311123
Stddev	.026451	.13104	.013424	.0009065	.1509470	.004531	.010927
%RSD	.2853414	.3454787	1.053069	1.281940	51.70582	.3966679	.8333774
#1	9.267612	38.08074	1.285816	.0714425	.2532445	1.138259	1.315679
#2	9.297311	37.85889	1.259839	.0709951	.1640977	1.141118	1.319034
#3	9.244549	37.84899	1.278704	.0696973	.4584602	1.147135	1.298655

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.007179	1.743936	.3264262	.0077095	.1770812	2.600234	.0008911
Stddev	.008007	.018528	.0047247	.0002250	.0047845	.017727	.0010068
%RSD	.7950061	1.062443	1.447386	2.918952	2.701842	.6817640	112.9916
#1	1.000545	1.761382	.3248346	.0075526	.1825618	2.585378	-.000041
#2	1.016074	1.724488	.3317411	.0079673	.1737383	2.595466	.001959
#3	1.004919	1.745938	.3227029	.0076086	.1749436	2.619858	.000756

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-03 Acquired: 1/29/2025 16:38:00 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8C9S Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.6848287	.0709029	.2237726
Stddev	.0039212	.0005327	.0017554
%RSD	.5725808	.7513310	.7844509
#1	.6807523	.0705935	.2227825
#2	.6851600	.0705972	.2257994
#3	.6885737	.0715180	.2227359

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3551.130	74783.27	14845.48	2498.132	3894.601
Stddev	20.817	286.07	107.69	15.656	30.436
%RSD	.5862209	.3825270	.7253787	.6267221	.7814970
#1	3533.563	74468.35	14768.89	2480.968	3869.746
#2	3574.123	75027.07	14968.61	2501.796	3928.547
#3	3545.704	74854.38	14798.95	2511.631	3885.510

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-04 Acquired: 1/29/2025 16:42:04 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D1 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0887378	-.011760	.0787777	.0693282	.0165920	121.9645	.3674591
Stddev	.0022932	.002327	.0018034	.0038167	.0006506	1.0064	.0024645
%RSD	2.584289	19.79146	2.289271	5.505237	3.921170	.8251620	.6706778
#1	.0911409	-.011266	.0794296	.0716241	.0158409	120.9884	.3650328
#2	.0865731	-.014295	.0801645	.0714381	.0169536	121.9065	.3673845
#3	.0884995	-.009719	.0767389	.0649223	.0169814	122.9987	.3699600

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0002061	.0044174	22.85970	.2406294	.1510998	.3629217	288.8741
Stddev	.0000574	.0000237	.14685	.0008478	.0008404	.0045191	1.6275
%RSD	27.85674	.5370632	.6423988	.3523202	.5562145	1.245186	.5633941
#1	.0002536	.0043903	22.72364	.2411317	.1505256	.3593829	287.2934
#2	.0002225	.0044344	22.84011	.2396506	.1507092	.3613700	288.7842
#3	.0001423	.0044277	23.01537	.2411060	.1520644	.3680121	290.5447

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	3.856474	69.45780	.5787482	-.001581	.1586748	.1877630	.8447507
Stddev	.019841	.23025	.0026737	.000255	.1504231	.0028125	.0072577
%RSD	.5144842	.3315005	.4619886	16.15163	94.79962	1.497916	.8591536
#1	3.837738	69.21319	.5770728	-.001681	.1412538	.1874028	.8371684
#2	3.854423	69.48987	.5773400	-.001771	.3170498	.1851479	.8454506
#3	3.877260	69.67034	.5818317	-.001290	.0177207	.1907383	.8516331

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	3.636893	4.628483	.5552343	.0078159	.1170053	3.369085	.0015378
Stddev	.003790	.020881	.0122962	.0001650	.0051089	.017887	.0003214
%RSD	.1041987	.4511315	2.214600	2.110623	4.366362	.5309281	20.90182
#1	3.634817	4.616401	.5424110	.0076416	.1225796	3.374185	.0017620
#2	3.641267	4.616455	.5563666	.0078366	.1125459	3.349201	.0011695
#3	3.634596	4.652594	.5669251	.0079696	.1158905	3.383868	.0016817

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-04 Acquired: 1/29/2025 16:42:04 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D1 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.2520343	.2451030	.2154560
Stddev	.0031067	.0020283	.0018797
%RSD	1.232661	.8275084	.8724049
#1	.2495242	.2429598	.2135534
#2	.2555089	.2453568	.2155029
#3	.2510698	.2469924	.2173118

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3445.026	74137.83	14975.68	2432.202	3706.353
Stddev	17.442	173.85	65.16	10.918	12.966
%RSD	.5062929	.2344890	.4350867	.4489023	.3498216
#1	3454.745	74246.64	14900.73	2444.213	3710.549
#2	3455.443	74229.52	15007.47	2429.514	3716.700
#3	3424.890	73937.34	15018.84	2422.878	3691.809

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-05 Acquired: 1/29/2025 16:46:01 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D3 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**1.256717**	**-.021119**	**.2933137**	**.0894242**	**.0383522**	**17.47713**
Stddev	.003641	.000248	.0003109	.0017594	.0016715	.07660
%RSD	.2897251	1.174566	.1059982	1.967506	4.358164	.4382918
#1	1.252528	-.021315	.2930750	.0897451	.0401157	17.40520
#2	1.258495	-.021200	.2932008	.0910011	.0381496	17.46853
#3	1.259127	-.020840	.2936653	.0875264	.0367912	17.55767

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2465302**	**.0006597**	**.0070313**	**303.5352**	**.0233365**	**.2057084**
Stddev	.0014390	.0001525	.0001416	1.9324	.0001904	.0003957
%RSD	.5837104	23.11815	2.013833	.6366232	.8160572	.1923707
#1	.2450057	.0007862	.0069185	305.7422	.0231441	.2058010
#2	.2467198	.0007026	.0069852	302.7163	.0235249	.2052746
#3	.2478650	.0004904	.0071902	302.1471	.0233405	.2060496

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.6357874**	**335.3643**	**5.291124**	**86.32386**	**.8198033**	**-.001542**
Stddev	.0034018	.9827	.020346	.35949	.0018325	.000145
%RSD	.5350502	.2930364	.3845346	.4164378	.2235309	9.431751
#1	.6386451	334.2462	5.271712	85.96757	.8203824	-.001656
#2	.6366924	335.7557	5.289370	86.68645	.8177512	-.001378
#3	.6320246	336.0911	5.312290	86.31755	.8212763	-.001591

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0789373**	**-.000262**	**.3997445**	**6.031671**	**8.785172**	**.5555663**
Stddev	.1228436	.000756	.0019542	.041413	.035136	.0057771
%RSD	155.6217	289.1233	.4888719	.6865925	.3999446	1.039858
#1	-.026121	-.001134	.3974895	6.077656	8.798267	.5542468
#2	.048928	.000135	.4007993	5.997317	8.745370	.5505631
#3	.214005	.000214	.4009448	6.020040	8.811881	.5618890

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-05 Acquired: 1/29/2025 16:46:01 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8D3 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0176206	F 148.8798	2.253039	-.001275	.0674164	.0308626
Stddev	.0005230	.4595	.025577	.000908	.0014263	.0003879
%RSD	2.968210	.3086108	1.135239	71.18077	2.115596	1.256726
#1	.0178769	148.9528	2.223514	-.001490	.0677750	.0313099
#2	.0179660	148.3882	2.267138	-.000279	.0686292	.0306188
#3	.0170189	149.2984	2.268464	-.002056	.0658451	.0306592

Elem	Sr4077
Units	ppm
Avg	3.750075
Stddev	.028509
%RSD	.7602258
#1	3.749366
#2	3.721926
#3	3.778931

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3424.983	74428.86	14738.65	2429.649	3453.599
Stddev	7.727	193.58	102.68	6.510	10.038
%RSD	.2255925	.2600862	.6966882	.2679283	.2906595
#1	3420.926	74382.17	14721.65	2422.598	3444.688
#2	3433.892	74262.90	14645.53	2435.430	3464.474
#3	3420.129	74641.52	14848.77	2430.918	3451.635

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-06 Acquired: 1/29/2025 16:50:14 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E2 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0501549	-.001240	.1224121	.0374812	.0075337	68.62378	.2786039
Stddev	.0021631	.003235	.0006409	.0044340	.0013166	.55767	.0024726
%RSD	4.312808	260.8047	.5235320	11.82998	17.47626	.8126516	.8875100
#1	.0517200	.002486	.1222881	.0351506	.0074955	69.26766	.2814569
#2	.0476866	-.003328	.1218423	.0346985	.0062366	68.29384	.2770808
#3	.0510580	-.002880	.1231059	.0425945	.0088690	68.30984	.2772740

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0007501	.0013262	11.36348	.0459947	.0614190	.3675516	140.7550
Stddev	.0000717	.0000858	.06465	.0002159	.0005908	.0018699	.8272
%RSD	9.556740	6.467776	.5689162	.4694046	.9618876	.5087346	.5877157
#1	.0006674	.0012471	11.43813	.0458904	.0615190	.3654069	141.7099
#2	.0007929	.0013141	11.32630	.0458507	.0607846	.3684085	140.3001
#3	.0007902	.0014173	11.32601	.0462429	.0619534	.3688396	140.2551

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.6125545	52.68390	.1649776	-.001030	.5003016	.0175115	.7279208
Stddev	.0023178	.21520	.0012326	.000298	.1801363	.0006896	.0057294
%RSD	.3783777	.4084760	.7471187	28.96343	36.00553	3.938028	.7870883
#1	.6143350	52.93196	.1642469	-.000925	.5696077	.0169213	.7284984
#2	.6099338	52.57256	.1642853	-.000798	.6354913	.0173436	.7219244
#3	.6133946	52.54717	.1664007	-.001367	.2958058	.0182695	.7333394

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	3.953129	2.934455	.2694166	.0216714	7.937990	4.289885	-.000420
Stddev	.101298	.025796	.0050015	.0001838	.067173	.024270	.000453
%RSD	2.562472	.8790612	1.856404	.8481026	.8462264	.5657504	107.7185
#1	4.069037	2.931643	.2747413	.0218113	7.918953	4.293313	.000084
#2	3.881562	2.910181	.2686909	.0214633	7.882390	4.312258	-.000552
#3	3.908788	2.961542	.2648177	.0217396	8.012628	4.264083	-.000793

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: Q1159-06 Acquired: 1/29/2025 16:50:14 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: YE8E2 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.1338812	.1732689	.0887259
Stddev	.0008944	.0016405	.0006002
%RSD	.6680438	.9467989	.6764925
#1	.1346043	.1751632	.0894023
#2	.1341582	.1723177	.0882567
#3	.1328811	.1723257	.0885188

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3402.878	72344.57	14367.31	2416.732	3864.416
Stddev	20.907	240.22	56.19	5.721	29.720
%RSD	.6144053	.3320534	.3910789	.2367054	.7690565
#1	3408.460	72109.34	14428.78	2411.159	3869.607
#2	3420.429	72334.87	14318.61	2416.449	3891.197
#3	3379.747	72589.50	14354.53	2422.589	3832.442

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: PB166301BL Acquired: 1/29/2025 16:54:14 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: PBS301 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0014722**	**.0005788**	**-.000162**	**-.000209**	**-.000888**	**.0034935**	**-.001386**
Stddev	.0016262	.0011777	.000134	.000890	.001241	.0022699	.000364
%RSD	110.4589	203.4647	82.83515	425.0691	139.7520	64.97396	26.29039
#1	.0027938	.0002126	-.000271	.000632	.000318	.0011899	-.000981
#2	.0019666	.0018960	-.000012	-.000119	-.000820	.0035624	-.001687
#3	-.000344	-.000372	-.000203	-.001141	-.002162	.0057281	-.001490

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000065**	**.0000037**	**.0006040**	**.0000265**	**-.000088**	**.0016828**	**.0012867**
Stddev	.000059	.0000537	.0043221	.0004206	.000046	.0018395	.0020630
%RSD	90.61835	1444.386	715.6025	1588.415	52.76473	109.3091	160.3251
#1	.000002	-.000058	-.001006	-.000379	-.000137	-.000152	.0033567
#2	-.000109	.000031	.005500	-.000003	-.000080	.001673	.0012727
#3	-.000086	.000039	-.002682	.000461	-.000046	.003527	-.000769

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000009**	**.0163660**	**.0000343**	**.0002192**	**-.051921**	**.0018158**	**.0001182**
Stddev	.000310	.0152790	.0001385	.0000848	.164522	.0005337	.0029826
%RSD	3612.855	93.35854	403.4249	38.68333	316.8716	29.39162	2524.196
#1	.000119	.0173273	.0001412	.0002970	.115684	.0024221	-.002983
#2	.000218	.0006290	.0000839	.0002317	-.213176	.0016084	.000371
#3	-.000362	.0311416	-.000122	.0001288	-.058270	.0014170	.002966

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.082991**	**-.000544**	**-.001887**	**.0000723**	**.0140713**	**.0020464**	**-.000790**
Stddev	.043761	.000712	.000507	.0002118	.0010214	.0025711	.000608
%RSD	52.73033	130.8203	26.84248	292.7730	7.258593	125.6384	76.93164
#1	-.035963	-.000722	-.001303	.0003136	.0152476	.0042574	-.001421
#2	-.090493	.000240	-.002201	-.000014	.0134097	-.000775	-.000209
#3	-.122516	-.001150	-.002158	-.000083	.0135565	.002657	-.000741

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: PB166301BL Acquired: 1/29/2025 16:54:14 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: PBS301 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0008493	-.001151	-.000035
Stddev	.0003171	.001222	.000020
%RSD	37.33305	106.1694	57.37050
#1	.0006801	-.001257	-.000054
#2	.0012151	.000120	-.000036
#3	.0006527	-.002318	-.000014

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3434.646	72163.04	13392.38	2452.905	4175.397
Stddev	2.399	126.32	41.20	7.232	6.759
%RSD	.0698387	.1750503	.3076184	.2948397	.1618852
#1	3432.762	72068.35	13349.34	2444.568	4172.126
#2	3437.346	72114.30	13396.36	2457.486	4183.170
#3	3433.830	72306.47	13431.45	2456.662	4170.895

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: PB166301BS Acquired: 1/29/2025 16:58:23 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LCS301 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0204015**	**.0533871**	**.0204333**	**.0696364**	**.1149056**	**.3743441**	**.3857782**
Stddev	.0020603	.0011946	.0011372	.0008329	.0006655	.0071780	.0057485
%RSD	10.09856	2.237617	5.565605	1.196045	.5791292	1.917494	1.490119
#1	.0213022	.0526877	.0214121	.0686946	.1154593	.3661194	.3804609
#2	.0180443	.0547665	.0207022	.0702761	.1141673	.3793454	.3918779
#3	.0218581	.0527072	.0191858	.0699384	.1150900	.3775674	.3849958

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0103759**	**.0101741**	**9.603222**	**.0220295**	**.0993005**	**.0540444**	**.2034108**
Stddev	.0000124	.0000791	.108865	.0003788	.0000607	.0017744	.0058525
%RSD	.1199413	.7774273	1.133626	1.719663	.0611091	3.283175	2.877188
#1	.0103898	.0101047	9.511716	.0222531	.0993062	.0543044	.2059993
#2	.0103657	.0102602	9.723617	.0222433	.0992371	.0556744	.2075227
#3	.0103721	.0101574	9.574333	.0215921	.0993581	.0521543	.1967104

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0309728**	**8.624251**	**.0806772**	**.0196446**	**9.472246**	**.1064658**	**.1198823**
Stddev	.0005916	.062660	.0001685	.0003003	.397996	.0019069	.0014560
%RSD	1.909907	.7265507	.2088680	1.528595	4.201704	1.791039	1.214505
#1	.0302907	8.577438	.0808069	.0193709	9.275993	.1082080	.1194766
#2	.0312824	8.695434	.0807380	.0199658	9.210491	.1067609	.1214981
#3	.0313453	8.599879	.0804867	.0195969	9.930253	.1044287	.1186722

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**9.211476**	**.0164769**	**-.001202**	**.0211628**	**.1814764**	**.8716308**	**.0134407**
Stddev	.112971	.0013291	.001173	.0000983	.0039241	.0045356	.0009027
%RSD	1.226418	8.066280	97.62356	.4642728	2.162291	.5203641	6.716086
#1	9.086019	.0169538	-.001973	.0210897	.1849568	.8670806	.0144690
#2	9.305155	.0149752	.000148	.0211243	.1822487	.8716603	.0127792
#3	9.243254	.0175017	-.001781	.0212745	.1772236	.8761517	.0130739

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: PB166301BS Acquired: 1/29/2025 16:58:23 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: LCS301 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.2080600	.0292012	.1964681
Stddev	.0013034	.0011893	.0027596
%RSD	.6264287	4.072850	1.404620
#1	.2073680	.0293204	.1937806
#2	.2095634	.0303265	.1992946
#3	.2072486	.0279568	.1963290

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3358.142	70595.31	13609.37	2370.478	4008.387
Stddev	5.275	680.25	56.62	20.041	3.913
%RSD	.1570865	.9635915	.4160270	.8454342	.0976280
#1	3359.037	70920.25	13559.92	2384.715	4005.895
#2	3362.912	69813.52	13597.07	2347.560	4012.897
#3	3352.477	71052.15	13671.13	2379.157	4006.369

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: CCV029 Acquired: 1/29/2025 17:02:27 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV029 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**5.138618**	**4.871049**	**24.74611**	**5.106162**	**5.195191**	**400.1911**	**10.57906**
Stddev	.004666	.033871	.01247	.017924	.017703	8.0587	.28465
%RSD	.0908082	.6953495	.0504108	.3510250	.3407505	2.013715	2.690697
#1	5.134306	4.834905	24.73613	5.086391	5.180835	391.0433	10.27558
#2	5.137977	4.902061	24.74211	5.110749	5.189766	406.2419	10.84012
#3	5.143572	4.876181	24.76010	5.121347	5.214971	403.2881	10.62148

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4963027**	**2.491449**	**406.6289**	**15.75585**	**2.507844**	**15.12346**	**406.6988**
Stddev	.0042664	.002536	8.4825	.36069	.003415	.06353	6.8989
%RSD	.8596333	.1017761	2.086056	2.289268	.1361807	.4200955	1.696324
#1	.4914756	2.490737	399.2950	15.35606	2.506132	15.05011	399.0782
#2	.4978637	2.494265	415.9184	16.05687	2.505624	15.15972	412.5191
#3	.4995687	2.489346	404.6731	15.85461	2.511777	15.16057	408.4992

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**15.54516**	**402.4020**	**2.497105**	**1.316177**	**388.2909**	**2.490063**	**15.86578**
Stddev	.28424	6.4836	.002375	.028090	1.2989	.013804	.43350
%RSD	1.828485	1.611228	.0951015	2.134229	.3345215	.5543536	2.732288
#1	15.24168	395.1436	2.495763	1.285061	387.0067	2.479007	15.42721
#2	15.80514	407.6198	2.495705	1.339666	388.2620	2.485647	16.29403
#3	15.58867	404.4427	2.499847	1.323804	389.6041	2.505534	15.87611

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**164.3148**	**4.982163**	**5.396442**	**5.038787**	**5.040049**	**4.890863**	**4.985871**
Stddev	2.9331	.013057	.056849	.013319	.011868	.024028	.009646
%RSD	1.785031	.2620662	1.053458	.2643236	.2354655	.4912817	.1934705
#1	161.0852	4.968407	5.330805	5.028852	5.037419	4.864580	4.975107
#2	166.8129	4.983700	5.430076	5.033587	5.053011	4.911702	4.988773
#3	165.0463	4.994384	5.428445	5.053921	5.029717	4.896306	4.993733

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: CCV029 Acquired: 1/29/2025 17:02:27 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV029 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	**5.007080**	**5.401779**	**5.385030**
Stddev	.019205	.110489	.104220
%RSD	.3835628	2.045422	1.935372
#1	4.985420	5.283238	5.280026
#2	5.013790	5.501902	5.488449
#3	5.022030	5.420196	5.386615

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2767.424**	**59931.80**	**12834.65**	**1943.987**	**3008.578**
Stddev	6.399	1073.69	39.64	48.667	3.297
%RSD	.2312185	1.791527	.3088727	2.503474	.1095744
#1	2769.802	61101.51	12868.05	1994.675	3008.553
#2	2772.293	58991.06	12845.06	1897.630	3011.888
#3	2760.177	59702.84	12790.84	1939.657	3005.295

Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: CCB029 Acquired: 1/29/2025 17:06:45 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB029 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0005161	.0004822	.0004229	-.000197	.0002698	.0028082	-.000049
Stddev	.0008616	.0014907	.0017112	.000885	.0025665	.0040995	.001067
%RSD	166.9242	309.1627	404.6330	448.9100	951.1562	145.9824	2165.134
#1	-.000444	.0007864	-.000202	-.000552	.0003166	.0025719	-.001215
#2	.000772	.0017973	-.000888	-.000850	.0028127	-.001168	.000188
#3	.001221	-.001137	.002359	.000811	-.002320	.007021	.000879

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000025	-.000009	.0126753	.0002820	-.000264	.0006676	.0012756
Stddev	.000066	.000085	.0057133	.0002602	.000113	.0003769	.0067152
%RSD	261.6348	986.6360	45.07415	92.25884	42.80054	56.45544	526.4178
#1	.000045	.000086	.0070665	.0000092	-.000232	.0009174	-.004984
#2	-.000084	-.000080	.0184876	.0005274	-.000390	.0002341	.008369
#3	-.000036	-.000032	.0124718	.0003095	-.000170	.0008513	.000442

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000044	.0111232	-.000005	-.000039	.0764491	.0011841	.0005432
Stddev	.000074	.0019353	.000534	.000074	.4911489	.0017759	.0012147
%RSD	170.6646	17.39868	11081.35	188.9181	642.4519	149.9798	223.6179
#1	-.000063	.0093486	.000050	.000004	.4575309	.0031458	.0016268
#2	.000039	.0131867	-.000564	-.000125	-.477836	-.000314	.0007726
#3	-.000106	.0108343	.000500	.000004	.249652	.000720	-.000770

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0886969	-.001276	.0023639	.0002095	.0066403	-.000141	-.000272
Stddev	.0223749	.000301	.0004744	.0003216	.0024157	.000466	.000051
%RSD	25.22620	23.55349	20.06705	153.5475	36.37993	329.2323	18.63826
#1	.1068021	-.001365	.0021266	-.000140	.0094218	-.000597	-.000330
#2	.0636823	-.000941	.0029100	.000493	.0054320	.000333	-.000242
#3	.0956064	-.001523	.0020550	.000276	.0050671	-.000160	-.000243


Reviewed By:Mohan
On:1/31/2025 7:33:47 AM
Inst Id :P4

Sample Name: CCB029 Acquired: 1/29/2025 17:06:45 Type: Unk
Method: EPA SFAM01.0(v59) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB029 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	-.000046	.0007411	.0000052
Stddev	.000410	.0005966	.0000571
%RSD	897.9000	80.50076	1098.683
#1	.000298	.0012986	-.000054
#2	.000065	.0001119	.000010
#3	-.000500	.0008127	.000060

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3363.619	72843.87	13860.85	2396.212	4111.113
Stddev	6.179	153.73	10.39	4.343	10.825
%RSD	.1837010	.2110445	.0749355	.1812621	.2633219
#1	3369.820	72678.29	13852.73	2400.212	4122.495
#2	3357.462	72982.07	13857.25	2391.592	4100.947
#3	3363.575	72871.24	13872.55	2396.831	4109.896

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




As 189.042 {479}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000011	Re-Slope:	1.000000
A1 (Gain):	0.065912	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998154	Status:	OK.
Std Error of Est:	0.000067		
Predicted MDL:	0.002414		
Predicted MQL:	0.008048		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00001	.000	1
S1	.01000	.00792	-.002	-20.8	.00051	.000	1
S3	2.5000	2.2591	-.241	-9.64	.14860	.001	1
S4	5.0000	4.9103	-.090	-1.79	.32305	.001	1
S5	10.000	10.490	.490	4.90	.69026	.002	1
S2	1.2500	1.0923	-.158	-12.6	.07184	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Tl 190.856 {477}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000098	Re-Slope:	1.000000
A1 (Gain):	0.052511	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999669	Status:	OK.
Std Error of Est:	0.000035		
Predicted MDL:	0.002590		
Predicted MQL:	0.008632		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00010	.000	1
S1	.02500	.02746	.002	9.84	.00148	.000	1
S3	2.5000	2.5564	.056	2.25	.13180	.000	1
S4	5.0000	5.1275	.128	2.55	.26427	.003	1
S5	10.000	9.7668	-.233	-2.33	.50281	.003	1
S2	1.2500	1.2969	.047	3.75	.06693	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Pb 220.353 {453}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000009	Re-Slope:	1.000000
A1 (Gain):	0.241062	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999906	Status:	OK.
Std Error of Est:	0.000124		
Predicted MDL:	0.001447		
Predicted MQL:	0.004824		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00001	.000	1
S1	.01000	.00906	-.001	-9.43	.00218	.000	1
S3	12.500	12.419	-.081	-.649	2.9912	.006	1
S4	25.000	25.563	.563	2.25	6.1571	.035	1
S5	50.000	49.604	-.396	-.792	11.948	.018	1
S2	6.2500	6.1653	-.085	-1.36	1.4850	.004	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Se 196.090 {472}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000367	Re-Slope:	1.000000
A1 (Gain):	0.070101	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998545	Status:	OK.
Std Error of Est:	0.000118		
Predicted MDL:	0.002826		
Predicted MQL:	0.009420		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00037	.000	1
S1	.03500	.02919	-.006	-16.6	.00241	.000	1
S3	2.5000	2.2755	-.224	-8.98	.15827	.001	1
S4	5.0000	4.9344	-.066	-1.31	.34304	.002	1
S5	10.000	10.426	.426	4.26	.72481	.002	1
S2	1.2500	1.1196	-.130	-10.4	.07804	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Sb 206.833 {463}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000145	Re-Slope:	1.000000
A1 (Gain):	0.149539	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998332	Status:	OK.
Std Error of Est:	0.000360		
Predicted MDL:	0.001610		
Predicted MQL:	0.005368		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00002	.000	.000	.00015	.000	1
S1	.06000	.05435	-.006	-9.41	.00826	.000	1
S3	2.5000	2.2701	-.230	-9.20	.34460	.001	1
S4	5.0000	4.9049	-.095	-1.90	.74359	.002	1
S5	10.000	10.481	.481	4.81	1.5874	.004	1
S2	1.2500	1.1000	-.150	-12.0	.16713	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Al 396.152 { 85}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000071	Re-Slope:	1.000000
A1 (Gain):	0.012817	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998414	Status:	OK.
Std Error of Est:	0.000450		
Predicted MDL:	0.008223		
Predicted MQL:	0.027411		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00007	.000	.000	.00007	.000	1
S1	.20000	.18357	-.016	-8.22	.00243	.000	1
S3	77.500	68.616	-8.88	-11.5	.88070	.004	1
S4	155.00	137.26	-17.7	-11.4	1.7617	.025	1
S5	310.00	317.10	7.10	2.29	4.0690	.001	1
S2	38.750	34.467	-4.28	-11.1	.44243	.002	1
S6	800.00	823.86	23.9	2.98	10.560	.051	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Ba 493.409 { 68}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.007260	Re-Slope:	1.000000
A1 (Gain):	0.420809	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.997347	Status:	OK.
Std Error of Est:	0.003264		
Predicted MDL:	0.000887		
Predicted MQL:	0.002958		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00003	.000	.000	.00727	.000	1
S1	.20000	.19166	-.008	-4.17	.08791	.000	1
S3	5.0000	4.6824	-.318	-6.35	1.9777	.012	1
S4	10.000	9.0765	-.924	-9.24	3.8267	.010	1
S5	20.000	21.349	1.35	6.75	8.9911	.093	1
S2	2.5000	2.4003	-.100	-3.99	1.0173	.004	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Be 234.861 {144}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000128	Re-Slope:	1.000000
A1 (Gain):	3.638766	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998511	Status:	OK.
Std Error of Est:	0.000743		
Predicted MDL:	0.000074		
Predicted MQL:	0.000246		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00013	.000	1
S1	.00500	.00516	.000	3.18	.01862	.000	1
S3	.25000	.25984	.010	3.94	.94127	.005	1
S4	.50000	.53717	.037	7.43	1.9463	.013	1
S5	1.0000	.95120	-.049	-4.88	3.4447	.016	1
S2	.12500	.12663	.002	1.30	.45860	.003	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Cd 214.438 {457}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000073	Re-Slope:	1.000000
A1 (Gain):	2.717444	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999800	Status:	OK.
Std Error of Est:	0.000457		
Predicted MDL:	0.000081		
Predicted MQL:	0.000270		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00007	.000	1
S1	.00500	.00511	.000	2.26	.01383	.000	1
S3	1.2500	1.2667	.017	1.33	3.4488	.000	1
S4	2.5000	2.5690	.069	2.76	6.9944	.045	1
S5	5.0000	4.9101	-.090	-1.80	13.370	.031	1
S2	.62500	.62919	.004	.670	1.7131	.003	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Ca 373.690 { 90}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000076	Re-Slope:	1.000000
A1 (Gain):	0.008614	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999189	Status:	OK.
Std Error of Est:	0.001211		
Predicted MDL:	0.009502		
Predicted MQL:	0.031675		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00082	.001	.000	.00008	.000	1
S2	62.500	60.236	-2.26	-3.62	.51895	.001	1
S3	125.00	117.97	-7.03	-5.62	1.0163	.004	1
S4	250.00	229.63	-20.4	-8.15	1.9781	.025	1
S5	500.00	510.94	10.9	2.19	4.4013	.016	1
S1	5.0000	4.8232	-.177	-3.54	.04162	.000	1
S6	800.00	818.90	18.9	2.36	7.0540	.033	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Cr 267.716 {126}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000013	Re-Slope:	1.000000
A1 (Gain):	0.164361	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999603	Status:	OK.
Std Error of Est:	0.000137		
Predicted MDL:	0.000424		
Predicted MQL:	0.001413		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00001	.000	1
S1	.01000	.01053	.001	5.26	.00172	.000	1
S3	7.7500	8.0010	.251	3.24	1.3154	.006	1
S4	15.500	15.901	.401	2.59	2.6142	.019	1
S5	31.000	30.189	-.811	-2.62	4.9631	.017	1
S2	3.8750	4.0334	.158	4.09	.66308	.003	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Co 228.616 {448}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000028	Re-Slope:	1.000000
A1 (Gain):	0.878522	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999933	Status:	OK.
Std Error of Est:	0.000272		
Predicted MDL:	0.000275		
Predicted MQL:	0.000918		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00003	.000	1
S1	.05000	.04996	-.000	-.074	.04409	.001	1
S3	1.2500	1.2492	-.001	-.064	1.1016	.003	1
S4	2.5000	2.5473	.047	1.89	2.2462	.012	1
S5	5.0000	4.9591	-.041	-.819	4.3734	.007	1
S2	.62500	.61948	-.006	-.884	.54634	.001	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Cu 324.754 {104}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.003008	Re-Slope:	1.000000
A1 (Gain):	0.111380	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999646	Status:	OK.
Std Error of Est:	0.000136		
Predicted MDL:	0.002548		
Predicted MQL:	0.008492		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00301	.000	1
S1	.02500	.02406	-.001	-3.76	.00569	.000	1
S3	7.5000	7.3233	-.177	-2.36	.81860	.007	1
S4	15.000	14.487	-.513	-3.42	1.6164	.004	1
S5	30.000	30.728	.728	2.43	3.4252	.016	1
S2	3.7500	3.7124	-.038	-1.00	.41645	.002	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Fe 259.837 {130}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000010	Re-Slope:	1.000000
A1 (Gain):	0.005259	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999616	Status:	OK.
Std Error of Est:	0.000064		
Predicted MDL:	0.006563		
Predicted MQL:	0.021875		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00001	.000	1
S1	.10000	.09730	-.003	-2.70	.00051	.000	1
S3	75.000	72.669	-2.33	-3.11	.38179	.002	1
S4	150.00	140.13	-9.87	-6.58	.73619	.010	1
S5	300.00	309.71	9.71	3.24	1.6273	.007	1
S2	37.500	37.306	-.194	-.518	.19601	.001	1
S6	800.00	802.68	2.68	.335	4.2215	.039	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Mn 257.610 {131}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000034	Re-Slope:	1.000000
A1 (Gain):	0.091048	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998985	Status:	OK.
Std Error of Est:	0.000146		
Predicted MDL:	0.000365		
Predicted MQL:	0.001216		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00003	.000	1
S1	.01500	.01615	.001	7.70	.00144	.000	1
S3	7.5000	7.2580	-.242	-3.23	.66032	.004	1
S4	15.000	14.068	-.932	-6.22	1.2799	.015	1
S5	30.000	31.202	1.20	4.01	2.8389	.010	1
S2	3.7500	3.7214	-.029	-.763	.33856	.001	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Mg 279.079 {121}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000085	Re-Slope:	1.000000
A1 (Gain):	0.002327	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998535	Status:	OK.
Std Error of Est:	0.000440		
Predicted MDL:	0.018409		
Predicted MQL:	0.061364		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00163	.002	.000	-.00008	.000	1
S2	62.500	57.507	-4.99	-7.99	.13374	.000	1
S3	125.00	114.42	-10.6	-8.47	.26617	.001	1
S4	250.00	225.31	-24.7	-9.88	.52422	.007	1
S5	500.00	513.45	13.5	2.69	1.1948	.004	1
S1	5.0000	4.3780	-.622	-12.4	.01010	.000	1
S6	800.00	827.44	27.4	3.43	1.9254	.013	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Ni 231.604 {446}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000403	Re-Slope:	1.000000
A1 (Gain):	0.627148	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999886	Status:	OK.
Std Error of Est:	0.000225		
Predicted MDL:	0.000432		
Predicted MQL:	0.001439		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00040	.000	1
S1	.04000	.04128	.001	3.20	.02551	.000	1
S3	1.2500	1.2581	.008	.651	.79047	.002	1
S4	2.5000	2.5552	.055	2.21	1.6057	.007	1
S5	5.0000	4.9353	-.065	-1.29	3.1021	.003	1
S2	.62500	.62508	.000	.013	.39253	.001	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Ag 328.068 {103}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000283	Re-Slope:	1.000000
A1 (Gain):	0.286681	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999736	Status:	OK.
Std Error of Est:	0.000053		
Predicted MDL:	0.000391		
Predicted MQL:	0.001304		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00028	.000	1
S1	.01000	.00941	-.001	-5.87	.00240	.000	1
S3	.62500	.60250	-.022	-3.60	.16613	.000	1
S4	1.2500	1.2479	-.002	-.171	.34483	.003	1
S5	2.5000	2.5409	.041	1.64	.70290	.001	1
S2	.31250	.29679	-.016	-5.03	.08164	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Na 818.326 { 41}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.002869	Re-Slope:	1.000000
A1 (Gain):	0.001935	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999004	Status:	OK.
Std Error of Est:	0.000267		
Predicted MDL:	0.436363		
Predicted MQL:	1.454542		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00087	.001	.000	-.00287	.000	1
S2	37.500	35.509	-1.99	-5.31	.06586	.001	1
S3	75.000	69.990	-5.01	-6.68	.13260	.001	1
S4	150.00	137.27	-12.7	-8.49	.26282	.001	1
S5	300.00	291.69	-8.31	-2.77	.56170	.003	1
S1	5.0000	5.1129	.113	2.26	.00703	.000	1
S6	800.00	827.93	27.9	3.49	1.5996	.009	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




V 292.402 {115}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000064	Re-Slope:	1.000000
A1 (Gain):	0.123461	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999954	Status:	OK.
Std Error of Est:	0.000030		
Predicted MDL:	0.002004		
Predicted MQL:	0.006679		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00006	.000	1
S1	.05000	.05285	.003	5.70	.00658	.000	1
S3	1.2500	1.2652	.015	1.21	.14724	.001	1
S4	2.5000	2.5065	.007	.260	.29147	.001	1
S5	5.0000	4.9652	-.035	-.697	.57697	.002	1
S2	.62500	.63515	.010	1.62	.07397	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Zn 213.856 {158}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000156	Re-Slope:	1.000000
A1 (Gain):	0.291517	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998477	Status:	OK.
Std Error of Est:	0.001150		
Predicted MDL:	0.001811		
Predicted MQL:	0.006038		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00016	.000	1
S1	.06000	.05848	-.002	-2.53	.01731	.000	1
S3	7.5000	7.0475	-.453	-6.03	2.0629	.012	1
S4	15.000	14.102	-.898	-5.99	4.1275	.025	1
S5	30.000	31.557	1.56	5.19	9.2326	.026	1
S2	3.7500	3.5448	-.205	-5.47	1.0376	.004	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




K 769.896 { 44}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.005877	Re-Slope:	1.000000
A1 (Gain):	0.003801	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.997831	Status:	OK.
Std Error of Est:	0.000517		
Predicted MDL:	0.051766		
Predicted MQL:	0.172555		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00133	.001	.000	.00588	.000	1
S2	37.500	34.316	-3.18	-8.49	.13631	.001	1
S3	75.000	69.080	-5.92	-7.89	.26844	.001	1
S4	150.00	141.08	-8.92	-5.95	.54209	.008	1
S5	300.00	318.55	18.5	6.18	1.2166	.005	1
S1	5.0000	4.4799	-.520	-10.4	.02290	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




P 177.495 {490}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.001307	Re-Slope:	1.000000
A1 (Gain):	0.049371	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999718	Status:	OK.
Std Error of Est:	0.000020		
Predicted MDL:	0.002314		
Predicted MQL:	0.007714		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00131	.000	1
S1	.01000	.00890	-.001	-11.0	-.00087	.000	1
S3	2.5000	2.4206	-.079	-3.18	.11732	.000	1
S4	5.0000	5.0965	.097	1.93	.24855	.001	1
S5	10.000	10.067	.067	.667	.49217	.001	1
S2	1.2500	1.1673	-.083	-6.61	.05589	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




B 249.678 {135}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000878	Re-Slope:	1.000000
A1 (Gain):	0.360096	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.996861	Status:	OK.
Std Error of Est:	0.000409		
Predicted MDL:	0.000792		
Predicted MQL:	0.002639		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00088	.000	1
S1	.01000	.00016	-.010	-98.4	.00075	.000	1
S3	2.5000	2.6577	.158	6.31	.82548	.004	1
S4	5.0000	5.3850	.385	7.70	1.6752	.011	1
S5	10.000	9.4135	-.587	-5.87	2.8609	.014	1
S2	1.2500	1.3047	.055	4.38	.40450	.003	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Mo 202.030 {467}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000206	Re-Slope:	1.000000
A1 (Gain):	0.782992	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999637	Status:	OK.
Std Error of Est:	0.000354		
Predicted MDL:	0.000284		
Predicted MQL:	0.000947		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00021	.000	1
S1	.01000	.01008	.000	.845	.00810	.000	1
S3	2.5000	2.3927	-.107	-4.29	1.8737	.006	1
S4	5.0000	4.9623	-.038	-.754	3.8856	.018	1
S5	10.000	10.216	.216	2.16	7.9994	.013	1
S2	1.2500	1.1787	-.071	-5.70	.92312	.001	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




S 182.034 {485}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000200	Re-Slope:	1.000000
A1 (Gain):	0.029188	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998962	Status:	OK.
Std Error of Est:	0.000071		
Predicted MDL:	0.003954		
Predicted MQL:	0.013179		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00003	.000	.000	.00020	.000	1
S1	.10000	.08193	-.018	-18.1	.00259	.000	1
S3	2.5000	2.3246	-.175	-7.02	.06814	.000	1
S4	5.0000	5.0501	.050	1.00	.14779	.001	1
S5	10.000	10.282	.282	2.82	.30067	.000	1
S2	1.2500	1.1118	-.138	-11.1	.03270	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Si 251.611 {134}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000445	Re-Slope:	1.000000
A1 (Gain):	0.031215	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.970316	Status:	OK.
Std Error of Est:	0.000415		
Predicted MDL:	0.005228		
Predicted MQL:	0.017428		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00033	-.000	.000	.00044	.000	1
S1	.10000	.44200	.342	342.	.01424	.000	1
S3	2.5000	2.4553	-.045	-1.79	.07732	.001	1
S4	5.0000	4.8605	-.140	-2.79	.15263	.000	1
S5	10.000	9.8739	-.126	-1.26	.30960	.001	1
S2	1.2500	1.2192	-.031	-2.46	.03862	.000	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Sn 189.989 {478}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000254	Re-Slope:	1.000000
A1 (Gain):	0.159209	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999872	Status:	OK.
Std Error of Est:	0.000036		
Predicted MDL:	0.000836		
Predicted MQL:	0.002785		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00025	.000	1
S1	.00700	.00691	-.000	-1.30	.00130	.000	1
S3	2.5000	2.5046	.005	.183	.39777	.000	1
S4	5.0000	5.1272	.127	2.54	.81408	.005	1
S5	10.000	9.8851	-.115	-1.15	1.5691	.002	1
S2	1.2500	1.2333	-.017	-1.34	.19599	.001	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Ti 336.121 {100}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.001797	Re-Slope:	1.000000
A1 (Gain):	0.350349	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999967	Status:	OK.
Std Error of Est:	0.000152		
Predicted MDL:	0.000941		
Predicted MQL:	0.003135		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	.00179	.000	1
S1	.10000	.10389	.004	3.89	.03819	.000	1
S3	2.5000	2.5313	.031	1.25	.88865	.006	1
S4	5.0000	4.9774	-.023	-.452	1.7456	.005	1
S5	10.000	9.9632	-.037	-.368	3.4924	.014	1
S2	1.2500	1.2742	.024	1.93	.44820	.002	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Li 670.784 { 50}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000363	Re-Slope:	1.000000
A1 (Gain):	0.145503	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.996087	Status:	OK.
Std Error of Est:	0.000265		
Predicted MDL:	0.001359		
Predicted MQL:	0.004531		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00036	.000	1
S5	10.000	10.830	.830	8.30	1.5762	.008	1
S4	5.0000	4.5281	-.472	-9.44	.65922	.010	1
S3	2.5000	2.2513	-.249	-9.95	.32794	.002	1
S1	.01500	.01395	-.001	-6.97	.00239	.000	1
S2	1.2500	1.1413	-.109	-8.69	.16643	.001	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Sr 407.771 { 83}

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000076	Re-Slope:	1.000000
A1 (Gain):	1.438087	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.997898	Status:	OK.
Std Error of Est:	0.004963		
Predicted MDL:	0.000073		
Predicted MQL:	0.000242		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00009	.000	1
S1	.10000	.09642	-.004	-3.58	.13873	.001	1
S3	2.5000	2.3875	-.113	-4.50	3.4335	.028	1
S4	5.0000	4.5521	-.448	-8.96	6.5464	.011	1
S5	10.000	10.582	.582	5.82	15.218	.027	1
S2	1.2500	1.2316	-.018	-1.47	1.7713	.008	1

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Y 224.306 {450}*

Date of Fit:	1/31/2025 22:44:26	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.000000	Status:	Warning Zero Gain
Std Error of Est:	0.000000		
Predicted MDL:	n/a		
Predicted MQL:	n/a		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



Y 360.073 { 94}*


Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

A2 (Curvature):	0.000000				
n (Exponent):	1.000000				
Correlation:	0.000000	Status:	Warning	Zero Gain	
Std Error of Est:	0.000000				
Predicted MDL:	n/a				
Predicted MQL:	n/a				

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis




Y 371.030 { 91}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.000000	Status:	Warning Zero Gain
Std Error of Est:	0.000000		
Predicted MDL:	n/a		
Predicted MQL:	n/a		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4




Y 224.306 {150}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.000000	Status:	Warning Zero Gain
Std Error of Est:	0.000000		
Predicted MDL:	n/a		
Predicted MQL:	n/a		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



In 230.606 {446}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

A2 (Curvature):		0.000000					
n (Exponent):		1.000000					
Correlation:		0.000000		Status:	Warning	Zero Gain	
Std Error of Est:		0.000000					
Predicted MDL:		n/a					
Predicted MQL:		n/a					

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S0 Acquired: 1/31/2025 16:26:48 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00001**	**.00010**	**.00001**	**.00037**	**.00015**	**.00007**	**.00727**	**-.00013**
Stddev	.00011	.00011	.00012	.00013	.00024	.00005	.00035	.00031
%RSD	1014.5	111.96	1336.7	36.193	164.81	74.716	4.8599	236.05
#1	-.00014	.00001	.00007	.00048	.00011	.00013	.00717	-.00043
#2	.00004	.00022	-.00013	.00022	-.00007	.00005	.00698	.00018
#3	.00007	.00007	.00009	.00041	.00041	.00003	.00767	-.00014

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00007**	**.00008**	**-.00001**	**.00003**	**.00301**	**.00001**	**-.00003**	**-.00008**
Stddev	.00013	.00008	.00004	.00011	.00010	.00002	.00004	.00004
%RSD	172.25	95.116	305.74	382.72	3.3159	187.91	117.42	51.826
#1	.00006	.00014	.00003	.00005	.00297	-.00001	-.00007	-.00013
#2	-.00020	-.00001	-.00003	.00012	.00312	.00003	-.00004	-.00005
#3	-.00008	.00012	-.00004	-.00009	.00293	.00001	.00001	-.00006

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**-.00040**	**-.00028**	**-.00287**	**.00006**	**.00016**	**.00588**	**-.00131**	**.00088**
Stddev	.00010	.00005	.00029	.00014	.00038	.00018	.00005	.00026
%RSD	25.776	17.434	10.170	221.48	239.64	3.0303	3.7108	29.134
#1	-.00052	-.00024	-.00260	.00010	-.00023	.00607	-.00136	.00109
#2	-.00038	-.00027	-.00283	.00018	.00053	.00587	-.00127	.00095
#3	-.00032	-.00034	-.00318	-.00009	.00018	.00571	-.00129	.00060

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00021**	**.00020**	**.00044**	**.00025**	**.00179**	**.00036**	**.00009**
Stddev	.00012	.00005	.00008	.00010	.00012	.00013	.00003
%RSD	55.777	26.602	18.237	41.187	6.4272	36.601	37.062
#1	.00033	.00014	.00034	.00021	.00184	.00050	.00008
#2	.00019	.00024	.00048	.00037	.00188	.00023	.00013
#3	.00010	.00022	.00048	.00018	.00166	.00035	.00007

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S0 Acquired: 1/31/2025 16:26:48 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3400.6	71457.	13593.	2376.4	4176.4
Stddev	2.0	50.	49.	9.1	7.7
%RSD	.05985	.07008	.35692	.38178	.18506
#1	3400.3	71469.	13564.	2370.0	4176.4
#2	3402.7	71500.	13649.	2386.8	4184.1
#3	3398.7	71402.	13565.	2372.4	4168.7

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S1 Acquired: 1/31/2025 16:31:04 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00051**	**.00148**	**.00218**	**.00241**	**.00826**	**.00243**	**.08791**	**.01862**
Stddev	.00008	.00010	.00021	.00019	.00013	.00009	.00036	.00011
%RSD	15.594	6.5160	9.8476	7.7092	1.5722	3.7844	.40967	.60656
#1	.00043	.00142	.00224	.00244	.00816	.00232	.08751	.01857
#2	.00058	.00144	.00194	.00221	.00840	.00247	.08821	.01875
#3	.00052	.00160	.00235	.00257	.00820	.00249	.08802	.01854

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.01383**	**.04162**	**.00172**	**.04409**	**.00569**	**.00051**	**.00144**	**.01010**
Stddev	.00019	.00011	.00002	.00058	.00036	.00003	.00003	.00003
%RSD	1.3568	.27568	1.3017	1.3177	6.3629	4.9383	1.8392	.29009
#1	.01367	.04155	.00169	.04343	.00561	.00049	.00146	.01011
#2	.01379	.04176	.00174	.04452	.00608	.00054	.00144	.01013
#3	.01404	.04156	.00172	.04431	.00537	.00050	.00141	.01007

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.02551**	**.00240**	**.00703**	**.00658**	**.01731**	**.02290**	**-.00087**	**.00075**
Stddev	.00025	.00004	.00014	.00020	.00038	.00011	.00004	.00019
%RSD	.98612	1.7137	1.9712	3.0203	2.1866	.46873	4.9768	25.097
#1	.02536	.00236	.00692	.00640	.01699	.02288	-.00092	.00087
#2	.02580	.00244	.00697	.00679	.01720	.02302	-.00086	.00085
#3	.02538	.00239	.00718	.00654	.01773	.02281	-.00083	.00053

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.00810**	**.00259**	**.01424**	**.00130**	**.03819**	**.00239**	**.13873**
Stddev	.00018	.00002	.00016	.00006	.00017	.00022	.00075
%RSD	2.2311	.78538	1.1328	4.6778	.43587	9.3462	.54266
#1	.00792	.00260	.01431	.00133	.03838	.00238	.13810
#2	.00828	.00261	.01406	.00123	.03809	.00218	.13956
#3	.00810	.00257	.01436	.00135	.03810	.00262	.13854

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S1 Acquired: 1/31/2025 16:31:04 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3399.7	71055.	13733.	2402.1	4115.8
Stddev	36.3	97.	59.	5.0	44.6
%RSD	1.0673	.13639	.43248	.20836	1.0845
#1	3441.2	71008.	13684.	2407.8	4165.6
#2	3374.1	70991.	13799.	2399.1	4079.4
#3	3383.8	71167.	13716.	2399.2	4102.3

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S2 Acquired: 1/31/2025 16:35:19 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.07184**	**.06693**	**1.4850**	**.07804**	**.16713**	**.44243**	**1.0173**	**.45860**
Stddev	.00019	.00022	.0042	.00024	.00040	.00216	.0040	.00258
%RSD	.26557	.32537	.28491	.30625	.24009	.48738	.39489	.56163
#1	.07182	.06699	1.4809	.07831	.16735	.44264	1.0165	.46061
#2	.07204	.06669	1.4846	.07785	.16667	.44447	1.0217	.45570
#3	.07166	.06711	1.4894	.07797	.16737	.44017	1.0138	.45949

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**1.7131**	**.51895**	**.66308**	**.54634**	**.41645**	**.19601**	**.33856**	**.13374**
Stddev	.0033	.00133	.00294	.00091	.00176	.00082	.00067	.00025
%RSD	.19363	.25535	.44379	.16657	.42175	.42074	.19850	.18438
#1	1.7097	.51883	.66432	.54565	.41762	.19596	.33873	.13382
#2	1.7132	.52032	.66519	.54600	.41443	.19686	.33913	.13394
#3	1.7163	.51768	.65972	.54737	.41730	.19521	.33781	.13346

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.39253**	**.08164**	**.06586**	**.07397**	**1.0376**	**.13631**	**.05589**	**.40450**
Stddev	.00055	.00020	.00075	.00045	.0035	.00063	.00022	.00322
%RSD	.14034	.24719	1.1355	.60695	.33876	.46031	.38906	.79671
#1	.39196	.08155	.06580	.07386	1.0379	.13649	.05567	.40494
#2	.39258	.08188	.06514	.07358	1.0410	.13682	.05589	.40108
#3	.39306	.08151	.06664	.07446	1.0340	.13561	.05610	.40748

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**.92312**	**.03270**	**.03862**	**.19599**	**.44820**	**.16643**	**1.7713**
Stddev	.00140	.00020	.00021	.00053	.00213	.00083	.0082
%RSD	.15207	.60471	.53097	.27052	.47568	.49642	.46376
#1	.92414	.03250	.03875	.19565	.44820	.16642	1.7703
#2	.92151	.03270	.03838	.19572	.44607	.16726	1.7799
#3	.92370	.03290	.03873	.19660	.45034	.16561	1.7636

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S2 Acquired: 1/31/2025 16:35:19 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3267.2	67374.	13395.	2284.5	3777.0
Stddev	9.5	231.	74.	8.8	6.3
%RSD	.29219	.34249	.55176	.38679	.16697
#1	3257.3	67292.	13362.	2281.2	3774.2
#2	3276.3	67196.	13479.	2277.9	3784.2
#3	3267.8	67635.	13343.	2294.6	3772.6

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S3 Acquired: 1/31/2025 16:39:17 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.14860	.13180	2.9912	.15827	.34460	.88070	1.9777	.94127
Stddev	.00064	.00024	.0058	.00102	.00147	.00386	.0124	.00503
%RSD	.43257	.18329	.19312	.64401	.42697	.43858	.62640	.53472
#1	.14809	.13161	2.9879	.15762	.34439	.88469	1.9909	.94692
#2	.14839	.13207	2.9879	.15773	.34324	.87698	1.9663	.93966
#3	.14932	.13171	2.9979	.15944	.34616	.88041	1.9758	.93725

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3.4488	1.0163	1.3154	1.1016	.81860	.38179	.66032	.26617
Stddev	.0003	.0043	.0064	.0032	.00668	.00153	.00444	.00070
%RSD	.00842	.42833	.48776	.28614	.81603	.40070	.67174	.26337
#1	3.4485	1.0210	1.3225	1.0996	.82608	.38332	.66503	.26683
#2	3.4487	1.0125	1.3102	1.1001	.81647	.38026	.65623	.26544
#3	3.4491	1.0153	1.3133	1.1053	.81325	.38179	.65970	.26626

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.79047	.16613	.13260	.14724	2.0629	.26844	.11732	.82548
Stddev	.00220	.00044	.00123	.00101	.0115	.00107	.00012	.00367
%RSD	.27830	.26469	.92434	.68793	.55773	.39713	.10289	.44429
#1	.78800	.16662	.13378	.14835	2.0744	.26940	.11745	.82972
#2	.79120	.16600	.13133	.14698	2.0514	.26729	.11730	.82345
#3	.79222	.16577	.13268	.14638	2.0627	.26863	.11721	.82329

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.8737	.06814	.07732	.39777	.88865	.32794	3.4335
Stddev	.0062	.00032	.00082	.00050	.00601	.00194	.0280
%RSD	.33213	.47390	1.0669	.12513	.67646	.59192	.81668
#1	1.8723	.06784	.07826	.39761	.89548	.33001	3.4579
#2	1.8683	.06811	.07670	.39737	.88634	.32616	3.4396
#3	1.8805	.06848	.07700	.39833	.88414	.32765	3.4029

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S3 Acquired: 1/31/2025 16:39:17 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3115.0	65791.	12827.	2210.2	3579.0
Stddev	6.1	314.	88.	5.9	8.2
%RSD	.19601	.47707	.68325	.26900	.22773
#1	3120.1	65430.	12733.	2203.5	3588.4
#2	3116.8	66000.	12844.	2212.8	3574.7
#3	3108.2	65943.	12905.	2214.5	3574.0

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S4 Acquired: 1/31/2025 16:43:19 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.32305	.26427	6.1571	.34304	.74359	1.7617	3.8267	1.9463
Stddev	.00129	.00280	.0347	.00199	.00247	.0254	.0096	.0130
%RSD	.39873	1.0581	.56274	.58004	.33264	1.4412	.25055	.66929
#1	.32206	.26399	6.1587	.34222	.74268	1.7329	3.8375	1.9614
#2	.32258	.26163	6.1217	.34160	.74170	1.7811	3.8236	1.9383
#3	.32450	.26720	6.1910	.34531	.74639	1.7709	3.8191	1.9393

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	6.9944	1.9781	2.6142	2.2462	1.6164	.73619	1.2799	.52422
Stddev	.0451	.0249	.0194	.0116	.0043	.00955	.0152	.00663
%RSD	.64436	1.2585	.74289	.51573	.26334	1.2976	1.1892	1.2645
#1	6.9958	1.9510	2.5932	2.2466	1.6193	.72559	1.2633	.51692
#2	6.9486	2.0000	2.6315	2.2344	1.6183	.74413	1.2932	.52986
#3	7.0387	1.9834	2.6178	2.2576	1.6115	.73885	1.2832	.52588

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.6057	.34483	.26282	.29147	4.1275	.54209	.24855	1.6752
Stddev	.0071	.00261	.00087	.00091	.0248	.00805	.00138	.0108
%RSD	.44034	.75809	.32924	.31251	.60139	1.4856	.55718	.64702
#1	1.6059	.34194	.26327	.29193	4.0994	.53323	.24826	1.6877
#2	1.5986	.34703	.26336	.29206	4.1464	.54898	.24733	1.6684
#3	1.6127	.34551	.26182	.29042	4.1368	.54405	.25006	1.6694

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3.8856	.14779	.15263	.81408	1.7456	.65922	6.5464
Stddev	.0178	.00057	.00023	.00462	.0050	.00950	.0114
%RSD	.45734	.38892	.15312	.56777	.28870	1.4415	.17374
#1	3.8828	.14771	.15286	.81550	1.7499	.64852	6.5518
#2	3.8694	.14726	.15264	.80891	1.7469	.66668	6.5541
#3	3.9046	.14840	.15240	.81782	1.7401	.66245	6.5334

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S4 Acquired: 1/31/2025 16:43:19 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2788.1**	**62499.**	**12080.**	**2054.0**	**3237.8**
Stddev	9.6	502.	70.	4.7	13.2
%RSD	.34255	.80356	.57849	.22849	.40718
#1	2790.3	63073.	12000.	2057.5	3238.4
#2	2796.4	62137.	12129.	2055.9	3250.7
#3	2777.6	62289.	12110.	2048.7	3224.4

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S5 Acquired: 1/31/2025 16:47:27 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.69026	.50281	11.948	.72481	1.5874	4.0690	8.9911	3.4447
Stddev	.00157	.00316	.018	.00160	.0039	.0013	.0932	.0157
%RSD	.22695	.62854	.15030	.22023	.24417	.03304	1.0366	.45516
#1	.68959	.49936	11.931	.72484	1.5865	4.0682	9.0121	3.4375
#2	.68914	.50351	11.944	.72319	1.5840	4.0684	9.0721	3.4627
#3	.69205	.50556	11.967	.72639	1.5916	4.0706	8.8893	3.4339

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	13.370	4.4013	4.9631	4.3734	3.4252	1.6273	2.8389	1.1948
Stddev	.031	.0163	.0173	.0070	.0161	.0065	.0098	.0043
%RSD	.23238	.37066	.34787	.16041	.47075	.39994	.34342	.36176
#1	13.338	4.3959	4.9778	4.3677	3.4088	1.6207	2.8300	1.1905
#2	13.370	4.4196	4.9674	4.3712	3.4410	1.6273	2.8493	1.1947
#3	13.400	4.3883	4.9441	4.3812	3.4258	1.6337	2.8375	1.1991

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3.1021	.70290	.56170	.57697	9.2326	1.2166	.49217	2.8609
Stddev	.0033	.00135	.00323	.00239	.0257	.0051	.00112	.0138
%RSD	.10604	.19248	.57549	.41508	.27888	.42191	.22714	.48103
#1	3.0989	.70139	.55869	.57471	9.2035	1.2118	.49104	2.8535
#2	3.1020	.70400	.56512	.57948	9.2419	1.2161	.49221	2.8768
#3	3.1054	.70332	.56128	.57672	9.2525	1.2220	.49327	2.8525

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707	Sr4077
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	7.9994	.30067	.30960	1.5691	3.4924	1.5762	15.218
Stddev	.0125	.00035	.00060	.0022	.0142	.0083	.027
%RSD	.15659	.11600	.19388	.13925	.40742	.52856	.17652
#1	7.9885	.30029	.30895	1.5671	3.4784	1.5673	15.222
#2	7.9967	.30075	.31013	1.5687	3.5068	1.5775	15.244
#3	8.0131	.30097	.30972	1.5715	3.4920	1.5838	15.190

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S5 Acquired: 1/31/2025 16:47:27 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2430.6**	**58748.**	**12893.**	**1894.0**	**2959.9**
Stddev	1.9	78.	47.	1.4	2.1
%RSD	.07651	.13264	.36391	.07429	.06947
#1	2432.4	58838.	12895.	1893.3	2961.0
#2	2428.7	58704.	12844.	1893.2	2957.5
#3	2430.7	58702.	12938.	1895.7	2961.2

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: S6 Acquired: 1/31/2025 16:52:07 Type: Cal
Method: EPA SFAM01.0(v60) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S06 Custom ID2: Custom ID3:
Comment:

Elem	Al3961	Ca3736	Fe2598	Mg2790	Na8183
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**10.560**	**7.0540**	**4.2215**	**1.9254**	**1.5996**
Stddev	.051	.0328	.0394	.0129	.0091
%RSD	.48263	.46458	.93323	.67168	.56950
#1	10.580	7.0498	4.2665	1.9402	1.5896
#2	10.597	7.0887	4.2047	1.9198	1.6074
#3	10.501	7.0236	4.1932	1.9163	1.6018

Int. Std.	Y_3600	Y_3710
Units	Cts/S	Cts/S
Avg	**56095.**	**12301.**
Stddev	147.	96.
%RSD	.26134	.78292
#1	55933.	12409.
#2	56133.	12271.
#3	56218.	12223.

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: ICV006 Acquired: 1/31/2025 17:17:28 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICV006 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.9822586	1.066711	1.010652	.9330015	.9759196	F 2.138289
Stddev	.0003771	.007260	.002947	.0040719	.0050825	.008911
%RSD	.0383883	.6805857	.2915799	.4364254	.5207881	.4167255
#1	.9826849	1.068637	1.011319	.9376952	.9785304	2.130197
#2	.9821222	1.058682	1.007429	.9308937	.9700623	2.136830
#3	.9819687	1.072813	1.013209	.9304157	.9791660	2.147839

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.4825508	.5184406	.5165063	9.551728	.5654049	.5150804
Stddev	.0001912	.0018402	.0024243	.018246	.0014050	.0022341
%RSD	.0396118	.3549469	.4693705	.1910207	.2484947	.4337296
#1	.4824942	.5191048	.5168413	9.541280	.5669817	.5157804
#2	.4827638	.5163606	.5139319	9.572797	.5642859	.5125801
#3	.4823943	.5198566	.5187457	9.541108	.5649471	.5168806

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5209667	9.991560	.5058778	F 5.179168	.5243344	.2375983
Stddev	.0023821	.010306	.0013232	.003956	.0017215	.0002367
%RSD	.4572428	.1031438	.2615620	.0763793	.3283272	.0996223
#1	.5215122	10.00051	.5067446	5.177829	.5236589	.2375207
#2	.5183592	9.99387	.5043547	5.183620	.5230530	.2378641
#3	.5230288	9.98029	.5065339	5.176056	.5262912	.2374101

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	9.383659	.5261798	1.049919	F 8.517718	F .0058026	F .0193004
Stddev	.328504	.0012767	.008566	.023671	.0019503	.0003158
%RSD	3.500814	.2426314	.8158337	.2779024	33.61137	1.636455
#1	9.533471	.5247929	1.056979	8.491052	.0078587	.0196137
#2	9.006954	.5273061	1.040390	8.536248	.0039788	.0193054
#3	9.610551	.5264403	1.052388	8.525855	.0055703	.0189821

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: ICV006 Acquired: 1/31/2025 17:17:28 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICV006 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F -.000474	F -.000481	F .0060277	F -.000755	F -.000674	F .0004842
Stddev	.000191	.000912	.0009419	.000351	.000088	.0007077
%RSD	40.35201	189.6715	15.62624	46.43667	13.06549	146.1666
#1	-.000685	-.001399	.0060846	-.001093	-.000775	.0011443
#2	-.000311	.000425	.0050587	-.000778	-.000628	.0005714
#3	-.000426	-.000468	.0069399	-.000393	-.000618	-.000263

Elem	Sr4077
Units	ppm
Avg	F .0011655
Stddev	.0000224
%RSD	1.920796
#1	.0011910
#2	.0011560
#3	.0011494

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3367.709	70656.87	13607.04	2396.590	3999.336
Stddev	11.761	168.28	59.51	8.189	13.986
%RSD	.3492286	.2381598	.4373685	.3416736	.3497086
#1	3362.536	70486.07	13583.29	2389.014	3994.340
#2	3381.169	70822.51	13674.76	2405.277	4015.134
#3	3359.420	70662.02	13563.07	2395.479	3988.535

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: ICB006 Acquired: 1/31/2025 17:21:25 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICB006 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0000982**	**.0014048**	**-.000240**	**.0002097**	**.0007064**	**-.004265**	**.0024687**
Stddev	.0014500	.0010229	.000939	.0020037	.0010282	.000557	.0005469
%RSD	1476.645	72.81338	391.6789	955.5018	145.5705	13.05510	22.15124
#1	.0005239	.0018185	.000542	.0010375	.0014876	-.004504	.0026084
#2	.0012877	.0021560	-.001281	.0016669	.0010900	-.004664	.0018656
#3	-.001517	.0002399	.000019	-.002075	-.000459	-.003629	.0029322

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0000491**	**.0000117**	**-.002980**	**.0000623**	**-.000045**	**-.003156**	**-.000406**
Stddev	.0000209	.0000045	.009639	.0003331	.000180	.000537	.004781
%RSD	42.58244	38.97476	323.4574	534.8323	399.7292	17.01416	1176.556
#1	.0000250	.0000139	-.013641	.0004045	-.000223	-.002555	-.003832
#2	.0000604	.0000064	.005118	-.000261	-.000051	-.003588	.005055
#3	.0000621	.0000147	-.000417	.000043	.000138	-.003324	-.002442

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0001770**	**.0122557**	**-.000116**	**-.000318**	**-.039517**	**.0014489**	**.0003953**
Stddev	.0000830	.0023333	.000181	.000461	.348566	.0011415	.0005781
%RSD	46.91015	19.03820	155.0883	144.9556	882.0723	78.78329	146.2341
#1	.0002683	.0149388	.000050	-.000069	.315338	.0002214	-.000207
#2	.0001062	.0107026	-.000092	-.000850	-.381433	.0024785	.000946
#3	.0001564	.0111256	-.000308	-.000035	-.052455	.0016469	.000447

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.006036**	**.0002353**	**.0023614**	**-.000092**	**-.003716**	**.0027113**	**.0003049**
Stddev	.034965	.0022680	.0007215	.000129	.001973	.0050194	.0006771
%RSD	579.2966	964.1013	30.55226	139.3720	53.09987	185.1292	222.0564
#1	-.046034	.0027780	.0019369	.000056	-.005313	-.000761	-.000429
#2	.009201	-.000493	.0019529	-.000179	-.004325	.000428	.000437
#3	.018726	-.001579	.0031945	-.000153	-.001510	.008466	.000906

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: ICB006 Acquired: 1/31/2025 17:21:25 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICB006 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0005464	-.000127	-.000009
Stddev	.0003369	.000528	.000036
%RSD	61.65996	415.2304	406.6464
#1	.0008115	-.000683	.000029
#2	.0001673	.000367	-.000013
#3	.0006604	-.000065	-.000042

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3459.634	71329.39	13458.89	2415.809	4215.324
Stddev	13.150	191.36	24.38	9.790	15.225
%RSD	.3800918	.2682761	.1811541	.4052346	.3611801
#1	3455.470	71119.10	13430.86	2405.920	4211.624
#2	3474.361	71493.29	13470.56	2425.496	4232.058
#3	3449.069	71375.78	13475.24	2416.012	4202.290

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: ICSA006 Acquired: 1/31/2025 17:25:34 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSA006 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0021171**	**-.003725**	**.0017538**	**.0160488**	**.0077991**	**216.5302**
Stddev	.0020339	.001539	.0018839	.0012738	.0005315	1.8875
%RSD	96.07016	41.32629	107.4137	7.936956	6.815474	.8716988
#1	-.000203	-.005241	.0010542	.0149562	.0080534	217.0352
#2	.002961	-.002164	.0003199	.0157425	.0081557	214.4416
#3	.003593	-.003769	.0038875	.0174479	.0071882	218.1139

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0045252**	**-.000464**	**.0002466**	**228.3647**	**.0611873**	**.0008073**
Stddev	.0008825	.000072	.0001129	1.1323	.0005416	.0002728
%RSD	19.50298	15.59136	45.80966	.4958370	.8851914	33.79473
#1	.0038017	-.000547	.0002423	228.0544	.0606024	.0006160
#2	.0055085	-.000433	.0001358	227.4198	.0612882	.0011198
#3	.0042654	-.000413	.0003616	229.6197	.0616714	.0006863

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.005140**	**95.75845**	**.0096116**	**225.9772**	**.0032081**	**-.003093**
Stddev	.002211	.45139	.0002978	1.3315	.0006016	.000199
%RSD	43.02294	.4713885	3.098060	.5892074	18.75307	6.439066
#1	-.002839	95.66345	.0094083	225.7205	.0038164	-.003300
#2	-.005332	95.36212	.0094731	224.7928	.0031944	-.003078
#3	-.007249	96.24978	.0099534	227.4184	.0026134	-.002903

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.147374**	**-.006674**	**-.006403**	**-.254217**	**.0080045**	F **.1242909**
Stddev	.567737	.000795	.001430	.002695	.0021774	.0029804
%RSD	385.2365	11.91500	22.33576	1.059945	27.20251	2.397929
#1	-.199221	-.006793	-.008020	-.252579	.0072679	.1217562
#2	-.687408	-.005826	-.005302	-.257327	.0062910	.1235421
#3	.444509	-.007402	-.005888	-.252745	.0104547	.1275743

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: ICSA006 Acquired: 1/31/2025 17:25:34 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSA006 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000211**	**.0158241**	**.0052122**	**-.004392**	**-.002176**	**.0043491**
Stddev	.000533	.0061856	.0016824	.000742	.000349	.0006022
%RSD	252.5799	39.08956	32.27841	16.89657	16.06125	13.84546
#1	.000356	.0171200	.0068111	-.005236	-.002180	.0037682
#2	-.000288	.0212591	.0034572	-.003839	-.001824	.0043087
#3	-.000701	.0090933	.0053683	-.004102	-.002523	.0049705

Elem	Sr4077
Units	ppm
Avg	**.0934777**
Stddev	.0003301
%RSD	.3531723
#1	.0935520
#2	.0931168
#3	.0937644

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3079.622**	**64413.24**	**12745.28**	**2143.420**	**3452.823**
Stddev	6.033	245.59	23.57	7.271	.828
%RSD	.1959140	.3812766	.1849052	.3392139	.0239764
#1	3086.529	64484.82	12745.43	2143.903	3452.692
#2	3076.950	64615.08	12721.63	2150.437	3453.709
#3	3075.385	64139.81	12768.77	2135.919	3452.069

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: ICSAB006 Acquired: 1/31/2025 17:41:34 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSAB006 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.1051486**	**.1026398**	**.0532430**	**.0651033**	**.5379053**	**227.7445**
Stddev	.0018453	.0053739	.0009150	.0018421	.0037602	.2684
%RSD	1.754894	5.235712	1.718458	2.829461	.6990494	.1178415
#1	.1044272	.1043605	.0524308	.0640067	.5408968	227.9738
#2	.1037731	.1069426	.0542343	.0640732	.5336842	227.4493
#3	.1072456	.0966163	.0530641	.0672300	.5391349	227.8104

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.5089985**	**.4997799**	**1.008776**	**240.1874**	**.6003782**	**.5079266**
Stddev	.0037165	.0003284	.002029	1.1537	.0024699	.0012363
%RSD	.7301502	.0657193	.2010943	.4803353	.4113869	.2434041
#1	.5094144	.4998107	1.006461	239.9693	.6003485	.5066112
#2	.5124895	.4994372	1.010243	241.4345	.6028628	.5090646
#3	.5050916	.5000919	1.009625	239.1582	.5979233	.5081040

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4930261**	**99.99812**	**.5159504**	**237.4410**	**1.019354**	**.1991699**
Stddev	.0029366	.32616	.0044976	1.1047	.000592	.0001446
%RSD	.5956332	.3261710	.8717015	.4652625	.0580992	.0725958
#1	.4909130	100.0294	.5160784	237.1137	1.018677	.1993045
#2	.4963794	100.3075	.5203825	238.6723	1.019613	.1991880
#3	.4917860	99.6574	.5113901	236.5368	1.019773	.1990170

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.627170**	**.4932875**	**.9710396**	**-.294932**	**.0086113**	F **.1690773**
Stddev	.133286	.0010677	.0074856	.046191	.0029973	.0018176
%RSD	21.25205	.2164429	.7708878	15.66171	34.80645	1.074999
#1	-.474049	.4921385	.9728241	-.340543	.0052585	.1683613
#2	-.717171	.4942491	.9774717	-.248181	.0095443	.1711438
#3	-.690290	.4934749	.9628230	-.296072	.0110311	.1677268

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: ICSAB006 Acquired: 1/31/2025 17:41:34 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: ICSAB006 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000170	.0203847	.0079025	-.004021	-.003336	.0035793
Stddev	.000396	.0036640	.0030116	.001855	.000432	.0005126
%RSD	232.2718	17.97446	38.10874	46.13170	12.95499	14.32204
#1	-.000227	.0244093	.0112368	-.005403	-.003153	.0036543
#2	.000251	.0172425	.0053802	-.004747	-.003025	.0040502
#3	-.000535	.0195021	.0070906	-.001913	-.003829	.0030332

Elem	Sr4077
Units	ppm
Avg	F .1000205
Stddev	.0009041
%RSD	.9039185
#1	.0998395
#2	.1010014
#3	.0992206

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3068.645	64187.95	13275.97	2163.611	3429.162
Stddev	1.391	188.35	18.68	12.943	1.338
%RSD	.0453336	.2934370	.1406841	.5982046	.0390055
#1	3067.897	64057.48	13260.76	2157.109	3430.471
#2	3070.250	64102.48	13296.82	2155.209	3427.797
#3	3067.787	64403.88	13270.33	2178.516	3429.217

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: CCV031 Acquired: 1/31/2025 17:54:59 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV031 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**4.773684**	**4.633970**	**24.28598**	**4.737344**	**4.771484**	**391.5748**	**10.04875**
Stddev	.022476	.028321	.08067	.015201	.016870	2.5072	.12155
%RSD	.4708224	.6111632	.3321523	.3208709	.3535562	.6402887	1.209578
#1	4.764182	4.641445	24.28104	4.729894	4.768628	389.8839	10.15553
#2	4.799351	4.657803	24.36900	4.754833	4.789599	394.4554	10.07424
#3	4.757521	4.602661	24.20789	4.727307	4.756224	390.3851	9.91647

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4843829**	**2.463182**	**398.8548**	**15.43414**	**2.463137**	**14.68958**	**403.9425**
Stddev	.0030567	.009817	1.2759	.05690	.008523	.04101	1.8958
%RSD	.6310534	.3985660	.3198848	.3686480	.3460108	.2791453	.4693151
#1	.4819002	2.464635	400.2718	15.43177	2.463084	14.65615	406.0991
#2	.4877969	2.472191	398.4954	15.49218	2.471686	14.73533	403.1898
#3	.4834514	2.452718	397.7972	15.37846	2.454641	14.67725	402.5387

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**15.13922**	**401.0167**	**2.460796**	**1.263566**	**375.5350**	**2.444044**	**15.25669**
Stddev	.04042	1.5197	.008267	.002335	.1223	.005012	.02678
%RSD	.2669682	.3789520	.3359401	.1848189	.0325577	.2050562	.1755482
#1	15.18136	402.7709	2.459119	1.265050	375.4239	2.438882	15.25936
#2	15.13552	400.1792	2.469772	1.264773	375.5152	2.444358	15.28203
#3	15.10078	400.1001	2.453495	1.260874	375.6660	2.448891	15.22866

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**156.1526**	**4.797199**	**5.246359**	**4.793605**	**4.883878**	**4.847305**	**4.942266**
Stddev	.9611	.020032	.019327	.017019	.028692	.035794	.014418
%RSD	.6155184	.4175714	.3683843	.3550448	.5874793	.7384286	.2917200
#1	157.2387	4.799980	5.228322	4.791540	4.889403	4.812674	4.942258
#2	155.8073	4.815694	5.266758	4.811563	4.909406	4.884158	4.956688
#3	155.4117	4.775921	5.243995	4.777712	4.852826	4.845082	4.927853

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: CCV031 Acquired: 1/31/2025 17:54:59 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV031 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	**4.916270**	**5.055856**	**5.132947**
Stddev	.013881	.027950	.051386
%RSD	.2823395	.5528188	1.001101
#1	4.901652	5.088067	5.191899
#2	4.929272	5.041485	5.109303
#3	4.917886	5.038015	5.097639

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2699.352**	**59746.64**	**12784.79**	**1943.524**	**3080.472**
Stddev	8.027	197.49	70.13	5.232	9.160
%RSD	.2973664	.3305410	.5485431	.2691968	.2973722
#1	2700.815	59594.27	12850.66	1940.364	3078.946
#2	2690.693	59675.88	12711.06	1940.644	3072.170
#3	2706.546	59969.76	12792.64	1949.563	3090.299

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: CCB031 Acquired: 1/31/2025 17:59:18 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB031 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.002217**	**.0009000**	**-.000935**	**.0018474**	**.0004628**	**.0041961**
Stddev	.003177	.0012023	.000973	.0018307	.0008170	.0108421
%RSD	143.2650	133.5957	104.0973	99.09387	176.5224	258.3848
#1	.001078	-.000486	-.000351	.0034420	.0013652	-.008312
#2	-.002469	.001664	-.002058	-.000152	.0002498	.009989
#3	-.005261	.001521	-.000395	.002252	-.000227	.010911

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.001336**	**.0000607**	**.0000609**	**.0033113**	**.0003751**	**-.000322**
Stddev	.000506	.0000669	.0000353	.0042079	.0001794	.000156
%RSD	37.88822	110.1325	58.06044	127.0775	47.82380	48.51027
#1	-.001136	.0000591	.0001014	.0018274	.0005772	-.000276
#2	-.000961	.0001284	.0000363	.0000464	.0003134	-.000496
#3	-.001912	-.000005	.0000449	.0080601	.0002347	-.000194

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.000939**	**.0048377**	**.0003035**	**.0252305**	**-.000086**	**-.000300**
Stddev	.001337	.0018183	.0003992	.0143859	.000359	.000329
%RSD	142.3228	37.58672	131.5551	57.01799	419.3534	109.4612
#1	-.001396	.0056138	.0004304	.0102821	-.000248	.000064
#2	-.001988	.0027601	.0006238	.0264308	-.000334	-.000575
#3	.000566	.0061392	-.000144	.0389787	.000326	-.000390

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.2386588**	**-.001370**	**.0012021**	**-.208446**	**.0031453**	F **.0114640**
Stddev	.2620667	.001848	.0014345	.049421	.0018805	.0002980
%RSD	109.8081	134.9317	119.3310	23.70906	59.78730	2.599555
#1	.1496260	-.002347	.0015299	-.264967	.0051569	.0117840
#2	.5336424	.000762	-.000368	-.173372	.0028473	.0114134
#3	.0327080	-.002524	.002444	-.186998	.0014316	.0111944

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: CCB031 Acquired: 1/31/2025 17:59:18 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB031 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0002042**	**-.001434**	**.0009826**	**-.000384**	**.0005041**	**-.000804**
Stddev	.0000701	.004301	.0041668	.000506	.0001070	.000774
%RSD	34.31139	299.9838	424.0542	131.9915	21.23212	96.20268
#1	.0001349	.001018	.0002454	-.000730	.0006201	-.001320
#2	.0002028	-.006400	-.002766	.000197	.0004091	.000085
#3	.0002750	.001081	.005469	-.000618	.0004832	-.001179

Elem	Sr4077
Units	ppm
Avg	**.0001213**
Stddev	.0000435
%RSD	35.86463
#1	.0001501
#2	.0001427
#3	.0000713

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**3491.176**	**72598.20**	**12866.94**	**2432.300**	**4232.979**
Stddev	11.643	65.57	9.97	11.814	17.802
%RSD	.3335041	.0903152	.0774673	.4856940	.4205518
#1	3501.229	72525.16	12855.45	2436.102	4247.170
#2	3493.881	72651.97	12873.26	2441.745	4238.762
#3	3478.419	72617.47	12872.11	2419.054	4213.004

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: Q1151-08A Acquired: 1/31/2025 18:03:27 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7A Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1693923	-.003171	.7346001	.0684300	.0855658	27.39035
Stddev	.0018254	.003204	.0012952	.0013648	.0011874	.15797
%RSD	1.077610	101.0403	.1763165	1.994375	1.387716	.5767311
#1	.1673023	-.004258	.7360411	.0690972	.0853204	27.20873
#2	.1706740	-.005689	.7342264	.0668600	.0845202	27.49576
#3	.1702006	.000435	.7335328	.0693327	.0868567	27.46657

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5223301	.0541781	.0075463	15.67410	.1814409	.2476846
Stddev	.0036506	.0003153	.0000574	.06271	.0009392	.0005970
%RSD	.6989151	.5820160	.7609079	.4000977	.5176407	.2410495
#1	.5181180	.0544046	.0075011	15.60259	.1805813	.2481064
#2	.5242931	.0538180	.0076109	15.69997	.1824433	.2470015
#3	.5245793	.0543117	.0075269	15.71975	.1812980	.2479460

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5926653	50.97950	.9418615	11.91599	.2602129	.0148075
Stddev	.0020562	.25259	.0035327	.00996	.0001443	.0001021
%RSD	.3469391	.4954730	.3750722	.0835488	.0554429	.6895180
#1	.5940311	50.68810	.9385317	11.90655	.2600611	.0148376
#2	.5903005	51.11447	.9414859	11.91502	.2603482	.0148912
#3	.5936644	51.13593	.9455670	11.92639	.2602294	.0146937

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	34.55718	.0970663	1.243031	5.252953	4.797260	.1360606
Stddev	.25943	.0014315	.005733	.053356	.012294	.0019900
%RSD	.7507392	1.474725	.4612284	1.015737	.2562610	1.462555
#1	34.65967	.0954625	1.237523	5.194424	4.811410	.1337726
#2	34.74971	.0975221	1.248966	5.265553	4.791164	.1370207
#3	34.26215	.0982144	1.242604	5.298881	4.789206	.1373884

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: Q1151-08A Acquired: 1/31/2025 18:03:27 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: MC0AZ7A Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Li6707
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0119523	F 40.40055	F 22.86682	.0191341	.8543998	.0201799
Stddev	.0000681	.10635	.08364	.0012495	.0014597	.0008498
%RSD	.5694236	.2632315	.3657903	6.530045	.1708447	4.211133
#1	.0119777	40.52335	22.94655	.0179864	.8560720	.0191993
#2	.0120040	40.33944	22.77974	.0204651	.8533805	.0207002
#3	.0118752	40.33887	22.87418	.0189507	.8537468	.0206402

Elem	Sr4077
Units	ppm
Avg	.3532916
Stddev	.0021014
%RSD	.5947942
#1	.3508863
#2	.3542176
#3	.3547710

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4151.321	86454.91	16519.83	2869.550	3941.061
Stddev	4.649	317.62	47.80	14.567	7.559
%RSD	.1119834	.3673853	.2893464	.5076543	.1917938
#1	4147.713	86821.40	16471.22	2884.077	3934.208
#2	4156.567	86283.86	16566.78	2854.942	3949.169
#3	4149.682	86259.47	16521.49	2869.630	3939.807

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: CCV032 Acquired: 1/31/2025 18:07:21 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV032 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**4.746165**	**4.657299**	**24.12692**	**4.695752**	**4.740783**	**389.4635**	**9.958834**
Stddev	.010258	.038273	.00957	.006284	.002507	2.5780	.058067
%RSD	.2161360	.8217768	.0396655	.1338322	.0528873	.6619478	.5830696
#1	4.748083	4.624778	24.11720	4.690421	4.742022	392.1636	10.02572
#2	4.755329	4.699474	24.12721	4.694153	4.737898	389.1989	9.92943
#3	4.735083	4.647644	24.13634	4.702681	4.742430	387.0279	9.92135

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.4837093**	**2.449252**	**395.3756**	**15.44960**	**2.450852**	**14.60910**	**400.9568**
Stddev	.0025947	.002166	2.4981	.05699	.001836	.01118	2.9864
%RSD	.5364135	.0884208	.6318291	.3689024	.0749221	.0765344	.7448100
#1	.4807257	2.448194	397.8591	15.50226	2.451116	14.60239	404.1682
#2	.4854371	2.451743	392.8631	15.38909	2.448898	14.62201	398.2632
#3	.4849653	2.447819	395.4046	15.45745	2.452542	14.60291	400.4388

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**14.99315**	**399.3655**	**2.446880**	**1.258010**	**372.8843**	**2.443611**	**15.16777**
Stddev	.08728	2.6971	.002850	.004489	1.2520	.000730	.09098
%RSD	.5821298	.6753400	.1164945	.3568185	.3357505	.0298684	.5998131
#1	15.08404	402.4106	2.446310	1.262494	372.1693	2.443225	15.24563
#2	14.91000	397.2777	2.444358	1.253516	372.1538	2.444453	15.06776
#3	14.98542	398.4080	2.449973	1.258019	374.3300	2.443156	15.18992

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**154.3776**	**4.789698**	**5.207455**	**4.787911**	**4.839866**	**4.848499**	**4.922782**
Stddev	1.0838	.010842	.008864	.003950	.006135	.025251	.005583
%RSD	.7020158	.2263561	.1702241	.0824980	.1267687	.5208034	.1134151
#1	155.5436	4.780144	5.199040	4.787149	4.844912	4.819456	4.917137
#2	153.4010	4.801481	5.206615	4.792186	4.833036	4.865259	4.922909
#3	154.1883	4.787468	5.216709	4.784398	4.841649	4.860780	4.928301

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: CCV032 Acquired: 1/31/2025 18:07:21 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCV032 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	**4.886894**	**5.002071**	**5.077647**
Stddev	.003189	.037794	.006021
%RSD	.0652650	.7555641	.1185868
#1	4.885740	5.045071	5.077071
#2	4.884443	4.974118	5.083935
#3	4.890500	4.987024	5.071934

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	**2719.442**	**59734.95**	**12733.66**	**1939.287**	**3100.012**
Stddev	2.523	320.44	42.32	14.620	1.736
%RSD	.0927630	.5364295	.3323568	.7538981	.0560015
#1	2716.581	59411.51	12778.40	1928.673	3098.766
#2	2720.403	60052.29	12728.31	1955.964	3101.994
#3	2721.344	59741.05	12694.27	1933.225	3099.274

Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: CCB032 Acquired: 1/31/2025 18:12:28 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB032 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.002519**	**.0015814**	**-.000710**	**.0032222**	**.0005529**	**-.002952**	**.0026951**
Stddev	.001377	.0012757	.001261	.0020697	.0008174	.000901	.0010084
%RSD	54.67128	80.67045	177.5033	64.23018	147.8378	30.51183	37.41535
#1	-.003957	.0015875	-.001862	.0009479	-.000085	-.002759	.0038564
#2	-.002388	.0028541	.000636	.0049949	.000270	-.003934	.0020415
#3	-.001212	.0003027	-.000905	.0037239	.001474	-.002164	.0021873

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0000507**	**.0000556**	**.0053823**	**.0003045**	**-.000109**	**-.001349**	**.0045798**
Stddev	.0000099	.0001019	.0081769	.0001273	.000258	.002069	.0029358
%RSD	19.46023	183.3310	151.9227	41.81678	236.0671	153.3849	64.10222
#1	.0000394	-.000051	.0140256	.0001664	-.000326	-.002085	.0055427
#2	.0000579	.000151	.0043517	.0003300	-.000178	.000987	.0012835
#3	.0000546	.000067	-.002230	.0004172	.000176	-.002948	.0069133

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**.0001455**	**.0098749**	**-.000142**	**-.000354**	**-.316374**	**-.000361**	**.0017080**
Stddev	.0001459	.0091596	.000216	.000402	.256341	.000833	.0025098
%RSD	100.3310	92.75692	152.3650	113.3611	81.02473	230.5926	146.9419
#1	-.000016	.0202301	-.000388	-.000754	-.325521	.000265	-.000841
#2	.000185	.0065619	.000011	.000050	-.055582	-.001307	.004177
#3	.000268	.0028327	-.000047	-.000359	-.568020	-.000042	.001788

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	**-.052209**	**.0022521**	**.0073774**	**.0000562**	**-.000619**	**.0011095**	**-.000179**
Stddev	.041257	.0009603	.0003741	.0000832	.002277	.0020814	.000313
%RSD	79.02221	42.64047	5.070385	148.1542	367.6292	187.5859	175.0756
#1	-.044286	.0018233	.0076755	-.000040	.001653	-.000873	-.000380
#2	-.015489	.0015809	.0074990	.000098	-.002902	.000924	.000182
#3	-.096854	.0033521	.0069577	.000110	-.000609	.003278	-.000339


Reviewed By:JANVI
On:2/10/2025 1:39:33 PM
Inst Id :P4

Sample Name: CCB032 Acquired: 1/31/2025 18:12:28 Type: Unk
Method: EPA SFAM01.0(v60) Mode: CONC Corr. Factor: 1.000000
User: Kareem Custom ID1: CCB032 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Li6707	Sr4077
Units	ppm	ppm	ppm
Avg	.0005023	-.000433	.0000790
Stddev	.0001857	.000345	.0000545
%RSD	36.97449	79.56806	69.02412
#1	.0004348	-.000828	.0000622
#2	.0007123	-.000194	.0000349
#3	.0003597	-.000277	.0001400

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3387.656	70473.84	13772.06	2344.041	4091.918
Stddev	20.365	1665.16	48.18	53.638	23.628
%RSD	.6011422	2.362810	.3498510	2.288268	.5774238
#1	3392.400	68554.60	13782.33	2282.106	4102.058
#2	3365.339	71332.64	13814.28	2374.654	4064.913
#3	3405.231	71534.28	13719.57	2375.361	4108.783

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




As 189.042 {478}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.152502	Re-Slope:	1.000000
A1 (Gain):	261.116852	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999641	Status:	OK.
Std Error of Est:	0.117261		
Predicted MDL:	0.003778		
Predicted MQL:	0.012593		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.15325	.542	1
S1	.01000	.01209	.002	20.9	3.0023	.757	1
S2	1.2500	1.3166	.067	5.32	343.23	1.29	1
S3	2.5000	2.5758	.076	3.03	671.65	1.07	1
S4	5.0000	5.0908	.091	1.82	1327.6	1.36	1
S5	10.000	9.7648	-.235	-2.35	2546.5	3.90	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Tl 190.856 {477}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000172	Re-Slope:	1.000000
A1 (Gain):	0.119814	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999506	Status:	OK.
Std Error of Est:	0.000099		
Predicted MDL:	0.001486		
Predicted MQL:	0.004952		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00017	.000	1
S1	.02500	.02621	.001	4.84	.00320	.000	1
S2	1.2500	1.3073	.057	4.58	.15507	.000	1
S3	2.5000	2.6158	.116	4.63	.31012	.000	1
S4	5.0000	5.1057	.106	2.11	.60497	.001	1
S5	10.000	9.7200	-.280	-2.80	1.1509	.003	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Pb 220.353 {453}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000153	Re-Slope:	1.000000
A1 (Gain):	0.233270	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999891	Status:	OK.
Std Error of Est:	0.000129		
Predicted MDL:	0.001819		
Predicted MQL:	0.006062		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00015	.000	1
S1	.01000	.01026	.000	2.56	.00222	.000	1
S2	6.2500	6.1007	-.149	-2.39	1.4196	.002	1
S3	12.500	12.663	.163	1.31	2.9472	.003	1
S4	25.000	25.489	.489	1.96	5.9324	.017	1
S5	50.000	49.496	-.504	-1.01	11.519	.016	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Se 196.090 {472}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000121	Re-Slope:	1.000000
A1 (Gain):	0.068097	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999758	Status:	OK.
Std Error of Est:	0.000047		
Predicted MDL:	0.003511		
Predicted MQL:	0.011702		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00012	.000	1
S1	.03500	.03171	-.003	-9.41	.00228	.000	1
S2	1.2500	1.1834	-.067	-5.33	.08058	.000	1
S3	2.5000	2.4261	-.074	-2.96	.16507	.000	1
S4	5.0000	4.9736	-.026	-.528	.33830	.001	1
S5	10.000	10.170	.170	1.70	.69166	.001	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Sb 206.833 {463}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000188	Re-Slope:	1.000000
A1 (Gain):	0.090929	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999746	Status:	OK.
Std Error of Est:	0.000087		
Predicted MDL:	0.003406		
Predicted MQL:	0.011354		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00019	.000	1
S1	.06000	.05470	-.005	-8.83	.00516	.000	1
S2	1.2500	1.1641	-.086	-6.87	.10984	.000	1
S3	2.5000	2.4447	-.055	-2.21	.23008	.001	1
S4	5.0000	4.9857	-.014	-.286	.46873	.000	1
S5	10.000	10.161	.161	1.61	.95448	.003	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Al 396.152 { 85}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000851	Re-Slope:	1.000000
A1 (Gain):	0.081490	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999966	Status:	OK.
Std Error of Est:	0.000417		
Predicted MDL:	0.020700		
Predicted MQL:	0.069000		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00002	-.000	.000	-.00085	.001	1
S1	.20000	.21843	.018	9.22	.01698	.001	1
S2	38.750	38.301	-.449	-1.16	3.1237	.014	1
S3	77.500	78.458	.958	1.24	6.3995	.035	1
S4	155.00	155.53	.525	.339	12.687	.017	1
S5	310.00	305.69	-4.31	-1.39	24.937	.092	1
S6	800.00	803.26	3.26	.407	65.457	.187	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Ba 493.409 { 68}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.185362	Re-Slope:	1.000000
A1 (Gain):	3.012758	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999868	Status:	OK.
Std Error of Est:	0.005196		
Predicted MDL:	0.001483		
Predicted MQL:	0.004943		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	.18532	.008	1
S1	.20000	.20954	.010	4.77	.81666	.002	1
S2	2.5000	2.4774	-.023	-.906	7.6490	.022	1
S3	5.0000	5.0849	.085	1.70	15.505	.055	1
S4	10.000	10.202	.202	2.02	30.921	.060	1
S5	20.000	19.726	-.274	-1.37	59.616	.791	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Be 234.861 {144}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000666	Re-Slope:	1.000000
A1 (Gain):	5.012945	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999672	Status:	OK.
Std Error of Est:	0.000480		
Predicted MDL:	0.000155		
Predicted MQL:	0.000517		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00067	.001	1
S1	.00500	.00542	.000	8.46	.02650	.000	1
S2	.12500	.12973	.005	3.78	.64679	.003	1
S3	.25000	.26026	.010	4.11	1.2983	.004	1
S4	.50000	.50682	.007	1.36	2.5285	.004	1
S5	1.0000	.97777	-.022	-2.22	4.8778	.023	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Cd 214.438 {457}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000185	Re-Slope:	1.000000
A1 (Gain):	4.606757	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999903	Status:	OK.
Std Error of Est:	0.000539		
Predicted MDL:	0.000065		
Predicted MQL:	0.000215		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	.00019	.000	1
S1	.00500	.00487	-.000	-2.54	.02272	.000	1
S2	.62500	.61106	-.014	-2.23	2.8196	.001	1
S3	1.2500	1.2625	.012	.997	5.8249	.006	1
S4	2.5000	2.5486	.049	1.94	11.759	.035	1
S5	5.0000	4.9530	-.047	-.940	22.853	.035	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Ca 373.690 { 90}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.001102	Re-Slope:	1.000000
A1 (Gain):	0.075125	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999758	Status:	OK.
Std Error of Est:	0.005774		
Predicted MDL:	0.018866		
Predicted MQL:	0.062887		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00090	-.001	.000	.00103	.002	1
S1	5.0000	5.4460	.446	8.92	.41023	.002	1
S2	62.500	65.018	2.52	4.03	4.8856	.022	1
S3	125.00	130.80	5.80	4.64	9.8277	.044	1
S4	250.00	257.53	7.53	3.01	19.348	.042	1
S5	500.00	492.81	-7.19	-1.44	37.023	.134	1
S6	800.00	790.89	-9.11	-1.14	59.417	.763	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Cr 267.716 {126}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000067	Re-Slope:	1.000000
A1 (Gain):	0.224665	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999644	Status:	OK.
Std Error of Est:	0.000177		
Predicted MDL:	0.000841		
Predicted MQL:	0.002802		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00007	.000	1
S1	.01000	.01139	.001	13.9	.00249	.000	1
S2	3.8750	3.9312	.056	1.45	.88382	.004	1
S3	7.7500	8.0272	.277	3.58	1.8047	.008	1
S4	15.500	15.928	.428	2.76	3.5811	.016	1
S5	31.000	30.237	-.763	-2.46	6.7985	.044	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Co 228.616 {448}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000121	Re-Slope:	1.000000
A1 (Gain):	0.766687	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999870	Status:	OK.
Std Error of Est:	0.000329		
Predicted MDL:	0.000368		
Predicted MQL:	0.001225		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00012	.000	1
S1	.05000	.05231	.002	4.61	.04011	.000	1
S2	.62500	.62756	.003	.410	.48257	.001	1
S3	1.2500	1.2766	.027	2.13	.98175	.000	1
S4	2.5000	2.5418	.042	1.67	1.9548	.005	1
S5	5.0000	4.9267	-.073	-1.47	3.7895	.008	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Cu 324.754 {104}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.002542	Re-Slope:	1.000000
A1 (Gain):	0.172810	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999860	Status:	OK.
Std Error of Est:	0.000133		
Predicted MDL:	0.005531		
Predicted MQL:	0.018437		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00254	.000	1
S1	.02500	.02832	.003	13.3	.00743	.001	1
S2	3.7500	3.7735	.024	.627	.65457	.003	1
S3	7.5000	7.7058	.206	2.74	1.3340	.005	1
S4	15.000	15.210	.210	1.40	2.6307	.002	1
S5	30.000	29.557	-.443	-1.48	5.1098	.015	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Fe 259.837 {130}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000475	Re-Slope:	1.000000
A1 (Gain):	0.026038	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999803	Status:	OK.
Std Error of Est:	0.000226		
Predicted MDL:	0.017806		
Predicted MQL:	0.059354		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00003	-.000	.000	-.00048	.000	1
S1	.10000	.11933	.019	19.3	.00263	.000	1
S2	37.500	39.417	1.92	5.11	1.0261	.002	1
S3	75.000	79.288	4.29	5.72	2.0644	.011	1
S4	150.00	153.59	3.59	2.39	3.9994	.010	1
S5	300.00	295.44	-4.56	-1.52	7.6939	.018	1
S6	800.00	794.74	-5.26	-.657	20.693	.140	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Mn 257.610 {131}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000325	Re-Slope:	1.000000
A1 (Gain):	0.622290	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999632	Status:	OK.
Std Error of Est:	0.000601		
Predicted MDL:	0.000810		
Predicted MQL:	0.002701		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	-.00033	.001	1
S1	.01500	.01752	.003	16.8	.01058	.000	1
S2	3.7500	3.8908	.141	3.76	2.4209	.006	1
S3	7.5000	7.8328	.333	4.44	4.8739	.025	1
S4	15.000	15.241	.241	1.60	9.4837	.020	1
S5	30.000	29.283	-.717	-2.39	18.222	.049	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Mg 279.079 {121}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000601	Re-Slope:	1.000000
A1 (Gain):	0.017434	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999783	Status:	OK.
Std Error of Est:	0.001267		
Predicted MDL:	0.035671		
Predicted MQL:	0.118903		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00074	-.001	.000	-.00061	.000	1
S1	5.0000	5.3216	.322	6.43	.09218	.001	1
S2	62.500	65.108	2.61	4.17	1.1345	.002	1
S3	125.00	130.99	5.99	4.79	2.2830	.014	1
S4	250.00	254.61	4.61	1.84	4.4383	.012	1
S5	500.00	488.89	-11.1	-2.22	8.5227	.030	1
S6	800.00	797.59	-2.41	-.301	13.905	.112	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Ni 231.604 {446}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000181	Re-Slope:	1.000000
A1 (Gain):	0.686397	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999929	Status:	OK.
Std Error of Est:	0.000194		
Predicted MDL:	0.000481		
Predicted MQL:	0.001604		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00018	.000	1
S1	.04000	.03936	-.001	-1.61	.02683	.000	1
S2	.62500	.61654	-.008	-1.35	.42301	.000	1
S3	1.2500	1.2660	.016	1.28	.86882	.001	1
S4	2.5000	2.5385	.038	1.54	1.7422	.005	1
S5	5.0000	4.9546	-.045	-.908	3.4006	.005	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Ag 328.068 {103}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000515	Re-Slope:	1.000000
A1 (Gain):	0.260714	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999921	Status:	OK.
Std Error of Est:	0.000027		
Predicted MDL:	0.001125		
Predicted MQL:	0.003749		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00052	.000	1
S1	.01000	.01104	.001	10.4	.00339	.000	1
S2	.31250	.30241	-.010	-3.23	.07818	.000	1
S3	.62500	.62376	-.001	-.198	.16079	.001	1
S4	1.2500	1.2680	.018	1.44	.32642	.003	1
S5	2.5000	2.4922	-.008	-.311	.64089	.003	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Na 818.326 { 41}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.002554	Re-Slope:	1.000000
A1 (Gain):	0.006852	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999879	Status:	OK.
Std Error of Est:	0.000329		
Predicted MDL:	0.438431		
Predicted MQL:	1.461435		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00004	.000	.000	.00255	.001	1
S1	5.0000	5.0463	.046	.926	.03713	.001	1
S2	37.500	37.135	-.365	-.972	.25700	.004	1
S3	75.000	75.840	.840	1.12	.52219	.002	1
S4	150.00	149.94	-.060	-.040	1.0299	.001	1
S5	300.00	291.57	-8.43	-2.81	2.0003	.005	1
S6	800.00	807.97	7.97	.996	5.5386	.038	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




V 292.402 {115}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000094	Re-Slope:	1.000000
A1 (Gain):	0.182705	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999745	Status:	OK.
Std Error of Est:	0.000105		
Predicted MDL:	0.004394		
Predicted MQL:	0.014646		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	.00009	.001	1
S1	.05000	.05453	.005	9.07	.01003	.001	1
S2	.62500	.63997	.015	2.39	.11244	.001	1
S3	1.2500	1.2934	.043	3.47	.22725	.001	1
S4	2.5000	2.5309	.031	1.24	.44420	.002	1
S5	5.0000	4.9060	-.094	-1.88	.85984	.000	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Zn 213.856 {158}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.000520	Re-Slope:	1.000000
A1 (Gain):	0.185219	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999796	Status:	OK.
Std Error of Est:	0.000268		
Predicted MDL:	0.002543		
Predicted MQL:	0.008476		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00052	.000	1
S1	.06000	.05949	-.001	-.845	.01053	.000	1
S2	3.7500	3.5514	-.199	-5.29	.66067	.001	1
S3	7.5000	7.3757	-.124	-1.66	1.3724	.009	1
S4	15.000	14.819	-.181	-1.21	2.7578	.023	1
S5	30.000	30.505	.505	1.68	5.6767	.025	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




K 769.896 { 44}

Date of Fit: 02/06/2025 5:56:42 Type of Fit: Linear Weighting: 1/Conc

A0 (Offset):	0.143555	Re-Slope:	1.000000
A1 (Gain):	0.013975	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999640	Status:	OK.
Std Error of Est:	0.000773		
Predicted MDL:	0.179845		
Predicted MQL:	0.599482		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00134	-.001	.000	.14354	.009	1
S1	5.0000	6.1542	1.15	23.1	.22956	.002	1
S2	37.500	38.296	.796	2.12	.67875	.002	1
S3	75.000	76.958	1.96	2.61	1.2191	.006	1
S4	150.00	150.69	.686	.457	2.2494	.007	1
S5	300.00	295.41	-4.59	-1.53	4.2719	.022	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




P 177.495 {490}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.004528	Re-Slope:	1.000000
A1 (Gain):	0.064651	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999731	Status:	OK.
Std Error of Est:	0.000025		
Predicted MDL:	0.002093		
Predicted MQL:	0.006978		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00000	.000	.000	-.00453	.000	1
S1	.01000	.00756	-.002	-24.4	-.00404	.000	1
S2	1.2500	1.1565	-.093	-7.48	.07012	.000	1
S3	2.5000	2.4494	-.051	-2.03	.15359	.000	1
S4	5.0000	5.0534	.053	1.07	.32171	.001	1
S5	10.000	10.093	.093	.932	.64706	.000	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




B 249.678 {135}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.001339	Re-Slope:	1.000000
A1 (Gain):	0.702690	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.998144	Status:	OK.
Std Error of Est:	0.000692		
Predicted MDL:	0.001452		
Predicted MQL:	0.004839		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00001	.000	.000	.00134	.001	1
S1	.01000	.00129	-.009	-87.1	.00221	.001	1
S2	1.2500	1.3678	.118	9.42	.92906	.005	1
S3	2.5000	2.7080	.208	8.32	1.8374	.009	1
S4	5.0000	5.1650	.165	3.30	3.4971	.012	1
S5	10.000	9.5183	-.482	-4.82	6.4225	.034	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Mo 202.030 {467}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000579	Re-Slope:	1.000000
A1 (Gain):	0.529005	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999967	Status:	OK.
Std Error of Est:	0.000072		
Predicted MDL:	0.000484		
Predicted MQL:	0.001613		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00058	.000	1
S1	.01000	.01046	.000	4.56	.00611	.000	1
S2	1.2500	1.2155	-.035	-2.76	.64358	.001	1
S3	2.5000	2.4860	-.014	-.558	1.3157	.003	1
S4	5.0000	5.0036	.004	.072	2.6475	.005	1
S5	10.000	10.044	.044	.444	5.3141	.014	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




S 182.034 {485}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000406	Re-Slope:	1.000000
A1 (Gain):	0.045796	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999521	Status:	OK.
Std Error of Est:	0.000076		
Predicted MDL:	0.003187		
Predicted MQL:	0.010623		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	.00002	.000	.000	.00041	.000	1
S1	.10000	.08693	-.013	-13.1	.00439	.000	1
S2	1.2500	1.1410	-.109	-8.72	.05284	.000	1
S3	2.5000	2.4079	-.092	-3.68	.11105	.000	1
S4	5.0000	5.0293	.029	.586	.23146	.000	1
S5	10.000	10.185	.185	1.85	.46830	.001	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Si 251.611 {134}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.012138	Re-Slope:	1.000000
A1 (Gain):	0.712224	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.956341	Status:	OK.
Std Error of Est:	0.011828		
Predicted MDL:	0.001459		
Predicted MQL:	0.004864		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00043	-.000	.000	.01183	.000	1
S1	.10000	.52316	.423	423.	.38575	.005	1
S2	1.2500	1.3279	.078	6.23	.97811	.003	1
S3	2.5000	2.6055	.105	4.22	1.9082	.007	1
S4	5.0000	5.0212	.021	.424	3.6692	.019	1
S5	10.000	9.3758	-.624	-6.24	6.8515	.029	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Sn 189.989 {478}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000633	Re-Slope:	1.000000
A1 (Gain):	0.169758	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999881	Status:	OK.
Std Error of Est:	0.000037		
Predicted MDL:	0.000852		
Predicted MQL:	0.002839		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00063	.000	1
S1	.00700	.00757	.001	8.13	.00187	.000	1
S2	1.2500	1.2330	-.017	-1.36	.20889	.000	1
S3	2.5000	2.5390	.039	1.56	.42952	.000	1
S4	5.0000	5.1004	.100	2.01	.86222	.002	1
S5	10.000	9.8770	-.123	-1.23	1.6688	.003	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Ti 336.121 {100}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000294	Re-Slope:	1.000000
A1 (Gain):	0.446632	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999786	Status:	OK.
Std Error of Est:	0.000491		
Predicted MDL:	0.002364		
Predicted MQL:	0.007881		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	.00029	.001	1
S1	.10000	.10715	.007	7.15	.04815	.000	1
S2	1.2500	1.2666	.017	1.33	.56600	.001	1
S3	2.5000	2.5862	.086	3.45	1.1554	.007	1
S4	5.0000	5.0721	.072	1.44	2.2657	.006	1
S5	10.000	9.8179	-.182	-1.82	4.3853	.014	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Sr 407.771 { 83}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	-0.002833	Re-Slope:	1.000000
A1 (Gain):	8.958101	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999836	Status:	OK.
Std Error of Est:	0.008886		
Predicted MDL:	0.000183		
Predicted MQL:	0.000611		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00001	-.000	.000	-.00296	.002	1
S1	.10000	.10970	.010	9.70	.98078	.006	1
S2	1.2500	1.2682	.018	1.45	11.694	.033	1
S3	2.5000	2.5896	.090	3.58	23.867	.103	1
S4	5.0000	5.0251	.025	.501	46.356	.506	1
S5	10.000	9.8577	-.142	-1.42	90.991	1.60	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5




Y 224.306 {450}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.000000	Status:	Warning Zero Gain
Std Error of Est:	0.000000		
Predicted MDL:	n/a		
Predicted MQL:	n/a		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



Y 360.073 { 94}*


Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.000000	Re-Slope:	1.000000
A1 (Gain):	0.000000	Y-int:	0.000000

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

A2 (Curvature):	0.000000					
n (Exponent):	1.000000					
Correlation:	0.000000		Status:	Warning	Zero Gain	
Std Error of Est:	0.000000					
Predicted MDL:	n/a					
Predicted MQL:	n/a					

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis




Y 371.030 { 91}*

Date of Fit:	<not fit>		Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):		0.000000		Re-Slope:	1.000000	
A1 (Gain):		0.000000		Y-int:	0.000000	
A2 (Curvature):		0.000000				
n (Exponent):		1.000000				
Correlation:		0.000000		Status:	Warning	Zero Gain
Std Error of Est:		0.000000				
Predicted MDL:		n/a				
Predicted MQL:		n/a				

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis


Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5



Y 224.306 {150}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):	0.000000		Re-Slope:	1.000000	
A1 (Gain):	0.000000		Y-int:	0.000000	
A2 (Curvature):	0.000000				
n (Exponent):	1.000000				
Correlation:	0.000000		Status:	Warning	Zero Gain
Std Error of Est:	0.000000				
Predicted MDL:	n/a				
Predicted MQL:	n/a				

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis




In 230.606 {446}*

Date of Fit:	<not fit>	Type of Fit:	Linear	Weighting:	1/Conc
A0 (Offset):	0.000000		Re-Slope:	1.000000	
A1 (Gain):	0.000000		Y-int:	0.000000	

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

A2 (Curvature):	0.000000				
n (Exponent):	1.000000				
Correlation:	0.000000	Status:	Warning	Zero Gain	
Std Error of Est:	0.000000				
Predicted MDL:	n/a				
Predicted MQL:	n/a				

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis



Li 670.784 { 50}

Date of Fit:	02/06/2025 5:56:42	Type of Fit:	Linear	Weighting:	1/Conc

A0 (Offset):	0.009448	Re-Slope:	1.000000
A1 (Gain):	0.692971	Y-int:	0.000000
A2 (Curvature):	0.000000		
n (Exponent):	1.000000		
Correlation:	0.999848	Status:	OK.
Std Error of Est:	0.000248		
Predicted MDL:	0.004449		
Predicted MQL:	0.014830		

Std. Name	Stated Conc.	Found Conc.	Difference	% Diff.	(S)IR	Std Dev	Emphasis
S0	.00000	-.00000	-.000	.000	.00945	.004	1
S5	10.000	9.8402	-.160	-1.60	6.8284	.016	1
S4	5.0000	5.0767	.077	1.53	3.5275	.001	1
S3	2.5000	2.5633	.063	2.53	1.7857	.003	1
S2	1.2500	1.2685	.019	1.48	.88851	.010	1
S1	.01500	.01618	.001	7.88	.02066	.004	1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S0 Acquired: 02/06/2025 12:47:36 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	-.15325	.00017	-.00015	.00012	.00019	-.00085	.18532	-.00067
Stddev	.54226	.00008	.00034	.00022	.00025	.00111	.00791	.00064
%RSD	353.84	48.436	222.53	184.97	131.23	130.32	4.2694	95.235
#1	-.63979	.00012	-.00038	-.00013	.00047	-.00154	.17619	-.00141
#2	.43135	.00027	.00024	.00031	.00000	-.00145	.19003	-.00035
#3	-.25131	.00013	-.00032	.00018	.00009	.00043	.18975	-.00026

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.00019	.00103	-.00007	-.00012	.00254	-.00048	-.00033	-.00061
Stddev	.00033	.00154	.00011	.00037	.00045	.00036	.00058	.00026
%RSD	178.99	149.14	166.99	296.48	17.571	76.258	178.26	42.027
#1	.00034	.00168	-.00019	.00011	.00240	-.00018	.00027	-.00082
#2	-.00020	-.00073	-.00005	-.00055	.00218	-.00037	-.00089	-.00032
#3	.00041	.00215	.00003	.00006	.00304	-.00088	-.00036	-.00070

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	-.00018	.00052	.00255	.00009	-.00052	.14354	-.00453	.00134
Stddev	.00017	.00008	.00102	.00068	.00035	.00879	.00004	.00112
%RSD	94.780	15.305	39.950	737.68	67.284	6.1227	.83031	83.439
#1	.00001	.00044	.00237	-.00056	-.00091	.13365	-.00457	.00229
#2	-.00033	.00051	.00164	.00080	-.00024	.14648	-.00451	.00163
#3	-.00022	.00060	.00365	.00004	-.00041	.15048	-.00450	.00011

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077	Li6707
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.00058	.00041	.01183	.00063	.00029	-.00296	.00945
Stddev	.00001	.00010	.00028	.00011	.00110	.00180	.00377
%RSD	2.4050	24.693	2.3589	17.330	381.08	60.911	39.958
#1	.00059	.00040	.01156	.00074	.00020	-.00462	.00513
#2	.00057	.00051	.01183	.00063	.00143	-.00105	.01215
#3	.00058	.00031	.01211	.00052	-.00077	-.00320	.01106

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S0 Acquired: 02/06/2025 12:47:36 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S0 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4527.2	38530.	5327.7	3153.7	5428.1
Stddev	8.1	132.	299.5	11.6	7.6
%RSD	.17928	.34253	5.6218	.36760	.13922
#1	4520.5	38639.	5673.3	3166.7	5419.6
#2	4524.9	38383.	5166.2	3144.4	5434.0
#3	4536.2	38569.	5143.6	3149.9	5430.6

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S1 Acquired: 02/06/2025 12:51:40 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3.0023	.00320	.00222	.00228	.00516	.01698	.81666	.02650
Stddev	.7567	.00012	.00035	.00025	.00029	.00115	.00160	.00023
%RSD	25.206	3.8859	15.730	10.865	5.6547	6.7846	.19542	.85331
#1	3.3057	.00322	.00210	.00199	.00517	.01576	.81830	.02669
#2	2.1409	.00332	.00195	.00243	.00487	.01805	.81511	.02625
#3	3.5602	.00307	.00262	.00242	.00545	.01711	.81657	.02655

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.02272	.41023	.00249	.04011	.00743	.00263	.01058	.09218
Stddev	.00011	.00208	.00008	.00010	.00082	.00024	.00016	.00056
%RSD	.50135	.50603	3.2402	.25118	10.990	9.0687	1.4734	.60845
#1	.02282	.40803	.00243	.03999	.00765	.00245	.01073	.09167
#2	.02274	.41215	.00258	.04015	.00653	.00255	.01059	.09208
#3	.02260	.41051	.00247	.04017	.00812	.00290	.01042	.09278

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.02683	.00339	.03713	.01003	.01053	.22956	-.00404	.00221
Stddev	.00009	.00050	.00085	.00108	.00028	.00245	.00007	.00072
%RSD	.32899	14.626	2.2896	10.751	2.6397	1.0665	1.8328	32.599
#1	.02682	.00395	.03631	.01052	.01037	.22727	-.00411	.00283
#2	.02676	.00322	.03708	.00880	.01038	.23214	-.00397	.00238
#3	.02693	.00300	.03800	.01078	.01085	.22928	-.00403	.00142

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077	Li6707
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.00611	.00439	.38575	.00187	.04815	.98078	.02066
Stddev	.00010	.00019	.00461	.00006	.00044	.00612	.00384
%RSD	1.6037	4.4025	1.1945	3.3295	.90764	.62449	18.600
#1	.00622	.00442	.39093	.00185	.04765	.97585	.01682
#2	.00607	.00456	.38424	.00182	.04838	.98764	.02451
#3	.00603	.00418	.38209	.00194	.04842	.97886	.02065

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S1 Acquired: 02/06/2025 12:51:40 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S01 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4485.6	38218.	5099.8	3129.4	5151.7
Stddev	17.8	37.	23.9	19.5	20.7
%RSD	.39721	.09758	.46952	.62314	.40161
#1	4505.8	38261.	5074.3	3151.7	5173.8
#2	4478.6	38203.	5103.3	3120.5	5148.4
#3	4472.3	38191.	5121.8	3115.9	5132.8

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S2 Acquired: 02/06/2025 12:55:43 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	343.23	.15507	1.4196	.08058	.10984	3.1237	7.6490	.64679
Stddev	1.29	.00019	.0020	.00017	.00016	.0141	.0218	.00346
%RSD	.37470	.12281	.14006	.21551	.14536	.45309	.28548	.53461
#1	343.54	.15523	1.4175	.08058	.10977	3.1295	7.6721	.64985
#2	341.82	.15486	1.4200	.08040	.11002	3.1075	7.6464	.64304
#3	344.33	.15512	1.4214	.08075	.10972	3.1340	7.6286	.64749

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2.8196	4.8856	.88382	.48257	.65457	1.0261	2.4209	1.1345
Stddev	.0007	.0224	.00438	.00074	.00291	.0020	.0065	.0022
%RSD	.02424	.45894	.49564	.15359	.44456	.19288	.26804	.19444
#1	2.8188	4.9114	.88727	.48173	.65763	1.0270	2.4245	1.1361
#2	2.8200	4.8748	.87889	.48315	.65423	1.0238	2.4134	1.1320
#3	2.8200	4.8706	.88530	.48282	.65184	1.0274	2.4248	1.1354

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.42301	.07818	.25700	.11244	.66067	.67875	.07012	.92906
Stddev	.00041	.00041	.00368	.00106	.00126	.00173	.00009	.00485
%RSD	.09605	.52923	1.4337	.93906	.19056	.25518	.13370	.52160
#1	.42266	.07847	.25666	.11265	.66121	.68069	.07021	.93277
#2	.42345	.07771	.25349	.11130	.66158	.67821	.07002	.92358
#3	.42292	.07837	.26084	.11338	.65924	.67736	.07014	.93084

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077	Li6707
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.64358	.05284	.97811	.20889	.56600	11.694	.88851
Stddev	.00146	.00002	.00299	.00017	.00082	.034	.00982
%RSD	.22651	.04043	.30543	.08091	.14532	.28646	1.1055
#1	.64219	.05285	.98152	.20869	.56519	11.701	.89232
#2	.64510	.05282	.97685	.20897	.56684	11.657	.89586
#3	.64344	.05286	.97596	.20900	.56597	11.723	.87736

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S2 Acquired: 02/06/2025 12:55:43 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S02 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4240.9	35600.	5018.1	2943.1	4506.4
Stddev	7.3	129.	13.0	14.5	9.7
%RSD	.17165	.36322	.25889	.49208	.21473
#1	4239.7	35451.	5003.4	2932.6	4503.4
#2	4234.3	35681.	5022.5	2937.1	4498.7
#3	4248.7	35669.	5028.2	2959.6	4517.3

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S3 Acquired: 02/06/2025 12:59:28 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	671.65	.31012	2.9472	.16507	.23008	6.3995	15.505	1.2983
Stddev	1.07	.00028	.0034	.00046	.00118	.0352	.055	.0035
%RSD	.15990	.08929	.11560	.27592	.51102	.55039	.35410	.27178
#1	670.82	.31019	2.9441	.16462	.22899	6.4280	15.475	1.2976
#2	672.86	.30981	2.9466	.16508	.22992	6.4105	15.568	1.3021
#3	671.27	.31035	2.9508	.16553	.23133	6.3602	15.471	1.2951

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	5.8249	9.8277	1.8047	.98175	1.3340	2.0644	4.8739	2.2830
Stddev	.0060	.0439	.0080	.00041	.0054	.0114	.0251	.0140
%RSD	.10211	.44698	.44540	.04182	.40579	.55177	.51538	.61169
#1	5.8241	9.8490	1.7968	.98141	1.3356	2.0703	4.8839	2.2931
#2	5.8194	9.8569	1.8044	.98163	1.3385	2.0717	4.8925	2.2888
#3	5.8312	9.7772	1.8129	.98220	1.3280	2.0513	4.8454	2.2671

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	.86882	.16079	.52219	.22725	1.3724	1.2191	.15359	1.8374
Stddev	.00112	.00059	.00184	.00123	.0085	.0055	.00024	.0091
%RSD	.12870	.36990	.35164	.54110	.61946	.45215	.15349	.49675
#1	.86870	.16024	.52407	.22768	1.3761	1.2245	.15386	1.8349
#2	.86777	.16071	.52211	.22821	1.3784	1.2191	.15344	1.8475
#3	.86999	.16142	.52040	.22587	1.3627	1.2135	.15347	1.8298

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077	Li6707
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.3157	.11105	1.9082	.42952	1.1554	23.867	1.7857
Stddev	.0030	.00022	.0072	.00039	.0070	.103	.0032
%RSD	.22564	.19583	.37533	.08981	.60388	.43160	.18071
#1	1.3136	.11083	1.9037	.42982	1.1590	23.908	1.7880
#2	1.3144	.11126	1.9165	.42908	1.1598	23.943	1.7872
#3	1.3191	.11105	1.9046	.42966	1.1474	23.750	1.7820

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S3 Acquired: 02/06/2025 12:59:28 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S03 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4008.9	33801.	4912.5	2794.0	4177.7
Stddev	11.8	49.	18.1	17.4	8.1
%RSD	.29444	.14533	.36936	.62130	.19320
#1	4011.6	33857.	4916.7	2801.2	4177.2
#2	4019.1	33766.	4892.6	2774.2	4185.9
#3	3995.9	33779.	4928.1	2806.5	4169.8

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S4 Acquired: 02/06/2025 13:03:13 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1327.6	.60497	5.9324	.33830	.46873	12.687	30.921	2.5285
Stddev	1.4	.00115	.0166	.00082	.00013	.017	.060	.0040
%RSD	.10262	.18999	.28015	.24198	.02759	.13717	.19367	.15699
#1	1326.1	.60409	5.9270	.33813	.46859	12.684	30.987	2.5299
#2	1328.8	.60456	5.9192	.33758	.46884	12.671	30.907	2.5240
#3	1327.8	.60627	5.9511	.33919	.46876	12.705	30.870	2.5315

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	11.759	19.348	3.5811	1.9548	2.6307	3.9994	9.4837	4.4383
Stddev	.035	.042	.0160	.0054	.0020	.0103	.0203	.0122
%RSD	.29954	.21897	.44787	.27803	.07437	.25657	.21409	.27476
#1	11.752	19.386	3.5627	1.9551	2.6327	3.9994	9.4950	4.4374
#2	11.727	19.302	3.5884	1.9493	2.6289	3.9892	9.4603	4.4265
#3	11.797	19.357	3.5923	1.9601	2.6304	4.0097	9.4959	4.4508

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	1.7422	.32642	1.0299	.44420	2.7578	2.2494	.32171	3.4971
Stddev	.0050	.00279	.0012	.00150	.0226	.0068	.00098	.0124
%RSD	.28669	.85361	.11745	.33857	.81931	.30223	.30367	.35445
#1	1.7397	.32324	1.0289	.44584	2.7826	2.2442	.32144	3.4832
#2	1.7390	.32757	1.0313	.44387	2.7526	2.2470	.32089	3.5015
#3	1.7480	.32845	1.0295	.44288	2.7383	2.2571	.32279	3.5068

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077	Li6707
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2.6475	.23146	3.6692	.86222	2.2657	46.356	3.5275
Stddev	.0049	.00035	.0185	.00238	.0064	.506	.0013
%RSD	.18572	.15139	.50499	.27641	.28335	1.0917	.03621
#1	2.6442	.23124	3.6479	.86072	2.2686	46.871	3.5261
#2	2.6451	.23128	3.6780	.86096	2.2583	45.859	3.5286
#3	2.6532	.23187	3.6817	.86496	2.2701	46.338	3.5278

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S4 Acquired: 02/06/2025 13:03:13 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S04 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3837.9	32668.	4908.3	2685.2	3974.8
Stddev	4.2	34.	5.7	26.5	10.7
%RSD	.10977	.10412	.11689	.98629	.26865
#1	3834.6	32631.	4901.8	2660.1	3970.4
#2	3842.6	32675.	4910.6	2682.5	3987.0
#3	3836.5	32698.	4912.5	2712.9	3967.0

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S5 Acquired: 02/06/2025 13:07:06 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934	Be2348
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	2546.5	1.1509	11.519	.69166	.95448	24.937	59.616	4.8778
Stddev	3.9	.0030	.016	.00144	.00338	.092	.791	.0232
%RSD	.15320	.25749	.14218	.20845	.35369	.36850	1.3276	.47554
#1	2545.7	1.1490	11.507	.69026	.95059	24.987	59.249	4.8759
#2	2543.0	1.1494	11.512	.69158	.95659	24.994	60.524	4.9019
#3	2550.7	1.1543	11.538	.69314	.95627	24.831	59.074	4.8556

Elem	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598	Mn2576	Mg2790
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	22.853	37.023	6.7985	3.7895	5.1098	7.6939	18.222	8.5227
Stddev	.035	.134	.0437	.0078	.0152	.0179	.049	.0300
%RSD	.15112	.36094	.64249	.20693	.29811	.23268	.26924	.35148
#1	22.834	37.158	6.8342	3.7822	5.1222	7.6973	18.258	8.5325
#2	22.832	37.022	6.8115	3.7884	5.1144	7.7099	18.243	8.5465
#3	22.893	36.890	6.7498	3.7978	5.0928	7.6746	18.166	8.4891

Elem	Ni2316	Ag3280	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3.4006	.64089	2.0003	.85984	5.6767	4.2719	.64706	6.4225
Stddev	.0051	.00269	.0051	.00044	.0251	.0217	.00048	.0344
%RSD	.15079	.41909	.25672	.05087	.44202	.50700	.07354	.53503
#1	3.3983	.63876	1.9987	.86023	5.6984	4.2808	.64663	6.4150
#2	3.3971	.64000	2.0061	.85992	5.6492	4.2877	.64699	6.4600
#3	3.4065	.64391	1.9962	.85936	5.6825	4.2472	.64757	6.3925

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077	Li6707
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	5.3141	.46830	6.8515	1.6688	4.3853	90.991	6.8284
Stddev	.0137	.00135	.0293	.0031	.0143	1.600	.0162
%RSD	.25729	.28770	.42692	.18679	.32664	1.7582	.23709
#1	5.2999	.46702	6.8328	1.6665	4.3982	89.872	6.8469
#2	5.3151	.46819	6.8852	1.6676	4.3879	92.824	6.8220
#3	5.3272	.46971	6.8365	1.6724	4.3699	90.278	6.8165

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S5 Acquired: 02/06/2025 13:07:06 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S05 Custom ID2: Custom ID3:
Comment:

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3571.8	31861.	4943.1	2476.6	3774.5
Stddev	6.7	60.	38.2	6.8	4.8
%RSD	.18690	.18757	.77246	.27255	.12590
#1	3579.5	31851.	4936.0	2471.2	3779.7
#2	3567.6	31807.	4909.0	2474.6	3773.5
#3	3568.2	31925.	4984.4	2484.2	3770.3

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: S6 Acquired: 02/06/2025 13:11:16 Type: Cal
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: IR Corr. Factor: 1.000000
User: Kareem Custom ID1: S06 Custom ID2: Custom ID3:
Comment:

Elem	Al3961	Ca3736	Fe2598	Mg2790	Na8183
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	65.457	59.417	20.693	13.905	5.5386
Stddev	.187	.763	.140	.112	.0383
%RSD	.28629	1.2837	.67472	.80718	.69111
#1	65.248	59.278	20.543	13.789	5.4948
#2	65.610	58.733	20.716	13.913	5.5555
#3	65.512	60.240	20.819	14.013	5.5655

Int. Std.	Y_3710
Units	Cts/S
Avg	4802.6
Stddev	37.0
%RSD	.76964
#1	4832.0
#2	4814.7
#3	4761.1

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: ICV002 Acquired: 02/06/2025 14:09:25 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: ICV002 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.078390	1.096619	.9927724	1.000393	.9084876	2.421396
Stddev	.003751	.001149	.0015494	.001800	.0035038	.072788
%RSD	.3477919	.1048206	.1560658	.1799739	.3856752	3.006019
#1	1.074123	1.095308	.9910177	.998484	.9111310	2.339933
#2	1.081164	1.097094	.9939521	1.000636	.9098185	2.444212
#3	1.079882	1.097454	.9933473	1.002060	.9045134	2.480042

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5234280	.5292396	.4898060	10.42960	.5514758	.5048443
Stddev	.0155471	.0124181	.0007719	.29143	.0018733	.0004997
%RSD	2.970256	2.346407	.1575822	2.794237	.3396892	.0989741
#1	.5055735	.5153155	.4889770	10.09380	.5533402	.5043959
#2	.5307348	.5332356	.4899372	10.57847	.5514935	.5047539
#3	.5339757	.5391679	.4905039	10.61651	.5495937	.5053829

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5247958	10.40608	.5315997	6.029586	.5037313	.2460558
Stddev	.0226659	.28610	.0149955	.146557	.0003227	.0012972
%RSD	4.318985	2.749354	2.820831	2.430631	.0640596	.5271992
#1	.4998789	10.07657	.5142947	5.860969	.5039719	.2464124
#2	.5303187	10.59132	.5407707	6.126354	.5033646	.2471374
#3	.5441898	10.55035	.5397336	6.101434	.5038573	.2446176

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	10.12224	.5161408	.9119059	8.985126	F -.001912	F .0044014
Stddev	.44950	.0148793	.0053540	.451682	.002793	.0008628
%RSD	4.440714	2.882801	.5871210	5.027000	146.0872	19.60187
#1	9.63387	.4990928	.9062434	8.466445	-.000442	.0050989
#2	10.21419	.5265137	.9125884	9.197094	-.005133	.0034366
#3	10.51865	.5228160	.9168859	9.291840	-.000161	.0046688

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: ICV002 Acquired: 02/06/2025 14:09:25 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: ICV002 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F .0000496	F .0030131	F -.000121	F .0015817	F .0005342	F -.009008
Stddev	.0007795	.0020526	.001285	.0006746	.0022562	.000444
%RSD	1571.151	68.12380	1059.415	42.65053	422.3750	4.934022
#1	.0008236	.0013392	-.001085	.0021533	-.002013	-.008497
#2	-.000735	.0053033	.001338	.0008376	.002281	-.009227
#3	.000061	.0023969	-.000617	.0017541	.001335	-.009301

Elem	Li6707
Units	ppm
Avg	F -.002802
Stddev	.003826
%RSD	136.5484
#1	-.002053
#2	.000594
#3	-.006947

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4353.721	36347.29	5058.016	3034.152	4897.165
Stddev	10.545	78.22	110.745	11.154	5.755
%RSD	.2422137	.2151920	2.189502	.3676185	.1175226
#1	4344.553	36295.07	5185.393	3045.974	4891.309
#2	4365.245	36309.59	5004.114	3032.666	4902.814
#3	4351.364	36437.22	4984.540	3023.815	4897.372

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: ICB002 Acquired: 02/06/2025 14:14:08 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: ICB002 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0020730	-.000583	.0001438	-.000614	.0002805	.0049590	.0009313
Stddev	.0025829	.001438	.0026294	.000680	.0018785	.0247410	.0000943
%RSD	124.5973	246.7565	1828.474	110.6850	669.6730	498.9077	10.12908
#1	.0049495	-.001664	-.001336	.000001	.0005882	.0139523	.0008600
#2	-.000047	-.001133	.003180	-.000500	.0019861	.0239456	.0010383
#3	.001317	.001049	-.001412	-.001344	-.001733	-.023021	.0008957

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000228	.0000557	.0133175	.0001157	.0000624	-.001387	.0034880
Stddev	.000042	.0000397	.0148946	.0004224	.0001756	.003830	.0108109
%RSD	18.64114	71.18764	111.8422	365.0481	281.5670	276.1454	309.9430
#1	-.000274	.0000147	.0304993	-.000313	-.000131	-.005633	.0159090
#2	-.000192	.0000939	.0040644	.000129	.000212	.001808	-.001643
#3	-.000216	.0000586	.0053889	.000531	.000105	-.000336	-.003802

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000210	-.010235	-.000345	.0002416	-.384774	-.002072	-.000834
Stddev	.000484	.002929	.000288	.0003427	.352161	.005459	.002994
%RSD	230.9375	28.61478	83.24464	141.8121	91.52409	263.4929	358.9167
#1	-.000741	-.011498	-.000018	-.000058	-.785301	-.004017	.001451
#2	.000207	-.006886	-.000460	.000167	-.245352	-.006292	-.004223
#3	-.000095	-.012319	-.000558	.000615	-.123670	.004093	.000269

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5865343	-.001014	-.000430	-.000320	-.004352	-.002561	.0014824
Stddev	.1243737	.000892	.001100	.000481	.000663	.000664	.0004543
%RSD	21.20485	87.95257	255.4829	150.1275	15.23864	25.91395	30.64285
#1	.4713859	-.001782	-.001500	-.000306	-.004584	-.002838	.0011661
#2	.7184352	-.001224	-.000490	.000153	-.003604	-.001804	.0020029
#3	.5697816	-.000036	.000698	-.000808	-.004868	-.003042	.0012781

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: ICB002 Acquired: 02/06/2025 14:14:08 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: ICB002 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Sr4077	Li6707
Units	ppm	ppm	ppm
Avg	.0009734	.0001134	.0005104
Stddev	.0005283	.0000261	.0019769
%RSD	54.27019	22.99590	387.3008
#1	.0015044	.0001125	.0008266
#2	.0009679	.0001399	-.001605
#3	.0004479	.0000878	.002310

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4364.427	37189.75	4916.953	3058.069	5231.033
Stddev	10.163	106.72	4.506	9.777	16.367
%RSD	.2328659	.2869601	.0916511	.3197233	.3128803
#1	4365.441	37078.78	4911.944	3046.785	5222.315
#2	4374.046	37198.82	4920.679	3064.013	5249.914
#3	4353.795	37291.64	4918.237	3063.410	5220.871

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: ICSA002 Acquired: 02/06/2025 14:18:10 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: ICSA002 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.002384	-.003203	.0018293	-.025783	.0039192	240.1811
Stddev	.002827	.000958	.0020524	.003810	.0024219	.9182
%RSD	118.6092	29.91687	112.1969	14.77713	61.79621	.3823042
#1	-.001502	-.002356	.0000786	-.028628	.0053997	240.6393
#2	-.000102	-.003010	.0040879	-.021455	.0011242	240.7801
#3	-.005546	-.004243	.0013213	-.027267	.0052336	239.1239

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0070301	.0025778	.0009324	249.3229	.0524308	.0295509
Stddev	.0010072	.0000427	.0000739	.6333	.0001527	.0002276
%RSD	14.32747	1.655674	7.920604	.2540273	.2912487	.7701021
#1	.0080149	.0025739	.0008488	249.6043	.0525825	.0296578
#2	.0060018	.0026223	.0009593	249.7668	.0524328	.0292896
#3	.0070737	.0025373	.0009890	248.5976	.0522771	.0297053

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.013900	101.3617	.0060612	247.0400	.0070465	-.008315
Stddev	.001480	.3969	.0006054	.5345	.0003479	.000395
%RSD	10.64413	.3915983	9.987599	.2163807	4.937076	4.751281
#1	-.012370	101.6970	.0056317	247.6254	.0067815	-.008315
#2	-.015323	101.4646	.0067535	246.9168	.0074405	-.007920
#3	-.014009	100.9234	.0057983	246.5778	.0069175	-.008710

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1062605	-.000218	-.033842	-1.01174	.0017806	F .0509463
Stddev	.0664170	.003401	.004082	.11211	.0009613	.0014107
%RSD	62.50388	1562.569	12.06295	11.08114	53.98734	2.769031
#1	.0430361	.003028	-.035240	-1.14026	.0021682	.0495966
#2	.1754655	-.003754	-.029244	-.93404	.0024877	.0524110
#3	.1002799	.000073	-.037041	-.96092	.0006860	.0508313

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: ICSA002 Acquired: 02/06/2025 14:18:10 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: ICSA002 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0039166	.0220594	-.007949	F .0099443	.0031083	.0032766
Stddev	.0004490	.0075728	.001942	.0009851	.0013933	.0001926
%RSD	11.46463	34.32893	24.42848	9.905863	44.82657	5.877384
#1	.0043894	.0305923	-.006636	.0107906	.0015495	.0032741
#2	.0038645	.0161377	-.007031	.0088630	.0042328	.0030853
#3	.0034959	.0194483	-.010180	.0101795	.0035425	.0034704

Elem	Li6707
Units	ppm
Avg	.0075111
Stddev	.0053760
%RSD	71.57379
#1	.0029599
#2	.0061308
#3	.0134427

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4008.335	32759.65	4845.681	2798.437	4130.946
Stddev	5.971	233.65	16.037	29.264	9.457
%RSD	.1489690	.7132403	.3309492	1.045730	.2289239
#1	4002.278	32679.83	4827.331	2784.583	4124.292
#2	4008.511	33022.75	4857.009	2832.056	4126.775
#3	4014.217	32576.36	4852.702	2778.673	4141.771

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: ICSAB002 Acquired: 02/06/2025 14:25:09 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: ICSAB002 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0970646	.0969064	.0505638	.0251493	.5404391	235.4937
Stddev	.0058432	.0002454	.0023814	.0024649	.0050663	1.5447
%RSD	6.019871	.2532490	4.709751	9.801173	.9374449	.6559464
#1	.1036632	.0969279	.0504317	.0252539	.5389555	233.7119
#2	.0949846	.0966509	.0482511	.0275603	.5362803	236.4564
#3	.0925461	.0971403	.0530085	.0226337	.5460816	236.3127

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5215429	.5095222	.9833905	247.1160	.5878444	.5176536
Stddev	.0021801	.0032843	.0010580	.6039	.0026729	.0006367
%RSD	.4180035	.6445791	.1075908	.2443856	.4546993	.1230024
#1	.5191937	.5057816	.9835095	246.4338	.5847628	.5183798
#2	.5235009	.5119336	.9822780	247.5823	.5892357	.5173900
#3	.5219340	.5108513	.9843840	247.3320	.5895347	.5171910

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.4914903	99.39877	.5060653	243.0205	.9844455	.2000793
Stddev	.0049180	.67826	.0026185	1.3772	.0007749	.0014902
%RSD	1.000621	.6823591	.5174279	.5667167	.0787174	.7447837
#1	.4922414	98.63774	.5030709	241.4310	.9850245	.1983965
#2	.4862400	99.61909	.5079257	243.8605	.9835651	.2006100
#3	.4959895	99.93947	.5071993	243.7698	.9847468	.2012315

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.2543729	.4943906	.8950811	-2.46382	.0013463	F .0489215
Stddev	.2401093	.0056127	.0053146	.11050	.0028682	.0009523
%RSD	94.39264	1.135281	.5937531	4.485049	213.0352	1.946611
#1	.5233797	.4938299	.8982051	-2.52499	-.000342	.0478806
#2	.0617404	.5002627	.8889447	-2.33626	-.000277	.0491348
#3	.1779987	.4890793	.8980936	-2.53022	.004658	.0497491

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: ICSAB002 Acquired: 02/06/2025 14:25:09 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: ICSAB002 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0035301	.0261269	-.006187	F .0094801	-.003118	.0041126
Stddev	.0004856	.0036218	.001096	.0007648	.002256	.0001745
%RSD	13.75578	13.86257	17.70964	8.067651	72.32891	4.243328
#1	.0029713	.0274360	-.004925	.0095825	-.003546	.0041602
#2	.0037689	.0289121	-.006739	.0101886	-.005129	.0042584
#3	.0038500	.0220325	-.006897	.0086693	-.000680	.0039193

Elem	Li6707
Units	ppm
Avg	.0058824
Stddev	.0017111
%RSD	29.08916
#1	.0044145
#2	.0054708
#3	.0077617

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4088.527	33027.63	4938.533	2859.671	4229.781
Stddev	17.178	83.50	32.230	5.678	19.886
%RSD	.4201541	.2528257	.6526155	.1985459	.4701411
#1	4069.226	33003.39	4959.175	2855.859	4207.498
#2	4094.218	32958.94	4901.394	2856.958	4236.121
#3	4102.137	33120.58	4955.029	2866.197	4245.724

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: CCV003 Acquired: 02/06/2025 14:29:02 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: CCV003 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	4.897817	4.946963	25.25169	4.968958	5.025551	405.7819	10.31806
Stddev	.006855	.005355	.01209	.001068	.006282	1.4676	.05355
%RSD	.1399577	.1082507	.0478591	.0214969	.1250053	.3616613	.5189572
#1	4.893888	4.941072	25.24521	4.968080	5.019428	404.1073	10.26362
#2	4.893829	4.948279	25.24422	4.970147	5.025245	406.8439	10.37067
#3	4.905732	4.951537	25.26563	4.968648	5.031982	406.3946	10.31989

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5062189	2.555506	409.1906	15.79171	2.541833	15.29538	408.6421
Stddev	.0040583	.002620	1.3193	.04806	.000974	.05107	1.7903
%RSD	.8016975	.1025080	.3224287	.3043279	.0383111	.3339150	.4381204
#1	.5015593	2.552810	407.6987	15.78382	2.542295	15.24162	406.6402
#2	.5081173	2.555667	410.2035	15.84322	2.540714	15.34325	410.0899
#3	.5089801	2.558041	409.6698	15.74808	2.542490	15.30127	409.1963

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	15.03079	404.0257	2.548769	1.262898	401.6293	2.524563	15.02723
Stddev	.06273	1.3785	.000851	.004078	.4603	.007680	.08195
%RSD	.4173487	.3411796	.0334022	.3228913	.1145994	.3042043	.5453496
#1	14.95901	402.4955	2.548857	1.262992	401.0984	2.517187	15.10804
#2	15.07507	405.1703	2.549573	1.266927	401.9144	2.532514	14.94418
#3	15.05829	404.4114	2.547877	1.258773	401.8753	2.523987	15.02948

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	152.5057	5.114138	5.043480	4.972645	5.153454	4.810930	5.098738
Stddev	.7160	.002518	.039827	.002899	.010716	.042248	.005108
%RSD	.4695064	.0492390	.7896690	.0583085	.2079451	.8781735	.1001797
#1	151.6883	5.112940	4.997675	4.972549	5.141667	4.762305	5.092926
#2	153.0218	5.112442	5.069928	4.969795	5.156084	4.838660	5.102516
#3	152.8070	5.117031	5.062838	4.975591	5.162610	4.831823	5.100771

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: CCV003 Acquired: 02/06/2025 14:29:02 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: CCV003 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Sr4077	Li6707
Units	ppm	ppm	ppm
Avg	5.074469	4.815236	5.123634
Stddev	.020797	.061993	.028236
%RSD	.4098328	1.287438	.5511000
#1	5.051907	4.749028	5.091332
#2	5.092872	4.871910	5.143625
#3	5.078628	4.824769	5.135944

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3651.707	31105.33	4806.042	2558.423	3735.720
Stddev	5.166	113.52	34.558	4.196	4.293
%RSD	.1414801	.3649394	.7190595	.1640248	.1149163
#1	3645.767	31054.43	4844.358	2554.878	3731.695
#2	3655.152	31026.17	4777.231	2563.057	3735.228
#3	3654.202	31235.39	4796.537	2557.335	3740.238

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: CCB003 Acquired: 02/06/2025 14:32:51 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: CCB003 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0005745	.0011764	-.000324	-.002572	.0030080	-.019291	.0017297
Stddev	.0020977	.0009888	.002316	.001928	.0026260	.008529	.0018664
%RSD	365.1219	84.05214	715.2915	74.98814	87.29956	44.21060	107.9006
#1	.0029753	.0005088	.000950	-.000563	.0059644	-.023160	.0031671
#2	-.000904	.0023124	-.002997	-.002744	.0009459	-.025200	-.000380
#3	-.000348	.0007081	.001076	-.004408	.0021139	-.009514	.002402

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000081	.0000734	.0133987	.0004990	.0003346	-.002870	.0279919
Stddev	.000121	.0000416	.0197206	.0002554	.0001359	.007841	.0039267
%RSD	148.7739	56.64379	147.1824	51.18549	40.60180	273.2210	14.02804
#1	-.000103	.0000917	.0359015	.0006433	.0003716	.000210	.0279169
#2	.000049	.0001027	.0051673	.0006495	.0001841	-.011783	.0319557
#3	-.000189	.0000258	-.000873	.0002041	.0004482	.002964	.0241033

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0005750	.0168537	-.000176	.0001743	-.135851	.0017609	.0004874
Stddev	.0006605	.0168535	.000510	.0003274	.425878	.0047811	.0020237
%RSD	114.8606	99.99883	290.2085	187.8129	313.4903	271.5222	415.1940
#1	.0011073	.0348296	.000116	.0000527	-.616106	.0004290	.0026665
#2	-.000164	.0014089	-.000765	.0005452	.195865	-.002213	-.001333
#3	.000782	.0143225	.000122	-.000075	.012689	.007067	.000129

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.6467297	-.000589	.0088263	.0006045	-.000843	-.001428	.0009983
Stddev	.0374253	.001195	.0013624	.0002007	.000897	.000192	.0000575
%RSD	5.786857	202.9229	15.43547	33.20598	106.3820	13.43441	5.763193
#1	.6107488	-.001864	.0072922	.0004203	.000063	-.001219	.0009319
#2	.6854491	-.000405	.0098949	.0005748	-.000862	-.001596	.0010326
#3	.6439913	.000503	.0092919	.0008185	-.001730	-.001470	.0010304

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: CCB003 Acquired: 02/06/2025 14:32:51 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: CCB003 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Sr4077	Li6707
Units	ppm	ppm	ppm
Avg	-.000116	.0001298	.0007911
Stddev	.001278	.0001015	.0026504
%RSD	1097.819	78.16925	335.0279
#1	-.000192	.0002123	.0030655
#2	-.001355	.0000165	-.002119
#3	.001197	.0001607	.001427

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4338.112	36892.40	4934.976	3051.072	5199.149
Stddev	4.984	123.09	29.087	14.461	10.943
%RSD	.1148780	.3336582	.5894064	.4739747	.2104813
#1	4333.910	36905.49	4944.367	3067.143	5189.365
#2	4336.809	36763.28	4958.208	3039.109	5197.115
#3	4343.618	37008.42	4902.354	3046.965	5210.966

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1151-13 Acquired: 02/06/2025 14:36:55 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MC0B02 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0006211	-.000538	.0008981	-.001941	.0008418	-.008331
Stddev	.0036013	.001422	.0022150	.004048	.0013260	.014388
%RSD	579.8341	264.0837	246.6346	208.5685	157.5082	172.7051
#1	.0028232	-.001456	.0001898	.002181	-.000603	-.023358
#2	-.003535	.001099	.0033806	-.002093	.002002	.005318
#3	.002575	-.001258	-.000876	-.005911	.001126	-.006952

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000510	-.000090	.0000024	-.002943	.0003237	.0003176
Stddev	.000554	.000067	.0000634	.019638	.0002679	.0001189
%RSD	108.5953	74.78240	2635.590	667.2471	82.75628	37.42508
#1	-.000866	-.000022	-.000030	.019357	.0000522	.0004335
#2	-.000793	-.000092	-.000038	-.010532	.0005878	.0003235
#3	.000128	-.000156	.000076	-.017654	.0003312	.0001959

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.009660	.0139941	-.000340	.0376820	.0003326	.0012592
Stddev	.004826	.0138960	.000190	.0192482	.0003331	.0009404
%RSD	49.96531	99.29921	55.88032	51.08068	100.1488	74.68399
#1	-.014405	-.001669	-.000401	.0481501	.0005757	.0022865
#2	-.009818	.018807	-.000491	.0154683	-.000047	.0010504
#3	-.004756	.024844	-.000127	.0494276	.000469	.0004407

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.123676	.0021858	.0001848	F -9.96484	.0056457	.0042529
Stddev	.583959	.0016675	.0011723	.08221	.0009019	.0009487
%RSD	472.1696	76.28757	634.3413	.8249869	15.97492	22.30702
#1	.455361	.0028618	.0015383	-9.88224	.0047517	.0035686
#2	-.113954	.0002865	-.000507	-9.96562	.0056300	.0038542
#3	-.712435	.0034091	-.000477	-10.0467	.0065553	.0053359

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1151-13 Acquired: 02/06/2025 14:36:55 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MC0B02 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0000900	-.003296	.0160634	-.004214	.0001958	-.000029
Stddev	.0001790	.002672	.0005965	.000211	.0021897	.000254
%RSD	198.9074	81.06845	3.713476	5.000980	1118.188	877.6784
#1	.0002911	-.005230	.0159595	-.004022	.0004931	.000108
#2	-.000052	-.000247	.0155256	-.004440	.0022217	.000127
#3	.000031	-.004412	.0167050	-.004179	-.002127	-.000321

Elem	Li6707
Units	ppm
Avg	-.008840
Stddev	.004127
%RSD	46.68667
#1	-.006766
#2	-.013592
#3	-.006161

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4594.514	38863.87	5098.709	3238.763	5637.524
Stddev	18.164	110.11	18.733	10.109	20.052
%RSD	.3953438	.2833284	.3673998	.3121237	.3556865
#1	4610.576	38739.73	5094.452	3231.377	5656.164
#2	4598.164	38949.77	5119.204	3250.284	5640.099
#3	4574.802	38902.10	5082.471	3234.628	5616.309

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1251-10 Acquired: 02/06/2025 14:41:00 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: E1498 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0007371	-.000286	.0027206	-.002383	.0002248	.0182975
Stddev	.0013517	.001226	.0005189	.001628	.0026503	.0110258
%RSD	183.3759	428.5499	19.07268	68.30550	1178.842	60.25834
#1	.0022734	.000362	.0025307	-.000926	.0032058	.0074350
#2	-.000270	.000480	.0023234	-.004140	-.001865	.0294795
#3	.000208	-.001701	.0033076	-.002084	-.000666	.0179779

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000750	-.000072	.0000634	.0214564	.0060285	.0003555
Stddev	.001907	.000153	.0000490	.0093155	.0005008	.0001494
%RSD	254.1407	212.0938	77.34458	43.41582	8.306308	42.03651
#1	-.002936	.000098	.0000826	.0318931	.0058582	.0002627
#2	.000577	-.000117	.0000999	.0184928	.0056352	.0005279
#3	.000108	-.000198	.0000077	.0139833	.0065922	.0002759

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0018144	.0837930	.0020767	-.003862	.0017612	-.000011
Stddev	.0067444	.0139527	.0007896	.030377	.0000950	.000313
%RSD	371.7154	16.65140	38.02172	786.6374	5.391264	2810.363
#1	.0092908	.0762727	.0026201	.030201	.0018648	-.000354
#2	-.000036	.0752136	.0024389	-.013642	.0016784	.000259
#3	-.003812	.0998925	.0011710	-.028144	.0017404	.000062

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1399145	.0021952	.0004139	F -10.0951	.0044706	.0072898
Stddev	.1372625	.0028615	.0016591	.1666	.0027089	.0011439
%RSD	98.10452	130.3551	400.8768	1.650624	60.59279	15.69242
#1	.2974162	.0006824	.0019523	-10.1207	.0022072	.0073563
#2	.0458047	.0004076	.0006335	-9.9172	.0037327	.0083990
#3	.0765226	.0054956	-.001344	-10.2475	.0074720	.0061140

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1251-10 Acquired: 02/06/2025 14:41:00 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: E1498 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000505	.0255590	.0409030	-.003758	.0016372	.0000867
Stddev	.000264	.0046044	.0021801	.000159	.0007663	.0000227
%RSD	52.21849	18.01463	5.330009	4.223904	46.80492	26.20775
#1	-.000500	.0253055	.0433750	-.003781	.0011481	.0000859
#2	-.000771	.0210866	.0392548	-.003904	.0025203	.0000644
#3	-.000243	.0302848	.0400791	-.003589	.0012431	.0001098

Elem	Li6707
Units	ppm
Avg	-.005193
Stddev	.004100
%RSD	78.95219
#1	-.009529
#2	-.001378
#3	-.004673

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4552.049	37931.68	5066.794	3200.115	5602.264
Stddev	7.994	91.38	11.052	15.605	7.781
%RSD	.1756174	.2408991	.2181313	.4876502	.1388856
#1	4558.472	38018.77	5063.007	3182.662	5610.776
#2	4543.096	37939.71	5079.242	3204.959	5595.518
#3	4554.578	37836.55	5058.132	3212.723	5600.499

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166571BL Acquired: 02/06/2025 14:45:04 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: PBW571 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0009511	-.001854	.0013262	.0019190	-.001839	-.013516	.0005400
Stddev	.0008329	.000191	.0016630	.0020830	.002650	.024267	.0007054
%RSD	87.57238	10.29776	125.3901	108.5486	144.0929	179.5442	130.6281
#1	.0019128	-.001660	.0010957	-.000193	.001075	.013696	.0006813
#2	.0004712	-.002042	.0030924	.001978	-.004105	-.032912	.0011641
#3	.0004692	-.001861	-.000209	.003972	-.002487	-.021331	-.000225

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000121	.0000371	-.004970	.0000720	.0002684	-.005235	.0028128
Stddev	.000041	.0000826	.014577	.0005460	.0002529	.003208	.0103983
%RSD	33.60314	222.8238	293.2820	758.8886	94.23475	61.27792	369.6779
#1	-.000075	-.000047	.008869	.0007017	.0000131	-.004878	.0145581
#2	-.000153	.000039	-.020186	-.000269	.0005189	-.002220	-.005219
#3	-.000135	.000119	-.003593	-.000217	.0002731	-.008605	-.000901

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0007437	.0137347	-.000077	.0013053	.0207204	-.000232	.0005736
Stddev	.0011087	.0124394	.000376	.0009507	.3368971	.001800	.0015159
%RSD	149.0916	90.56892	487.4441	72.83612	1625.923	775.4713	264.2696
#1	.0020026	.0053961	.000355	.0023107	.3972160	-.001686	-.000603
#2	-.000087	.0077753	-.000334	.0004208	-.252309	-.000791	.002284
#3	.000316	.0280326	-.000253	.0011844	-.082746	.001781	.000040

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1563866	-.000276	.0019366	-.000301	-.004830	-.003269	.0001329
Stddev	.1674007	.000440	.0014959	.000858	.004109	.001386	.0008158
%RSD	107.0429	159.0090	77.24069	284.9254	85.07275	42.39387	613.6864
#1	.2409299	-.000646	.0019011	-.001233	-.002710	-.002933	-.000488
#2	.2646551	-.000393	.0004588	-.000124	-.002214	-.002082	-.000170
#3	-.036425	.000210	.0034499	.000454	-.009567	-.004791	.001057

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166571BL Acquired: 02/06/2025 14:45:04 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: PBW571 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Sr4077	Li6707
Units	ppm	ppm	ppm
Avg	-.000463	.0001094	-.000330
Stddev	.002511	.0000970	.004810
%RSD	542.0256	88.63093	1459.406
#1	-.000354	.0002191	-.005829
#2	.001991	.0000350	.003095
#3	-.003027	.0000742	.001745

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4382.662	36614.56	4979.039	3057.955	5249.321
Stddev	13.624	237.47	28.949	16.965	17.371
%RSD	.3108721	.6485758	.5814215	.5547761	.3309098
#1	4368.433	36346.63	4946.567	3048.796	5236.203
#2	4383.966	36697.99	4988.400	3047.538	5242.739
#3	4395.588	36799.06	5002.149	3077.530	5269.020

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166571BS Acquired: 02/06/2025 14:49:08 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: LCS571 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0244538	.0522066	.0178718	.0659741	.1085260	.4134502
Stddev	.0023150	.0008312	.0022384	.0017633	.0018047	.0122109
%RSD	9.466912	1.592216	12.52504	2.672707	1.662883	2.953409
#1	.0260420	.0515900	.0186779	.0665580	.1066441	.4139216
#2	.0217975	.0518778	.0195955	.0639929	.1086918	.4254185
#3	.0255218	.0531519	.0153419	.0673713	.1102420	.4010104

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.4164419	.0105990	.0097214	10.63717	.0218159	.1039138
Stddev	.0005271	.0000639	.0000110	.00911	.0003865	.0002142
%RSD	.1265615	.6029431	.1132436	.0856322	1.771644	.2060947
#1	.4163202	.0105319	.0097260	10.63814	.0219685	.1041033
#2	.4170192	.0106591	.0097088	10.62761	.0213763	.1036815
#3	.4159864	.0106062	.0097293	10.64575	.0221027	.1039565

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0486557	.2029766	.0321149	10.19501	.0785074	.0196612
Stddev	.0024212	.0310180	.0001053	.08748	.0003515	.0007904
%RSD	4.976261	15.28155	.3278388	.8580954	.4477650	4.020003
#1	.0498563	.2062597	.0319939	10.24118	.0787695	.0198810
#2	.0458688	.1704477	.0321854	10.09412	.0781079	.0187842
#3	.0502420	.2322225	.0321655	10.24974	.0786449	.0203184

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	10.31588	.1092650	.1198085	10.65257	.0156689	F .0012580
Stddev	.29449	.0025040	.0015605	.11772	.0012219	.0017847
%RSD	2.854734	2.291645	1.302477	1.105075	7.798476	141.8743
#1	9.97772	.1080214	.1180699	10.75353	.0166234	.0018337
#2	10.51598	.1121473	.1202680	10.52327	.0160914	-.000744
#3	10.45394	.1076262	.1210877	10.68092	.0142917	.002684

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166571BS Acquired: 02/06/2025 14:49:08 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: LCS571 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0203076	.1655490	F 1.003342	.0151852	.2047885	.2127685
Stddev	.0002005	.0028355	.007997	.0008204	.0018090	.0004514
%RSD	.9874015	1.712777	.7970346	5.402633	.8833674	.2121368
#1	.0204719	.1630414	1.004018	.0159615	.2059416	.2125016
#2	.0200842	.1686260	.995028	.0143269	.2027035	.2132897
#3	.0203668	.1649797	1.010979	.0152673	.2057204	.2125143

Elem	Li6707
Units	ppm
Avg	.0305765
Stddev	.0017705
%RSD	5.790336
#1	.0308948
#2	.0321663
#3	.0286685

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4340.552	36372.82	5039.773	3039.453	4897.539
Stddev	10.504	113.10	24.946	17.480	13.806
%RSD	.2420051	.3109588	.4949807	.5751152	.2818969
#1	4328.756	36454.62	5034.460	3025.704	4881.635
#2	4344.006	36243.75	5066.948	3033.529	4906.437
#3	4348.895	36420.10	5017.912	3059.125	4904.546

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166568BL Acquired: 02/06/2025 14:53:06 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: PBW568 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0013223	-.000047	-.000477	-.003850	-.000442	-.015221	.0013266
Stddev	.0022963	.000761	.001702	.000513	.001199	.010297	.0010159
%RSD	173.6669	1611.096	356.6412	13.32202	271.2274	67.65347	76.58264
#1	-.001276	.000804	.001335	-.004337	-.001361	-.024923	.0023459
#2	.003081	-.000663	-.000725	-.003315	-.000880	-.004417	.0013199
#3	.002161	-.000283	-.002042	-.003900	.000914	-.016322	.0003140

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000202	-.000001	.0037212	.0004598	.0000981	-.006259	.0197528
Stddev	.000172	.000008	.0069497	.0003059	.0001859	.003208	.0062623
%RSD	84.80329	727.3143	186.7602	66.52973	189.5540	51.25048	31.70365
#1	-.000350	-.000005	.0112029	.0005587	.0001676	-.002709	.0269701
#2	-.000014	.000008	-.002533	.0007040	-.000113	-.007119	.0165315
#3	-.000243	-.000006	.002494	.0001167	.000239	-.008948	.0157568

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000215	.0131270	-.000392	.0014215	-.441751	.0036387	-.002400
Stddev	.000387	.0146596	.000111	.0009518	.399716	.0048134	.002055
%RSD	179.4891	111.6748	28.22685	66.95966	90.48461	132.2819	85.61377
#1	-.000565	.0274403	-.000284	.0006354	-.902625	.0011098	-.000936
#2	-.000282	.0137966	-.000505	.0011493	-.232981	.0006170	-.001516
#3	.000200	-.001856	-.000385	.0024797	-.189646	.0091895	-.004749

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5266897	.0006331	.0004716	-.000359	-.004199	-.001249	.0004828
Stddev	.0477154	.0010423	.0011334	.000524	.001131	.001189	.0005880
%RSD	9.059489	164.6329	240.3079	145.9075	26.92990	95.17799	121.8040
#1	.5730117	.0017223	-.000181	.000132	-.002899	-.000410	.0002541
#2	.5293639	-.000355	-.000185	-.000911	-.004746	-.002609	.0011508
#3	.4776934	.000532	.001780	-.000298	-.004953	-.000727	.0000434

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166568BL Acquired: 02/06/2025 14:53:06 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: PBW568 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Sr4077	Li6707
Units	ppm	ppm	ppm
Avg	.0000832	-.000062	-.002459
Stddev	.0002043	.000008	.002502
%RSD	245.5273	13.09413	101.7171
#1	-.000002	-.000054	-.003444
#2	.000316	-.000064	-.004319
#3	-.000064	-.000070	.000385

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4420.878	37413.20	5025.620	3090.190	5296.057
Stddev	13.783	60.04	20.302	12.393	16.650
%RSD	.3117812	.1604718	.4039756	.4010315	.3143881
#1	4425.894	37368.95	5044.407	3101.793	5299.039
#2	4431.451	37481.54	5028.369	3091.642	5311.015
#3	4405.289	37389.11	5004.083	3077.135	5278.118

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166568BS Acquired: 02/06/2025 14:57:06 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: LCS568 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0240339	.0522156	.0184160	.0634187	.1089415	.4233959
Stddev	.0027037	.0017592	.0005689	.0046364	.0052945	.0054780
%RSD	11.24943	3.369040	3.088988	7.310713	4.859921	1.293814
#1	.0239722	.0534223	.0190671	.0685478	.1028305	.4296842
#2	.0213616	.0501971	.0180151	.0595258	.1121492	.4208440
#3	.0267679	.0530273	.0181658	.0621824	.1118448	.4196594

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.4153705	.0108129	.0095305	10.62019	.0207528	.1033437
Stddev	.0019627	.0001143	.0000311	.04577	.0009158	.0007498
%RSD	.4725277	1.057294	.3261706	.4310072	4.412706	.7255086
#1	.4136852	.0108936	.0095015	10.59674	.0218048	.1024931
#2	.4175255	.0108630	.0095634	10.67294	.0201342	.1036295
#3	.4149009	.0106821	.0095267	10.59090	.0203193	.1039086

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0532201	.2282413	.0328893	10.32030	.0780583	.0204635
Stddev	.0021048	.0147155	.0003964	.09702	.0004420	.0002638
%RSD	3.954816	6.447322	1.205319	.9401030	.5662027	1.289135
#1	.0508344	.2130971	.0332269	10.24960	.0775706	.0207653
#2	.0548143	.2424868	.0324528	10.43091	.0784323	.0203486
#3	.0540118	.2291400	.0329882	10.28039	.0781720	.0202767

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	10.34987	.1136562	.1174315	10.52132	.0181947	F .0014512
Stddev	.34622	.0075934	.0019699	.31859	.0028865	.0015716
%RSD	3.345151	6.681039	1.677493	3.028077	15.86457	108.2993
#1	9.95367	.1155188	.1187051	10.66741	.0198626	.0019500
#2	10.59422	.1053048	.1184270	10.74068	.0148617	-.000309
#3	10.50171	.1201450	.1151626	10.15589	.0198600	.002713

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166568BS Acquired: 02/06/2025 14:57:06 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: LCS568 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0205207	.1667959	F 1.010989	.0141663	.2047641	.2143031
Stddev	.0004917	.0013405	.004441	.0010819	.0007811	.0004181
%RSD	2.396011	.8036967	.4393039	7.637100	.3814698	.1951180
#1	.0201130	.1654350	1.009553	.0129926	.2040267	.2139351
#2	.0203823	.1681151	1.015970	.0143824	.2055826	.2147578
#3	.0210667	.1668376	1.007442	.0151238	.2046831	.2142164

Elem	Li6707
Units	ppm
Avg	.0296244
Stddev	.0026038
%RSD	8.789275
#1	.0326305
#2	.0281705
#3	.0280724

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4282.279	36133.26	4948.025	2980.691	4852.984
Stddev	8.711	94.19	21.369	15.524	5.252
%RSD	.2034232	.2606766	.4318638	.5208220	.1082225
#1	4273.009	36050.73	4956.232	2967.730	4847.653
#2	4290.295	36113.19	4923.770	2976.447	4853.144
#3	4283.535	36235.87	4964.074	2997.896	4858.154

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166494TB Acquired: 02/06/2025 15:01:00 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: LEB494 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0038289	-.002249	-.000450	.0035083	.0016644	-.025220
Stddev	.0028837	.000562	.002165	.0005635	.0009511	.013561
%RSD	75.31388	24.98009	480.7270	16.06171	57.14151	53.77106
#1	.0005015	-.001671	.001659	.0030706	.0008826	-.009747
#2	.0056021	-.002793	-.002667	.0041441	.0013873	-.035042
#3	.0053832	-.002285	-.000342	.0033103	.0027232	-.030872

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.001473	-.000039	-.000007	.0141217	.0021578	.0007695
Stddev	.001237	.000116	.000044	.0172082	.0003847	.0002406
%RSD	83.97143	294.9312	678.2325	121.8568	17.82704	31.26621
#1	-.000848	.000076	-.000058	-.000490	.0017137	.0005073
#2	-.002897	-.000039	.000016	.009766	.0023860	.0009802
#3	-.000673	-.000155	.000022	.033089	.0023736	.0008210

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.009654	.0133344	.0009584	.0505846	.0031683	.0009771
Stddev	.007321	.0041783	.0010869	.0028001	.0003977	.0011088
%RSD	75.82982	31.33440	113.4110	5.535528	12.55166	113.4700
#1	-.009171	.0085847	.0010231	.0538051	.0030998	-.000252
#2	-.002587	.0149757	.0020116	.0487258	.0035958	.001902
#3	-.017205	.0164428	-.000159	.0492228	.0028093	.001281

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F 1387.901	.0004322	.0005361	F -8.74701	.0001817	-.000540
Stddev	6.191	.0053768	.0031532	.14613	.0016982	.002412
%RSD	.4461029	1243.937	588.2243	1.670651	934.7427	446.3546
#1	1381.802	-.004888	.0028528	-8.90633	-.001492	-.003310
#2	1394.181	.000320	.0018102	-8.71549	.001904	.001105
#3	1387.721	.005864	-.003055	-8.61922	.000133	.000583

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: PB166494TB Acquired: 02/06/2025 15:01:00 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: LEB494 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0003084	.0244430	-.004281	-.001907	.0019962	.0001164
Stddev	.0002344	.0025518	.001141	.000862	.0018114	.0003298
%RSD	75.99901	10.43977	26.65895	45.17621	90.74056	283.2837
#1	.0005634	.0220543	-.005570	-.001758	-.000035	.0004801
#2	.0001026	.0271315	-.003877	-.001130	.003444	.0000323
#3	.0002591	.0241433	-.003397	-.002834	.002579	-.000163

Elem	Li6707
Units	ppm
Avg	-.009093
Stddev	.001933
%RSD	21.25944
#1	-.010819
#2	-.007004
#3	-.009457

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4214.901	33469.94	5323.463	2939.796	4236.942
Stddev	13.592	94.81	28.783	11.737	13.141
%RSD	.3224647	.2832669	.5406806	.3992416	.3101617
#1	4202.412	33444.85	5350.436	2936.486	4223.646
#2	4229.376	33390.20	5293.159	2930.069	4249.923
#3	4212.916	33574.77	5326.792	2952.832	4237.259

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1272-03A Acquired: 02/06/2025 15:05:00 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2A Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1209910	-.041184	.4344795	-.043044	.1385913	115.3771	1.025544
Stddev	.0030860	.001339	.0062736	.001719	.0029325	.4188	.002517
%RSD	2.550635	3.252322	1.443931	3.992450	2.115902	.3629975	.2453866
#1	.1200952	-.041083	.4363853	-.043035	.1357666	114.8949	1.022777
#2	.1244258	-.042571	.4274740	-.041331	.1383864	115.5855	1.027696
#3	.1184519	-.039898	.4395791	-.044768	.1416208	115.6508	1.026159

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0165688	-.000346	85.59022	.3097389	.2065893	.2236408	310.8348
Stddev	.0001962	.000076	.21931	.0018070	.0021981	.0017734	1.2000
%RSD	1.184131	22.09923	.2562331	.5834089	1.063980	.7929864	.3860466
#1	.0163434	-.000258	85.44853	.3077469	.2058047	.2252485	309.4523
#2	.0167012	-.000393	85.84284	.3112730	.2048912	.2239353	311.4460
#3	.0166617	-.000387	85.47930	.3101967	.2090720	.2217385	311.6062

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	8.066574	86.97952	.3723281	-.018405	1.869422	.3763821	2.156257
Stddev	.031506	.36918	.0045088	.001460	.239769	.0043828	.004005
%RSD	.3905710	.4244442	1.210971	7.932636	12.82584	1.164464	.1857259
#1	8.030230	86.55324	.3700350	-.018887	2.128608	.3723057	2.160214
#2	8.086139	87.19577	.3694267	-.016765	1.824126	.3810177	2.152207
#3	8.083353	87.18955	.3775225	-.019563	1.655531	.3758229	2.156350

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	6.731157	5.477019	.2094207	.0171019	2.367719	7.621283	.0575880
Stddev	.223963	.063852	.0036623	.0002287	.030887	.049921	.0025400
%RSD	3.327258	1.165820	1.748756	1.337097	1.304513	.6550203	4.410582
#1	6.475518	5.450086	.2064373	.0168959	2.350258	7.571589	.0578230
#2	6.825121	5.431046	.2135079	.0170618	2.349517	7.671428	.0549387
#3	6.892831	5.549925	.2083168	.0173480	2.403382	7.620832	.0600023

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1272-03A Acquired: 02/06/2025 15:05:00 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2A Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Sr4077	Li6707
Units	ppm	ppm	ppm
Avg	3.849619	.3760081	.3155430
Stddev	.007237	.0010272	.0035514
%RSD	.1879843	.2731887	1.125503
#1	3.841298	.3748220	.3193344
#2	3.853121	.3765944	.3150007
#3	3.854439	.3766079	.3122938

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	5161.086	42633.15	6208.990	3650.207	4487.755
Stddev	38.928	22.48	14.442	5.719	43.865
%RSD	.7542664	.0527333	.2325907	.1566808	.9774335
#1	5181.042	42658.20	6225.476	3646.377	4506.997
#2	5185.990	42626.53	6198.575	3647.462	4518.710
#3	5116.226	42614.72	6202.921	3656.781	4437.558

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-01 Acquired: 02/06/2025 15:08:47 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA0 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0053967	.0064452	-.000715	-.004172	-.011076	.1542328
Stddev	.0018590	.0020245	.001401	.002546	.003977	.0164402
%RSD	34.44606	31.41119	195.8360	61.02483	35.90856	10.65936
#1	.0033366	.0071330	-.000068	-.002297	-.015476	.1690407
#2	.0059044	.0080361	-.002323	-.007071	-.007737	.1365417
#3	.0069490	.0041664	.000245	-.003148	-.010016	.1571159

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	2.558497	.0003785	.0019935	85.64776	.0024457	.0265129
Stddev	.009197	.0002109	.0000409	.41606	.0004364	.0004233
%RSD	.3594613	55.73194	2.049578	.4857762	17.84250	1.596385
#1	2.563210	.0005037	.0019844	85.69124	.0019424	.0266780
#2	2.547899	.0001349	.0019580	85.21167	.0027173	.0268287
#3	2.564382	.0004968	.0020382	86.04036	.0026775	.0260320

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0033831	.0958555	1.678662	14.59721	.0042393	.0010627
Stddev	.0067537	.0249099	.007109	.09136	.0006456	.0016009
%RSD	199.6311	25.98690	.4234911	.6258813	15.22782	150.6400
#1	.0039373	.0673904	1.672296	14.53196	.0036029	-.000584
#2	.0098426	.1136667	1.677355	14.55805	.0042214	.001159
#3	-.003631	.1065093	1.686333	14.70163	.0048936	.002613

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F 1340.901	-.000097	1.753945	-.850751	.1285282	.9546525
Stddev	3.737	.005415	.014205	.122652	.0007556	.0113672
%RSD	.2786770	5573.733	.8098633	14.41685	.5878598	1.190711
#1	1341.758	-.002368	1.761809	-.991845	.1283481	.9447307
#2	1336.810	.006083	1.762479	-.769578	.1278790	.9521717
#3	1344.134	-.004007	1.737548	-.790831	.1293575	.9670552

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-01 Acquired: 02/06/2025 15:08:47 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA0 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0029293	3.083888	2.985400	.0006934	.0034509	.6046202
Stddev	.0006066	.008158	.028213	.0005849	.0023255	.0024039
%RSD	20.70783	.2645292	.9450323	84.34691	67.38762	.3975880
#1	.0028510	3.074812	2.963316	.0012447	.0015604	.6026264
#2	.0023656	3.086241	2.975701	.0000799	.0027447	.6039446
#3	.0035712	3.090610	3.017183	.0007556	.0060476	.6072896

Elem	Li6707
Units	ppm
Avg	-.001246
Stddev	.003166
%RSD	254.0698
#1	-.004822
#2	-.000119
#3	.001202

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4234.250	33967.57	5304.907	2983.475	4178.865
Stddev	11.802	144.51	47.067	11.823	10.441
%RSD	.2787292	.4254295	.8872276	.3962969	.2498512
#1	4220.866	33927.10	5342.536	2977.541	4169.197
#2	4238.720	34128.00	5320.052	2975.794	4177.463
#3	4243.164	33847.62	5252.132	2997.090	4189.937

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-02 Acquired: 02/06/2025 15:12:37 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA1 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0011381	.0085276	.0013761	-.001379	-.011852	.1790766
Stddev	.0019895	.0016464	.0021090	.001252	.003815	.0241548
%RSD	174.8013	19.30610	153.2651	90.79655	32.18820	13.48852
#1	.0009713	.0086743	-.001035	-.001725	-.015625	.1818795
#2	.0032058	.0068128	.002283	.000010	-.011933	.1536426
#3	-.000763	.0100957	.002880	-.002421	-.007997	.2017077

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	2.714315	.0008179	.0006568	104.2454	.0031566	.0399164
Stddev	.008165	.0000767	.0000358	.2456	.0004560	.0002945
%RSD	.3008267	9.373095	5.457531	.2356182	14.44633	.7379090
#1	2.705012	.0007635	.0006387	103.9728	.0031319	.0399539
#2	2.717639	.0009055	.0006981	104.3139	.0036245	.0401904
#3	2.720294	.0007846	.0006336	104.4495	.0027134	.0396049

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0403304	.0187715	1.717882	25.51666	.0190368	.0026381
Stddev	.0061682	.0152182	.008917	.15346	.0002212	.0001272
%RSD	15.29427	81.07050	.5190695	.6013937	1.161925	4.823115
#1	.0434322	.0046274	1.709060	25.46077	.0192673	.0026627
#2	.0443320	.0168130	1.717696	25.39898	.0190168	.0027512
#3	.0332269	.0348741	1.726891	25.69023	.0188263	.0025004

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F 1323.103	.0016787	.7845885	-3.15322	.0092764	.4948601
Stddev	3.880	.0036822	.0026892	.14640	.0033047	.0043743
%RSD	.2932839	219.3442	.3427477	4.642794	35.62497	.8839563
#1	1319.881	.0039876	.7867529	-2.99931	.0124383	.4898101
#2	1322.018	-.002568	.7854345	-3.16965	.0095456	.4974750
#3	1327.411	.003616	.7815781	-3.29072	.0058453	.4972951

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-02 Acquired: 02/06/2025 15:12:37 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA1 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0026032	1.800613	5.018493	.0003203	-.000949	.5605711
Stddev	.0005014	.003243	.038878	.0005153	.003065	.0030289
%RSD	19.26016	.1800879	.7746851	160.8936	323.0803	.5403337
#1	.0031817	1.796921	4.973683	.0002186	-.001691	.5576406
#2	.0023338	1.803000	5.043236	.0008789	-.003573	.5603829
#3	.0022941	1.801917	5.038562	-.000137	.002419	.5636897

Elem	Li6707
Units	ppm
Avg	.0237098
Stddev	.0035565
%RSD	15.00024
#1	.0202535
#2	.0235172
#3	.0273587

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4142.834	33439.79	5230.917	2913.292	4064.045
Stddev	6.597	106.72	36.563	5.263	6.736
%RSD	.1592460	.3191281	.6989743	.1806645	.1657362
#1	4149.772	33324.42	5268.725	2915.136	4071.686
#2	4136.640	33534.97	5228.282	2917.385	4058.965
#3	4142.091	33459.97	5195.742	2907.355	4061.485

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-03 Acquired: 02/06/2025 15:16:29 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0038979	.0138338	.0271375	-.004980	-.016066	.1138464
Stddev	.0010293	.0035830	.0022870	.004195	.000877	.0115741
%RSD	26.40698	25.90033	8.427417	84.24088	5.461242	10.16637
#1	.0035785	.0097719	.0268865	-.000691	-.016974	.1008321
#2	.0030662	.0151837	.0249864	-.009075	-.016002	.1177212
#3	.0050491	.0165458	.0295397	-.005175	-.015223	.1229860

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.948409	.0000063	.0028485	200.4475	.0033780	.0346011
Stddev	.006094	.0002151	.0000073	.4703	.0006352	.0004979
%RSD	.3127716	3425.818	.2559751	.2346073	18.80320	1.439064
#1	1.941509	.0001126	.0028404	199.9364	.0026539	.0349914
#2	1.953054	.0001475	.0028507	200.8620	.0038408	.0340403
#3	1.950663	-.000241	.0028545	200.5440	.0036394	.0347714

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0687463	.0480927	3.995862	32.44588	.0097944	.0021433
Stddev	.0026204	.0110771	.002182	.08741	.0002336	.0001548
%RSD	3.811771	23.03291	.0546046	.2693909	2.385362	7.222114
#1	.0658344	.0538342	3.994242	32.34660	.0095746	.0023206
#2	.0694899	.0353235	3.995000	32.51122	.0100398	.0020736
#3	.0709146	.0551204	3.998343	32.47984	.0097690	.0020355

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F 1349.907	.0010464	.4741510	4.489561	.0848179	.2511780
Stddev	3.328	.0021821	.0031686	.212213	.0012688	.0017350
%RSD	.2465717	208.5332	.6682633	4.726817	1.495904	.6907406
#1	1346.102	.0022535	.4721978	4.333058	.0845266	.2515442
#2	1352.280	-.001473	.4724483	4.404518	.0862070	.2492892
#3	1351.339	.002358	.4778069	4.731105	.0837200	.2527007

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-03 Acquired: 02/06/2025 15:16:29 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0030814	1.798972	3.332333	.0010469	-.001000	1.421465
Stddev	.0004803	.004572	.005144	.0012102	.001088	.004127
%RSD	15.58693	.2541221	.1543758	115.5990	108.7663	.2903332
#1	.0035027	1.801543	3.326913	-.000130	-.002021	1.417013
#2	.0025584	1.793694	3.337148	.000983	-.001125	1.422219
#3	.0031832	1.801679	3.332939	.002288	.000145	1.425163

Elem	Li6707
Units	ppm
Avg	.0030903
Stddev	.0040464
%RSD	130.9378
#1	.0022069
#2	-.000441
#3	.007505

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4100.250	33245.64	5210.686	2865.847	4026.844
Stddev	11.530	8.94	12.603	9.672	6.576
%RSD	.2811934	.0268821	.2418724	.3375055	.1633045
#1	4103.104	33239.69	5224.483	2858.461	4028.526
#2	4110.085	33255.91	5199.778	2876.795	4032.416
#3	4087.562	33241.31	5207.797	2862.284	4019.590

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-04 Acquired: 02/06/2025 15:20:21 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2D Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0038759	.0124035	.0253369	-.004312	-.015301	.1012850
Stddev	.0013674	.0027755	.0007728	.002969	.003503	.0264763
%RSD	35.27824	22.37670	3.050045	68.84907	22.89392	26.14040
#1	.0026362	.0155683	.0247413	-.007739	-.012693	.1135992
#2	.0053425	.0103834	.0250592	-.002519	-.013927	.1193616
#3	.0036490	.0112590	.0262101	-.002678	-.019283	.0708944

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.819256	.0000245	.0026331	185.9746	.0034381	.0325020
Stddev	.008786	.0000538	.0000840	.9039	.0005229	.0004051
%RSD	.4829476	219.3655	3.191742	.4860232	15.20866	1.246247
#1	1.829133	.0000336	.0025361	186.9506	.0040064	.0329646
#2	1.816322	-.000033	.0026847	185.8067	.0029773	.0323306
#3	1.812312	.000073	.0026786	185.1664	.0033307	.0322109

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0615425	.0479698	3.696928	30.00559	.0088822	.0018635
Stddev	.0022542	.0043803	.022113	.25959	.0008609	.0009741
%RSD	3.662785	9.131316	.5981346	.8651284	9.692000	52.27213
#1	.0593733	.0488637	3.711434	30.26567	.0093991	.0029857
#2	.0613811	.0518341	3.707873	30.00461	.0078884	.0013693
#3	.0638730	.0432115	3.671477	29.74650	.0093590	.0012356

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F 1255.189	.0024052	.4481132	3.341609	.0782225	.2366001
Stddev	6.844	.0029209	.0049288	.165124	.0003695	.0009197
%RSD	.5452635	121.4413	1.099901	4.941459	.4723710	.3886957
#1	1260.985	.0035601	.4455451	3.531557	.0778140	.2372495
#2	1256.945	-.000917	.4537957	3.232293	.0785334	.2370029
#3	1247.638	.004572	.4449988	3.260976	.0783200	.2355477

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-04 Acquired: 02/06/2025 15:20:21 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2D Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0033529	1.697694	3.132505	-.000150	-.003096	1.317534
Stddev	.0000398	.005222	.026937	.000994	.002722	.009239
%RSD	1.187449	.3075988	.8599302	664.0871	87.91058	.7012156
#1	.0033083	1.699297	3.163316	.000999	-.006205	1.323022
#2	.0033848	1.691858	3.120795	-.000724	-.001940	1.322714
#3	.0033656	1.701927	3.113405	-.000723	-.001143	1.306868

Elem	Li6707
Units	ppm
Avg	.0021556
Stddev	.0032670
%RSD	151.5623
#1	.0057512
#2	.0013460
#3	-.000631

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4236.631	34258.75	5477.697	2974.326	4171.807
Stddev	28.812	187.33	49.347	10.980	25.294
%RSD	.6800743	.5468049	.9008651	.3691648	.6063027
#1	4260.810	34244.11	5422.949	2983.722	4193.996
#2	4244.332	34079.17	5491.393	2962.256	4177.162
#3	4204.751	34452.97	5518.748	2977.001	4144.265

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-03LX5 Acquired: 02/06/2025 15:24:12 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2L Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0008580	.0039022	.0037619	-.004789	-.007916	.0056832	.3779745
Stddev	.0047701	.0008278	.0031042	.002168	.001092	.0206173	.0026345
%RSD	555.9597	21.21518	82.51796	45.27978	13.79175	362.7723	.6969961
#1	.0001777	.0033162	.0025984	-.004697	-.006936	-.016906	.3749430
#2	.0059318	.0048492	.0072798	-.002668	-.009093	.010470	.3797090
#3	-.003535	.0035410	.0014075	-.007001	-.007718	.023486	.3792715

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.000099	.0005856	39.01354	.0006779	.0175086	.0101244	.0355775
Stddev	.000107	.0000540	.27060	.0003623	.0004722	.0005416	.0090251
%RSD	107.7159	9.228699	.6935978	53.43517	2.697118	5.349576	25.36749
#1	.000004	.0006457	38.70486	.0002597	.0170486	.0095534	.0436723
#2	-.000210	.0005411	39.12588	.0008935	.0179921	.0106309	.0372142
#3	-.000092	.0005700	39.20987	.0008806	.0174851	.0101888	.0258460

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.7657056	6.313585	.0012491	.0007220	260.2455	.0009825	.0833293
Stddev	.0043853	.056015	.0002837	.0003481	1.4860	.0020886	.0045354
%RSD	.5727102	.8872082	22.71027	48.21167	.5710084	212.5813	5.442725
#1	.7606576	6.249011	.0014576	.0010281	258.5400	.0033934	.0835313
#2	.7678854	6.342658	.0013635	.0007945	260.9342	-.000279	.0786963
#3	.7685739	6.349085	.0009260	.0003434	261.2622	-.000166	.0877603

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	3.009717	.0111998	.0545050	.0016047	.3335440	.6872810	.0009914
Stddev	.324827	.0031715	.0017987	.0003135	.0060265	.0081040	.0013506
%RSD	10.79262	28.31716	3.300023	19.53718	1.806795	1.179131	136.2398
#1	2.727674	.0143059	.0544382	.0014980	.3279669	.6782106	.0005334
#2	2.936608	.0079667	.0563361	.0013585	.3399368	.6898239	-.000071
#3	3.364868	.0113269	.0527406	.0019576	.3327283	.6938085	.002511

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-03LX5 Acquired: 02/06/2025 15:24:12 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2L Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Sr4077	Li6707
Units	ppm	ppm	ppm
Avg	.0017600	.2697571	.0243972
Stddev	.0007702	.0017401	.0037523
%RSD	43.76342	.6450764	15.37995
#1	.0015652	.2677611	.0206294
#2	.0026090	.2705554	.0281337
#3	.0011059	.2709549	.0244285

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4209.849	34292.02	5034.554	2959.965	4371.800
Stddev	13.642	109.96	27.370	16.251	19.156
%RSD	.3240420	.3206476	.5436388	.5490251	.4381778
#1	4219.312	34185.71	5061.406	2941.751	4383.408
#2	4194.211	34405.29	5006.694	2972.980	4349.689
#3	4216.023	34285.04	5035.562	2965.164	4382.302

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-05 Acquired: 02/06/2025 15:28:08 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2S Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0030952	.0128836	.0268476	-.006681	-.016428	.1104922
Stddev	.0010408	.0010922	.0002699	.001702	.004965	.0252400
%RSD	33.62686	8.477813	1.005223	25.46723	30.22466	22.84320
#1	.0037709	.0140656	.0265751	-.007079	-.013008	.1165920
#2	.0018966	.0119116	.0271148	-.008149	-.022123	.1321233
#3	.0036180	.0126738	.0268527	-.004816	-.014152	.0827614

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	1.969573	-.000015	.0028126	201.5828	.0026797	.0339928
Stddev	.006398	.000091	.0000200	.2143	.0009076	.0006859
%RSD	.3248546	602.7768	.7121137	.1063253	33.86882	2.017748
#1	1.962477	.000089	.0028357	201.3353	.0036145	.0334620
#2	1.971338	-.000083	.0028013	201.7035	.0026225	.0337491
#3	1.974903	-.000051	.0028008	201.7094	.0018020	.0347673

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0813390	.0398734	3.986759	32.32035	.0098437	.0013983
Stddev	.0037068	.0150511	.011392	.04981	.0004550	.0001021
%RSD	4.557266	37.74707	.2857496	.1541149	4.622062	7.304271
#1	.0817191	.0251437	3.980939	32.29823	.0094556	.0014651
#2	.0848412	.0552264	3.999885	32.37739	.0103444	.0012807
#3	.0774568	.0392502	3.979452	32.28544	.0097311	.0014490

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	F 1354.419	-.000416	.4719165	4.704351	.0860466	.2498278
Stddev	2.564	.002785	.0008850	.046345	.0035081	.0024120
%RSD	.1892894	668.8283	.1875359	.9851445	4.076929	.9654692
#1	1356.167	.001037	.4714008	4.651128	.0833378	.2506240
#2	1355.613	.001341	.4714102	4.735786	.0900093	.2517411
#3	1351.476	-.003627	.4729384	4.726140	.0847927	.2471184

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: Q1273-05 Acquired: 02/06/2025 15:28:08 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: MBHHA2S Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0033199	1.814655	3.344048	.0007267	-.001981	1.421911
Stddev	.0008444	.007322	.016810	.0006544	.001476	.004300
%RSD	25.43450	.4034800	.5026923	90.04916	74.50932	.3024054
#1	.0026812	1.811493	3.353481	.0001629	-.003673	1.423610
#2	.0030013	1.809447	3.354025	.0014442	-.000954	1.425102
#3	.0042772	1.823027	3.324640	.0005729	-.001317	1.417021

Elem	Li6707
Units	ppm
Avg	.0026815
Stddev	.0042135
%RSD	157.1340
#1	-.001520
#2	.006907
#3	.002657

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4123.787	33317.23	5254.037	2894.372	4059.552
Stddev	14.539	122.71	7.797	6.204	10.804
%RSD	.3525758	.3682950	.1484094	.2143486	.2661419
#1	4122.112	33448.61	5245.057	2901.263	4060.612
#2	4139.091	33297.49	5257.965	2889.231	4069.786
#3	4110.157	33205.60	5259.089	2892.623	4048.256

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: CCV004 Acquired: 02/06/2025 15:31:59 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: CCV004 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961	Ba4934
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	4.946935	4.927557	25.16357	4.979684	5.048762	404.5170	10.22991
Stddev	.005791	.002792	.02011	.014690	.005647	2.0854	.03600
%RSD	.1170628	.0566638	.0799162	.2949922	.1118464	.5155245	.3519042
#1	4.950997	4.929711	25.18460	4.983656	5.055279	402.7008	10.23027
#2	4.940304	4.928557	25.16156	4.991980	5.045330	404.0557	10.19373
#3	4.949503	4.924402	25.14454	4.963417	5.045676	406.7944	10.26573

Elem	Be2348	Cd2144	Ca3736	Cr2677	Co2286	Cu3247	Fe2598
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.5047959	2.541482	406.2170	15.63628	2.528157	15.16069	406.0647
Stddev	.0017410	.002580	1.7925	.02690	.003138	.06312	1.7042
%RSD	.3448978	.1014999	.4412583	.1720061	.1241306	.4163725	.4196988
#1	.5030656	2.543984	405.8008	15.63581	2.530119	15.14347	404.5178
#2	.5047746	2.541632	404.6693	15.66341	2.529814	15.10797	405.7847
#3	.5065475	2.538831	408.1810	15.60962	2.524537	15.23065	407.8916

Elem	Mn2576	Mg2790	Ni2316	Ag3280	Na8183	V_2924	Zn2138
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	14.92323	400.7920	2.538796	1.251160	399.0791	2.508524	15.00620
Stddev	.07030	1.8694	.000460	.004090	2.9566	.008537	.04203
%RSD	.4710952	.4664266	.0181026	.3268750	.7408673	.3403164	.2800729
#1	14.87108	399.1971	2.538945	1.251791	398.2527	2.501908	15.05449
#2	14.89543	400.3296	2.538280	1.254898	396.6235	2.505503	14.97788
#3	15.00319	402.8492	2.539162	1.246792	402.3610	2.518160	14.98623

Elem	K_7698	P_1774	B_2496	Mo2020	S_1820	Si2516	Sn1899
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Avg	153.1942	5.107492	5.013436	4.963208	5.169283	4.776902	5.079407
Stddev	1.0482	.007484	.022671	.000323	.008620	.029399	.002215
%RSD	.6842563	.1465336	.4521964	.0065023	.1667568	.6154326	.0436024
#1	152.2288	5.114676	4.990708	4.962836	5.165021	4.744137	5.080556
#2	153.0445	5.108059	5.013552	4.963403	5.179204	4.785595	5.076854
#3	154.3092	5.099740	5.036049	4.963385	5.163624	4.800973	5.080811

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: CCV004 Acquired: 02/06/2025 15:31:59 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: CCV004 Custom ID2: Custom ID3:
Comment:

Elem	Ti3361	Sr4077	Li6707
Units	ppm	ppm	ppm
Avg	5.047730	4.816639	5.065178
Stddev	.039722	.064153	.028918
%RSD	.7869215	1.331897	.5709176
#1	5.022844	4.763856	5.052009
#2	5.026806	4.888042	5.045189
#3	5.093539	4.798019	5.098337

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	3684.451	31602.28	4888.721	2568.685	3777.266
Stddev	4.788	86.09	17.444	12.179	5.892
%RSD	.1299585	.2724262	.3568281	.4741203	.1559898
#1	3682.572	31564.71	4908.816	2562.777	3774.042
#2	3680.888	31541.36	4879.882	2560.588	3773.688
#3	3689.894	31700.78	4877.466	2582.691	3784.066

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: CCB004 Acquired: 02/06/2025 15:35:43 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: CCB004 Custom ID2: Custom ID3:
Comment:

Elem	As1890	Tl1908	Pb2203	Se1960	Sb2068	Al3961
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0036847	.0000550	-.000007	-.004828	.0000186	-.006411
Stddev	.0026105	.0013978	.000915	.004639	.0028314	.005224
%RSD	70.84662	2540.397	13281.82	96.09266	15258.20	81.49164
#1	.0029785	-.001018	.000554	-.007407	.0025689	-.009553
#2	.0015000	-.000453	-.001063	.000528	.0005150	-.009300
#3	.0065757	.001636	.000489	-.007605	-.003028	-.000380

Elem	Ba4934	Be2348	Cd2144	Ca3736	Cr2677	Co2286
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0016872	.0000762	.0001357	.0071051	.0011149	.0007158
Stddev	.0007536	.0001972	.0000531	.0102056	.0002776	.0002281
%RSD	44.66615	258.8970	39.13522	143.6383	24.90002	31.86027
#1	.0025180	-.000151	.0001773	.0187936	.0012413	.0004758
#2	.0014961	.000181	.0001539	.0025600	.0013069	.0007420
#3	.0010476	.000199	.0000759	-.000038	.0007966	.0009296

Elem	Cu3247	Fe2598	Mn2576	Mg2790	Ni2316	Ag3280
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	-.006334	.0195428	.0007233	.0489625	-.000141	.0008649
Stddev	.005753	.0187941	.0008595	.0182055	.000774	.0007467
%RSD	90.82235	96.16899	118.8339	37.18252	549.7923	86.32940
#1	-.011507	.0410410	-.000245	.0366825	.000749	.0015101
#2	-.000138	.0062266	.001018	.0698789	-.000509	.0010377
#3	-.007359	.0113609	.001397	.0403262	-.000663	.0000470

Elem	Na8183	V_2924	Zn2138	K_7698	P_1774	B_2496
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.1911111	.0021598	-.000037	1.197418	.0010610	.0065817
Stddev	.1419942	.0013140	.000233	.305769	.0003215	.0007231
%RSD	74.29928	60.83920	621.9783	25.53567	30.30155	10.98625
#1	.0394787	.0007012	-.000158	.935296	.0012038	.0073251
#2	.2129082	.0025273	.000231	1.533329	.0006928	.0065393
#3	.3209463	.0032509	-.000185	1.123627	.0012863	.0058808

Reviewed By:JANVI
On:2/10/2025 1:38:43 PM
Inst Id :P5

Sample Name: CCB004 Acquired: 02/06/2025 15:35:43 Type: Unk
Method: SFAM01.1 INSTRUMENT P5 WITH 6 POINT ICAL-2(v132) Mode: CONC Corr. Factor: 1.00000
User: Kareem Custom ID1: CCB004 Custom ID2: Custom ID3:
Comment:

Elem	Mo2020	S_1820	Si2516	Sn1899	Ti3361	Sr4077
Units	ppm	ppm	ppm	ppm	ppm	ppm
Avg	.0001879	-.003434	-.001764	.0003105	.0013424	.0002742
Stddev	.0002170	.001620	.000514	.0011967	.0027931	.0001969
%RSD	115.5048	47.18230	29.15132	385.4404	208.0739	71.80302
#1	.0001028	-.001715	-.001209	-.000431	-.000770	.0003707
#2	.0000264	-.004933	-.002223	.001691	.004509	.0000477
#3	.0004346	-.003656	-.001859	-.000328	.000288	.0004042

Elem	Li6707
Units	ppm
Avg	F .0174513
Stddev	.0025087
%RSD	14.37558
#1	.0159811
#2	.0160248
#3	.0203481

Int. Std.	Y_2243	Y_3600	Y_3710	Y_2243	In2306
Units	Cts/S	Cts/S	Cts/S	Cts/S	Cts/S
Avg	4376.907	37398.28	4974.395	3050.928	5250.814
Stddev	4.898	163.72	41.451	8.025	3.640
%RSD	.1119001	.4377694	.8332910	.2630361	.0693314
#1	4382.562	37524.71	4962.167	3056.774	5249.519
#2	4374.075	37456.78	4940.434	3054.231	5254.925
#3	4374.083	37213.35	5020.585	3041.779	5247.998

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900, Fax : 908 789 8922

Prep Standard - Chemical Standard Summary

Order ID : Q1151

Test : Metals CLP Full

Prepbatch ID : PB166229,PB166568,

Sequence ID/Qc Batch ID: LB134438,LB134438,LB134460,LB134460,LB134475,LB134517,LB134617,LB134617,

Standard ID :

MP83500,MP84041,MP84063,MP84070,MP84204,MP84206,MP84207,MP84208,MP84209,MP84210,MP84211,MP84212,MP84213,MP84214,MP84215,MP84216,MP84218,MP84219,MP84297,MP84338,MP84339,MP84340,MP84341,MP84381,MP84382,MP84383,MP84384,MP84385,MP84386,MP84387,MP84388,MP84389,MP84390,MP84391,MP84392,

Chemical ID :

M4884,M5130,M5218,M5223,M5289,M5295,M5298,M5393,M5429,M5466,M5467,M5472,M5476,M5496,M5497,M5498,M5513,M5519,M5565,M5658,M5697,M5798,M5799,M5800,M5801,M5802,M5806,M5811,M5815,M5817,M5819,M5875,M5942,M5959,M5961,M5962,M5976,M5977,M5978,M5985,M5990,M6021,M6023,M6025,M6028,M6030,M6032,M6077,M6121,M6125,M6126,M6127,M6128,M6144,M6145,M6146,M6147,M6148,M6149,W3112,

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
902	ICP AES CAL BLK (SO/ICB/CCB)	MP83500	12/06/2024	01/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 12/09/2024

FROM 125.00000ml of M6121 + 2350.00000ml of W3112 + 25.00000ml of M6126 = Final Quantity: 2500.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
169	1:1HNO3	MP84041	01/14/2025	07/14/2025	Eman Mughal	None	None	Sarabjit Jaswal 01/16/2025

FROM 1250.00000ml of M6126 + 1250.00000ml of W3112 = Final Quantity: 2500.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
994	ICPAES ISM01.2 S1 (CONC.)	MP84063	01/14/2025	02/14/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/16/2025

FROM 0.02000ml of M5815 + 0.03000ml of M5429 + 0.10000ml of M5798 + 0.10000ml of M6028 + 0.14000ml of M5799 + 0.20000ml of M5298 + 0.20000ml of M5476 + 0.20000ml of M5658 + 0.20000ml of M5801 + 0.20000ml of M5817 + 0.20000ml of M5976 + 0.20000ml of M6025 + 0.20000ml of M6030 + 0.30000ml of M6128 + 0.40000ml of M5496 + 0.50000ml of M5697 + 0.50000ml of M6023 + 0.70000ml of M5962 + 0.80000ml of M5961 + 1.00000ml of M5800 + 1.00000ml of M6021 + 1.20000ml of M5802 + 1.20000ml of M5819 + 10.00000ml of M5497 + 10.00000ml of M5519 + 10.00000ml of M5806 + 10.00000ml of M6127 + 2.00000ml of M5942 + 4.00000ml of M6032 + 34.24000ml of MP83500 = Final Quantity: 100.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
921	ICPAES SPIKE SOL#6	MP84070	01/14/2025	02/14/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/16/2025

FROM 2.50000ml of M5962 + 50.00000ml of M5565 + 50.00000ml of M5990 + 147.50000ml of MP83500 = Final Quantity: 250.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
902	ICP AES CAL BLK (SO/ICB/CCB)	MP84204	01/24/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 125.00000ml of M6121 + 2350.00000ml of W3112 + 25.00000ml of M6126 = Final Quantity: 2500.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
2480	ICP AES STD 6 ISM01.3	MP84206	01/24/2025	02/04/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 4.00000ml of M5289 + 4.00000ml of M5298 + 4.00000ml of M5497 + 4.00000ml of M6127 + 4.00000ml of M6144 + 30.00000ml of MP84204 = Final Quantity: 50.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1004	ICPAES ISM01.2 (S5)	MP84207	01/24/2025	02/04/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 0.25000ml of M5798 + 0.50000ml of M5429 + 0.50000ml of M5476 + 0.50000ml of M5815 + 0.50000ml of M5817 + 12.50000ml of M5519 + 12.50000ml of M5819 + 12.50000ml of M6128 + 12.50000ml of M6144 + 13.75000ml of M5697 + 14.50000ml of M5298 + 14.50000ml of M5496 + 14.50000ml of M5658 + 2.00000ml of M5513 + 22.50000ml of M5497 + 22.50000ml of M6127 + 5.00000ml of M5393 + 5.00000ml of M5802 + 5.00000ml of M5875 + 5.00000ml of M6077 + 303.50000ml of MP84204 = Final Quantity: 500.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1005	ICPAES ISM01.2(S4)	MP84208	01/24/2025	02/04/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 250.00000ml of MP84204 + 250.00000ml of MP84207 = Final Quantity: 500.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1007	ICPAES ISM01.2(S3)	MP84209	01/24/2025	02/04/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 25.00000ml of MP84207 + 75.00000ml of MP84204 = Final Quantity: 100.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1008	ICPAES ISM01.2(S2)	MP84210	01/24/2025	02/04/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 12.50000ml of MP84207 + 87.50000ml of MP84204 = Final Quantity: 100.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
994	ICPAES ISM01.2 S1 (CONC.)	MP84211	01/24/2025	02/04/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 0.02000ml of M5815 + 0.03000ml of M5429 + 0.10000ml of M5798 + 0.10000ml of M6028 + 0.14000ml of M5799 + 0.20000ml of M5298 + 0.20000ml of M5476 + 0.20000ml of M5658 + 0.20000ml of M5801 + 0.20000ml of M5817 + 0.20000ml of M5977 + 0.20000ml of M6025 + 0.20000ml of M6030 + 0.30000ml of M6128 + 0.40000ml of M5496 + 0.50000ml of M5697 + 0.50000ml of M6023 + 0.70000ml of M5962 + 0.80000ml of M5961 + 1.00000ml of M5800 + 1.00000ml of M6021 + 1.20000ml of M5802 + 1.20000ml of M5819 + 10.00000ml of M5497 + 10.00000ml of M5519 + 10.00000ml of M6127 + 10.00000ml of M6144 + 2.00000ml of M5978 + 4.00000ml of M6032 + 34.24000ml of MP84204 = Final Quantity: 100.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1003	ICPAES ISM01.2 S1	MP84212	01/24/2025	02/04/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 0.50000ml of MP84211 + 99.50000ml of MP84204 = Final Quantity: 100.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
912	ICP AES ICV SOLN	MP84213	01/24/2025	02/05/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 0.02500ml of M5429 + 0.02500ml of M5815 + 0.02500ml of M5817 + 0.10000ml of M5466 + 0.25000ml of M5218 + 0.25000ml of M5472 + 10.00000ml of M5295 + 89.77500ml of MP84204 = Final Quantity: 100.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
904	ICP AES ICSA SOLN	MP84214	01/24/2025	02/07/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 25.00000ml of M5130 + 225.00000ml of MP84204 = Final Quantity: 250.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
905	ICP AES ICSAB SOLN	MP84215	01/24/2025	02/07/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 25.00000ml of M5130 + 25.00000ml of M5223 + 200.00000ml of MP84204 = Final Quantity: 250.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1119	ICPAES ISM01.2(CCV)	MP84216	01/24/2025	02/04/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 0.75000ml of M5497 + 0.75000ml of M6127 + 1.22500ml of M5496 + 1.25000ml of M5298 + 1.25000ml of M6144 + 19.77500ml of MP84204 + 25.00000ml of MP84207 = Final Quantity: 50.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
919	ICP AES INTERNAL STD	MP84218	01/24/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 1.00000ml of M5959 + 10.00000ml of M5985 + 1969.00000ml of W3112 + 20.00000ml of M6126 = Final Quantity: 2000.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
903	ICP AES RINSE SOLN	MP84219	01/24/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 01/27/2025

FROM 200.00000ml of M6126 + 9800.00000ml of W3112 = Final Quantity: 10000.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
170	1:1HCL	MP84297	01/31/2025	02/28/2025	Eman Mughal	None	None	Sarabjit Jaswal 01/31/2025

FROM 1250.00000ml of M6121 + 1250.00000ml of W3112 = Final Quantity: 2500.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1389	AS 100PPM	MP84338	12/18/2024	02/18/2025	Kareem Khairalla	None	None	Sohil Jodhani 02/11/2025

FROM 1.00000ml of M5801 + 9.00000ml of MP84204 = Final Quantity: 10.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
955	BE 10.0PPM	MP84339	01/14/2025	02/14/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/05/2025

FROM 0.10000ml of M5798 + 9.90000ml of MP84204 = Final Quantity: 10.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
935	CU 100.0PPM	MP84340	01/15/2025	02/15/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/05/2025

FROM 1.00000ml of M5697 + 9.00000ml of MP84204 = Final Quantity: 10.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
3559	SE 100PPM	MP84341	01/14/2025	02/14/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/05/2025

FROM 1.00000ml of M5962 + 9.00000ml of MP84204 = Final Quantity: 10.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
2480	ICP AES STD 6 ISM01.3	MP84381	01/27/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 4.00000ml of M5289 + 4.00000ml of M5497 + 4.00000ml of M5811 + 4.00000ml of M6127 + 4.00000ml of M6144 + 30.00000ml of MP84204 = Final Quantity: 50.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1004	ICPAES ISM01.2 (S5)	MP84382	01/27/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 0.25000ml of M5798 + 0.50000ml of M5429 + 0.50000ml of M5476 + 0.50000ml of M5815 + 0.50000ml of M5817 + 12.50000ml of M5519 + 12.50000ml of M6128 + 12.50000ml of M6144 + 13.75000ml of M5697 + 14.50000ml of M5496 + 14.50000ml of M5658 + 14.50000ml of M5811 + 2.00000ml of M5513 + 22.50000ml of M5497 + 22.50000ml of M6127 + 5.00000ml of M4884 + 5.00000ml of M5393 + 5.00000ml of M5875 + 5.00000ml of M6077 + 5.00000ml of M6146 + 303.50000ml of MP84204 = Final Quantity: 500.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1004	ICPAES ISM01.2 (S5)	MP84383	01/27/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 0.25000ml of M5798 + 0.50000ml of M5429 + 0.50000ml of M5476 + 0.50000ml of M5815 + 0.50000ml of M5817 + 12.50000ml of M5519 + 12.50000ml of M6128 + 12.50000ml of M6144 + 12.50000ml of M6145 + 13.75000ml of M5697 + 14.50000ml of M5496 + 14.50000ml of M5658 + 14.50000ml of M5811 + 2.00000ml of M5513 + 22.50000ml of M5497 + 22.50000ml of M6127 + 5.00000ml of M4884 + 5.00000ml of M5393 + 5.00000ml of M5875 + 5.00000ml of M6077 + 5.00000ml of M6146 + 303.50000ml of MP84204 = Final Quantity: 500.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1005	ICPAES ISM01.2(S4)	MP84384	01/27/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 250.00000ml of MP84204 + 250.00000ml of MP84382 = Final Quantity: 500.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1007	ICPAES ISM01.2(S3)	MP84385	01/27/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 25.00000ml of MP84382 + 75.00000ml of MP84204 = Final Quantity: 100.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1008	ICPAES ISM01.2(S2)	MP84386	01/27/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 12.50000ml of MP84382 + 87.50000ml of MP84204 = Final Quantity: 100.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
994	ICPAES ISM01.2 S1 (CONC.)	MP84387	01/27/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 0.02000ml of M5815 + 0.03000ml of M5429 + 0.10000ml of M5798 + 0.10000ml of M6028 + 0.14000ml of M5799 + 0.20000ml of M5476 + 0.20000ml of M5658 + 0.20000ml of M5801 + 0.20000ml of M5811 + 0.20000ml of M5817 + 0.20000ml of M5977 + 0.20000ml of M6025 + 0.20000ml of M6030 + 0.30000ml of M6128 + 0.40000ml of M5496 + 0.50000ml of M5697 + 0.50000ml of M6023 + 0.70000ml of M5962 + 0.80000ml of M5961 + 1.00000ml of M5800 + 1.00000ml of M6021 + 1.20000ml of M6145 + 1.20000ml of M6146 + 10.00000ml of M4884 + 10.00000ml of M5498 + 10.00000ml of M5519 + 10.00000ml of M6127 + 10.00000ml of M6144 + 2.00000ml of M5978 + 4.00000ml of M6032 + 34.24000ml of MP84204 = Final Quantity: 100.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1003	ICPAES ISM01.2 S1	MP84388	01/27/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 0.50000ml of MP84387 + 99.50000ml of MP84204 = Final Quantity: 100.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
912	ICP AES ICV SOLN	MP84389	01/27/2025	02/08/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 0.02500ml of M5429 + 0.02500ml of M5815 + 0.02500ml of M5817 + 0.10000ml of M5467 + 0.25000ml of M5218 + 0.25000ml of M5472 + 10.00000ml of M6147 + 89.77500ml of MP84204 = Final Quantity: 100.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
904	ICP AES ICSA SOLN	MP84390	01/27/2025	02/08/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 25.00000ml of M6148 + 225.00000ml of MP84204 = Final Quantity: 250.000 ml

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
905	ICP AES ICSAB SOLN	MP84391	01/27/2025	02/08/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 25.00000ml of M6148 + 25.00000ml of M6149 + 200.00000ml of MP84204 = Final Quantity: 250.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Metals STANDARD PREPARATION LOG

Recipe ID	NAME	NO.	Prep Date	Expiration Date	Prepared By	ScaleID	PipetteID	Supervised By
1119	ICPAES ISM01.2(CCV)	MP84392	01/27/2025	02/24/2025	Kareem Khairalla	None	None	Sarabjit Jaswal 02/10/2025

FROM 0.75000ml of M5498 + 0.75000ml of M6127 + 1.22500ml of M5496 + 1.25000ml of M5811 + 1.25000ml of M6144 + 19.77500ml of MP84204 + 25.00000ml of MP84382 = Final Quantity: 50.000 ml

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57014 / Si, 1000 PPM, 125 ml	030921	03/09/2025	08/06/2021 / jaswal	08/05/2021 / jaswal	M4884

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
EPA	PART A / ICSA (ICP) STOCK SOLN	ICSA-1211	01/31/2025	05/20/2024 /jaswal	04/20/2021 / bin	M5130

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CHEM-QC-4 / CHEM-QC-4, Second Source, 1000 ug/ml, B, Mo, Si, Sn, Ti	S2-MEB711674	11/02/2026	07/01/2022 / bin	09/10/2021 / bin	M5218

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
EPA	PART B / ICSAB (ICP) STOCK SOLN	ICSB-0710	01/31/2025	05/20/2024 /jaswal	04/20/2021 / bin	M5223

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58113 / Aluminum (Al) 10,000PPM	070622	07/06/2025	09/02/2022 / jaswal	07/12/2022 / jaswal	M5289

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
EPA	ICV-1 / ICV (ICP/ICPMS) STOCK SOLN	ICV-1014	02/05/2025	08/07/2024 / jaswal	04/20/2021 / bin	M5295

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58126 / Fe, 10000 PPM, 500 ml	020422	02/04/2025	05/02/2023 / jaswal	06/15/2022 / jaswal	M5298

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CLPP-CAL-3 / CLP CAL SOLUTION #3, 125mL	T2-MEB714159	01/13/2027	10/12/2022 / bin	09/19/2022 / bin	M5393

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57103 / Li, 10000 PPM, 125 ml	070622	07/06/2025	01/30/2023 / bin	01/26/2023 / bin	M5429

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57058 / Cerium, 1000PPM, 100ML	061322	06/13/2025	03/06/2023 / bin	03/01/2023 / bin	M5466

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57058 / Cerium, 1000PPM, 100ML	020623	02/06/2026	03/06/2023 / bin	03/01/2023 / bin	M5467

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57038 / Sr, 1000 PPM, 125 ml	082922	08/29/2025	01/14/2025 / Jaswal	03/16/2023 / jaswal	M5472

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57138 / Sr, 10000 PPM, 125 ml	082922	08/29/2025	07/29/2024 /jaswal	03/16/2023 / jaswal	M5476

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58113 / Al, 10000 PPM, 500 ml	011623	01/16/2026	08/15/2023 / jaswal	03/17/2023 / bin	M5496

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58120 / Ca, 10000 PPM, 500 ml	031523	03/15/2026	03/18/2023 / bin	03/17/2023 / bin	M5497

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58120 / Ca, 10000 PPM, 500 ml	031523	03/15/2026	08/15/2023 / jaswal	03/17/2023 / bin	M5498

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57182 / Pb, 10000 PPM, 125 ml	061522	06/15/2025	03/19/2023 / bin	03/17/2023 / bin	M5513

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57119 / Potassium (K) 10,000PPM	120822	12/08/2025	01/08/2024 / bin	03/17/2023 / bin	M5519

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CLPP-SPK-1 / SOIL/WATER SPIKE SOLN 1, 125mL	T2-MEB721963	07/27/2027	05/30/2023 / jaswal	05/26/2023 / jaswal	M5565

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58024 / Chromium, Cr, 500 ml, 1000 PPM	060523	06/05/2026	08/28/2023 / jaswal	08/25/2023 / jaswal	M5658

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58029 / Cu, 1000 PPM, 500 ml	102523	10/25/2026	04/03/2024 / jaswal	10/27/2023 / jaswal	M5697

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57004 / Be, 1000 PPM, 125 ml	102523	10/25/2026	02/09/2024 / bin	02/09/2024 / bin	M5798

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57050 / Sn, 1000 PPM, 125 ml	071123	07/11/2026	02/09/2024 / bin	02/09/2024 / bin	M5799

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57027 / CO, 1000 PPM, 125 ml	091923	09/19/2026	05/31/2024 / bin	02/09/2024 / bin	M5800

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57033 / As, 1000 PPM, 125 ml	111323	11/13/2026	02/09/2024 / bin	02/09/2024 / bin	M5801

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57051 / Sb, 1000 PPM, 125 ml	120523	12/05/2026	08/07/2024 / jaswal	01/03/2024 / jaswal	M5802

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58111 / Na, 10000 PPM, 500 ml	122223	12/22/2026	08/01/2024 / Jaswal	01/03/2024 / jaswal	M5806

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58126 / Fe, 10000 PPM, 500 ml	051523	05/15/2026	02/06/2025 / kareem	01/03/2024 / jaswal	M5811

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57115 / P, 10000 PPM, 125 ml	041723	04/17/2026	05/21/2024 / Jaswal	02/09/2024 / jaswal	M5815

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57116 / S, 10000 PPM, 125 ml	071123	07/11/2026	03/01/2024 / jaswal	02/09/2024 / jaswal	M5817

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58030 / Zinc, Zn, 500 ml, 1000 PPM	111623	11/16/2026	03/20/2024 / jaswal	02/09/2024 / jaswal	M5819

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CLPP-CAL-1 / CLP CAL SOLUTION #1, 125mL	T2-MEB714417	01/27/2027	04/19/2024 / jaswal	02/22/2024 / jaswal	M5875

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CGTI1-1 / TITANIUM 125mL 1000ug/mL	T2-TI719972	06/17/2027	06/18/2024 / Jaswal	02/22/2024 / Jaswal	M5942

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CGY10-1 / YTTRIUM 125mL 10,000ug/mL	V2-Y740548	02/20/2029	07/01/2024 / Jaswal	06/14/2024 / Jaswal	M5959

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57028 / Ni, 1000 PPM, 125 ml	041124	04/11/2027	07/02/2024 / Jaswal	06/11/2024 / Jaswal	M5961

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57034 / Se, 1000 PPM, 125 ml	060624	06/06/2027	07/02/2024 / Jaswal	06/14/2024 / Jaswal	M5962

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CGMO1-1 / MOLYBDENUM 125mL 1000ug/mL	T2-MO720876	07/17/2027	08/07/2024 / jaswal	02/22/2024 / Jaswal	M5976

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CGMO1-1 / MOLYBDENUM 125mL 1000ug/mL	T2-MO720876	07/17/2027	01/16/2025 / JANVI	02/22/2024 / Jaswal	M5977

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CGTI1-1 / TITANIUM 125mL 1000ug/mL	T2-TI719972	06/17/2027	08/07/2024 / jaswal	02/22/2024 / Jaswal	M5978

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CGIN10-5 / INDIUM 1 x 500 ml	U2-IN729349	02/21/2028	10/08/2024 / Jaswal	06/14/2024 / Jaswal	M5985

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	CLPP-SPK-5 / CLP Spike Standard 5	V2-MEB742037	03/12/2029	10/04/2024 / Jaswal	02/22/2024 / Jaswal	M5990

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57023 / V, 1000 PPM, 125 ml	062424	06/24/2027	09/28/2024 / jaswal	08/05/2024 / Jaswal	M6021

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57081 / Tl, 1000 PPM, 125 ml	0624724	06/27/2027	08/05/2024 / kareem	08/05/2024 / Jaswal	M6023

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57082 / Pb, 1000 PPM, 125 ml	061224	11/09/2026	08/05/2024 / Jaswal	08/05/2024 / Jaswal	M6025

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57048 / Cd, 1000 PPM, 125 ml	070124	07/01/2027	08/05/2024 / kareem	08/05/2024 / Jaswal	M6028

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57047 / Ag, 1000 PPM, 125 ml	122823	12/28/2026	08/05/2024 / kareem	08/05/2024 / Jaswal	M6030

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57056 / Ba, 1000 PPM, 125 ml	010924	01/09/2027	01/14/2025 / Jaswal	08/05/2024 / Jaswal	M6032

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Inorganic Ventures	Z9651Q / CHEM-CLP-4/.25L	V2-MEB746762	09/06/2029	01/23/2025 / kareem	09/19/2024 / kareem	M6077

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Seidler Chemical	BA-9530-33 / Hydrochloric Acid, Instra-Analyzed (cs/6x2.5L)	0000275677	05/13/2025	11/13/2024 / Eman	10/13/2024 / Eman	M6121

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
PCI Scientific Supply, Inc.	1403 / Hydrogen Peroxide, 30% 1 gal	820803	05/25/2025	11/26/2024 / Eman	11/22/2024 / Eman	M6125

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Seidler Chemical	BA-9598-34 / Nitric Acid, Instra-Analyzed (cs/4x2.5L)	24D1062002	06/03/2025	12/03/2024 / Janvi	11/12/2024 / Janvi	M6126

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58112 / Mg, 10000 PPM, 500 ml	112124	11/21/2027	01/13/2025 / kareem	01/13/2025 / kareem	M6127

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58025 / Mn, 1000 PPM, 500 ml	101124	10/11/2027	01/13/2025 / kareem	01/13/2025 / kareem	M6128

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58111 / Na, 10000 PPM, 500 ml	072424	07/24/2027	01/23/2025 / kareem	01/13/2025 / Jaswal	M6144

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

CHEMICAL RECEIPT LOG BOOK

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	58030 / Zinc, Zn, 500 ml, 1000 PPM	121724	12/17/2027	02/04/2025 /jaswal	01/13/2025 / Jaswal	M6145

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Absolute Standards, Inc.	57051 / Sb, 1000 PPM, 125 ml	071724	07/17/2027	01/31/2025 / kareem	10/18/2024 / kareem	M6146

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
EPA	ICV-1 / ICV (ICP/ICPMS) STOCK SOLN	ICV1-1014	02/08/2025	02/06/2025 / kareem	02/20/2020 / kareem	M6147

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
EPA	PART A / ICSA (ICP) STOCK SOLN	ICSA-1211	02/08/2025	02/06/2025 / kareem	04/20/2021 / kareem	M6148

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
EPA	PART B / ICSAB (ICP) STOCK SOLN	ICSB-0710	02/08/2025	02/06/2025 / kareem	04/20/2021 / kareem	M6149

Supplier	ItemCode / ItemName	Lot #	Expiration Date	Date Opened / Opened By	Received Date / Received By	Chemtech Lot #
Seidler Chemical	DIW / DI Water	Daily Lab-Certified	07/03/2029	07/03/2024 / Iwona	07/03/2024 / Iwona	W3112

INORGANIC VENTURES™

Refine your results. Redefine your industry.

Certificate of Analysis

R: 02/22/24 M5986 M5987, M5988, M5989-M5990

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 883.01 ACCREDITED Reference Material Producer Certificate 883.02

2.0 PRODUCT DESCRIPTION

Product Code:	Multi Analyte Custom Grade Solution
Catalog Number:	CLPP-SPK-5
Lot Number:	V2-MEB742037
Matrix:	5% (v/v) HNO3
Value / Analyte(s):	100 µg/mL ea: Antimony,
	50 µg/mL ea: Selenium, Cadmium, Thallium,
	40 µg/mL ea: Arsenic,
	20 µg/mL ea: Lead

3.0 CERTIFIED VALUES AND UNCERTAINTIES

ANALYTE	CERTIFIED VALUE	ANALYTE	CERTIFIED VALUE
Antimony, Sb	100.0 ± 0.7 µg/mL	Arsenic, As	40.00 ± 0.26 µg/mL
Cadmium, Cd	49.99 ± 0.22 µg/mL	Lead, Pb	19.99 ± 0.09 µg/mL
Selenium, Se	50.00 ± 0.23 µg/mL	Thallium, Tl	50.00 ± 0.22 µg/mL

Density: 1.025 g/mL (measured at 20 ± 4 °C)

Assay Information:

ANALYTE	METHOD	NIST SRM#	SRM LOT#
As	ICP Assay	3103a	100818
Cd	ICP Assay	3108	130116
Cd	EDTA	928	928
Cd	Calculated		See Sec. 4.2
Pb	ICP Assay	3128	101026
Pb	EDTA	928	928
Pb	Calculated		See Sec. 4.2
Sb	ICP Assay	3102a	140911
Se	ICP Assay	3149	100901
Se	Calculated		See Sec. 4.2
Tl	ICP Assay	3158	151215
Tl	Calculated		See Sec. 4.2

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{1/2}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{1/2}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{1/2}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

N/A

6.0 INTENDED USE

6.1 This standard is intended for the calibration of analytical instruments and validation of analytical methods as appropriate. This CRM may be used in connection with EPA Methods 6010, 6020 (all versions), Standard Methods 3120 B and USP <232> / ICH Q3D.

6.2 For products attaining traceability through Inorganic Ventures' Primary Certified Reference Materials (PCRM™) see the Limited License to Use PCRM™ in the Inorganic Ventures Terms and Conditions of Sale, https://www.inorganicventures.com/terms-and-conditions-sale. The Terms and Conditions contain information on the use of materials traceable to PCRM™ certified reference materials. This Limited License agreement is especially pertinent for laboratories accredited under ISO:17034.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

March 12, 2024

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- March 12, 2029

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Joseph Burns
Custom VS Manager



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M6032

R: 8/5/24

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com


CERTIFIED WEIGHT REPORT:

Part Number:	**57056**		**Lot #**		
Lot Number:	**010924**	**Solvent:**	24002546	Nitric Acid	
Description:	**Barium (Ba)**				
		2%	40.0 (mL)	Nitric Acid	
Expiration Date:	010927				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**1000**				
NIST Test Number:	6UTB	5E-05	Balance Uncertainty		
Weight shown below was diluted to (mL):	2000.02	0.058	Flask Uncertainty		

Giovanni Esposito

Formulated By:	Giovanni Esposito	010924
Reviewed By:	Pedro L. Rentas	010924

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Barium nitrate (Ba)	IN023	BAD022019A1	1000	99.999	0.10	52.3	3.82417	3.82441	**1000.1**	**2.0**	10022-31-8	0.5 mg/m3	orl-rat 355 mg/kg	3104a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	T	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R 8/5/24

M6028

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com


CERTIFIED WEIGHT REPORT:

Part Number:	**57048**		**Lot #**		
Lot Number:	**070124**	**Solvent:**	24002546	Nitric Acid	
Description:	**Cadmium (Cd)**	2%	40.0 (mL)	Nitric Acid	
Expiration Date:	070127				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**1000**				
NIST Test Number:	6UTB	5E-05	Balance Uncertainty		
Weight shown below was diluted to (mL):	2000.07	0.100	Flask Uncertainty		

Aleah O'Brady

Formulated By:	Aleah O'Brady	070124
Reviewed By:	Pedro L. Rentas	070124

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Cadmium nitrate tetrahydrate (Cd)	IN024	CDM092021A1	1000	99.999	0.10	36.5	5.4797	5.4804	**1000.1**	**2.0**	10022-68-1	0.01 mg/m3	orl-rat 60.2mg/kg	3108



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	T	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

INORGANIC VENTURES™
Refine your results. Redefine your industry.

Certificate of Analysis

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 883.01
ACCREDITED Reference Material Producer Certificate 883.02

2.0 PRODUCT DESCRIPTION

Product Code:	Multi Analyte Custom Grade Solution
Catalog Number:	CLPP-CAL-1
Lot Number:	T2-MEB714417
Matrix:	5% (v/v) HNO3
Value / Analyte(s):	5 000 µg/mL ea: Calcium, Potassium, Magnesium, Sodium, 2 000 µg/mL ea: Aluminum, Barium, 1 000 µg/mL ea: Iron, 500 µg/mL ea: Nickel, Vanadium, Zinc, Cobalt, Manganese, 250 µg/mL ea: Silver, Copper, 200 µg/mL ea: Chromium, 50 µg/mL ea: Beryllium

3.0 CERTIFIED VALUES AND UNCERTAINTIES

ANALYTE	CERTIFIED VALUE	ANALYTE	CERTIFIED VALUE
Aluminum, Al	**2 000 ± 7 µg/mL**	**Barium, Ba**	**2 000 ± 9 µg/mL**
Beryllium, Be	**50.00 ± 0.26 µg/mL**	**Calcium, Ca**	**5 000 ± 22 µg/mL**
Chromium, Cr	**200.0 ± 1.0 µg/mL**	**Cobalt, Co**	**500.0 ± 2.4 µg/mL**
Copper, Cu	**250.0 ± 1.0 µg/mL**	**Iron, Fe**	**1 000 ± 4 µg/mL**
Magnesium, Mg	**5 000 ± 20 µg/mL**	**Manganese, Mn**	**500.0 ± 2.0 µg/mL**
Nickel, Ni	**500.0 ± 2.2 µg/mL**	**Potassium, K**	**5 000 ± 19 µg/mL**
Silver, Ag	**250.0 ± 1.1 µg/mL**	**Sodium, Na**	**5 000 ± 18 µg/mL**
Vanadium, V	**499.7 ± 2.2 µg/mL**	**Zinc, Zn**	**500.0 ± 2.2 µg/mL**

Density: 1.118 g/mL (measured at 20 ± 4 ºC)

Assay Information:

ANALYTE	METHOD	NIST SRM#	SRM LOT#
Ag	ICP Assay	3151	160729
Ag	Volhard	999c	999c
Al	ICP Assay	3101a	140903
Al	EDTA	928	928
Ba	ICP Assay	3104a	140909
Ba	Gravimetric		See Sec. 4.2
Be	ICP Assay	3105a	090514
Be	Calculated		See Sec. 4.2
Ca	ICP Assay	3109a	130213
Ca	EDTA	928	928
Co	ICP Assay	3113	190630
Co	EDTA	928	928
Cr	ICP Assay	3112a	170630
Cr	Calculated		See Sec. 4.2
Cu	ICP Assay	3114	121207
Cu	EDTA	928	928
Fe	ICP Assay	3126a	140812
Fe	EDTA	928	928
K	ICP Assay	3141a	140813
K	Gravimetric		See Sec. 4.2
Mg	ICP Assay	3131a	140110
Mg	EDTA	928	928
Mn	ICP Assay	3132	050429
Mn	EDTA	928	928
Na	ICP Assay	3152a	120715
Na	Gravimetric		See Sec. 4.2
Ni	ICP Assay	3136	120619
Ni	EDTA	928	928
V	IC Assay	3165	160906
V	EDTA	928	928
Zn	ICP Assay	3168a	120629
Zn	EDTA	928	928

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

N/A

6.0 INTENDED USE

- For the calibration of analytical instruments and validation of analytical methods as appropriate.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

Note: This solution contains Silver (Ag), please refer to our Sample Preparation Guide for more information.

https://www.inorganicventures.com/sample-preparation-guide/samples-containing-silver

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

January 27, 2022

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- **January 27, 2027**

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity


- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Thomas Kozikowski
Manager, Quality Control



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



INORGANIC VENTURES™
Refine your results. Redefine your industry.

Certificate of Analysis

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 883.01
ACCREDITED Reference Material Producer Certificate 883.02

2.0 PRODUCT DESCRIPTION

Product Code:	Multi Analyte Custom Grade Solution
Catalog Number:	CLPP-CAL-3
Lot Number:	T2-MEB714159
Matrix:	7% (v/v) HNO3
Value / Analyte(s):	1 000 µg/mL ea: Arsenic, Lead, Selenium, Thallium, 500 µg/mL ea: Cadmium

3.0 CERTIFIED VALUES AND UNCERTAINTIES

ANALYTE	CERTIFIED VALUE	ANALYTE	CERTIFIED VALUE
Arsenic, As	**1 000 ± 8 µg/mL**	**Cadmium, Cd**	**500.0 ± 2.1 µg/mL**
Lead, Pb	**1 000 ± 5 µg/mL**	**Selenium, Se**	**1 000 ± 8 µg/mL**
Thallium, Tl	**1 000 ± 7 µg/mL**		

Density: 1.043 g/mL (measured at 20 ± 4 ºC)

Assay Information:

ANALYTE	METHOD	NIST SRM#	SRM LOT#
As	ICP Assay	3103a	100818
Cd	ICP Assay	3108	130116
Cd	EDTA	928	928
Pb	ICP Assay	3128	101026
Pb	EDTA	928	928
Se	ICP Assay	3149	100901
Tl	ICP Assay	3158	151215

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

N/A

6.0 INTENDED USE

- For the calibration of analytical instruments and validation of analytical methods as appropriate.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

January 13, 2022

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- **January 13, 2027**

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity


- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Thomas Kozikowski
Manager, Quality Control



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R : 01/03/24. M5810, M5811

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 58126
Lot Number: 051523
Description: Iron (Fe)


Expiration Date: 051526
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 5000.1 ± 0.12 Flask Uncertainty

		Lot #	
Solvent:	21110221	Nitric Acid	
	5.0%	250.0 (mL)	Nitric Acid
	5E-05	Balance Uncertainty	

Giovanni Esposito

Formulated By:	Giovanni Esposito	051523
Reviewed By:	Pedro L. Rentas	051523

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Iron (Fe)	IN346	2302010-500	10000	99.995	0.10	100.0	50.0034	50.0111	**10001.5**	**20.0**	7439-89-6	5 mg/m3	orl-rat 7500mg/kg	3126a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.10	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.10	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.05	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.10	Ge	<0.10	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.10
B	<0.02	Cu	<0.10	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R: 8/15/24 M6025

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 57182
Lot Number: 110923
Description: Lead (Pb)

Expiration Date: 110926
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB


Weight shown below was diluted to (mL): 2000.02 0.058 Flask Uncertainty

		Lot #	
Solvent:	24002546	Nitric Acid	
2%	40.0 (mL)	Nitric Acid	

5E-05 Balance Uncertainty

Formulated By:	Lawence Barry	110923
Reviewed By:	Pedro L. Rentas	110923

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Lead(II) nitrate (Pb)	IN029	PBD122016A1	10000	99.999	0.10	62.5	32.0006	32.0040	**10001.1**	**20.0**	10099-74-8	0.05 mg/m3	intrvns-rat 93 mg/kg	3128



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	T	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

		Lot #	Solvent:	
Part Number:	**57014**	19410105	Nitric Acid	
Lot Number:	**030921**			
Description:	**Silicon (Si)**			
		2.0%	60.0	Nitric Acid
Expiration Date:	030924		(mL)	
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Volume shown below was diluted to (mL):	3000.41	0.058	Flask Uncertainty	

Formulated By:	Lawrence Barry 030921
Reviewed By:	Pedro L. Rentas 030921

	Part	Lot	Dilution	Initial	Uncertainty	Nominal	Initial	**Final**	Expanded Uncertainty	**SDS Information** (Solvent Safety Info. On Attached pg.)			NIST
Compound	Number	Number	Factor	Vol. (mL)	Pipette (mL)	Conc. (µg/mL)	Conc. (µg/mL)	**Conc. (µg/mL)**	+/- (µg/mL)	CAS#	OSHA PEL (TWA)	LD50	SRM
1. Ammonium hexafluorosilicate (Si)	58114	070120	0.1000	300.0	0.084	1000	10000.0	**1000.0**	**2.1**	16919-19-0	2.50 mg/m3	orl-rat 70 mg/kg	NA



Instrumental Analysis by Inductively Coupled Plasma Mass Spectroscopy (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	T	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
"An ISO 9001:2015 Certified Program"

Instructions for QATS Reference Material: *ICP-AES ICS*

QATS LABORATORY INORGANIC REFERENCE MATERIAL INTERFERENCE CHECK SAMPLE SET FOR ICP-AES (ICSA WITH ICSB)

NOTE: These instructions are for advisory purposes only. If any apparent conflict exists between these instructions and the analytical protocol or your contract, disregard these instructions.

APPLICATION: For use with the CLP SFAM01.0 SOW and revisions.

CAUTION: Read instructions carefully before opening bottle(s) and proceeding with the analyses.

Contains Heavy Metals
HAZARDOUS MATERIAL

Safety Data Sheets
Available Upon Request

(A) *SAMPLE DESCRIPTION*

Enclosed is a set of one (1) or more bottles of Aqueous Reference Material, each composed of metals at various concentrations and prepared with nitrate salts and oxy-acids of the respective elements in a 5% nitric acid matrix. **For the reference material source in reporting ICSA and ICSAB mixture use "USEPA". For the reference material lot number for the ICSA use "ICSA-1211" and for the ICSAB mixture use "ICSA-1211+ICSB-0710".**

CAUTION: The bottle(s) should be protected from light during storage to ensure the stability of silver which is contained in the ICSB solution. The bottle(s) should be stored at room temperature. **Do not allow the solution(s) to freeze.**

(B) *BREAKAGE OR MISSING ITEMS*

Check the contents of the shipment carefully for any broken, leaking, or missing items. Check that the seal is intact on each bottle. Refer to the enclosed chain of custody record. Report any problems to Mr. Keith Strout, APTIM Federal Services, LLC, at (702) 895-8722. If requested, return the chain-of-custody record with appropriate annotations and signatures to the address provided below.

QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
APTIM Federal Services, LLC
2700 Chandler Avenue - Building C
Las Vegas, NV 89120

(C) *ANALYSIS OF SAMPLES*

The interference check sample set is to be used to verify inter-element and background correction factors of inductively-coupled plasma (ICP) spectrometers. This reference material set consists of two (2) concentrated solutions. The ICSA solution contains the four (4) interferent elements: Al, Ca, Fe, and Mg. The ICSB solution contains the analytes: Ag, As, Sb, Ba, Be,

The Quality Assurance Technical Support (QATS) contract is operated by APTIM Federal Services, LLC.

Cd, Co, Cr, Cu, Mn, Ni, Pb, Tl, Se, V, and Zn. This instruction sheet provides the nominal values for ICP-AES Part A and Part B target analytes when diluted as directed.

Using Class "A" glassware, preparation and analysis must be performed according to the following instructions:

ICSA-1211, Interferents: Pipet 10 mL of the ICSA solution into a 100 mL volumetric flask and dilute to volume with 2% v/v HNO_3. Analyze this ICSA solution by ICP-AES.

ICSB-0710, Analytes, mixed with ICSA-1211, Interferents: Pipet 10 mL of the ICSA solution and 10 mL of the ICSB solution into a 100 mL volumetric flask and dilute to volume with 2% v/v HNO_3. Analyze this ICSAB solution by ICP-AES.

(D) *"CERTIFIED VALUE" CONCENTRATIONS OF QATS ICP-AES ICS SOLUTION(S)*

The "Certified Value" concentrations of the elements, listed in Table 1 below, were derived from statistically pooled analysis results from the following sources, if available: QATS Laboratory, CLP laboratories, Quarterly Blind (QB)/Proficiency Testing (PT) events, CLP pre-award events, and external referee laboratories.

Table 1. "CERTIFIED VALUES" FOR INTERFERENCE CHECK SAMPLE ICP-AES ICSA-1211, AND ICSA-1211 MIXED WITH ICSB-0710

Element	CRQL	Part A (µg/L)	Low Limit (µg/L)	High Limit (µg/L)	Part A +Part B (µg/L)	Low Limit (µg/L)	High Limit (µg/L)
Al	200	255000	216000	294000	247000	209000	285000
Sb	60	(0.0)	-60.0	60.0	618	525	711
As	10	(0.0)	-10.0	10.0	104	88.4	120
Ba	200	(6.0)	-194	206	(537)	337	737
Be	5.0	(0.0)	-5.0	5.0	495	420	570
Cd	5.0	(1.0)	-4.0	6.0	972	826	1120
Ca	5000	245000	208000	282000	235000	199000	271000
Cr	10	(52.0)	42.0	62.0	542	460	624
Co	50	(0.0)	-50.0	50.0	476	404	548
Cu	25	(2.0)	-23.0	27.0	511	434	588
Fe	100	101000	85600	116500	99300	84400	114500
Pb	10	(0.0)	-10.0	10.0	(49.0)	39.0	59.0
Mg	5000	255000	216000	294000	248000	210000	286000
Mn	15	(7.0)	-8.0	22.0	507	430	584
Ni	40	(2.0)	-38.0	42.0	954	810	1100
Se	35	(0.0)	-35.0	35.0	(46.0)	11.0	81.0
Ag	10	(0.0)	-10.0	10.0	201	170	232
Tl	25	(0.0)	-25.0	25.0	(108)	83.0	133
V	50	(0.0)	-50.0	50.0	491	417	565
Zn	60	(0.0)	-60.0	60.0	952	809	1095

ICSA M5126 M5127 M5128 M5129 M5130

ICSB M5219 M5220 M5221 M5222 M5223

The acceptance ranges for all analytes in parentheses in the above table were determined using the listed certified value ± 1 times the associated CLP SOW CRQL. The acceptance ranges for all other analytes were determined using the certified value ± 15 percent of the listed certified value.

INORGANIC VENTURES™
Refine your results. Redefine your industry.

Certificate of Analysis

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED
Testing Laboratory
Certificate 883.01

ACCREDITED
Reference Material Producer
Certificate 883.02

2.0 PRODUCT DESCRIPTION

Product Code:	Multi Analyte Custom Grade Solution
Catalog Number:	CHEM-QC-4
Lot Number:	S2-MEB711674
Matrix:	3% (v/v) HNO3 3% (v/v) HF
Value / Analyte(s):	1 000 µg/mL ea: Boron, Molybdenum, Silicon, Tin, Titanium

Second Source: Whenever possible, this solution was manufactured from a second set of concentrates in our manufacturing facility.

3.0 CERTIFIED VALUES AND UNCERTAINTIES

ANALYTE	CERTIFIED VALUE	ANALYTE	CERTIFIED VALUE
Boron, B	**1 000 ± 7 µg/mL**	**Molybdenum, Mo**	**1 000 ± 5 µg/mL**
Silicon, Si	**1 000 ± 7 µg/mL**	**Tin, Sn**	**1 000 ± 5 µg/mL**
Titanium, Ti	**1 001 ± 6 µg/mL**		

Density: 1.032 g/mL (measured at 20 ± 4 ºC)

Assay Information:

ANALYTE	METHOD	NIST SRM#	SRM LOT#
B	ICP Assay	3107	110830
Mo	ICP Assay	3134	130418
Si	ICP Assay	3150	130912
Sn	ICP Assay	3161a	140917
Ti	ICP Assay	3162a	130925

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

N/A

6.0 INTENDED USE

- For the calibration of analytical instruments and validation of analytical methods as appropriate.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

HF Note: This standard should not be prepared or stored in glass.

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

November 02, 2021

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- **November 02, 2026**

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Michael Booth
Director, Quality Control



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
"An ISO 9001:2015 Certified Program"

Instructions for QATS Reference Material: *ICP-AES ICS*

QATS LABORATORY INORGANIC REFERENCE MATERIAL INTERFERENCE CHECK SAMPLE SET FOR ICP-AES (ICSA WITH ICSB)

NOTE: These instructions are for advisory purposes only. If any apparent conflict exists between these instructions and the analytical protocol or your contract, disregard these instructions.

APPLICATION: For use with the CLP SFAM01.0 SOW and revisions.

CAUTION: Read instructions carefully before opening bottle(s) and proceeding with the analyses.

Contains Heavy Metals
HAZARDOUS MATERIAL

Safety Data Sheets
Available Upon Request

(A) *SAMPLE DESCRIPTION*

Enclosed is a set of one (1) or more bottles of Aqueous Reference Material, each composed of metals at various concentrations and prepared with nitrate salts and oxy-acids of the respective elements in a 5% nitric acid matrix. **For the reference material source in reporting ICSA and ICSAB mixture use "USEPA". For the reference material lot number for the ICSA use "ICSA-1211" and for the ICSAB mixture use "ICSA-1211+ICSB-0710".**

CAUTION: The bottle(s) should be protected from light during storage to ensure the stability of silver which is contained in the ICSB solution. The bottle(s) should be stored at room temperature. **Do not allow the solution(s) to freeze.**

(B) *BREAKAGE OR MISSING ITEMS*

Check the contents of the shipment carefully for any broken, leaking, or missing items. Check that the seal is intact on each bottle. Refer to the enclosed chain of custody record. Report any problems to Mr. Keith Strout, APTIM Federal Services, LLC, at (702) 895-8722. If requested, return the chain-of-custody record with appropriate annotations and signatures to the address provided below.

QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
APTIM Federal Services, LLC
2700 Chandler Avenue - Building C
Las Vegas, NV 89120

(C) *ANALYSIS OF SAMPLES*

The interference check sample set is to be used to verify inter-element and background correction factors of inductively-coupled plasma (ICP) spectrometers. This reference material set consists of two (2) concentrated solutions. The ICSA solution contains the four (4) interferent elements: Al, Ca, Fe, and Mg. The ICSB solution contains the analytes: Ag, As, Sb, Ba, Be,

The Quality Assurance Technical Support (QATS) contract is operated by APTIM Federal Services, LLC.

Cd, Co, Cr, Cu, Mn, Ni, Pb, Tl, Se, V, and Zn. This instruction sheet provides the nominal values for ICP-AES Part A and Part B target analytes when diluted as directed.

Using Class "A" glassware, preparation and analysis must be performed according to the following instructions:

ICSA-1211, Interferents: Pipet 10 mL of the ICSA solution into a 100 mL volumetric flask and dilute to volume with 2% v/v HNO_3. Analyze this ICSA solution by ICP-AES.

ICSB-0710, Analytes, mixed with ICSA-1211, Interferents: Pipet 10 mL of the ICSA solution and 10 mL of the ICSB solution into a 100 mL volumetric flask and dilute to volume with 2% v/v HNO_3. Analyze this ICSAB solution by ICP-AES.

(D) *"CERTIFIED VALUE" CONCENTRATIONS OF QATS ICP-AES ICS SOLUTION(S)*

The "Certified Value" concentrations of the elements, listed in Table 1 below, were derived from statistically pooled analysis results from the following sources, if available: QATS Laboratory, CLP laboratories, Quarterly Blind (QB)/Proficiency Testing (PT) events, CLP pre-award events, and external referee laboratories.

Table 1. "CERTIFIED VALUES" FOR INTERFERENCE CHECK SAMPLE ICP-AES ICSA-1211, AND ICSA-1211 MIXED WITH ICSB-0710

Element	CRQL	Part A (µg/L)	Low Limit (µg/L)	High Limit (µg/L)	Part A +Part B (µg/L)	Low Limit (µg/L)	High Limit (µg/L)
Al	200	255000	216000	294000	247000	209000	285000
Sb	60	(0.0)	-60.0	60.0	618	525	711
As	10	(0.0)	-10.0	10.0	104	88.4	120
Ba	200	(6.0)	-194	206	(537)	337	737
Be	5.0	(0.0)	-5.0	5.0	495	420	570
Cd	5.0	(1.0)	-4.0	6.0	972	826	1120
Ca	5000	245000	208000	282000	235000	199000	271000
Cr	10	(52.0)	42.0	62.0	542	460	624
Co	50	(0.0)	-50.0	50.0	476	404	548
Cu	25	(2.0)	-23.0	27.0	511	434	588
Fe	100	101000	85600	116500	99300	84400	114500
Pb	10	(0.0)	-10.0	10.0	(49.0)	39.0	59.0
Mg	5000	255000	216000	294000	248000	210000	286000
Mn	15	(7.0)	-8.0	22.0	507	430	584
Ni	40	(2.0)	-38.0	42.0	954	810	1100
Se	35	(0.0)	-35.0	35.0	(46.0)	11.0	81.0
Ag	10	(0.0)	-10.0	10.0	201	170	232
Tl	25	(0.0)	-25.0	25.0	(108)	83.0	133
V	50	(0.0)	-50.0	50.0	491	417	565
Zn	60	(0.0)	-60.0	60.0	952	809	1095

ICSA M5126 M5127 M5128 M5129 M5130

ICSB M5219 M5220 M5221 M5222 M5223

The acceptance ranges for all analytes in parentheses in the above table were determined using the listed certified value ± 1 times the associated CLP SOW CRQL. The acceptance ranges for all other analytes were determined using the certified value ± 15 percent of the listed certified value.

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

M5289 R: 07/12/22 (BH)

Certified Reference Material CRM


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number:	**58113**			**Lot #**	
Lot Number:	**070622**		**Solvent:**	20370011	Nitric Acid
Description:	**Aluminum (Al)**				
			2%	40.0 (mL)	Nitric Acid
Expiration Date:	070625				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**10000**				
NIST Test Number:	6UTB	5E-05	Balance Uncertainty		
Weight shown below was diluted to (mL):	2000.02	0.058	Flask Uncertainty		

Formulated By:	Lawrence Barry	070622
Reviewed By:	Pedro L. Rentas	070622

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	**Actual Conc. (µg/mL)**	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Aluminum nitrate nonahydrate (Al)	IN022	ALD012021A1	10000	99.999	0.10	7.10	281.6956	281.6977	**10000.1**	**20.0**	7784-27-2	2 mg/m3	orl-rat 3671 mg/kg	3101a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectroscopy (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	T	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

QATS LABORATORY INORGANIC REFERENCE MATERIAL INITIAL CALIBRATION VERIFICATION SOLUTIONS (ICV1, ICV5, AND ICV6)

NOTE: These instructions are for advisory purposes only. If any apparent conflict exists between these instructions and the analytical protocol or your contract, disregard these instructions.

APPLICATION: For use with the CLP SFAM01.0 SOW and revisions.

CAUTION: Read instructions carefully before opening bottle(s) and proceeding with the analyses.

Contains Metals in Dilute Acidic or Cyanide in Basic Aqueous Solutions
HAZARDOUS MATERIAL

Safety Data Sheets Available Upon Request

M5291
M5292
M5293
M5294
M5295

(A) *SAMPLE DESCRIPTION*

Enclosed is a set of one (1) or more Aqueous Inorganic Reference Materials containing various analyte concentrations. ICV1 and ICV5 are in a matrix of dilute nitric acid. ICV6 is in a matrix of dilute basic solution. **For the reference material source in reporting ICVs use "USEPA". For the reference material lot number for the ICV1, ICV5, and ICV6 solutions use "ICV1-1014", "ICV5-0415", and "ICV6-0400", respectively.**

(B) *BREAKAGE OR MISSING ITEMS*

Check the contents of the shipment carefully for any broken, leaking, or missing items. Check that the seal is intact on each bottle. Refer to the enclosed chain of custody record. Report any problems to Mr. Keith Strout, APTIM Federal Services, LLC, at (702) 895-8722. If requested, return the chain-of-custody record with appropriate annotations and signatures to the address provided below.

QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
APTIM Federal Services, LLC
2700 Chandler Avenue - Building C
Las Vegas, NV 89120

(C) *ANALYSIS OF SAMPLES*

The Initial Calibration Verification Solutions (ICVs) are to be used to evaluate the accuracy of the initial calibrations of ICP, AA, and Cyanide colorimetric instruments, and are to be used with the CLP SOWs and revisions. The values for each element in the ICVs are listed below in µg/L (ppb) for the resulting solution(s) after the dilution of the concentrate(s) according to the following instructions. Use Class 'A' glassware to prepare the solution(s).

ICV1-1014 For ICP-AES analysis, use a 10-fold dilution by pipetting 10 mL of the ICV1 concentrate into a 100 mL volumetric flask and dilute to volume with 2% (v/v) nitric acid.

The Quality Assurance Technical Support (QATS) contract is operated by APTIM Federal Services, LLC.

ICV1-1014 For ICP-MS analysis, use a 50-fold dilution by pipetting 2 mL of the ICV1 concentrate into a 100 mL volumetric flask and dilute to volume with 1% (v/v) nitric acid.

ICV5-0415 For the cold vapor analysis of mercury by AA, use a 100-fold dilution by pipetting 1 mL of the ICV5 concentrate into a 100 mL volumetric flask and dilute to volume with 2% (v/v) nitric acid. The ICV5 concentrate is prepared in 0.05% (w/v) $K_2Cr_2O_7$ and 5% (v/v) nitric acid.

ICV6-0400 For the analysis of cyanide, use a 100-fold dilution by pipetting 1 mL of the ICV6 concentrate into a 100 mL volumetric flask and dilute to volume with Type II water. Distill this solution along with the samples before analysis. The cyanide concentrate is prepared from $K_3Fe(CN)_6$, Type II water, and 0.1 % sodium hydroxide, and will decompose rapidly if exposed to light.

NOTE: USE TYPE II WATER AND HIGH-PURITY ACIDS FOR ALL DILUTIONS.

(D) *CERTIFIED CONCENTRATIONS OF QATS ICV1, ICV5, AND ICV6 SOLUTIONS*

ICV1-1014		
Element	**Concentration (µg/L) (after 10-fold dilution)**	**Concentration (µg/L) (after 50-fold dilution)**
Al	2500	500
Sb	1000	200
As	1000	200
Ba	520	100
Be	510	100
Cd	510	100
Ca	10000	2000
Cr	520	100
Co	520	100
Cu	510	100
Fe	10000	2000
Pb	1000	200
Mg	6000	1200
Mn	520	100
Ni	530	110
K	9900	2000
Se	1000	200
Ag	250	50
Na	10000	2000
Tl	1000	210
V	500	100
Zn	1000	200

ICV5-0415		ICV6-0400	
Element	**Concentration (µg/L) (after 100-fold dilution)**	**Analyte**	**Concentration (µg/L) (after 100-fold dilution)**
Hg	4.0	**CN^-**	99

SJ 6/15/22

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 58126
Lot Number: 020422
Description: Iron (Fe)

M5298

Expiration Date: 020425
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 3000.41


	Lot #		
Solvent:	20370011	Nitric Acid	
5.0%	150.0 (mL)	Nitric Acid	

5E-05 Balance Uncertainty
0.058 Flask Uncertainty

Giovanni Esposito
Formulated By: Giovanni Esposito 020422

Pedro Rentas
Reviewed By: Pedro L. Rentas 020422

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Iron(III) nitrate nonahydrate (Fe)	IN346	221035107	10000	99.999	0.10	100.0	30.0044	30.0090	**10001.5**	**20.0**	7782-61-8	5 mg/m3	orl-rat 7500mg/kg	3126a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.10	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.10	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.5	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.10	Ge	<0.10	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.10	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M5429 R1 01/26/23 BH

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 57103
Lot Number: 070622
Description: Lithium (Li)


Expiration Date: 070625
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 1000.12

	Lot #		
Solvent:	20510011	Nitric Acid	
2%	20.0 (mL)	Nitric Acid	

5E-05 Balance Uncertainty
0.058 Flask Uncertainty

Formulated By:	Lawrence Barry	070622
Reviewed By:	Pedro L. Rentas	070622

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Lithium nitrate (Li)	IN019	LIZ042018A1	10000	99.999	0.10	10.0	100.0134	100.0173	**10000.4**	**20.0**	7790-69-4	5 mg/m3	orl-rat 1426 mg/kg	NA



Instrumental Analysis by Inductively Coupled Plasma Mass Spectroscopy (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	T	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

IN 5466
R: 03/01/23 BH

Certified Reference Material CRM

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:


Part Number: 57058
Lot Number: 061322
Description: Cerium (Ce)

Expiration Date: 061325
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 1000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 1000.12 5E-05 Balance Uncertainty 0.058 Flask Uncertainty

	Lot #	
Solvent:	20510011	Nitric Acid
2%	20.0 (mL)	Nitric Acid

Formulated By:	Lawrence Barry	061322
Reviewed By:	Pedro L. Rentas	061322

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Cerium nitrate hexahydrate (Ce)	IN146	Z512CEB1	1000	99.999	0.10	32.8	3.04919	3.04923	1000.0	2.0	10294-41-4	NA	NA	NA



Instrumental Analysis by Inductively Coupled Plasma Mass Spectroscopy (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	T	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M5467 R: 03/01/23 (LA)

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 57058
Lot Number: 020623
Description: Cerium (Ce)

Expiration Date: 020626
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 1000
NIST Test Number: 6UTB


Weight shown below was diluted to (mL): 1000.12 0.058 Flask Uncertainty

		Lot #	
Solvent:	21110221	Nitric Acid	
2%	20.0 (mL)	Nitric Acid	

5E-05 Balance Uncertainty

Formulated By:	Lawrence Barry	020623
Reviewed By:	Pedro L. Rentas	020623

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Cerium nitrate hexahydrate (Ce)	IN146	Z512CEB1	1000	99.999	0.10	32.8	3.04919	3.04921	**1000.0**	**2.0**	10294-41-4	NA	NA	NA



Instrumental Analysis by Inductively Coupled Plasma Mass Spectroscopy (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	T	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M5496 R 7/20/23

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com


CERTIFIED WEIGHT REPORT:

Part Number:	**58113**		**Lot #**		
Lot Number:	**011623**	**Solvent:**	20510011	Nitric Acid	
Description:	**Aluminum (Al)**	2%	40.0 (mL)	Nitric Acid	
Expiration Date:	011626				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**10000**				
NIST Test Number:	6UTB	5E-05	Balance Uncertainty		
Weight shown below was diluted to (mL):	2000.02	0.058	Flask Uncertainty		

Giovanni Esposito

Formulated By:	Giovanni Esposito	011623
Reviewed By:	Pedro L. Rentas	011623

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Aluminum nitrate nonahydrate (Al)	IN022	ALM112021A1	10000	99.999	0.10	7.30	273.9779	274.0078	**10001.1**	**20.0**	7784-27-2	2 mg/m3	orl-rat 3671 mg/kg	3101a



Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

IN5497 - IN5498 R: 03/17/23 BH

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 58120
Lot Number: 031523
Description: Calcium (Ca)


Expiration Date: 031526
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 3000.41 ± 0.058 Flask Uncertainty

		Lot #	
Solvent:	21110221	Nitric Acid	
2%	60.0 (mL)	Nitric Acid	
	5E-05	Balance Uncertainty	

Giovanni Esposito

Formulated By:	Giovanni Esposito	031523
Reviewed By:	Pedro L. Rentas	031523

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Calcium carbonate (Ca)	IN014	CAD072022A1	10000	99.999	0.10	39.9	75.1990	75.2093	**10001.4**	**20.0**	471-34-1	5 mg/m3	orl-rat >2000mg/kg	3109a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	T	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

IN5497 - IN5498 R: 03/17/23 BH

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 58120
Lot Number: 031523
Description: Calcium (Ca)


Expiration Date: 031526
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 3000.41 ± 0.058 Flask Uncertainty

		Lot #	
Solvent:	21110221	Nitric Acid	
2%	60.0 (mL)	Nitric Acid	
	5E-05	Balance Uncertainty	

Giovanni Esposito

Formulated By:	Giovanni Esposito	031523
Reviewed By:	Pedro L. Rentas	031523

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Calcium carbonate (Ca)	IN014	CAD072022A1	10000	99.999	0.10	39.9	75.1990	75.2093	**10001.4**	**20.0**	471-34-1	5 mg/m3	orl-rat >2000mg/kg	3109a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	T	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

MS513 R:03/17/23 BE

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 57182
Lot Number: 061522
Description: Lead (Pb)

Expiration Date: 061525
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 2000.02


	Lot #		
Solvent:	20510011	Nitric Acid	
2%	40.0 (mL)	Nitric Acid	

5E-05 Balance Uncertainty
0.058 Flask Uncertainty

Giovanni Esposito

Formulated By:	Giovanni Esposito	061522
Reviewed By:	Pedro L. Rentas	061522

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Lead(II) nitrate (Pb)	IN029	PBD122016A1	10000	99.999	0.10	62.5	32.0006	32.0041	**10001.1**	**20.0**	10099-74-8	0.05 mg/m3	Intrvns-rat 93 mg/kg	3128



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	T	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M519. M520 (BH) R:03/17/23

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 58119
Lot Number: 120822
Description: Potassium (K)

Expiration Date: 120825
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 3000.4


Lot #		
Solvent: 20510011		Nitric Acid
2%	60.0 (mL)	Nitric Acid

5E-05 Balance Uncertainty
0.06 Flask Uncertainty

Giovanni Esposito

Formulated By:	Giovanni Esposito	120822
Reviewed By:	Pedro L. Rentas	120822

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Potassium nitrate (K)	IN034	KD022021A1	10000	99.999	0.10	37.6	79.7990	79.8075	**10001.1**	**20.0**	7757-79-1	5 mg/m3	orl-rat 3015 mg/kg	3141a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	T	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

INORGANIC VENTURES
Refine your results. Redefine your industry.

Certificate of Analysis

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

2.0 PRODUCT DESCRIPTION

Product Code:	Multi Analyte Custom Grade Solution
Catalog Number:	CLPP-SPK-1
Lot Number:	T2-MEB721963
Matrix:	7% (v/v) HNO3
Value / Analyte(s):	2 000 µg/mL ea: Aluminum, Barium,
	1 000 µg/mL ea: Iron,
	500 µg/mL ea: Manganese, Nickel, Vanadium, Zinc, Cobalt,
	250 µg/mL ea: Copper,
	200 µg/mL ea: Chromium,
	50 µg/mL ea: Beryllium, Silver

3.0 CERTIFIED VALUES AND UNCERTAINTIES

ANALYTE	CERTIFIED VALUE	ANALYTE	CERTIFIED VALUE
Aluminum, Al	2 000 ± 7 µg/mL	Barium, Ba	2 000 ± 9 µg/mL
Beryllium, Be	50.00 ± 0.26 µg/mL	Chromium, Cr	200.0 ± 1.1 µg/mL
Cobalt, Co	500.0 ± 2.4 µg/mL	Copper, Cu	250.0 ± 1.0 µg/mL
Iron, Fe	1 000 ± 4 µg/mL	Manganese, Mn	500.0 ± 2.0 µg/mL
Nickel, Ni	500.0 ± 2.2 µg/mL	Silver, Ag	50.00 ± 0.22 µg/mL
Vanadium, V	500.0 ± 2.2 µg/mL	Zinc, Zn	500.0 ± 2.2 µg/mL

Density: 1.070 g/mL (measured at 20 ± 4 °C)

Assay Information:

ANALYTE	METHOD	NIST SRM#	SRM LOT#
Ag	ICP Assay	3151	160729
Ag	Volhard	999c	999c
Ag	Calculated		See Sec. 4.2
Al	ICP Assay	3101a	140903
Al	EDTA	928	928
Ba	ICP Assay	3104a	140909
Ba	Gravimetric		See Sec. 4.2
Be	ICP Assay	3105a	090514
Be	Calculated		See Sec. 4.2
Co	ICP Assay	3113	190630
Co	EDTA	928	928
Cr	ICP Assay	3112a	170630
Cu	ICP Assay	3114	121207
Cu	EDTA	928	928
Fe	ICP Assay	3126a	140812
Fe	EDTA	928	928
Mn	ICP Assay	3132	050429
Mn	EDTA	928	928
Ni	ICP Assay	3136	120619
Ni	EDTA	928	928
V	IC Assay	3165	160906
V	EDTA	928	928
Zn	ICP Assay	3168a	120629
Zn	EDTA	928	928

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method I with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{1/2}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{1/2}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{1/2}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

N/A

6.0 INTENDED USE

- For the calibration of analytical instruments and validation of analytical methods as appropriate.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

Note: This solution contains Silver (Ag), please refer to our Sample Preparation Guide for more information.

https://www.inorganicventures.com/sample-preparation-guide/samples-containing-silver

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

July 27, 2022

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- July 27, 2027

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Thomas Kozikowski
Manager, Quality Control



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M5658 R ! 8/25/23


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

		Lot #	Solvent:	
Part Number:	**58024**	21110221	Nitric Acid	
Lot Number:	**060523**			
Description:	**Chromium (Cr)**			
		2.0%	40.0 (mL)	Nitric Acid
Expiration Date:	060526			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Volume shown below was diluted to (mL):	2000.02	0.058	Flask Uncertainty	

Formulated By:	Lawrence Barry	060523
Reviewed By:	Pedro L. Rentas	060523

Compound	Part Number	Lot Number	Dilution Factor	Initial Vol. (mL)	Uncertainty Pipette (mL)	Nominal Conc. (µg/mL)	Initial Conc. (µg/mL)	Final Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Chromium(III) nitrate nonahydrate (Cr)	58124	071122	0.1000	200.0	0.084	1000	10000.1	**1000.0**	**2.2**	7789-02-8	0.5 mg(Cr)/m3	orl-rat 3250 mg/kg	3112a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	T	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M5697 R: 10/27/23


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

		Lot #	Solvent:	
Part Number:	**58029**	24002546	Nitric Acid	
Lot Number:	**102523**			
Description:	**Copper (Cu)**			
		2.0%	40.0 (mL)	Nitric Acid
Expiration Date:	102526			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Volume shown below was diluted to (mL):	2000.02	0.058	Flask Uncertainty	

Formulated By:	Benson Chan	102523
Reviewed By:	Pedro L. Rentas	102523

Compound	Part Number	Lot Number	Dilution Factor	Initial Vol. (mL)	Uncertainty Pipette (mL)	Nominal Conc. (µg/mL)	Initial Conc. (µg/mL)	Final Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Copper(II) nitrate trihydrate (Cu)	58129	100223	0.1000	200.0	0.084	1000	10000.1	**1000.0**	**2.2**	10031-43-3	1 mg/m3	orl-rat 794 mg/kg	3114



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	T	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R: 02/09/24 M5798


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

		Lot #	Solvent:	
Part Number:	**57004**	24002546	Nitric Acid	
Lot Number:	**102523**			
Description:	**Beryllium (Be)**	2.0%	40.0 (mL)	Nitric Acid
Expiration Date:	102526			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Volume shown below was diluted to (mL):	2000.02	0.058	Flask Uncertainty	

Formulated By:	Benson Chan	102523
Reviewed By:	Pedro L. Rentas	102523

Compound	Part Number	Lot Number	Dilution Factor	Initial Vol. (mL)	Uncertainty Pipette (mL)	Nominal Conc. (µg/mL)	Initial Conc. (µg/mL)	Final Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Beryllium nitrate (Be)	58104	091423	0.1000	200.0	0.084	1000	10001.5	**1000.0**	**2.2**	13597-99-4	0.2ug/m3	intrvns-rat 3.16mg/kg	NA



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	T	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R? 02/09/24 IV15799

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 57050
Lot Number: 071123
Description: Tin (Sn)


Expiration Date: 071126
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 1000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 499.93

	Lot #	
Solvents:	21110221	Nitric Acid
	22D0562008	Hydrochloric acid
2%	10.0	Nitric Acid
6%	30.0	Hydrochloric acid
	(mL)	

5E-05 Balance Uncertainty
0.058 Flask Uncertainty

Formulated By:	Benson Chan	071123
Reviewed By:	Pedro L. Rentas	071123

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Ammonium hexafluorostannate(IV) (Sn)	IN010	SND042023A1	1000	99.999	0.10	44.2	1.13107	1.13286	**1001.6**	**2.0**	16919-24-7	7 mg/m3	NA	3161a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<500	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	T	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R: 02/09/24 IM5800 BH


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

		Lot #	Solvent:		
Part Number:	**57027**	24002546	Nitric Acid		
Lot Number:	**091923**				
Description:	**Cobalt (Co)**	2.0%	40.0 (mL)	Nitric Acid	
Expiration Date:	091926				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**1000**				
NIST Test Number:	6UTB	5E-05	Balance Uncertainty		
Volume shown below was diluted to (mL):	2000.02	0.058	Flask Uncertainty		

Formulated By:	Lawrence Barry	091923
Reviewed By:	Pedro L. Rentas	091923

Compound	Part Number	Lot Number	Dilution Factor	Initial Vol. (mL)	Uncertainty Pipette (mL)	Nominal Conc. (µg/mL)	Initial Conc. (µg/mL)	Final Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Cobalt(II) nitrate hexahydrate (Co)	58127	050923	0.1000	200.0	0.084	1000	10000.0	**1000.0**	**2.2**	10026-22-9	0.02 mg/m3	orl-rat 691 mg/kg	3113



Instrumental Analysis by Inductively Coupled Plasma Mass Spectroscopy (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	T	Gé	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R: 02/09/24 IM5801 BH


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED **WEIGHT** REPORT:

		Lot #	Solvent:		
Part Number:	**57033**	24002546	Nitric Acid		
Lot Number:	**111323**				
Description:	**Arsenic (As)**	2.0%	80.0 (mL)	Nitric Acid	
Expiration Date:	111326				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**1000**				
NIST Test Number:	6UTB	5E-05	Balance Uncertainty		
Volume shown below was diluted to (mL):	4000.0	0.06	Flask Uncertainty		

Formulated By:	Lawrence Barry	111323
Reviewed By:	Pedro L. Rentas	111323

Compound	Part Number	Lot Number	Dilution Factor	Initial Vol. (mL)	Uncertainty Pipette (mL)	Nominal Conc. (µg/mL)	Initial Conc. (µg/mL)	Final Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Arsenic (As)	58133	020522	0.1000	400.0	0.084	1000	10001.0	**1000.0**	**2.0**	7440-38-2	0.5 mg/m3	orl-rat 500 mg/kg	3103a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	T	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge*	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R1 02/09/24. M58165


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

			Lot #	
Part Number:	**57115**	**Solvent:**	21110221	Nitric Acid
Lot Number:	**041723**			
Description:	**Phosphorous (P)**	2%	40.0 (mL)	Nitric Acid
Expiration Date:	041726			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**10000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Weight shown below was diluted to (mL):	2000.02	0.058	Flask Uncertainty	

Formulated By:	Lawrence Barry	041723
Reviewed By:	Pedro L. Rentas	041723

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Ammonium dihydrogen phosphate (P)	IN008	PV082019A1	10000	99.999	0.10	27.5	72.7287	72.7289	**10000.0**	**20.0**	7722-76-1	5 mg/m3	orl-rat >2000mg/kg	3186



Instrumental Analysis by Inductively Coupled Plasma Mass Spectroscopy (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	T	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R: 02/09/24 M5817

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:


Part Number: 57116
Lot Number: 071123
Description: Sulfur (S)

Lot #
Solvent: 071123 ASTM Type 1 Water

Expiration Date: 071126
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB 5E-05 Balance Uncertainty
Weight shown below was diluted to (mL): 1999.48 0.058 Flask Uncertainty

Formulated By:	Lawrence Barry	071123
Reviewed By:	Pedro L. Rentas	071123

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Ammonium sulfate (S)	IN117	SLBR7225V	10000	99.9	0.10	24.3	82.4675	82.4682	**10000.1**	**20.0**	7783-20-2	NA	orl-rat 4250mg/kg	3181



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	T	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R: 02/09/24 M5819

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 58030
Lot Number: 111623
Description: Zinc (Zn)

Expiration Date: 111626
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 1000
NIST Test Number: 6UTB


Weight shown below was diluted to (mL): 3000.4 0.06 Flask Uncertainty

		Lot #		
Solvent:	24002546	Nitric Acid		
	2%	60.0 (mL)	Nitric Acid	

5E-05 Balance Uncertainty

Formulated By:	Benson Chan	111623
Reviewed By:	Pedro L. Rentas	111623

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Zinc nitrate hexahydrate (Zn)	IN016	ZNE032021A1	1000	99.999	0.10	24.3	12.3475	12.3502	**1000.2**	**2.0**	10196-18-6	1 mg/m3	orl-rat 1190mg/kg	3168



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	T
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

INORGANIC VENTURES™
Refine your results. Redefine your industry.

Certificate of Analysis

R: 02/22/24 M5942

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 883.01
ACCREDITED Reference Material Producer Certificate 883.02

2.0 PRODUCT DESCRIPTION

Product Code:	Single Analyte Custom Grade Solution
Catalog Number:	CGTI1
Lot Number:	T2-TI719972
Matrix:	2% (v/v) HNO3 tr. HF
Value / Analyte(s):	1 000 µg/mL ea: Titanium
Starting Material:	Ti Metal
Starting Material Lot#:	2094
Starting Material Purity:	99.9975%

3.0 CERTIFIED VALUES AND UNCERTAINTIES

Certified Value: 1002 ± 5 µg/mL

Density: 1.012 g/mL (measured at 20 ± 4 °C)

Assay Information:

Assay Method #1 **1002 ± 4 µg/mL**
ICP Assay NIST SRM 3162a Lot Number: 130925

- The Calculated Value is a value calculated from the weight of a starting material that has been certified directly vs. a National Institute of Standards and Technology (NIST) SRM/RM. See Sec 4.2 for balance traceability.

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\ (u_{char\ i})^2)]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\ (u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

CRM/RMs are tested for trace metallic impurities by Axial ICP-OES and ICP-MS. The result from the most sensitive method for each element, is reported below. Solutions tested by ICP-MS were analyzed in an ULPA-Filtered Clean Room. An ULPA-Filter is 99.9985% efficient for the removal of particles down to 0.3 µm.

M	Ag	<	0.000536	M	Eu	<	0.000268	O	Na	<	0.032670	M	Se		0.001204	O	Zn	<	0.003267
O	Al		0.000872	O	Fe		0.003225	O	Nb	<	0.043560	O	Si		0.004735	O	Zr	<	0.043560
M	As	<	0.008586	M	Ga	<	0.000268	M	Nd	<	0.000268	M	Sm	<	0.000268				
M	Au	<	0.004577	M	Gd	<	0.000268	O	Ni	<	0.010890	M	Sn		0.000096				
O	B	<	0.008929	M	Ge	<	0.002146	M	Os	<	0.000269	O	Sr		0.000096				
M	Ba	<	0.002683	M	Hf		0.002161	O	P	<	0.054450	M	Ta		0.010560				
M	Be	<	0.005366	M	Hg	<	0.003231	M	Pb	<	0.001073	M	Tb	<	0.000268				
M	Bi	<	0.001609	M	Ho	<	0.000268	M	Pd	<	0.000268	M	Te	<	0.001341				
O	Ca		0.000676	M	In	<	0.002683	M	Pr	<	0.000268	M	Th	<	0.053663				
M	Cd	<	0.000268	M	Ir	<	0.000269	M	Pt	<	0.000536	s	Ti	<					
M	Ce	<	0.000268	M	K		0.001172	M	Rb	<	0.000268	M	Tl	<	0.000268				
M	Co	<	0.004293	M	La	<	0.000268	M	Re	<	0.000268	M	Tm	<	0.000268				
M	Cr		0.000752	O	Li	<	0.027225	M	Rh	<	0.000268	M	U	<	0.000268				
M	Cs	<	0.000268	M	Lu	<	0.000268	M	Ru	<	0.000269	M	V	<	0.019855				
O	Cu	<	0.010890	O	Mg	<	0.005445	i	S	<		M	W		0.000473				
M	Dy	<	0.000268	O	Mn	<	0.003267	M	Sb	<	0.006976	M	Y	<	0.002146				
M	Er	<	0.000268	M	Mo		0.000774	O	Sc	<	0.004900	M	Yb	<	0.000536				

M - Checked by ICP-MS O - Checked by ICP-OES i - Spectral Interference
n - Not Checked For s - Solution Standard Element

6.0 INTENDED USE

- For the calibration of analytical instruments and validation of analytical methods as appropriate.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

Atomic Weight; Valence; Coordination Number; Chemical Form in Solution - 47.87 +4 6 Ti(F)6-2

Chemical Compatibility - Soluble in concentrated HCl, HF, H3PO4 H2SO4 and HNO3. Avoid neutral to basic media. Unstable at ppm levels with metals that would pull F- away (i.e. Do not mix with Alkaline or Rare Earths or high levels of transition elements unless they are fluorinated). Stable with most inorganic anions with a tendency to hydrolyze forming the hydrated oxide in all dilute acids except HF.

Stability - 2-100 ppb levels stable (Alone or mixed with all other metals) as the Ti(F)6-2 for months in 1% HNO3 / LDPE container. 1-10,000 ppm single element solutions as the Ti(F)6-2 chemically stable for years in 2-5% HNO3 / trace HF in an LDPE container.

Ti Containing Samples (Preparation and Solution) - Metal (Soluble in H2O / HF caution -powder reacts violently); Oxide - low temperature history anatase or rutile (Dissolved by heating in 1:1:1 H2O / HF / H2SO4); Oxide - high temperature history (~800EC) brookite (fuse in Pt0 with K2S2O7); Ores (fuse in Pt0 with KF + K2S2O7 - no KF if silica not present); Organic Matrices (Dry ash at 450EC in Pt0 and dissolve by heating with 1:1:1 H2O / HF / H2SO4 or fuse ash with pyrosulfate if oxide is as plastic pigment and likely in brookite crystalline form).

Atomic Spectroscopic Information (ICP-OES D.L.s are given as radial/axial view):

Technique/Line	**Estimated D.L.**	**Order**	**Interferences** (underlined indicates severe)
ICP-MS 48 amu	14 ppt	N/A	32S16O, 32S14N, 14N16O18O, 14N17N2, 36Ar12C, 48Ca, [96X=2 (where X = Zr, Mo, Ru)]
ICP-OES 323.452 nm	0.0054 / 0.00092 µg/mL	1	Ce, Ar, Ni
ICP-OES 334.941 nm	0.0038 / 0.000028 µg/mL	1	Nb, Ta, Cr, U
ICP-OES 336.121 nm	0.0053 / 0.000034 µg/mL	1	W, Mo, Co

HF Note: This standard should not be prepared or stored in glass.

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

June 17, 2022

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- **June 17, 2027**

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Thomas Kozikowski
Manager, Quality Control



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



INORGANIC VENTURES
Refine your results. Redefine your industry.

Certificate of Analysis

M5959 R: 6/14/24.

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 863.01
ACCREDITED Reference Material Producer Certificate 863.02

2.0 PRODUCT DESCRIPTION

Product Code:	Single Analyte Custom Grade Solution
Catalog Number:	CGY10
Lot Number:	V2-Y740548
Matrix:	2% (v/v) HNO3
Value / Analyte(s):	10 000 µg/mL ea: Yttrium
Starting Material:	Yttrium Oxide
Starting Material Lot#:	2661 and 06230520YL
Starting Material Purity:	99.9984%

3.0 CERTIFIED VALUES AND UNCERTAINTIES

Certified Value: 10000 ± 30 µg/mL

Density: 1.032 g/mL (measured at 20 ± 4 °C)

Assay Information:

Assay Method #1	**10011 ± 25 µg/mL** EDTA NIST SRM 928 Lot Number: 928
Assay Method #2	**9997 ± 50 µg/mL** ICP Assay NIST SRM 3167a Lot Number: 190730
Assay Method #3	**9984 ± 31 µg/mL** Calculated NIST SRM Lot Number: See Sec. 4.2

- The Calculated Value is a value calculated from the weight of a starting material that has been certified directly vs. a National Institute of Standards and Technology (NIST) SRM/RM. See Sec 4.2 for balance traceability.

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{1/2}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{1/2}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{1/2}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

CRM/RMs are tested for trace metallic impurities by Axial ICP-OES and ICP-MS. The result from the most sensitive method for each element, is reported below. Solutions tested by ICP-MS were analyzed in an ULPA-Filtered Clean Room. An ULPA-Filter is 99.9985% efficient for the removal of particles down to 0.3 µm.

M	Ag	<	0.004600	M	Eu		0.009037	M	Na		0.086360	M	Se	<	0.005200	M	Zn		0.030125
M	Al		0.014862	O	Fe		0.002410	M	Nb	<	0.000570	O	Si		0.024100	O	Zr	<	0.002600
M	As	<	0.003500	M	Ga	<	0.000570	M	Nd		0.000923	M	Sm		0.000461				
M	Au	<	0.001700	M	Gd	<	0.003500	M	Ni	<	0.005700	M	Sn	<	0.002300				
O	B		0.002209	M	Ge	<	0.005200	M	Os	<	0.001200	M	Sr	<	0.004600				
O	Ba	<	0.002500	M	Hf	<	0.000570	n	P	<		M	Ta	<	0.000570				
O	Be	<	0.001400	M	Hg	<	0.000570	M	Pb		0.005020	M	Tb		0.001044				
M	Bi	<	0.003500	M	Ho		0.009037	M	Pd	<	0.005100	M	Te	<	0.002300				
O	Ca		0.009841	M	In	<	0.002300	M	Pr	<	0.002300	M	Th	<	0.000570				
M	Cd	<	0.000570	M	Ir	<	0.000570	M	Pt	<	0.000570	M	Ti	<	0.003500				
M	Ce	<	0.002300	O	K		0.018677	M	Rb	<	0.000570	M	Tl	<	0.000570				
M	Co	<	0.000570	M	La		0.000461	M	Re	<	0.000570	M	Tm	<	0.003500				
M	Cr	<	0.004000	O	Li	<	0.009300	M	Rh	<	0.008000	M	U	<	0.000570				
M	Cs	<	0.000570	M	Lu		0.000582	M	Ru	<	0.000570	M	V		0.001265				
M	Cu		0.002610	O	Mg		0.001486	n	S	<		M	W	<	0.002300				
M	Dy		0.003815	M	Mn		0.000582	M	Sb		0.005422	s	Y	<					
M	Er		0.003615	M	Mo	<	0.005700	M	Sc	<	0.001200	M	Yb		0.001827				

M - Checked by ICP-MS O - Checked by ICP-OES i - Spectral Interference
n - Not Checked For s - Solution Standard Element

6.0 INTENDED USE

6.1 This standard is intended for the calibration of analytical instruments and validation of analytical methods as appropriate. This CRM may be used in connection with EPA Methods 6010, 6020 (all versions), Standard Methods 3120 B and USP <232> / ICH Q3D.

6.2 For products attaining traceability through Inorganic Ventures' Primary Certified Reference Materials (PCRM™) see the Limited License to Use PCRM™ in the Inorganic Ventures Terms and Conditions of Sale, https://www.inorganicventures.com/terms-and-conditions-sale. The Terms and Conditions contain information on the use of materials traceable to PCRM™ certified reference materials. This Limited License agreement is especially pertinent for laboratories accredited under ISO:17034.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

Atomic Weight; Valence; Coordination Number; Chemical Form in Solution - 88.91 +3 6 Y(OH)(H2O)x+2

Chemical Compatibility -Soluble in HCl, H2SO4 and HNO3. Avoid HF, H3PO4 and neutral to basic media. Stable with most metals and inorganic anions forming an insoluble carbonate, oxide, oxalate, and fluoride. Avoid mixing with elements / solutions containing moderate amounts of fluoride.

Stability - 2-100 ppb levels stable for months in 1% HNO3 / LDPE container. 1-10,000 ppm solutions chemically stable for years in 2-5% HNO3 / LDPE container.

Y Containing Samples (Preparation and Solution) - Metal (Soluble in acids); Oxide (Dissolve by heating in H2O/ HNO3); Ores (Carbonate fusion in Pt0 followed by HCl dissolution); Organic Matrices (Dry ash and dissolve in 1:1 H2O / HCl or HNO3).

Atomic Spectroscopic Information (ICP-OES D.L.s are given as radial/axial view):

Technique/Line	**Estimated D.L.**	**Order**	**Interferences** (underlined indicates severe)
ICP-MS 89 amu	0.8 ppt	N/A	73Ge16O, 178Hf+2
ICP-OES 360.073 nm	0.005 / 0.000036 µg/mL	1	Ce, Th
ICP-OES 371.030 nm	0.004 / 0.00007 µg/mL	1	Ce
ICP-OES 377.433 nm	0.005 / 0.0009 µg/mL	1	Ta, Th

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

February 20, 2024

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- February 20, 2029

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Prepared By:

Uyen Truong
Custom Processing Supervisor



Certificate Approved By:

Muzzammil Khan
Stock Laboratory Supervisor



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M5961 R: 6/11/24


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

			Lot #	
Part Number:	**57028**	**Solvent:**	24002546	Nitric Acid
Lot Number:	**041124**			
Description:	**Nickel (Ni)**			
		2%	5.0 (mL)	Nitric Acid
Expiration Date:	041127			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Weight shown below was diluted to (mL):	249.85	0.002	Flask Uncertainty	

Formulated By:	Brian Geddes	041124
Reviewed By:	Pedro L. Rentas	041124

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Nickel(II) nitrate hexahydrate (Ni)	IN033	NIM052023A1	1000	99.999	0.10	20.2	1.2369	1.2369	**1000.0**	**2.0**	13478-00-7	1 mg/m3	orl-rat 1620 mg/kg	3136



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	T	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M5962 R! 06/14/24.


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

		Lot #	Solvent:	
Part Number:	**57034**	24002546	Nitric Acid	
Lot Number:	**060624**			
Description:	**Selenium (Se)**			
		2.0%	40.0 (mL)	Nitric Acid
Expiration Date:	060627			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Volume shown below was diluted to (mL):	2000.07	0.100	Flask Uncertainty	

Formulated By:	Benson Chan	060624
Reviewed By:	Pedro L. Rentas	060624

Compound	Part Number	Lot Number	Dilution Factor	Initial Vol. (mL)	Uncertainty Pipette (mL)	Nominal Conc. (µg/mL)	Initial Conc. (µg/mL)	Final Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Selenium (Se)	58134	071223	0.1000	200.0	0.084	1000	10002.5	**1000.0**	**2.2**	7782-49-2	0.2 mg/m3	orl-rat 6700 mg/kg	3149



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																		
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	T	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

INORGANIC VENTURES
Refine your results. Redefine your industry.

Certificate of Analysis

M5976, M5977
R: 02/22/24

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 883.01
ACCREDITED Reference Material Producer Certificate 883.02

2.0 PRODUCT DESCRIPTION

Product Code:	Single Analyte Custom Grade Solution
Catalog Number:	CGMO1
Lot Number:	T2-MO720876
Matrix:	H2O tr. NH4OH
Value / Analyte(s):	1 000 µg/mL ea: Molybdenum
Starting Material:	Ammonium Molybdate
Starting Material Lot#:	2361
Starting Material Purity:	99.9893%

3.0 CERTIFIED VALUES AND UNCERTAINTIES

Certified Value: 998 ± 7 µg/mL

Density: 1.000 g/mL (measured at 20 ± 4 °C)

Assay Information:

Assay Method #1 **998 ± 4 µg/mL**
ICP Assay NIST SRM 3134 Lot Number: 130418

- The Calculated Value is a value calculated from the weight of a starting material that has been certified directly vs. a National Institute of Standards and Technology (NIST) SRM/RM. See Sec 4.2 for balance traceability.

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance.

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

CRM/RMs are tested for trace metallic impurities by Axial ICP-OES and ICP-MS. The result from the most sensitive method for each element, is reported below. Solutions tested by ICP-MS were analyzed in an ULPA-Filtered Clean Room. An ULPA-Filter is 99.9985% efficient for the removal of particles down to 0.3 µm.

M	Ag	<	0.000590	M	Eu	<	0.000300	M	Na		0.000879	M	Se	<	0.008000	M	Zn		0.000598
M	Al		0.000563	M	Fe	<	0.006500	M	Nb	<	0.029000	i	Si	<		M	Zr	<	0.001800
M	As	<	0.002100	M	Ga	<	0.000300	i	Nd	<		M	Sm	<	0.000300				
M	Au	<	0.000300	M	Gd	<	0.000300	M	Ni	<	0.008000	M	Sn	<	0.008900				
M	B	<	0.003300	M	Ge	<	0.000300	M	Os	<	0.000590	M	Sr		0.000175				
M	Ba		0.001689	M	Hf	<	0.001800	i	P	<		M	Ta	<	0.004200				
M	Be	<	0.000890	M	Hg	<	0.003300	M	Pb	<	0.000300	M	Tb	<	0.000300				
M	Bi	<	0.000890	M	Ho	<	0.000300	M	Pd	<	0.001800	M	Te	<	0.021000				
O	Ca		0.006334	M	In	<	0.032000	M	Pr	<	0.013000	M	Th	<	0.000300				
O	Cd	<	0.026000	M	Ir	<	0.000300	M	Pt	<	0.000300	O	Tl	<	0.032000				
M	Ce	<	0.008300	M	K		0.130213	M	Rb		0.004575	M	Tl		0.001266				
M	Co		0.000598	M	La	<	0.000300	M	Re	<	0.000300	M	Tm	<	0.000300				
M	Cr		0.000527	O	Li		0.000059	M	Rh	<	0.000300	M	U	<	0.005300				
M	Cs		0.000527	M	Lu	<	0.000300	M	Ru	<	0.079000	M	V	<	0.000890				
M	Cu		0.002252	M	Mg		0.000563	i	S	<		M	W		0.087982				
M	Dy	<	0.000300	M	Mn	<	0.005900	M	Sb		0.001513	M	Y	<	0.000300				
M	Er	<	0.000300	s	Mo	<		M	Sc	<	0.001200	M	Yb	<	0.000300				

M - Checked by ICP-MS O - Checked by ICP-OES i - Spectral Interference
n - Not Checked For s - Solution Standard Element

6.0 INTENDED USE

- For the calibration of analytical instruments and validation of analytical methods as appropriate.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

Atomic Weight; Valence; Coordination Number; Chemical Form in Solution - 95.94 +6 6,7,8,9 [MoO4]-2(chemical form as received)

Chemical Compatibility -Mo is received in a NH4OH matrix giving the operator the option of using HCl or HF to stabilize acidic solutions. The [MoO4]-2 is soluble in concentrated HCl [MoOCl5]-2, dilute HF / HNO3 [MoOF5]-2 and basic media [MoO4]-2. Stable at ppm levels with some metals provided it is fluorinated. Do not mix with Alkaline or Rare Earths when HF is present. Stable with most inorganic anions provided it is in the [MoO4]-2 chemical form.

Stability - 2-100 ppb levels stable (alone or mixed with all other metals that are at comparable levels) as the [MoOF5]-2 for months in 1% HNO3 / LDPE container. 1-10,000 ppm single element solutions as the [MoO4]-2 chemically stable for years in 1% NH4OH in a LDPE container.

Mo Containing Samples (Preparation and Solution) -Metal (Soluble in HF / HNO3 or hot dilute HCl); Oxide (soluble in HF or NH4OH) ; Organic Matrices (Dry ash at 450EC in Pt0 and dissolve oxide with HF or HCl).

Atomic Spectroscopic Information (ICP-OES D.L.s are given as radial/axial view):

Technique/Line	**Estimated D.L.**	**Order**	**Interferences** (underlined indicates severe)
ICP-MS 95 amu	3 ppt	n/a	40Ar39K16O,79Br1 6O,190Os2+,190Pt 2+
ICP-OES 202.030 nm	0.008 / 0.0002 µg/mL	1	Os, Hf
ICP-OES 203.844 nm	0.012 / 0.002 µg/mL	1	
ICP-OES 204.598 nm	0.012 / 0.001 µg/mL	1	Ir, Ta

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

July 17, 2022

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- July 17, 2027

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Prepared By:

Uyen Truong
Supervisor, Product Documentation



Certificate Approved By:

Michael Booth
Director, Technical



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



INORGANIC VENTURES
Refine your results. Redefine your industry.

Certificate of Analysis

M5976, M5977
R: 02/22/24

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 883.01
ACCREDITED Reference Material Producer Certificate 883.02

2.0 PRODUCT DESCRIPTION

Product Code:	Single Analyte Custom Grade Solution
Catalog Number:	CGMO1
Lot Number:	T2-MO720876
Matrix:	H2O tr. NH4OH
Value / Analyte(s):	1 000 µg/mL ea: Molybdenum
Starting Material:	Ammonium Molybdate
Starting Material Lot#:	2361
Starting Material Purity:	99.9893%

3.0 CERTIFIED VALUES AND UNCERTAINTIES

Certified Value: 998 ± 7 µg/mL

Density: 1.000 g/mL (measured at 20 ± 4 °C)

Assay Information:

Assay Method #1 **998 ± 4 µg/mL**
ICP Assay NIST SRM 3134 Lot Number: 130418

- The Calculated Value is a value calculated from the weight of a starting material that has been certified directly vs. a National Institute of Standards and Technology (NIST) SRM/RM. See Sec 4.2 for balance traceability.

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance.

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

CRM/RMs are tested for trace metallic impurities by Axial ICP-OES and ICP-MS. The result from the most sensitive method for each element, is reported below. Solutions tested by ICP-MS were analyzed in an ULPA-Filtered Clean Room. An ULPA-Filter is 99.9985% efficient for the removal of particles down to 0.3 µm.

M	Ag	<	0.000590	M	Eu	<	0.000300	M	Na		0.000879	M	Se	<	0.008000	M	Zn		0.000598
M	Al		0.000563	M	Fe	<	0.006500	M	Nb	<	0.029000	i	Si	<		M	Zr	<	0.001800
M	As	<	0.002100	M	Ga	<	0.000300	i	Nd	<		M	Sm	<	0.000300				
M	Au	<	0.000300	M	Gd	<	0.000300	M	Ni	<	0.008000	M	Sn	<	0.008900				
M	B	<	0.003300	M	Ge	<	0.000300	M	Os	<	0.000590	M	Sr		0.000175				
M	Ba		0.001689	M	Hf	<	0.001800	i	P	<		M	Ta	<	0.004200				
M	Be	<	0.000890	M	Hg	<	0.003300	M	Pb	<	0.000300	M	Tb	<	0.000300				
M	Bi	<	0.000890	M	Ho	<	0.000300	M	Pd	<	0.001800	M	Te	<	0.021000				
O	Ca		0.006334	M	In	<	0.032000	M	Pr	<	0.013000	M	Th	<	0.000300				
O	Cd	<	0.026000	M	Ir	<	0.000300	M	Pt	<	0.000300	O	Tl	<	0.032000				
M	Ce	<	0.008300	M	K		0.130213	M	Rb		0.004575	M	Tl		0.001266				
M	Co		0.000598	M	La	<	0.000300	M	Re	<	0.000300	M	Tm	<	0.000300				
M	Cr		0.000527	O	Li		0.000059	M	Rh	<	0.000300	M	U	<	0.005300				
M	Cs		0.000527	M	Lu	<	0.000300	M	Ru	<	0.079000	M	V	<	0.000890				
M	Cu		0.002252	M	Mg		0.000563	i	S	<		M	W		0.087982				
M	Dy	<	0.000300	M	Mn	<	0.005900	M	Sb		0.001513	M	Y	<	0.000300				
M	Er	<	0.000300	s	Mo	<		M	Sc	<	0.001200	M	Yb	<	0.000300				

M - Checked by ICP-MS O - Checked by ICP-OES i - Spectral Interference
n - Not Checked For s - Solution Standard Element

6.0 INTENDED USE

- For the calibration of analytical instruments and validation of analytical methods as appropriate.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

Atomic Weight; Valence; Coordination Number; Chemical Form in Solution - 95.94 +6 6,7,8,9 [MoO4]-2(chemical form as received)

Chemical Compatibility -Mo is received in a NH4OH matrix giving the operator the option of using HCl or HF to stabilize acidic solutions. The [MoO4]-2 is soluble in concentrated HCl [MoOCl5]-2, dilute HF / HNO3 [MoOF5]-2 and basic media [MoO4]-2. Stable at ppm levels with some metals provided it is fluorinated. Do not mix with Alkaline or Rare Earths when HF is present. Stable with most inorganic anions provided it is in the [MoO4]-2 chemical form.

Stability - 2-100 ppb levels stable (alone or mixed with all other metals that are at comparable levels) as the [MoOF5]-2 for months in 1% HNO3 / LDPE container. 1-10,000 ppm single element solutions as the [MoO4]-2 chemically stable for years in 1% NH4OH in a LDPE container.

Mo Containing Samples (Preparation and Solution) -Metal (Soluble in HF / HNO3 or hot dilute HCl); Oxide (soluble in HF or NH4OH) ; Organic Matrices (Dry ash at 450EC in Pt0 and dissolve oxide with HF or HCl).

Atomic Spectroscopic Information (ICP-OES D.L.s are given as radial/axial view):

Technique/Line	**Estimated D.L.**	**Order**	**Interferences** (underlined indicates severe)
ICP-MS 95 amu	3 ppt	n/a	40Ar39K16O,79Br1 6O,190Os2+,190Pt 2+
ICP-OES 202.030 nm	0.008 / 0.0002 µg/mL	1	Os, Hf
ICP-OES 203.844 nm	0.012 / 0.002 µg/mL	1	
ICP-OES 204.598 nm	0.012 / 0.001 µg/mL	1	Ir, Ta

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

July 17, 2022

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- July 17, 2027

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Prepared By:

Uyen Truong
Supervisor, Product Documentation



Certificate Approved By:

Michael Booth
Director, Technical



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



M5978, M5979

INORGANIC VENTURES
Refine your results. Redefine your industry.

Certificate of Analysis

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

R: 2/22/24

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 883.01 ACCREDITED Reference Material Producer Certificate 883.02

2.0 PRODUCT DESCRIPTION

Product Code:	Single Analyte Custom Grade Solution
Catalog Number:	CGTI1
Lot Number:	T2-TI719972
Matrix:	2% (v/v) HNO_3 tr. HF
Value / Analyte(s):	1 000 µg/mL ea: Titanium
Starting Material:	Ti Metal
Starting Material Lot#:	2094
Starting Material Purity:	99.9975%

3.0 CERTIFIED VALUES AND UNCERTAINTIES

Certified Value: 1002 ± 5 µg/mL

Density: 1.012 g/mL (measured at 20 ± 4 °C)

Assay Information:

Assay Method #1 **1002 ± 4 µg/mL**
ICP Assay NIST SRM 3162a Lot Number: 130925

- The Calculated Value is a value calculated from the weight of a starting material that has been certified directly vs. a National Institute of Standards and Technology (NIST) SRM/RM. See Sec 4.2 for balance traceability.

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance

$w_i = (1/u_{char\ i}^2) / (\Sigma(1/u_{char\ i}^2))$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\ (u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma(w_i)^2\ (u_{char\ i})^2]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\ (u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\ (u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

CRM/RMs are tested for trace metallic impurities by Axial ICP-OES and ICP-MS. The result from the most sensitive method for each element, is reported below. Solutions tested by ICP-MS were analyzed in an ULPA-Filtered Clean Room. An ULPA-Filter is 99.9985% efficient for the removal of particles down to 0.3 µm.

M	Ag	<	0.000536	M	Eu	<	0.000268	O	Na	<	0.032670	M	Se		0.001204	O	Zn	<	0.003267
O	Al		0.000872	O	Fe		0.003225	O	Nb	<	0.043560	O	Si		0.004735	O	Zr	<	0.043560
M	As	<	0.008586	M	Ga	<	0.000268	M	Nd	<	0.000268	M	Sm	<	0.000268				
M	Au	<	0.004577	M	Gd	<	0.000268	O	Ni	<	0.010890	M	Sn		0.000096				
O	B	<	0.008929	M	Ge	<	0.002146	M	Os	<	0.000269	O	Sr		0.000096				
M	Ba	<	0.002683	M	Hf		0.002161	O	P	<	0.054450	M	Ta		0.010560				
M	Be	<	0.005366	M	Hg	<	0.003231	M	Pb	<	0.001073	M	Tb	<	0.000268				
M	Bi	<	0.001609	M	Ho	<	0.000268	M	Pd	<	0.000268	M	Te	<	0.001341				
O	Ca		0.000676	M	In	<	0.002683	M	Pr	<	0.000268	M	Th	<	0.053663				
M	Cd	<	0.000268	M	Ir	<	0.000269	M	Pt	<	0.000536	s	Ti	<					
M	Ce	<	0.000268	M	K		0.001172	M	Rb	<	0.000268	M	Tl	<	0.000268				
M	Co	<	0.004293	M	La	<	0.000268	M	Re	<	0.000268	M	Tm	<	0.000268				
M	Cr		0.000752	O	Li	<	0.027225	M	Rh	<	0.000268	M	U	<	0.000268				
M	Cs	<	0.000268	M	Lu	<	0.000268	M	Ru	<	0.000269	M	V	<	0.019855				
O	Cu	<	0.010890	O	Mg	<	0.005445	i	S	<		M	W		0.000473				
M	Dy	<	0.000268	O	Mn	<	0.003267	M	Sb	<	0.006976	M	Y	<	0.002146				
M	Er	<	0.000268	M	Mo		0.000774	O	Sc	<	0.004900	M	Yb	<	0.000536				

M - Checked by ICP-MS O - Checked by ICP-OES i - Spectral Interference
n - Not Checked For s - Solution Standard Element

6.0 INTENDED USE

- For the calibration of analytical instruments and validation of analytical methods as appropriate.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

Atomic Weight; Valence; Coordination Number; Chemical Form in Solution - 47.87 +4 6 Ti(F)6-2

Chemical Compatibility - Soluble in concentrated HCl, HF, H3PO4 H2SO4 and HNO3. Avoid neutral to basic media. Unstable at ppm levels with metals that would pull F- away (i.e. Do not mix with Alkaline or Rare Earths or high levels of transition elements unless they are fluorinated). Stable with most inorganic anions with a tendency to hydrolyze forming the hydrated oxide in all dilute acids except HF.

Stability - 2-100 ppb levels stable (Alone or mixed with all other metals) as the Ti(F)6-2 for months in 1% HNO3 / LDPE container. 1-10,000 ppm single element solutions as the Ti(F)6-2 chemically stable for years in 2-5% HNO3 / trace HF in an LDPE container.

Ti Containing Samples (Preparation and Solution) - Metal (Soluble in H2O / HF caution -powder reacts violently); Oxide - low temperature history anatase or rutile (Dissolved by heating in 1:1:1 H2O / HF / H2SO4); Oxide - high temperature history (~800EC) brookite (fuse in Pt0 with K2S2O7); Ores (fuse in Pt0 with KF + K2S2O7 - no KF if silica not present); Organic Matrices (Dry ash at 450EC in Pt0 and dissolve by heating with 1:1:1 H2O / HF / H2SO4 or fuse ash with pyrosulfate if oxide is as plastic pigment and likely in brookite crystalline form).

Atomic Spectroscopic Information (ICP-OES D.L.s are given as radial/axial view):

Technique/Line	Estimated D.L.	Order	Interferences (underlined indicates severe)
ICP-MS 48 amu	14 ppt	N/A	32S16O, 32S14N, 14N16O18O, 14N17N2, 36Ar12C, 48Ca, [96X=2 (where X = Zr, Mo, Ru)]
ICP-OES 323.452 nm	0.0054 / 0.00092 µg/mL	1	Ce, Ar, Ni
ICP-OES 334.941 nm	0.0038 / 0.000028 µg/mL	1	Nb, Ta, Cr, U
ICP-OES 336.121 nm	0.0053 / 0.000034 µg/mL	1	W, Mo, Co

HF Note: This standard should not be prepared or stored in glass.

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

June 17, 2022

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- June 17, 2027

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Thomas Kozikowski
Manager, Quality Control



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



INORGANIC VENTURES™
Refine your results. Redefine your industry.

Certificate of Analysis

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

MS985
R: 6/14/24

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 863.01
ACCREDITED Reference Material Producer Certificate 863.02

2.0 PRODUCT DESCRIPTION

Product Code:	Single Analyte Custom Grade Solution
Catalog Number:	CGIN10
Lot Number:	U2-IN729349
Matrix:	5% (v/v) HNO3
Value / Analyte(s):	10 000 µg/mL ea: Indium
Starting Material:	Indium Metal
Starting Material Lot#:	2511
Starting Material Purity:	99.9995%

3.0 CERTIFIED VALUES AND UNCERTAINTIES

Certified Value: 10022 ± 30 µg/mL

Density: 1.044 g/mL (measured at 20 ± 4 °C)

Assay Information:

Assay Method #1	**10021 ± 56 µg/mL** ICP Assay NIST SRM 3124a Lot Number: 110516
Assay Method #2	**10035 ± 25 µg/mL** EDTA NIST SRM 928 Lot Number: 928
Assay Method #3	**10001 ± 33 µg/mL** Calculated NIST SRM Lot Number: See Sec. 4.2

- The Calculated Value is a value calculated from the weight of a starting material that has been certified directly vs. a National Institute of Standards and Technology (NIST) SRM/RM. See Sec 4.2 for balance traceability.

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\ (u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\ (u_{char\ i})^2)]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\ (u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\ (u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

CRM/RMs are tested for trace metallic impurities by Axial ICP-OES and ICP-MS. The result from the most sensitive method for each element, is reported below. Solutions tested by ICP-MS were analyzed in an ULPA-Filtered Clean Room. An ULPA-Filter is 99.9985% efficient for the removal of particles down to 0.3 µm.

M	Ag	<	0.000760	M	Eu	<	0.000760	O	Na		0.012771	M	Se	<	0.023000	M	Zn	<	0.006100
M	Al		0.003385	O	Fe		0.004462	M	Nb	<	0.000760	O	Si		0.024619	M	Zr	<	0.000760
M	As	<	0.004600	M	Ga	<	0.000760	M	Nd	<	0.000760	M	Sm	<	0.000760				
M	Au	<	0.002300	M	Gd	<	0.000760	O	Ni	<	0.005100	M	Sn	<	0.000760				
O	B		0.003692	M	Ge	<	0.001600	M	Os	<	0.000760	O	Sr	<	0.000610				
M	Ba	<	0.001600	M	Hf	<	0.000760	n	P	<		M	Ta	<	0.000760				
O	Be	<	0.000130	M	Hg	<	0.003100	M	Pb		0.001400	M	Tb	<	0.000760				
M	Bi	<	0.000760	M	Ho	<	0.000760	M	Pd	<	0.001600	M	Te	<	0.000760				
O	Ca		0.004616	s	In	<		M	Pr	<	0.000760	M	Th	<	0.000760				
M	Cd	<	0.000760	M	Ir	<	0.000760	M	Pt	<	0.000760	O	Ti	<	0.001100				
M	Ce	<	0.000760	O	K		0.007078	M	Rb	<	0.000760	M	Tl	<	0.000760				
M	Co	<	0.000760	M	La	<	0.000760	M	Re	<	0.000760	M	Tm	<	0.000760				
O	Cr	<	0.001300	O	Li	<	0.000130	M	Rh	<	0.000760	M	U	<	0.000760				
M	Cs	<	0.000760	M	Lu	<	0.000760	M	Ru	<	0.000760	M	V	<	0.001600				
M	Cu	<	0.003800	O	Mg		0.000707	n	S	<		M	W	<	0.001600				
M	Dy	<	0.000760	O	Mn		0.000149	M	Sb	<	0.000760	M	Y	<	0.000760				
M	Er	<	0.000760	M	Mo	<	0.002300	M	Sc	<	0.000760	M	Yb	<	0.000760				

M - Checked by ICP-MS O - Checked by ICP-OES i - Spectral Interference
n - Not Checked For s - Solution Standard Element

6.0 INTENDED USE

6.1 This standard is intended for the calibration of analytical instruments and validation of analytical methods as appropriate. This CRM may be used in connection with EPA Methods 6010, 6020 (all versions), Standard Methods 3120 B and USP <232> / ICH Q3D.

6.2 For products attaining traceability through Inorganic Ventures' Primary Certified Reference Materials (PCRM™) see the Limited License to Use PCRM™ in the Inorganic Ventures Terms and Conditions of Sale, https://www.inorganicventures.com/terms-and-conditions-sale. The Terms and Conditions contain information on the use of materials traceable to PCRM™ certified reference materials. This Limited License agreement is especially pertinent for laboratories accredited under ISO:17034.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

Atomic Weight; Valence; Coordination Number; Chemical Form in Solution - 114.82 +3 6 In(H2O)6+3

Chemical Compatibility -Soluble in HCl, HNO3, and H2SO4. Avoid neutral and basic media. Stable with most metals and inorganic anions. The oxalate, sulfide, carbonate, hydroxide and phosphate are insoluble in water.

Stability - 2-100 ppb levels stable for months in 1% HNO3 / LDPE container. 1-10,000 ppm solutions chemically stable for years in 2-5% HNO3 / LDPE container.

In Containing Samples (Preparation and Solution) -Metal (Best dissolved in HCl / HNO3); Oxide (Soluble in mineral acids); Ores (Carbonate fusion in Pt0 followed by HCl dissolution); Organic Matrices (Sulfuric/peroxide digestion or dry ash and dissolution in dilute HCl).

Atomic Spectroscopic Information (ICP-OES D.L.s are given as radial/axial view):

Technique/Line	**Estimated D.L.**	**Order**	**Interferences** (underlined indicates severe)
ICP-MS 115 amu	1 ppt	n/a	115Sn, 99Ru16O
ICP-OES 158.583 nm	0.05 / 0.002 µg/mL	1	
ICP-OES 230.606 nm	0.1 / 0.03 µg/mL	1	Ni, Os
ICP-OES 325.609 nm	0.2 / 0.05 µg/mL	1	Mn, Mo, Th

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

February 21, 2023

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- February 21, 2028

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Thomas Kozikowski
Manager, Quality Control



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



INORGANIC VENTURES™
Refine your results. Redefine your industry.

Certificate of Analysis

M6074
M6075
M6076
M6077

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

EXP.: 9/6/2029

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 883.01
ACCREDITED Reference Material Producer Certificate 883.02

2.0 PRODUCT DESCRIPTION

Product Code:	Multi Analyte Custom Grade Solution
Catalog Number:	CHEM-CLP-4
Lot Number:	V2-MEB746762
Matrix:	3% (v/v) HNO3 3% (v/v) HF
Value / Analyte(s):	1 000 µg/mL ea: Boron, Molybdenum, Silicon, Tin, Titanium

3.0 CERTIFIED VALUES AND UNCERTAINTIES

ANALYTE	CERTIFIED VALUE	ANALYTE	CERTIFIED VALUE
Boron, B	**1 000 ± 5 µg/mL**	**Molybdenum, Mo**	**1 000 ± 5 µg/mL**
Silicon, Si	**1 000 ± 7 µg/mL**	**Tin, Sn**	**1 000 ± 5 µg/mL**
Titanium, Ti	**1 000 ± 6 µg/mL**		

Density: 1.033 g/mL (measured at 20 ± 4 °C)

Assay Information:

ANALYTE	METHOD	NIST SRM#	SRM LOT#
B	ICP Assay	3107	190605
B	Calculated		See Sec. 4.2
Mo	ICP Assay	traceable to 3134	U2-MO739068
Si	ICP Assay	Traceable to 3150	S2-SI702546
Sn	ICP Assay	3161a	140917
Ti	ICP Assay	traceable to 3162a	T2-TI725816

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

N/A

6.0 INTENDED USE

6.1 This standard is intended for the calibration of analytical instruments and validation of analytical methods as appropriate. This CRM may be used in connection with EPA Methods 6010, 6020 (all versions), Standard Methods 3120 B and USP <232> / ICH Q3D.

6.2 For products attaining traceability through Inorganic Ventures' Primary Certified Reference Materials (PCRM™) see the Limited License to Use PCRM™ in the Inorganic Ventures Terms and Conditions of Sale, https://www.inorganicventures.com/terms-and-conditions-sale. The Terms and Conditions contain information on the use of materials traceable to PCRM™ certified reference materials. This Limited License agreement is especially pertinent for laboratories accredited under ISO:17034.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

HF Note: This standard should not be prepared or stored in glass.

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

September 06, 2024

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- September 06, 2029

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Joseph Burns
Custom VS Manager



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



Hydrochloric Acid, 36.5-38.0%
BAKER INSTRA-ANALYZED® Reagent
For Trace Metal Analysis

avantor™ | J.T.Baker®

R → 10/13/24
Met dig

M 6/21

Material No.: 9530-33
Batch No.: 0000275677
Manufactured Date: 2020/12/16
Retest Date: 2025/12/15
Revision No: 1

Certificate of Analysis

Test	Specification	Result
ACS - Assay (as HCl) (by acid-base titrn)	36.5 - 38.0 %	37.6
ACS - Color (APHA)	<= 10	5
ACS - Residue after Ignition	<= 3 ppm	1
ACS - Specific Gravity at 60°/60°F	1.185 - 1.192	1.190
ACS - Bromide (Br)	<= 0.005 %	< 0.005
ACS - Extractable Organic Substances	<= 5 ppm	1
ACS - Free Chlorine (as Cl_2)	<= 0.5 ppm	< 0.5
Phosphate (PO_4)	<= 0.05 ppm	< 0.03
Sulfate (SO_4)	<= 0.5 ppm	< 0.3
Sulfite (SO_3)	<= 0.8 ppm	0.3
Ammonium (NH_4)	<= 3 ppm	< 1
Trace Impurities - Arsenic (As)	<= 0.010 ppm	< 0.003
Trace Impurities - Aluminum (Al)	<= 10.0 ppb	< 0.2
Arsenic and Antimony (as As)	<= 5 ppb	< 3
Trace Impurities - Barium (Ba)	<= 1.0 ppb	< 0.2
Trace Impurities - Beryllium (Be)	<= 1.0 ppb	< 0.2
Trace Impurities - Bismuth (Bi)	<= 10.0 ppb	< 1.0
Trace Impurities - Boron (B)	<= 20.0 ppb	< 5.0
Trace Impurities - Cadmium (Cd)	<= 1.0 ppb	< 0.3
Trace Impurities - Calcium (Ca)	<= 50.0 ppb	29.7
Trace Impurities - Chromium (Cr)	<= 1.0 ppb	< 0.4
Trace Impurities - Cobalt (Co)	<= 1.0 ppb	< 0.3
Trace Impurities - Copper (Cu)	<= 1.0 ppb	< 0.1
Trace Impurities - Gallium (Ga)	<= 1.0 ppb	< 0.2


For questions on this Certificate of Analysis please contact Technical Services at 855.282.6867 or +1.610.386.1700
Avantor Performance Materials, LLC
100 Matsonford Rd, Suite 200, Radnor, PA 19087. U.S.A. Phone: 610.386.1700

Material No.: 9530-33
Batch No.: 0000275677

Test	Specification	Result
Trace Impurities - Germanium (Ge)	<= 3.0 ppb	< 2.0
Trace Impurities - Gold (Au)	<= 4.0 ppb	< 0.2
Heavy Metals (as Pb)	<= 100 ppb	< 50
Trace Impurities - Iron (Fe)	<= 15.0 ppb	<1
Trace Impurities - Lead (Pb)	<= 1.0 ppb	< 0.5
Trace Impurities - Lithium (Li)	<= 1.0 ppb	0.2
Trace Impurities - Magnesium (Mg)	<= 10.0 ppb	0.4
Trace Impurities - Manganese (Mn)	<= 1.0 ppb	< 0.4
Trace Impurities - Mercury (Hg)	<= 0.5 ppb	0.1
Trace Impurities - Molybdenum (Mo)	<= 10.0 ppb	< 5.0
Trace Impurities - Nickel (Ni)	<= 4.0 ppb	< 0.3
Trace Impurities - Niobium (Nb)	<= 1.0 ppb	< 0.2
Trace Impurities - Potassium (K)	<= 9.0 ppb	< 2.0
Trace Impurities - Selenium (Se), For Information Only	ppb	1.0
Trace Impurities - Silicon (Si)	<= 100.0 ppb	< 10.0
Trace Impurities - Silver (Ag)	<= 1.0 ppb	< 0.3
Trace Impurities - Sodium (Na)	<= 100.0 ppb	< 5.0
Trace Impurities - Strontium (Sr)	<= 1.0 ppb	< 0.2
Trace Impurities - Tantalum (Ta)	<= 1.0 ppb	< 0.9
Trace Impurities - Thallium (Tl)	<= 5.0 ppb	< 2.0
Trace Impurities - Tin (Sn)	<= 5.0 ppb	< 0.8
Trace Impurities - Titanium (Ti)	<= 1.0 ppb	0.2
Trace Impurities - Vanadium (V)	<= 1.0 ppb	< 0.2
Trace Impurities - Zinc (Zn)	<= 5.0 ppb	0.3
Trace Impurities - Zirconium (Zr)	<= 1.0 ppb	< 0.1

For Laboratory, Research or Manufacturing Use
Product Information (not specifications):
Appearance (clear, fuming liquid)
Meets ACS Specifications

Country of Origin: US
Packaging Site: Phillipsburg Mfg Ctr & DC



Jamie Ethier
Vice President Global Quality

For questions on this Certificate of Analysis please contact Technical Services at 855.282.6867 or +1.610.386.1700
Avantor Performance Materials, LLC
100 Matsonford Rd, Suite 200, Radnor, PA 19087. U.S.A. Phone: 610.386.1700

M6125 Receive -> 11/22/24

CORCO CHEMICAL CORPORATION

Manufacturers of ACS Reagents and Semiconductor Grade Chemicals


Office and Plant
299 Cedar Lane
Fairless Hills, PA 19030

Phone: 215-295-5006
Fax: 215-295-0781

Hydrogen Peroxide 30%, ACS

Reagent Grade

SPECIFICATION	MAXIMUM LIMITS
Appearance	Colorless and free from suspended matter or sediment
Assay	29-32%
Color (APHA)	10
Residue after Evaporation	0.002%
Titratable Acid	0.0006 meq/g
Chloride (Cl)	3 ppm
Nitrate (NO_3)	2 ppm
Phosphate	2 ppm
Sulfate (SO_4)	5 ppm
Ammonium (NH_4)	5 ppm
Heavy Metals (as Pb)	1 ppm
Iron (Fe)	0.5 ppm



Nitric Acid 69%
CMOS

avantor™ | J.T.Baker®

R -> 11/12/24

M6126

Material No.: 9606-03
Batch No.: 24D1062002
Manufactured Date: 2024-03-26
Retest Date: 2029-03-25
Revision No.: 0

Certificate of Analysis

Test	Specification	Result
Assay (HNO_3)	69.0 - 70.0 %	69.7 %
Appearance	Passes Test	Passes Test
Color (APHA)	≤ 10	5
Residue after Ignition	≤ 2 ppm	1 ppm
Chloride (Cl)	≤ 0.08 ppm	< 0.03 ppm
Phosphate (PO_4)	≤ 0.10 ppm	< 0.03 ppm
Sulfate (SO_4)	≤ 0.2 ppm	< 0.2 ppm
Trace Impurities - Aluminum (Al)	≤ 40.0 ppb	< 1.0 ppb
Arsenic and Antimony (as As)	≤ 5.0 ppb	< 2.0 ppb
Trace Impurities - Barium (Ba)	≤ 10.0 ppb	< 1.0 ppb
Trace Impurities - Beryllium (Be)	≤ 10.0 ppb	< 1.0 ppb
Trace Impurities - Bismuth (Bi)	≤ 20.0 ppb	< 10.0 ppb
Trace Impurities - Boron (B)	≤ 10.0 ppb	< 5.0 ppb
Trace Impurities - Cadmium (Cd)	≤ 50 ppb	< 1 ppb
Trace Impurities - Calcium (Ca)	≤ 50.0 ppb	2.3 ppb
Trace Impurities - Chromium (Cr)	≤ 30.0 ppb	< 1.0 ppb
Trace Impurities - Cobalt (Co)	≤ 10.0 ppb	< 1.0 ppb
Trace Impurities - Copper (Cu)	≤ 10.0 ppb	< 1.0 ppb
Trace Impurities - Gallium (Ga)	≤ 10.0 ppb	< 1.0 ppb
Trace Impurities - Germanium (Ge)	≤ 20 ppb	< 10 ppb
Trace Impurities - Gold (Au)	≤ 20 ppb	< 5 ppb
Heavy Metals (as Pb)	≤ 100 ppb	100 ppb
Trace Impurities - Iron (Fe)	≤ 40.0 ppb	< 1.0 ppb
Trace Impurities - Lead (Pb)	≤ 20.0 ppb	< 10.0 ppb
Trace Impurities - Lithium (Li)	≤ 10.0 ppb	< 1.0 ppb
Trace Impurities - Magnesium (Mg)	≤ 20 ppb	< 1 ppb
Trace Impurities - Manganese (Mn)	≤ 10.0 ppb	< 1.0 ppb
Trace Impurities - Nickel (Ni)	≤ 20.0 ppb	< 5.0 ppb

>>> Continued on page 2 >>>

Nitric Acid 69%
CMOS

avantor™ | J.T.Baker®

Material No.: 9606-03
Batch No.: 24D1062002

Test	Specification	Result

For Microelectronic Use

Country of Origin: USA
Packaging Site: Phillipsburg Mfg Ctr & DC

Jamie Croak
Director Quality Operations, Bioscience Production

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

R -> 1/13/25


M 6127

			Lot #	
Part Number:	**58112**	**Solvent:**	24012496	Nitric Acid
Lot Number:	**112124**			
Description:	**Magnesium (Mg)**	2%	40.0 (mL)	Nitric Acid
Expiration Date:	112127			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**10000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Weight shown below was diluted to (mL):	2000.07	0.100	Flask Uncertainty	

Giovanni Esposito

Formulated By:	Giovanni Esposito	112124
Reviewed By:	Pedro L. Rentas	112124

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Magnesium nitrate hexahydrate (Mg)	IN030	MGD052023A1	10000	99.999	0.10	8.51	234.9183	234.9459	**10001.2**	**20.0**	13446-18-9	NA	orl-rat 5440 mg/kg	3131a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	T	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

R->1/13/28

M6128

Part Number:	**58025**	**Solvent:**	**Lot #** 24002546	Nitric Acid
Lot Number:	**101124**			
Description:	**Manganese (Mn)**	2%	80.0 (mL)	Nitric Acid
Expiration Date:	101127			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Weight shown below was diluted to (mL):	4000.2	0.10	Flask Uncertainty	


Giovanni Esposito

Formulated By:	Giovanni Esposito	101124

Pedro Rentas

Reviewed By:	Pedro L. Rentas	101124

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	**Actual Conc. (µg/mL)**	Expanded Uncertainty +/- (µg/mL)	**SDS Information** (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Manganese(II) nitrate hydrate (Mn)	IN031	MNM092020A1	1000	99.999	0.10	20.8	19.2322	19.2344	**1000.1**	**2.0**	15710-66-4	5 mg/m3	orl-rat >300mg/kg	3132



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	T	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com


CERTIFIED WEIGHT REPORT:

R->1/13/25

Part Number:	**58111**		**Lot #**		
Lot Number:	**072424**	**Solvent:**	24002546	Nitric Acid	
Description:	**Sodium (Na)**				
		MG144 2%	80.0 (mL)	Nitric Acid	
Expiration Date:	072427				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**10000**				
NIST Test Number:	6UTB	5E-05	Balance Uncertainty		
Weight shown below was diluted to (mL):	4000.2	0.10	Flask Uncertainty		

Formulated By:	Benson Chan 072424
Reviewed By:	Pedro L. Rentas 072424

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Sodium nitrate (Na)	IN036	NAV012015I1	10000	99.999	0.10	26.9	148.7096	######	**10000.0**	**20.0**	7631-99-4	5 mg/m3	orl-rat 3430 mg/kg	3152a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Sc	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	T	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com


CERTIFIED WEIGHT REPORT:

Part Number:	**58030**	R → 1/13/25	**Solvent:**	**Lot #** 24012496	Nitric Acid
Lot Number:	**121724**				
Description:	**Zinc (Zn)**	M6145	2%	40.0 (mL)	Nitric Acid
Expiration Date:	121727				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**1000**				
NIST Test Number:	6UTB	5E-05 Balance Uncertainty			
Weight shown below was diluted to (mL):	2000.1	0.10 Flask Uncertainty			

Aleah O'Brady

Formulated By:	Aleah O'Brady	121724
Reviewed By:	Pedro L. Rentas	121724

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Zinc nitrate hexahydrate (Zn)	IN016	ZNE032021A1	1000	99.999	0.10	24.3	8.2308	8.2311	**1000.0**	**2.0**	10196-18-6	1 mg/m3	orl-rat 1190mg/kg	3168



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	T
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R: 01/03/24 M5806, M5807

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 58111
Lot Number: 122223
Description: Sodium (Na)

Expiration Date: 122226
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB

Weight shown below was diluted to (mL): 3000.4 0.06 Flask Uncertainty


	Lot #		
Solvent:	24002546	Nitric Acid	
2%	60.0 (mL)	Nitric Acid	

5E-05 Balance Uncertainty

Aleah O'Brady

Formulated By:	Aleah O'Brady	122223
Reviewed By:	Pedro L. Rentas	122223

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Sodium nitrate (Na)	IN036	NAV012015I1	10000	99.999	0.10	26.9	111.5406	111.5479	**10000.7**	**20.0**	7631-99-4	5 mg/m3	orl-rat 3430 mg/kg	3152a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	T	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:



* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com


R: 01/03/24 M5802, M5803

CERTIFIED WEIGHT REPORT:

		Lot #	Solvent:	
Part Number:	**57051**	24002546	Nitric Acid	
Lot Number:	**120523**			
Description:	**Antimony (Sb)**			
		2.0%	60.0 (mL)	Nitric Acid
Expiration Date:	120526			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Volume shown below was diluted to (mL):	3000.41	0.058	Flask Uncertainty	

Formulated By:	Lawrence Barry	120523
Reviewed By:	Pedro L. Rentas	120523

Compound	Part Number	Lot Number	Dilution Factor	Initial Vol. (mL)	Uncertainty Pipette (mL)	Nominal Conc. (µg/mL)	Initial Conc. (µg/mL)	Final Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Antimony (Sb)	58151	100923	0.1000	300.0	0.084	1000	10001.4	**1000.0**	2.1	7440-36-0	0.5 mg/m3	orl-rat 7000 mg/kg	3102a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	T	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M6030

R: 8/5/24


ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number:	**57047**		**Lot #**		
Lot Number:	**122823**	**Solvent:**	24002546	Nitric Acid	
Description:	**Silver (Ag)**	2%	80.0 (mL)	Nitric Acid	
Expiration Date:	122826				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**1000**				
NIST Test Number:	6UTB	5E-05	Balance Uncertainty		
Weight shown below was diluted to (mL):	4000.30	0.058	Flask Uncertainty		

Formulated By:	Benson Chan	122823
Reviewed By:	Pedro L. Rentas	122823

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Silver nitrate (Ag)	IN035	J0612AGA1	1000.0	99.9999	0.10	63.7	6.27992	6.27998	**1000.0**	**2.0**	7761-88-8	10 ug/m3	NA	3151



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	T	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R: 10/18/24

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

MG146

		Lot #	Solvent:	
Part Number:	**57051**	24002546	Nitric Acid	
Lot Number:	**071724**			
Description:	**Antimony (Sb)**			
		2.0%	40.0 (mL)	Nitric Acid
Expiration Date:	071727			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Volume shown below was diluted to (mL):	2000.26	0.058	Flask Uncertainty	


Giovanni Esposito

Formulated By:	Giovanni Esposito	071724

Pedro Rentas

Reviewed By:	Pedro L. Rentas	071724

Compound	Part Number	Lot Number	Dilution Factor	Initial Vol. (mL)	Uncertainty Pipette (mL)	Nominal Conc. (µg/mL)	Initial Conc. (µg/mL)	**Final Conc. (µg/mL)**	Expanded Uncertainty +/- (µg/mL)	**SDS Information** (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Antimony (Sb)	58151	060324	0.1000	200.0	0.084	1000	10001.4	**1000.0**	**2.2**	7440-36-0	0.5 mg/m3	orl-rat 7000 mg/kg	3102a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	T	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

QATS LABORATORY INORGANIC REFERENCE MATERIAL INITIAL CALIBRATION VERIFICATION SOLUTIONS (ICV1, ICV5, AND ICV6)

M6147

NOTE: These instructions are for advisory purposes only. If any apparent conflict exists between these instructions and the analytical protocol or your contract, disregard these instructions.

APPLICATION: For use with the CLP SFAM01.0 SOW and revisions.

CAUTION: Read instructions carefully before opening bottle(s) and proceeding with the analyses.

Contains Metals in Dilute Acidic or Cyanide in Basic Aqueous Solutions
HAZARDOUS MATERIAL

Safety Data Sheets Available Upon Request

(A) *SAMPLE DESCRIPTION*

Enclosed is a set of one (1) or more Aqueous Inorganic Reference Materials containing various analyte concentrations. ICV1 and ICV5 are in a matrix of dilute nitric acid. ICV6 is in a matrix of dilute basic solution. **For the reference material source in reporting ICVs use "USEPA". For the reference material lot number for the ICV1, ICV5, and ICV6 solutions use "ICV1-1014", "ICV5-0415", and "ICV6-0400", respectively.**

(B) *BREAKAGE OR MISSING ITEMS*

Check the contents of the shipment carefully for any broken, leaking, or missing items. Check that the seal is intact on each bottle. Refer to the enclosed chain of custody record. Report any problems to Mr. Keith Strout, APTIM Federal Services, LLC, at (702) 895-8722. If requested, return the chain-of-custody record with appropriate annotations and signatures to the address provided below.

QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
APTIM Federal Services, LLC
2700 Chandler Avenue - Building C
Las Vegas, NV 89120

(C) *ANALYSIS OF SAMPLES*

The Initial Calibration Verification Solutions (ICVs) are to be used to evaluate the accuracy of the initial calibrations of ICP, AA, and Cyanide colorimetric instruments, and are to be used with the CLP SOWs and revisions. The values for each element in the ICVs are listed below in µg/L (ppb) for the resulting solution(s) after the dilution of the concentrate(s) according to the following instructions. Use Class 'A' glassware to prepare the solution(s).

ICV1-1014 For ICP-AES analysis, use a 10-fold dilution by pipetting 10 mL of the ICV1 concentrate into a 100 mL volumetric flask and dilute to volume with 2% (v/v) nitric acid.

The Quality Assurance Technical Support (QATS) contract is operated by APTIM Federal Services, LLC.

Instructions for QATS Reference Material: *Inorganic ICV Solutions*

ICV1-1014 For ICP-MS analysis, use a 50-fold dilution by pipetting 2 mL of the ICV1 concentrate into a 100 mL volumetric flask and dilute to volume with 1% (v/v) nitric acid.

ICV5-0415 For the cold vapor analysis of mercury by AA, use a 100-fold dilution by pipetting 1 mL of the ICV5 concentrate into a 100 mL volumetric flask and dilute to volume with 2% (v/v) nitric acid. The ICV5 concentrate is prepared in 0.05% (w/v) $K_2Cr_2O_7$ and 5% (v/v) nitric acid.

ICV6-0400 For the analysis of cyanide, use a 100-fold dilution by pipetting 1 mL of the ICV6 concentrate into a 100 mL volumetric flask and dilute to volume with Type II water. Distill this solution along with the samples before analysis. The cyanide concentrate is prepared from $K_3Fe(CN)_6$, Type II water, and 0.1 % sodium hydroxide, and will decompose rapidly if exposed to light.

NOTE: USE TYPE II WATER AND HIGH-PURITY ACIDS FOR ALL DILUTIONS.

(D) *CERTIFIED CONCENTRATIONS OF QATS ICV1, ICV5, AND ICV6 SOLUTIONS*

ICV1-1014		
Element	**Concentration (µg/L) (after 10-fold dilution)**	**Concentration (µg/L) (after 50-fold dilution)**
Al	2500	500
Sb	1000	200
As	1000	200
Ba	520	100
Be	510	100
Cd	510	100
Ca	10000	2000
Cr	520	100
Co	520	100
Cu	510	100
Fe	10000	2000
Pb	1000	200
Mg	6000	1200
Mn	520	100
Ni	530	110
K	9900	2000
Se	1000	200
Ag	250	50
Na	10000	2000
Tl	1000	210
V	500	100
Zn	1000	200

ICV5-0415		ICV6-0400	
Element	**Concentration (µg/L) (after 100-fold dilution)**	**Analyte**	**Concentration (µg/L) (after 100-fold dilution)**
Hg	4.0	CN^-	99

APTIM

QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
"An ISO 9001:2015 Certified Program"

M6148

Instructions for QATS Reference Material: *ICP-AES ICS*

QATS LABORATORY INORGANIC REFERENCE MATERIAL INTERFERENCE CHECK SAMPLE SET FOR ICP-AES (ICSA WITH ICSB)

NOTE: These instructions are for advisory purposes only. If any apparent conflict exists between these instructions and the analytical protocol or your contract, disregard these instructions.

APPLICATION: For use with the CLP SFAM01.0 SOW and revisions.

CAUTION: Read instructions carefully before opening bottle(s) and proceeding with the analyses.

Contains Heavy Metals
HAZARDOUS MATERIAL

Safety Data Sheets
Available Upon Request

(A) *SAMPLE DESCRIPTION*

Enclosed is a set of one (1) or more bottles of Aqueous Reference Material, each composed of metals at various concentrations and prepared with nitrate salts and oxy-acids of the respective elements in a 5% nitric acid matrix. **For the reference material source in reporting ICSA and ICSAB mixture use "USEPA". For the reference material lot number for the ICSA use "ICSA-1211" and for the ICSAB mixture use "ICSA-1211+ICSB-0710".**

CAUTION: The bottle(s) should be protected from light during storage to ensure the stability of silver which is contained in the ICSB solution. The bottle(s) should be stored at room temperature. **Do not allow the solution(s) to freeze.**

(B) *BREAKAGE OR MISSING ITEMS*

Check the contents of the shipment carefully for any broken, leaking, or missing items. Check that the seal is intact on each bottle. Refer to the enclosed chain of custody record. Report any problems to Mr. Keith Strout, APTIM Federal Services, LLC, at (702) 895-8722. If requested, return the chain-of-custody record with appropriate annotations and signatures to the address provided below.

QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
APTIM Federal Services, LLC
2700 Chandler Avenue - Building C
Las Vegas, NV 89120

(C) *ANALYSIS OF SAMPLES*

The interference check sample set is to be used to verify inter-element and background correction factors of inductively-coupled plasma (ICP) spectrometers. This reference material set consists of two (2) concentrated solutions. The ICSA solution contains the four (4) interferent elements: Al, Ca, Fe, and Mg. The ICSB solution contains the analytes: Ag, As, Sb, Ba, Be,

The Quality Assurance Technical Support (QATS) contract is operated by APTIM Federal Services, LLC.

Cd, Co, Cr, Cu, Mn, Ni, Pb, Tl, Se, V, and Zn. This instruction sheet provides the nominal values for ICP-AES Part A and Part B target analytes when diluted as directed.

Using Class "A" glassware, preparation and analysis must be performed according to the following instructions:

ICSA-1211, Interferents: Pipet 10 mL of the ICSA solution into a 100 mL volumetric flask and dilute to volume with 2% v/v HNO_3. Analyze this ICSA solution by ICP-AES.

ICSB-0710, Analytes, mixed with ICSA-1211, Interferents: Pipet 10 mL of the ICSA solution and 10 mL of the ICSB solution into a 100 mL volumetric flask and dilute to volume with 2% v/v HNO_3. Analyze this ICSAB solution by ICP-AES.

(D) *"CERTIFIED VALUE" CONCENTRATIONS OF QATS ICP-AES ICS SOLUTION(S)*

The "Certified Value" concentrations of the elements, listed in Table 1 below, were derived from statistically pooled analysis results from the following sources, if available: QATS Laboratory, CLP laboratories, Quarterly Blind (QB)/Proficiency Testing (PT) events, CLP pre-award events, and external referee laboratories.

Table 1. "CERTIFIED VALUES" FOR INTERFERENCE CHECK SAMPLE ICP-AES ICSA-1211, AND ICSA-1211 MIXED WITH ICSB-0710

Element	CRQL	Part A (µg/L)	Low Limit (µg/L)	High Limit (µg/L)	Part A +Part B (µg/L)	Low Limit (µg/L)	High Limit (µg/L)
Al	200	255000	216000	294000	247000	209000	285000
Sb	60	(0.0)	-60.0	60.0	618	525	711
As	10	(0.0)	-10.0	10.0	104	88.4	120
Ba	200	(6.0)	-194	206	(537)	337	737
Be	5.0	(0.0)	-5.0	5.0	495	420	570
Cd	5.0	(1.0)	-4.0	6.0	972	826	1120
Ca	5000	245000	208000	282000	235000	199000	271000
Cr	10	(52.0)	42.0	62.0	542	460	624
Co	50	(0.0)	-50.0	50.0	476	404	548
Cu	25	(2.0)	-23.0	27.0	511	434	588
Fe	100	101000	85600	116500	99300	84400	114500
Pb	10	(0.0)	-10.0	10.0	(49.0)	39.0	59.0
Mg	5000	255000	216000	294000	248000	210000	286000
Mn	15	(7.0)	-8.0	22.0	507	430	584
Ni	40	(2.0)	-38.0	42.0	954	810	1100
Se	35	(0.0)	-35.0	35.0	(46.0)	11.0	81.0
Ag	10	(0.0)	-10.0	10.0	201	170	232
Tl	25	(0.0)	-25.0	25.0	(108)	83.0	133
V	50	(0.0)	-50.0	50.0	491	417	565
Zn	60	(0.0)	-60.0	60.0	952	809	1095

The acceptance ranges for all analytes in parentheses in the above table were determined using the listed certified value ± 1 times the associated CLP SOW CRQL. The acceptance ranges for all other analytes were determined using the certified value ± 15 percent of the listed certified value.

QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
"An ISO 9001:2015 Certified Program"

M 6149

APTIM

Instructions for QATS Reference Material: *ICP-AES ICS*

QATS LABORATORY INORGANIC REFERENCE MATERIAL INTERFERENCE CHECK SAMPLE SET FOR ICP-AES (ICSA WITH ICSB)

NOTE: These instructions are for advisory purposes only. If any apparent conflict exists between these instructions and the analytical protocol or your contract, disregard these instructions.

APPLICATION: For use with the CLP SFAM01.0 SOW and revisions.

CAUTION: Read instructions carefully before opening bottle(s) and proceeding with the analyses.

Contains Heavy Metals
HAZARDOUS MATERIAL

Safety Data Sheets
Available Upon Request

(A) *SAMPLE DESCRIPTION*

Enclosed is a set of one (1) or more bottles of Aqueous Reference Material, each composed of metals at various concentrations and prepared with nitrate salts and oxy-acids of the respective elements in a 5% nitric acid matrix. **For the reference material source in reporting ICSA and ICSAB mixture use "USEPA". For the reference material lot number for the ICSA use "ICSA-1211" and for the ICSAB mixture use "ICSA-1211+ICSB-0710".**

CAUTION: The bottle(s) should be protected from light during storage to ensure the stability of silver which is contained in the ICSB solution. The bottle(s) should be stored at room temperature. **Do not allow the solution(s) to freeze.**

(B) *BREAKAGE OR MISSING ITEMS*

Check the contents of the shipment carefully for any broken, leaking, or missing items. Check that the seal is intact on each bottle. Refer to the enclosed chain of custody record. Report any problems to Mr. Keith Strout, APTIM Federal Services, LLC, at (702) 895-8722. If requested, return the chain-of-custody record with appropriate annotations and signatures to the address provided below.

QUALITY ASSURANCE TECHNICAL SUPPORT LABORATORY
APTIM Federal Services, LLC
2700 Chandler Avenue - Building C
Las Vegas, NV 89120

(C) *ANALYSIS OF SAMPLES*

The interference check sample set is to be used to verify inter-element and background correction factors of inductively-coupled plasma (ICP) spectrometers. This reference material set consists of two (2) concentrated solutions. The ICSA solution contains the four (4) interferent elements: Al, Ca, Fe, and Mg. The ICSB solution contains the analytes: Ag, As, Sb, Ba, Be,

The Quality Assurance Technical Support (QATS) contract is operated by APTIM Federal Services, LLC.

Cd, Co, Cr, Cu, Mn, Ni, Pb, Tl, Se, V, and Zn. This instruction sheet provides the nominal values for ICP-AES Part A and Part B target analytes when diluted as directed.

Using Class "A" glassware, preparation and analysis must be performed according to the following instructions:

ICSA-1211, Interferents: Pipet 10 mL of the ICSA solution into a 100 mL volumetric flask and dilute to volume with 2% v/v HNO_3. Analyze this ICSA solution by ICP-AES.

ICSB-0710, Analytes, mixed with ICSA-1211, Interferents: Pipet 10 mL of the ICSA solution and 10 mL of the ICSB solution into a 100 mL volumetric flask and dilute to volume with 2% v/v HNO_3. Analyze this ICSAB solution by ICP-AES.

(D) *"CERTIFIED VALUE" CONCENTRATIONS OF QATS ICP-AES ICS SOLUTION(S)*

The "Certified Value" concentrations of the elements, listed in Table 1 below, were derived from statistically pooled analysis results from the following sources, if available: QATS Laboratory, CLP laboratories, Quarterly Blind (QB)/Proficiency Testing (PT) events, CLP pre-award events, and external referee laboratories.

Table 1. "CERTIFIED VALUES" FOR INTERFERENCE CHECK SAMPLE ICP-AES ICSA-1211, AND ICSA-1211 MIXED WITH ICSB-0710

Element	CRQL	Part A (µg/L)	Low Limit (µg/L)	High Limit (µg/L)	Part A +Part B (µg/L)	Low Limit (µg/L)	High Limit (µg/L)
Al	200	255000	216000	294000	247000	209000	285000
Sb	60	(0.0)	-60.0	60.0	618	525	711
As	10	(0.0)	-10.0	10.0	104	88.4	120
Ba	200	(6.0)	-194	206	(537)	337	737
Be	5.0	(0.0)	-5.0	5.0	495	420	570
Cd	5.0	(1.0)	-4.0	6.0	972	826	1120
Ca	5000	245000	208000	282000	235000	199000	271000
Cr	10	(52.0)	42.0	62.0	542	460	624
Co	50	(0.0)	-50.0	50.0	476	404	548
Cu	25	(2.0)	-23.0	27.0	511	434	588
Fe	100	101000	85600	116500	99300	84400	114500
Pb	10	(0.0)	-10.0	10.0	(49.0)	39.0	59.0
Mg	5000	255000	216000	294000	248000	210000	286000
Mn	15	(7.0)	-8.0	22.0	507	430	584
Ni	40	(2.0)	-38.0	42.0	954	810	1100
Se	35	(0.0)	-35.0	35.0	(46.0)	11.0	81.0
Ag	10	(0.0)	-10.0	10.0	201	170	232
Tl	25	(0.0)	-25.0	25.0	(108)	83.0	133
V	50	(0.0)	-50.0	50.0	491	417	565
Zn	60	(0.0)	-60.0	60.0	952	809	1095

The acceptance ranges for all analytes in parentheses in the above table were determined using the listed certified value ± 1 times the associated CLP SOW CRQL. The acceptance ranges for all other analytes were determined using the certified value ± 15 percent of the listed certified value.

INORGANIC VENTURES™
Refine your results. Redefine your industry.

Certificate of Analysis

R: 8/5/24 M6019

300 Technology Drive
Christiansburg, VA 24073 USA
inorganicventures.com

P: 800-669-6799/540-585-3030
F: 540-585-3012
info@inorganicventures.com

1.0 ACCREDITATION / REGISTRATION

INORGANIC VENTURES is accredited to ISO 17034, "General Requirements for the Competence of Reference Material Producers" and ISO/IEC 17025, "General Requirements for the Competence of Testing and Calibration Laboratories". Inorganic Ventures is also an ISO 9001 registered manufacturer (QSR Certificate Number QSR-1034).

ACCREDITED Testing Laboratory Certificate 888.01
ACCREDITED Reference Material Producer Certificate 888.02

2.0 PRODUCT DESCRIPTION

Product Code:	Single Analyte Custom Grade Solution
Catalog Number:	CGSR1
Lot Number:	U2-SR730227
Matrix:	0.1% (v/v) HNO3
Value / Analyte(s):	1 000 µg/mL ea: Strontium
Starting Material:	SrCO3
Starting Material Lot#:	M2-2192
Starting Material Purity:	99.9993%

3.0 CERTIFIED VALUES AND UNCERTAINTIES

Certified Value: 1001 ± 3 µg/mL

Density: 1.000 g/mL (measured at 20 ± 4 °C)

Assay Information:

Assay Method #1 **998 ± 4 µg/mL**
ICP Assay NIST SRM Traceable to 3153a Lot Number: K2-SR650985

Assay Method #2 **1001 ± 3 µg/mL**
EDTA NIST SRM 928 Lot Number: 928

Assay Method #3 **1001 ± 2 µg/mL**
Calculated NIST SRM Lot Number: See Sec. 4.2

- The Calculated Value is a value calculated from the weight of a starting material that has been certified directly vs. a National Institute of Standards and Technology (NIST) SRM/RM. See Sec 4.2 for balance traceability.

The following equations are used in the calculation of the certified value and the uncertainty. Reported uncertainties represent expanded uncertainties expressed at approximately the 95% confidence level using a coverage factor of k = 2.

Characterization of CRM/RM by Two or More Methods

Certified Value, $X_{CRM/RM}$, where two or more methods of characterization are used is the weighted mean of the results:

$X_{CRM/RM} = \Sigma(w_i)(X_i)$

X_i = mean of Assay Method i with standard uncertainty $u_{char\ i}$

w_i = the weighting factors for each method calculated using the inverse square of the variance:

$w_i = (1/u_{char\ i})^2 / (\Sigma(1/(u_{char\ i})^2)$

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char} = [\Sigma((w_i)^2\,(u_{char\ i})^2)]^{½}$ where $u_{char\ i}$ are the errors from each characterization method

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

Characterization of CRM/RM by One Method

Certified Value, $X_{CRM/RM}$, where one method of characterization is used is the mean of individual results:

$X_{CRM/RM} = (X_a)\,(u_{char\ a})$

X_a = mean of Assay Method A with

$u_{char\ a}$ = the standard uncertainty of characterization Method A

CRM/RM Expanded Uncertainty (±) = $U_{CRM/RM} = k\,(u^2_{char\ a} + u^2_{bb} + u^2_{lts} + u^2_{ts})^{½}$

k = coverage factor = 2

$u_{char\ a}$ = the errors from characterization

u_{bb} = bottle to bottle homogeneity standard uncertainty

u_{lts} = long term stability standard uncertainty (storage)

u_{ts} = transport stability standard uncertainty

4.0 TRACEABILITY TO NIST

- This product is traceable to NIST via an unbroken chain of comparisons. The uncertainties for each certified value are reported, taking into account the SRM/RM uncertainty error and the measurement, weighing and volume dilution errors. In rare cases where no NIST SRM/RM are available, the term 'in-house std.' is specified.

4.1 Thermometer Calibration

- All thermometers are NIST traceable through thermometers that are calibrated by an accredited calibration laboratory.

4.2 Balance Calibration

- All analytical balances are calibrated by an accredited calibration laboratory and procedure. The weights used for testing are annually compared to master weights and are traceable to NIST.

4.3 Glassware Calibration

- An in-house procedure is used to calibrate all Class A glassware used in the manufacturing and quality control of CRM/RMs.

5.0 TRACE METALLIC IMPURITIES (TMI) DETERMINED BY ICP-MS AND ICP-OES (µg/mL)

CRM/RMs are tested for trace metallic impurities by Axial ICP-OES and ICP-MS. The result from the most sensitive method for each element, is reported below. Solutions tested by ICP-MS were analyzed in an ULPA-Filtered Clean Room. An ULPA-Filter is 99.9985% efficient for the removal of particles down to 0.3 µm.

M	Ag	<	0.001980	M	Eu	<	0.000495	O	Na		0.000200	M	Se	<	0.013862	O	Zn		0.000143
O	Al		0.000370	O	Fe		0.000410	M	Nb	<	0.000495	i	Si	<		M	Zr	<	0.000495
M	As	<	0.000495	M	Ga	<	0.000495	M	Nd	<	0.000495	M	Sm	<	0.000495				
M	Au	<	0.000989	M	Gd	<	0.000495	O	Ni	<	0.007631	M	Sn	<	0.000990				
M	B	<	0.039606	M	Ge	<	0.000495	M	Os	<	0.000494	s	Sr	<					
M	Ba		0.006486	M	Hf	<	0.000495	i	P	<		M	Ta	<	0.000495				
M	Be	<	0.000990	M	Hg	<	0.000989	M	Pb	<	0.002970	M	Tb	<	0.000495				
M	Bi	<	0.000495	M	Ho	<	0.000495	M	Pd	<	0.003957	M	Te	<	0.027724				
O	Ca		0.004255	M	In	<	0.000495	M	Pr	<	0.000495	M	Th	<	0.000990				
M	Cd		0.001339	M	Ir	<	0.000494	M	Pt	<	0.002970	M	Ti	<	0.005940				
M	Ce	<	0.004950	O	K	<	0.008184	M	Rb	<	0.002970	M	Tl	<	0.000495				
M	Co	<	0.000495	M	La	<	0.000495	M	Re	<	0.000495	M	Tm	<	0.000495				
O	Cr	<	0.003207	O	Li	<	0.000884	O	Rh	<	0.012829	M	U	<	0.001485				
M	Cs	<	0.000990	M	Lu	<	0.002970	M	Ru	<	0.000989	M	V	<	0.001980				
M	Cu		0.000099	O	Mg		0.000064	i	S	<		M	W	<	0.003960				
M	Dy	<	0.000495	O	Mn		0.000066	M	Sb	<	0.014852	O	Y	<	0.000995				
M	Er	<	0.000495	M	Mo	<	0.001980	M	Sc	<	0.001980	M	Yb	<	0.000495				

M - Checked by ICP-MS O - Checked by ICP-OES i - Spectral Interference
n - Not Checked For s - Solution Standard Element

6.0 INTENDED USE

6.1 This standard is intended for the calibration of analytical instruments and validation of analytical methods as appropriate. This CRM may be used in connection with EPA Methods 6010, 6020 (all versions), Standard Methods 3120 B and USP <232> / ICH Q3D.

6.2 For products attaining traceability through Inorganic Ventures' Primary Certified Reference Materials (PCRM™) see the Limited License to Use PCRM™ in the Inorganic Ventures Terms and Conditions of Sale, https://www.inorganicventures.com/terms-and-conditions-sale. The Terms and Conditions contain information on the use of materials traceable to PCRM™ certified reference materials. This Limited License agreement is especially pertinent for laboratories accredited under ISO:17034.

7.0 INSTRUCTIONS FOR THE CORRECT USE OF THIS REFERENCE MATERIAL

7.1 Storage and Handling Recommendations

- Store between approximately 4° - 30° C while in sealed TCT bag.

- While stored in the sealed TCT bag, transpiration of this CRM/RM is negligible. After opening the sealed TCT bag transpiration of the CRM/RM will occur, resulting in a gradual increase in the analyte concentration(s). It is the responsibility of the user to account for this effect. When the bottle is weighed both before and after being placed in storage, the mass difference observed will be a measure of transpiration mass loss.

- After opening the sealed TCT bag, keep cap tightly sealed when not in use and store between 4° - 24° C to minimize the effects of transpiration. Use at 20° ± 4° C to minimize volumetric dilution error when using the reported density. Do not pipette from the container. Do not return removed aliquots to container.

- For more information, visit **www.inorganicventures.com/TCT**

Atomic Weight; Valence; Coordination Number; Chemical Form in Solution - 87.62 +2 6 $Sr(H_2O)_6^{+2}$

Chemical Compatibility - Soluble in HCl, and HNO_3. Avoid H_2SO_4, HF and neutral to basic media. Stable with most metals and inorganic anions forming insoluble silicate, carbonate, hydroxide, oxide, fluoride, sulfate, oxalate, chromate, arsenate and tungstate in neutral aqueous media.

Stability - 2-100 ppb levels stable for months in 1% HNO_3 / LDPE container. 1-10,000 ppm solutions chemically stable for years in 1 - 3.5% HNO_3 / LDPE container.

Sr Containing Samples (Preparation and Solution) -Metal (Best dissolved in diluted HNO_3); Ores (Carbonate fusion in Pt0 followed by HCl dissolution); Organic Matrices (Dry ash and dissolution in dilute HCl).

Atomic Spectroscopic Information (ICP-OES D.L.s are given as radial/axial view):

Technique/Line	**Estimated D.L.**	**Order**	**Interferences** (underlined indicates severe)
ICP-MS 88 amu	1200 ppt	N/A	72Ge16O, 176Yb+2, 176Lu+2 , 176Hf+2
ICP-OES 407.771 nm	0.0004 / 0.00006 µg/mL	1	U, Ce
ICP-OES 421.552 nm	0.0008 / 0.00004 µg/mL	1	Rb
ICP-OES 460.733 nm	0.07 / 0.003 µg/mL	1	Ce

8.0 HAZARDOUS INFORMATION

- Please refer to the Safety Data Sheet for information regarding this CRM/RM.

9.0 HOMOGENEITY

- This solution was mixed according to an in-house procedure and is guaranteed to be homogeneous. Homogeneity data indicate that the end user should take a minimum sample size of 0.2 mL to assure homogeneity.

10.0 QUALITY STANDARD DOCUMENTATION

10.1 ISO 9001 Quality Management System Registration

- QSR Certificate Number QSR-1034

10.2 ISO/IEC 17025 "General Requirements for the Competence of Testing and Calibration Laboratories"

- Chemical Testing - Accredited / A2LA Certificate Number 883.01

10.3 ISO 17034 "General Requirements for the Competence of Reference Material Producers"

- Reference Material Producer - Accredited / A2LA Certificate Number 883.02

Inorganic Ventures, 300 Technology Drive, Christiansburg, Va. 24073, USA; Telephone: 800.669.6799; 540.585.3030, Fax: 540.585.3012; inorganicventures.com; info@inorganicventures.com

11.0 CERTIFICATION, LOT EXPIRATION AND PERIOD OF VALIDITY

11.1 Certification Issue Date

March 03, 2023

- The certification is valid within the measurement uncertainty specified provided the CRM/RM is stored and handled in accordance with instructions given in Sec 7.1. This certification is nullified if instructions in Sec 7.1 are not followed or if the CRM/RM is damaged, contaminated, or otherwise modified.

11.2 Lot Expiration Date

- **March 03, 2028**

- The date after which this CRM/RM should not be used.

- The lot expiration date reflects the period of time that the stability of a CRM/RM can be supported by long term stability studies conducted on properly stored and handled CRM/RMs. Lot expiration is limited primarily by transpiration (loss of water from the solution) and infrequently by chemical stability.

11.3 Period of Validity

- Sealed TCT Bag Open Date: _____

- This CRM/RM should not be used longer than one year (or six months in the case of a 30 mL bottle) from the date of opening the aluminized bag or after the date given in Sec. 11.2, whichever comes first. This is contingent upon the CRM/RM being stored and handled in accordance with the instructions given in Sec. 7.1.

12.0 NAMES AND SIGNATURES OF CERTIFYING OFFICERS

Certificate Approved By:

Thomas Kozikowski
Manager, Quality Control



Certifying Officer:

Paul Gaines
Chairman / Senior Technical Director



Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R: 03/16/23 M5473, M5474, M5475, M5476

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

CERTIFIED WEIGHT REPORT:

Part Number: 56138
Lot Number: 082922
Description: Strontium (Sr)


Expiration Date: 082925
Recommended Storage: Ambient (20 °C)
Nominal Concentration (µg/mL): 10000
NIST Test Number: 6UTB
Weight shown below was diluted to (mL): 1000.12

	Lot #		
Solvent:	20510011	Nitric Acid	
2%	20.0 (mL)	Nitric Acid	

5E-05 Balance Uncertainty
0.058 Flask Uncertainty

Formulated By:	Lawrence Barry	082922
Reviewed By:	Pedro L. Rentas	082922

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Strontium nitrate (Sr)	IN017	SRZ022018A1	10000	99.997	0.10	41.2	24.2756	24.2758	**10000.1**	**20.0**	10042-76-9	NA	orl-rat >2000mg/kg	3153a



Instrumental Analysis by Inductively Coupled Plasma Mass Spectroscopy (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	T	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T)= Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

R ! 8/5/24

M6023

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com


CERTIFIED WEIGHT REPORT:

Part Number:	**57081**		**Lot #**		
Lot Number:	**062724**	**Solvent:**	24002546	Nitric Acid	
Description:	**Thallium (Tl)**				
		2%	40.0 (mL)	Nitric Acid	
Expiration Date:	062727				
Recommended Storage:	Ambient (20 °C)				
Nominal Concentration (µg/mL):	**1000**				
NIST Test Number:	6UTB	5E-05	Balance Uncertainty		
Weight shown below was diluted to (mL):	2000.1	0.10	Flask Uncertainty		

Aleah O'Brady

Formulated By:	Aleah O'Brady	062724
Reviewed By:	Pedro L. Rentas	062724

Compound	RM#	Lot Number	Nominal Conc. (µg/mL)	Purity (%)	Uncertainty Purity (%)	Assay (%)	Target Weight (g)	Actual Weight (g)	Actual Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Thallium nitrate (Tl)	IN037	BCCF4399	1000	99.999	0.10	77.0	2.5975	2.5977	**1000.1**	**2.0**	10102-45-1	0.1 mg/m3	orl-mus 15mg/kg	3158



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)																	
Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	T	V	<0.02
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

Certified by:

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Absolute Standards, Inc.
800-368-1131
www.absolutestandards.com

Certified Reference Material CRM

M6021

ANAB ISO 17034 Accredited
AR-1539 Certificate Number
https://Absolutestandards.com

Bc. 8/5/24

CERTIFIED WEIGHT REPORT:

		Lot #	Solvent:	
Part Number:	**57023**			
Lot Number:	**062424**	24002546	Nitric Acid	
Description:	**Vanadium (V)**			
		2.0%	40.0 (mL)	Nitric Acid
Expiration Date:	062427			
Recommended Storage:	Ambient (20 °C)			
Nominal Concentration (µg/mL):	**1000**			
NIST Test Number:	6UTB	5E-05	Balance Uncertainty	
Volume shown below was diluted to (mL):	2000.3	0.06	Flask Uncertainty	


Aleah O'Brady

Formulated By:	Aleah O'Brady	062424

Pedro Rentas

Reviewed By:	Pedro L. Rentas	062424

Compound	Part Number	Lot Number	Dilution Factor	Initial Vol. (mL)	Uncertainty Pipette (mL)	Nominal Conc. (µg/mL)	Initial Conc. (µg/mL)	Final Conc. (µg/mL)	Expanded Uncertainty +/- (µg/mL)	SDS Information (Solvent Safety Info. On Attached pg.) CAS#	OSHA PEL (TWA)	LD50	NIST SRM
1. Ammonium metavanadate (V)	58123	021224	0.1000	200.0	0.084	1000	10000.3	**1000.0**	**2.2**	7803-55-6	0.05 mg/m3	orl-rat 58.1mg/kg	3165



Instrumental Analysis by Inductively Coupled Plasma Mass Spectrometry (ICP-MS):

Trace Metals Verification by ICP-MS (µg/mL)

Al	<0.02	Cd	<0.02	Dy	<0.02	Hf	<0.02	Li	<0.02	Ni	<0.02	Pr	<0.02	Se	<0.2	Tb	<0.02	W	<0.02
Sb	<0.02	Ca	<0.2	Er	<0.02	Ho	<0.02	Lu	<0.02	Nb	<0.02	Re	<0.02	Si	<0.02	Te	<0.02	U	<0.02
As	<0.2	Ce	<0.02	Eu	<0.02	In	<0.02	Mg	<0.01	Os	<0.02	Rh	<0.02	Ag	<0.02	Tl	<0.02	V	T
Ba	<0.02	Cs	<0.02	Gd	<0.02	Ir	<0.02	Mn	<0.02	Pd	<0.02	Rb	<0.02	Na	<0.2	Th	<0.02	Yb	<0.02
Be	<0.01	Cr	<0.02	Ga	<0.02	Fe	<0.2	Hg	<0.2	P	<0.02	Ru	<0.02	Sr	<0.02	Tm	<0.02	Y	<0.02
Bi	<0.02	Co	<0.02	Ge	<0.02	La	<0.02	Mo	<0.02	Pt	<0.02	Sm	<0.02	S	<0.02	Sn	<0.02	Zn	<0.02
B	<0.02	Cu	<0.02	Au	<0.02	Pb	<0.02	Nd	<0.02	K	<0.2	Sc	<0.02	Ta	<0.02	Ti	<0.02	Zr	<0.02

(T) = Target analyte

Physical Characterization:

Certified by:

Homogeneity: No heterogeneity was observed in the preparation of this standard.

* The certified value is the concentration calculated from gravimetric and volumetric measurements unless otherwise stated.
* Purified acids, 18.2 megohm deionized water, calibrated Class A glassware and the highest purity raw materials are used in the preparation of all standards.
* All standard containers are meticulously cleaned prior to use.
* Standards are prepared gravimetrically using balances that are calibrated with weights traceable to NIST (see above).
* Standards are certifed (+/-) 0.5% of the stated value, unless otherwise stated.
* All Standards should be stored with caps tight and under appropriate laboratory conditions.
* Uncertainty Reference: Taylor, B.N. and Kuyat, C.E., "Guidelines for Evaluating and Expressing the Uncertainty of NIST Measurement Result," NIST Technical Note 1297, U.S. Government Printing Office, Washington, D.C. (1994).

Alliance TECHNICAL GROUP

Soil/Sludge Metals Preparation Sheet

PB166229

SOP ID : M3050B-Digestion-20, MSFAM01.1-Trace Metals-2

SDG No : MC0AZ0,ME2946

Matrix : SOIL

Pippete ID: ICP A

Balance ID : M SC-2

Filter paper ID : N/A

pH Strip ID : N/A

Hood ID : #3

Block ID: 1. HOT BLOCK #5 2. N/A

Start Digest Date: 01/24/2025 **Time :** 10:40 **Temp :** 96 °C

End Digest Date: 01/24/2025 **Time :** 12:45 **Temp :** 96 °C

Digestion tube ID: M6054

Block thermometer ID: MET-DIG. #5

Dig Technician Signature: GLD.

Supervisor Signature:

Temp : 1. 96°C 2. N/A

Standared Name	MLS USED	STD REF. # FROM LOG
LCSS	1.00	MP84063
Spike Sol 6	1.00	MP84070
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A

Chemical Used	ML/SAMPLE USED	Lot Number
1:1 HNO3	10.00	MP84041
Conc. HNO3	5.00	M6126
30% H2O2	3.00	M6125
Conc. HCL	10.00	M6121
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A

Extraction Conformance/Non-Conformance Comments:

HOT BLOCK #5 CELL #35 : 96 C

Date / Time	Prepped Sample Relinquished By/Location	Received By/Location
01/24/25 13:45	SPD. met digestion	
	Preparation Group	Analysis Group

Alliance TECHNICAL GROUP

Soil/Sludge Metals Preparation Sheet

PB166229

Lab Sample ID	Client Sample ID	pH	Initial Weight (g)	Final Vol (ml)	Color Before	Color After	Texture	Artifact	Comment	Prep Pos
PB166229BL	PBS229	N/A	1.00	100	Colorless	Colorless	Fine	N/A	N/A	1
PB166229BS	LCS229	N/A	1.00	100	Colorless	Colorless	Fine	N/A	MP84063	2
Q1151-01	MC0AZ0	N/A	1.20	100	Black	Yellow	Medium	N/A	N/A	3
Q1151-02	MC0AZ1	N/A	1.17	100	Brown	Yellow	Medium	N/A	N/A	4
Q1151-03	MC0AZ2	N/A	1.04	100	Brown	Yellow	Medium	N/A	N/A	5
Q1151-04	MC0AZ3	N/A	1.24	100	Brown	Yellow	Medium	N/A	N/A	6
Q1151-05	MC0AZ4	N/A	1.45	100	Black	Yellow	Medium	N/A	N/A	7
Q1151-06	MC0AZ5	N/A	1.24	100	Brown	Yellow	Medium	N/A	N/A	8
Q1151-07	MC0AZ6	N/A	1.15	100	Brown	Yellow	Medium	N/A	N/A	9
Q1151-08	MC0AZ7	N/A	1.10	100	Black	Yellow	Medium	N/A	N/A	10
Q1151-09	MC0AZ7D	N/A	1.28	100	Black	Yellow	Medium	N/A	N/A	11
Q1151-10	MC0AZ7S	N/A	1.28	100	Black	Yellow	Medium	N/A	MP84070	12
Q1151-11	MC0B00	N/A	1.12	100	Black	Yellow	Medium	N/A	N/A	13
Q1151-12	MC0B01	N/A	1.44	100	Brown	Yellow	Medium	N/A	N/A	14
Q1163-01	ME2946	N/A	1.39	100	Brown	Yellow	Medium	N/A	N/A	15
Q1163-02	ME2947	N/A	1.27	100	Brown	Yellow	Medium	N/A	N/A	16
Q1163-03	ME2947D	N/A	1.17	100	Brown	Yellow	Medium	N/A	N/A	17
Q1163-04	ME2947S	N/A	1.29	100	Brown	Yellow	Medium	N/A	MP84070	18

Alliance TECHNICAL GROUP

Water Metals Preparation Sheet

PB166568

SOP ID : M200.7-Trace Elements-22, MSFAM01.1-Trace Metals-2

SDG No : MC0AZ0, E1491

Matrix : WATER

Pippete ID: ICP A

Balance ID : N/A

Filter paper ID : N/A

pH Strip ID : M6069

Hood ID : #3

Block ID: 1. HOT BLOCK #1 2. N/A

Start Digest Date: 02/05/2025 **Time :** 10:20 **Temp :** 96 °C

End Digest Date: 02/05/2025 **Time :** 11:10 **Temp :** 96 °C

Digestion tube ID: M5595

Block thermometer ID: MET-DIG. #1

Dig Technician Signature: SJD.

Supervisor Signature:

Temp : 1. 96°C 2. N/A

Standared Name	MLS USED	STD REF. # FROM LOG
LCSW	0.50	MP84063
Spike Sol 6	0.25	MP84070
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A

Chemical Used	ML/SAMPLE USED	Lot Number
1:1 HNO3	1.00	MP84041
1:1 HCL	0.50	MP84297
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A
N/A	N/A	N/A

Extraction Conformance/Non-Conformance Comments:

HOT BLOCK #1 CELL #55 :96

Date / Time	Prepped Sample Relinquished By/Location	Received By/Location
02/05/25 12:10	SJD. met. dig.	metals lab
	Preparation Group	Analysis Group

Alliance TECHNICAL GROUP

Water Metals Preparation Sheet

PB166568

Lab Sample ID	Client Sample ID	pH	Initial Vol (ml)	Final Vol (ml)	Color Before	Color After	Clarity Before	Clarity After	Comment	Prep Pos
PB166568BL	PBW568	<2	50	50	Colorless	Colorless	Clear	Clear	N/A	29
PB166568BS	LCS568	<2	50	50	Colorless	Colorless	Clear	Clear	MP84063	30
Q1151-13	MC0B02	<2	50	50	Colorless	Colorless	Clear	Clear	N/A	31
Q1251-10	E1498	<2	50	50	Colorless	Colorless	Clear	Clear	N/A	32

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134438

Review By	Sarabjit Jaswal	Review On	1/28/2025 6:59:17 AM
Supervise By	Kareem Khairalla	Supervise On	1/28/2025 12:16:01 PM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	
LCS Standard	MP84063
Chk Standard	MP84218,MP84219

Sr#	SampleId	ClientID	QcType	Date	Comment	Operator	Status
1	S0	S0	CAL1	01/27/25 14:23		Kareem	OK
2	S1	S01	CAL2	01/27/25 14:27		Kareem	OK
3	S2	S02	CAL3	01/27/25 14:32		Kareem	OK
4	S3	S03	CAL4	01/27/25 14:36		Kareem	OK
5	S4	S04	CAL5	01/27/25 14:40		Kareem	OK
6	S5	S05	CAL6	01/27/25 14:44		Kareem	OK
7	S6	S06	CAL7	01/27/25 14:48		Kareem	OK
8	ICV003	ICV003	ICV	01/27/25 15:41	Inst. paused for calibration review	Kareem	OK
9	ICB003	ICB003	ICB	01/27/25 15:45		Kareem	OK
10	ICSA003	ICSA003	ICSA	01/27/25 15:56	Inst. paused for review	Kareem	OK
11	ICSAB003	ICSAB003	ICSAB	01/27/25 16:01		Kareem	OK
12	CCV021	CCV021	CCV	01/27/25 16:10	Inst. paused for review	Kareem	OK
13	CCB021	CCB021	CCB	01/27/25 16:14		Kareem	OK
14	Q1106-01DL	YE8G3	SAM	01/27/25 16:19	2x for Ca	Kareem	Confirms
15	Q1106-02DL	YE8G5	SAM	01/27/25 16:23	2x for Mn	Kareem	Confirms
16	Q1106-07DL	YE8H1	SAM	01/27/25 16:27	2x for Mn	Kareem	Confirms
17	Q1106-12DL	YE8H6	SAM	01/27/25 16:31	2x for Mn	Kareem	Confirms
18	Q1045-17DL	GCQ12	SAM	01/27/25 16:39	2x for Ba	Kareem	Confirms

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134438

Review By	Sarabjit Jaswal	Review On	1/28/2025 6:59:17 AM
Supervise By	Kareem Khairalla	Supervise On	1/28/2025 12:16:01 PM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	
LCS Standard	MP84063
Chk Standard	MP84218,MP84219

19	PB166225TB	LEB225	MB	01/27/25 16:43		Kareem	OK
20	Q1136-01	YE8F5	SAM	01/27/25 16:47		Kareem	OK
21	Q1136-02	YE8F7	SAM	01/27/25 16:56	NOT USE	Kareem	Not Ok
22	Q1105-01DL	YE8G3	SAM	01/27/25 17:00	5x for Ca	Kareem	Confirms
23	Q1136-03	YE8F7D	DUP	01/27/25 17:04	NOT USE	Kareem	Not Ok
24	Q1136-02L	YE8F7L	SD	01/27/25 17:08	NOT USE	Kareem	Not Ok
25	Q1136-04	YE8F7S	MS	01/27/25 17:12	NOT USE	Kareem	Not Ok
26	Q1136-05	YE8F8	SAM	01/27/25 17:16		Kareem	OK
27	Q1136-06	YE8E3	SAM	01/27/25 17:20		Kareem	OK
28	Q1136-07	YE8E4	SAM	01/27/25 17:24		Kareem	OK
29	Q1136-08	YE8E5	SAM	01/27/25 17:28		Kareem	OK
30	Q1136-09	YE8E6	SAM	01/27/25 17:32		Kareem	OK
31	Q1136-10	YE8E7	SAM	01/27/25 17:36		Kareem	OK
32	Q1136-11	YE8E8	SAM	01/27/25 17:40		Kareem	OK
33	Q1136-12	YE8D1	SAM	01/27/25 17:44		Kareem	OK
34	CCV022	CCV022	CCV	01/27/25 17:57		Kareem	OK
35	CCB022	CCB022	CCB	01/27/25 18:01		Kareem	OK
36	Q1136-13	YE8D2	SAM	01/27/25 18:05		Kareem	OK
37	Q1136-14	YE8D4	SAM	01/27/25 18:09		Kareem	OK
38	Q1136-15	YE8C3	SAM	01/27/25 18:13		Kareem	OK

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134438

Review By	Sarabjit Jaswal	Review On	1/28/2025 6:59:17 AM
Supervise By	Kareem Khairalla	Supervise On	1/28/2025 12:16:01 PM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	
LCS Standard	MP84063
Chk Standard	MP84218,MP84219

39	Q1136-17	YE8D5	SAM	01/27/25 18:17		Kareem	OK
40	PB166225BL	PBW225	MB	01/27/25 18:21		Kareem	OK
41	PB166225BS	LCS225	LCS	01/27/25 18:26		Kareem	OK
42	Q1151-01	MC0AZ0	SAM	01/27/25 18:30	NOT USE	Kareem	Not Ok
43	Q1151-02	MC0AZ1	SAM	01/27/25 18:34	Co,Ni high	Kareem	Dilution
44	Q1151-03	MC0AZ2	SAM	01/27/25 18:38	Co,Ni high	Kareem	Dilution
45	Q1151-04	MC0AZ3	SAM	01/27/25 18:42		Kareem	OK
46	Q1151-05	MC0AZ4	SAM	01/27/25 18:46	Co high	Kareem	Dilution
47	Q1151-06	MC0AZ5	SAM	01/27/25 18:50		Kareem	OK
48	Q1151-07	MC0AZ6	SAM	01/27/25 18:54		Kareem	OK
49	Q1151-08	MC0AZ7	SAM	01/27/25 18:58		Kareem	OK
50	Q1151-09	MC0AZ7D	DUP	01/27/25 19:01		Kareem	OK
51	Q1151-08L	MC0AZ7L	SD	01/27/25 19:05		Kareem	OK
52	Q1151-10	MC0AZ7S	MS	01/27/25 19:09	MS fail for As(76.26 ppb), Be(17.66 ppb), Cu(243.04 ppb), Mn(384.13 ppb), Zn(541.32 ppb) & Sb,Se,Ag (Below RL)	Kareem	OK
53	Q1151-11	MC0B00	SAM	01/27/25 19:13		Kareem	OK
54	CCV023	CCV023	CCV	01/27/25 19:21		Kareem	OK
55	CCB023	CCB023	CCB	01/27/25 19:26		Kareem	OK
56	Q1151-12	MC0B01	SAM	01/27/25 19:30		Kareem	OK

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134438

Review By	Sarabjit Jaswal	Review On	1/28/2025 6:59:17 AM
Supervise By	Kareem Khairalla	Supervise On	1/28/2025 12:16:01 PM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	
LCS Standard	MP84063
Chk Standard	MP84218,MP84219

57	Q1163-01	ME2946	SAM	01/27/25 19:34	Fe high	Kareem	Dilution
58	Q1163-02	ME2947	SAM	01/27/25 19:38	Ca high	Kareem	Dilution
59	Q1163-03	ME2947D	DUP	01/27/25 19:42	Ca high	Kareem	Dilution
60	Q1163-02L	ME2947L	SD	01/27/25 19:47	Ca high	Kareem	Dilution
61	Q1163-04	ME2947S	MS	01/27/25 19:51		Kareem	OK
62	PB166229BL	PBS229	MB	01/27/25 19:55		Kareem	OK
63	PB166229BS	LCS229	LCS	01/27/25 19:59		Kareem	OK
64	Q1181-01	MBHH96	SAM	01/27/25 20:03		Kareem	OK
65	Q1181-02	MBHH97	SAM	01/27/25 20:07		Kareem	OK
66	Q1181-03	MBHH98	SAM	01/27/25 20:11		Kareem	OK
67	Q1181-04	MBHH99	SAM	01/27/25 20:15		Kareem	OK
68	Q1181-05	MBHH99D	DUP	01/27/25 20:19		Kareem	OK
69	Q1181-04L	MBHH99L	SD	01/27/25 20:23		Kareem	OK
70	Q1181-06	MBHH99S	MS	01/27/25 20:27		Kareem	OK
71	PB166278BL	PBS278	MB	01/27/25 20:31		Kareem	OK
72	PB166278BS	LCS278	LCS	01/27/25 20:35		Kareem	OK
73	CCV024	CCV024	CCV	01/27/25 20:44		Kareem	OK
74	CCB024	CCB024	CCB	01/27/25 20:48		Kareem	OK

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134460

Review By	Kareem Khairalla	Review On	1/29/2025 10:02:19 AM
Supervise By	Sarabjit Jaswal	Supervise On	1/30/2025 7:27:43 AM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	
LCS Standard	
Chk Standard	MP84218,MP84219

Sr#	SampleId	ClientID	QcType	Date	Comment	Operator	Status
1	S0	S0	CAL1	01/28/25 17:57		Kareem	OK
2	S1	S01	CAL2	01/28/25 18:01		Kareem	OK
3	S2	S02	CAL3	01/28/25 18:05		Kareem	OK
4	S3	S03	CAL4	01/28/25 18:09		Kareem	OK
5	S4	S04	CAL5	01/28/25 18:14		Kareem	OK
6	S5	S05	CAL6	01/28/25 18:18		Kareem	OK
7	S6	S06	CAL7	01/28/25 18:22		Kareem	OK
8	ICV004	ICV004	ICV	01/28/25 19:08	Inst. paused for calibration review	Kareem	OK
9	ICB004	ICB004	ICB	01/28/25 19:12		Kareem	OK
10	ICSA004	ICSA004	ICSA	01/28/25 19:29	Inst. paused for review	Kareem	OK
11	ICSAB004	ICSAB004	ICSAB	01/28/25 19:33		Kareem	OK
12	CCV025	CCV025	CCV	01/28/25 19:37		Kareem	OK
13	CCB025	CCB025	CCB	01/28/25 19:41		Kareem	OK
14	Q1136-02	YE8F7	SAM	01/28/25 19:45	NOT USE	Kareem	Not Ok
15	Q1136-03	YE8F7D	DUP	01/28/25 19:49	NOT USE	Kareem	Not Ok
16	Q1136-02L	YE8F7L	SD	01/28/25 19:53	NOT USE	Kareem	Not Ok
17	Q1136-04	YE8F7S	MS	01/28/25 19:57	NOT USE	Kareem	Not Ok
18	Q1151-01	MC0AZ0	SAM	01/28/25 20:01	Cr,Co,Ni high	Kareem	Dilution

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134460

Review By	Kareem Khairalla	Review On	1/29/2025 10:02:19 AM
Supervise By	Sarabjit Jaswal	Supervise On	1/30/2025 7:27:43 AM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	
LCS Standard	
Chk Standard	MP84218,MP84219

19	Q1151-01DL	MC0AZ0	SAM	01/28/25 20:05	NOT USE	Kareem	Not Ok
20	Q1151-02DL	MC0AZ1	SAM	01/28/25 20:10	2x for Co,Ni high, Still Co,Ni high	Kareem	Not Ok
21	Q1151-03DL	MC0AZ2	SAM	01/28/25 20:13	2x for Co,Ni	Kareem	Confirms
22	Q1151-05DL	MC0AZ4	SAM	01/28/25 20:17	2x for Co	Kareem	Confirms
23	Q1151-08A	MC0AZ7A	PS	01/28/25 20:21	NOT USE	Kareem	Not Ok
24	Q1163-01DL	ME2946	SAM	01/28/25 20:25	5x for Fe	Kareem	Confirms
25	Q1163-02DL	ME2947	SAM	01/28/25 20:29	2x for Ca	Kareem	Confirms
26	Q1163-03DL	ME2947D	DUP	01/28/25 20:33	2x for Ca	Kareem	Confirms
27	Q1163-02LDL	ME2947L	SD	01/28/25 20:37	10x for Ca	Kareem	Confirms
28	Q1163-04DL	ME2947S	MS	01/28/25 20:41	not required	Kareem	Not Ok
29	PB166236TB	LEB236	MB	01/28/25 20:45		Kareem	OK
30	Q1164-01	ME2946	SAM	01/28/25 20:50		Kareem	OK
31	Q1164-02	ME2947	SAM	01/28/25 20:54		Kareem	OK
32	Q1164-03	ME2947D	DUP	01/28/25 20:58		Kareem	OK
33	Q1164-02L	ME2947L	SD	01/28/25 21:02		Kareem	OK
34	CCV026	CCV026	CCV	01/28/25 21:11		Kareem	OK
35	CCB026	CCB026	CCB	01/28/25 21:15		Kareem	OK
36	Q1164-04	ME2947S	MS	01/28/25 21:19		Kareem	OK
37	Q1182-01	MBHH96	SAM	01/28/25 21:24		Kareem	OK

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134460

Review By	Kareem Khairalla	Review On	1/29/2025 10:02:19 AM
Supervise By	Sarabjit Jaswal	Supervise On	1/30/2025 7:27:43 AM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	
LCS Standard	
Chk Standard	MP84218,MP84219

38	Q1182-02	MBHH97	SAM	01/28/25 21:28		Kareem	OK
39	Q1182-03	MBHH98	SAM	01/28/25 21:32		Kareem	OK
40	Q1182-04	MBHH99	SAM	01/28/25 21:36		Kareem	OK
41	Q1182-05	MBHH99D	DUP	01/28/25 21:40		Kareem	OK
42	Q1182-04L	MBHH99L	SD	01/28/25 21:44		Kareem	OK
43	Q1182-06	MBHH99S	MS	01/28/25 21:49		Kareem	OK
44	PB166272BL	PBW272	MB	01/28/25 21:53		Kareem	OK
45	PB166272BS	LCS272	LCS	01/28/25 21:57		Kareem	OK
46	PB166267TB	LEB267	MB	01/28/25 22:01		Kareem	OK
47	Q1160-01	YE8C9	SAM	01/28/25 22:05		Kareem	OK
48	Q1160-02	YE8C9D	DUP	01/28/25 22:09		Kareem	OK
49	Q1160-01L	YE8C9L	SD	01/28/25 22:13		Kareem	OK
50	Q1160-03	YE8C9S	MS	01/28/25 22:17		Kareem	OK
51	Q1160-04	YE8D0	SAM	01/28/25 22:21		Kareem	OK
52	Q1160-05	YE8D3	SAM	01/28/25 22:25		Kareem	OK
53	PB166267BL	PBW267	MB	01/28/25 22:29		Kareem	OK
54	PB166267BS	LCS267	LCS	01/28/25 22:33		Kareem	OK
55	CCV027	CCV027	CCV	01/28/25 22:42		Kareem	OK
56	CCB027	CCB027	CCB	01/28/25 22:46		Kareem	OK

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134475

Review By	Kareem Khairalla	Review On	1/30/2025 3:36:15 PM
Supervise By	Mohan Bera	Supervise On	1/31/2025 7:33:47 AM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	
LCS Standard	
Chk Standard	MP84218,MP84219

Sr#	SampleId	ClientID	QcType	Date	Comment	Operator	Status
1	S0	S0	CAL1	01/29/25 14:56		Kareem	OK
2	S1	S01	CAL2	01/29/25 15:00		Kareem	OK
3	S2	S02	CAL3	01/29/25 15:04		Kareem	OK
4	S3	S03	CAL4	01/29/25 15:08		Kareem	OK
5	S4	S04	CAL5	01/29/25 15:12		Kareem	OK
6	S5	S05	CAL6	01/29/25 15:16		Kareem	OK
7	S6	S06	CAL7	01/29/25 15:21		Kareem	OK
8	ICV005	ICV005	ICV	01/29/25 15:31	Inst. paused for calibration review	Kareem	OK
9	ICB005	ICB005	ICB	01/29/25 15:35		Kareem	OK
10	ICSA005	ICSA005	ICSA	01/29/25 15:41	Inst. paused for review	Kareem	OK
11	ICSAB005	ICSAB005	ICSAB	01/29/25 15:45		Kareem	OK
12	CCV028	CCV028	CCV	01/29/25 15:49		Kareem	OK
13	CCB028	CCB028	CCB	01/29/25 15:53		Kareem	OK
14	Q1136-02	YE8F7	SAM	01/29/25 15:58		Kareem	OK
15	Q1136-03	YE8F7D	DUP	01/29/25 16:01		Kareem	OK
16	Q1136-02L	YE8F7L	SD	01/29/25 16:05		Kareem	OK
17	Q1136-04	YE8F7S	MS	01/29/25 16:09	MS fail for Cd,Co,Pb,Ni,Ag,Tl	Kareem	OK
18	Q1151-01DL	MC0AZ0	SAM	01/29/25 16:13	20x for Cr,Co,Ni, Still Co,Ni high	Kareem	Dilution

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134475

Review By	Kareem Khairalla	Review On	1/30/2025 3:36:15 PM
Supervise By	Mohan Bera	Supervise On	1/31/2025 7:33:47 AM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	
LCS Standard	
Chk Standard	MP84218,MP84219

19	Q1151-02DL	MC0AZ1	SAM	01/29/25 16:18	5x for Co,Ni	Kareem	Confirms
20	Q1159-01	YE8C9	SAM	01/29/25 16:21		Kareem	OK
21	Q1151-01DL2	MC0AZ0	SAM	01/29/25 16:25	40x for Co,Ni	Kareem	Confirms
22	Q1159-02	YE8C9D	DUP	01/29/25 16:29		Kareem	OK
23	Q1159-01L	YE8C9L	SD	01/29/25 16:33		Kareem	OK
24	Q1159-03	YE8C9S	MS	01/29/25 16:38		Kareem	OK
25	Q1159-04	YE8D1	SAM	01/29/25 16:42		Kareem	OK
26	Q1159-05	YE8D3	SAM	01/29/25 16:46		Kareem	OK
27	Q1159-06	YE8E2	SAM	01/29/25 16:50		Kareem	OK
28	PB166301BL	PBS301	MB	01/29/25 16:54		Kareem	OK
29	PB166301BS	LCS301	LCS	01/29/25 16:58		Kareem	OK
30	CCV029	CCV029	CCV	01/29/25 17:02		Kareem	OK
31	CCB029	CCB029	CCB	01/29/25 17:06		Kareem	OK
32	Q1136-02A	YE8F7A	PS	01/29/25 17:49	PS for Cd,Co,Pb,Ni,Tl(0.01 ML MP84292, 0.02 ML MP84296, 0.02 ML MP84294, 0.002 ML M5961, 0.005 ML MP84293)	Kareem	OK
33	CCV030	CCV030	CCV	01/29/25 18:01		Kareem	OK
34	CCB030	CCB030	CCB	01/29/25 18:06		Kareem	OK

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134517

Review By	Kareem Khairalla	Review On	2/4/2025 12:30:01 PM
Supervise By	Janvi Patel	Supervise On	2/10/2025 1:39:33 PM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	MP84338,MP84339,MP84340,MP84341,M6128,M5819
LCS Standard	
Chk Standard	MP84218,MP84219

Sr#	SampleId	ClientID	QcType	Date	Comment	Operator	Status
1	S0	S0	CAL1	01/31/25 16:26		Kareem	OK
2	S1	S01	CAL2	01/31/25 16:31		Kareem	OK
3	S2	S02	CAL3	01/31/25 16:35		Kareem	OK
4	S3	S03	CAL4	01/31/25 16:39		Kareem	OK
5	S4	S04	CAL5	01/31/25 16:43		Kareem	OK
6	S5	S05	CAL6	01/31/25 16:47		Kareem	OK
7	S6	S06	CAL7	01/31/25 16:52		Kareem	OK
8	ICV006	ICV006	ICV	01/31/25 17:17	Inst. paused for calibration review	Kareem	OK
9	ICB006	ICB006	ICB	01/31/25 17:21		Kareem	OK
10	ICSA006	ICSA006	ICSA	01/31/25 17:25		Kareem	OK
11	ICSAB006	ICSAB006	ICSAB	01/31/25 17:41	Inst. paused for review	Kareem	OK
12	CCV031	CCV031	CCV	01/31/25 17:54	Inst. paused for review	Kareem	OK
13	CCB031	CCB031	CCB	01/31/25 17:59		Kareem	OK
14	Q1151-08A	MC0AZ7A	PS	01/31/25 18:03	PS for As,Be,Cu,Mn,Se,Zn(0.015 ML MP84338, 0.04 ML MP84339, 0.048 ML MP84340, 0.0076 ML M6128, 0.007 ML MP84341, 0.01 ML M5819)	Kareem	OK
15	CCV032	CCV032	CCV	01/31/25 18:07		Kareem	OK

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P4

Daily Analysis Runlog For Sequence/QCBatch ID # LB134517

Review By	Kareem Khairalla	Review On	2/4/2025 12:30:01 PM
Supervise By	Janvi Patel	Supervise On	2/10/2025 1:39:33 PM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84212,MP84210,MP84209,MP84208,MP84207,MP84206
ICV Standard	MP84213
CCV Standard	MP84216
ICSA Standard	MP84214,MP84215
CRI Standard	MP84338,MP84339,MP84340,MP84341,M6128,M5819
LCS Standard	
Chk Standard	MP84218,MP84219

16	CCB032	CCB032	CCB	01/31/25 18:12		Kareem	OK

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P5

Daily Analysis Runlog For Sequence/QCBatch ID # LB134617

Review By	Kareem Khairalla	Review On	2/7/2025 3:55:23 PM
Supervise By	Janvi Patel	Supervise On	2/10/2025 1:38:43 PM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84388,MP84386,MP84385,MP84384,MP84383,MP84381
ICV Standard	MP84389
CCV Standard	MP84392
ICSA Standard	MP84390,MP84391
CRI Standard	
LCS Standard	MP84063
Chk Standard	MP84218,MP84219

Sr#	SampleId	ClientID	QcType	Date	Comment	Operator	Status
1	S0	S0	CAL1	02/06/25 12:47		Kareem	OK
2	S1	S01	CAL2	02/06/25 12:51		Kareem	OK
3	S2	S02	CAL3	02/06/25 12:55		Kareem	OK
4	S3	S03	CAL4	02/06/25 12:59		Kareem	OK
5	S4	S04	CAL5	02/06/25 13:03		Kareem	OK
6	S5	S05	CAL6	02/06/25 13:07		Kareem	OK
7	S6	S06	CAL7	02/06/25 13:11		Kareem	OK
8	ICV002	ICV002	ICV	02/06/25 14:09	Inst. paused for calibration review	Kareem	OK
9	ICB002	ICB002	ICB	02/06/25 14:14		Kareem	OK
10	ICSA002	ICSA002	ICSA	02/06/25 14:18		Kareem	OK
11	ICSAB002	ICSAB002	ICSAB	02/06/25 14:25	Inst. paused for review	Kareem	OK
12	CCV003	CCV003	CCV	02/06/25 14:29		Kareem	OK
13	CCB003	CCB003	CCB	02/06/25 14:32		Kareem	OK
14	Q1151-13	MC0B02	SAM	02/06/25 14:36		Kareem	OK
15	Q1251-10	E1498	SAM	02/06/25 14:41		Kareem	OK
16	PB166571BL	PBW571	MB	02/06/25 14:45		Kareem	OK
17	PB166571BS	LCS571	LCS	02/06/25 14:49		Kareem	OK
18	PB166568BL	PBW568	MB	02/06/25 14:53		Kareem	OK

284 Sheffield Street, Mountainside, New Jersey 07092, Phone : 908 789 8900,
Fax : 908 789 8922

Instrument ID: P5

Daily Analysis Runlog For Sequence/QCBatch ID # LB134617

Review By	Kareem Khairalla	Review On	2/7/2025 3:55:23 PM
Supervise By	Janvi Patel	Supervise On	2/10/2025 1:38:43 PM

STD. NAME	STD REF.#
ICAL Standard	MP84204,MP84388,MP84386,MP84385,MP84384,MP84383,MP84381
ICV Standard	MP84389
CCV Standard	MP84392
ICSA Standard	MP84390,MP84391
CRI Standard	
LCS Standard	MP84063
Chk Standard	MP84218,MP84219

19	PB166568BS	LCS568	LCS	02/06/25 14:57		Kareem	OK
20	PB166494TB	LEB494	MB	02/06/25 15:01		Kareem	OK
21	Q1272-03A	MBHHA2A	PS	02/06/25 15:05	NOT USE	Kareem	Not Ok
22	Q1273-01	MBHHA0	SAM	02/06/25 15:08		Kareem	OK
23	Q1273-02	MBHHA1	SAM	02/06/25 15:12		Kareem	OK
24	Q1273-03	MBHHA2	SAM	02/06/25 15:16	NOT USE	Kareem	Not Ok
25	Q1273-04	MBHHA2D	DUP	02/06/25 15:20	NOT USE	Kareem	Not Ok
26	Q1273-03L	MBHHA2L	SD	02/06/25 15:24	NOT USE	Kareem	Not Ok
27	Q1273-05	MBHHA2S	MS	02/06/25 15:28	NOT USE	Kareem	Not Ok
28	CCV004	CCV004	CCV	02/06/25 15:31		Kareem	OK
29	CCB004	CCB004	CCB	02/06/25 15:35		Kareem	OK