

TOTAL VOLATILE SOLIDS 160.4

TEMP1 IN: 104 °C 09/02/2020 16:00 **TEMP1 OUT:** 104 °C 09/03/2020 07:15
TEMP2 IN: 104 °C 09/03/2020 08:00 **TEMP2 OUT:** 104 °C 09/03/2020 09:30
TEMP3 IN: 540 °C 09/03/2020 10:00 **TEMP3 OUT:** 540 °C 09/03/2020 11:30
TEMP4 IN: 540 °C 09/03/2020 12:00 **TEMP4 OUT:** 540 °C 09/03/2020 13:30

Run Number: LB110791

SUPERVISOR: apatel

ANALYST: JIGNESH

BalanceID: WC SC-3

OvenID: WC OVEN-1

Dish #	Lab ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Empty Dish + Sample Weight (g)	1st Dish + SampleWt Drying @103-@105°C (g)	Final Dish + SampleWt Drying @103-@105°C (g)	Dish + Samplewt Drying @550 (±50) °C (g)	Final Dish + Samplewt Drying @550 (±50) °C (g)	Weight Diff (g)	Result (%)
1	LB110791BL	65.3487	65.3487	86.5417	65.3487	65.3487	65.3487	65.3487	0.0000	0
2	L3887-02	59.9796	59.9796	74.8613	74.8395	74.8395	73.9908	73.9908	0.8487	5.7
3	L3887-02DUP	57.1835	57.1835	78.5696	78.5376	78.5376	77.3315	77.3315	1.2061	5.6

A = Sample Weight (g)

B = Final Dish + Samplewt Drying @550 (±50) °C (g)

C = Final Dish + SampleWt Drying @103-@105°C (g)

D = Weight (g)

E = Final Empty Dish Weight (g)

F = Final Dish + SampleWt Drying @103-@105°C (g)

Weight D = C - B

Result % = $\frac{D}{F - E} \star 100$

MS 110791

WORKLIST(Hardcopy Internal Chain)

WorkList Name : TVS L3887 WorkList ID : 142012 Department : Wet-Chemistry Date : 09-02-2020 14:41:41

Due Date	Matrix	Sample	Test	Preservative	Customer	Storage Location	Customer Sample	Collect Date	Method
09/07/2020	Solid	L3887-02	TVS	Cool 4 deg C	PSEG01	M13	CONCRETE-PILE	09/02/2020	160.4

Date/Time 09.02.2020 14:15:00
Received by: JP (wet) Mem
Relinquished by: KS (Wetchem)

Date/Time 09.02.2020 17:11:10
Received by: KS (Wetchem)
Relinquished by: JP (wet) Mem,