



TOTAL VOLATILE SOLIDS 160.4

Run Number: LB113566

SUPERVISOR: apatel

ANALYST: jignesh

BalanceID: WC SC-3

OvenID: WC OVEN-1

TEMP1 IN: 104 °C 03/18/2021 16:00 TEMP1 OUT: 103 °C 03/19/2021 08:00
TEMP2 IN: 103 °C 03/19/2021 08:35 TEMP2 OUT: 104 °C 03/19/2021 10:10
TEMP3 IN: 540 °C 03/19/2021 10:35 TEMP3 OUT: 540 °C 03/19/2021 12:15
TEMP4 IN: 560 °C 03/19/2021 12:40 TEMP4 OUT: 560 °C 03/19/2021 14:00

Dish #	Lab ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Empty Dish + Sample Weight (g)	1st Dish + SampleWt Drying @103-@105°C (g)	Final Dish + SampleWt Drying @103-@105°C (g)	Dish + Samplewt Drying @550 (±50) °C (g)	Final Dish + Samplewt Drying @550 (±50) °C (g)	Weight Diff (g)	Result (%)
1	LB113566BL	59.5610	59.5610	80.2714	59.5616	59.5616	59.5616	59.5616	0.0000	0
2	M1712-17	59.5615	59.5615	80.2714	79.3201	79.3201	78.5669	78.5669	0.7532	3.8
3	M1712-19	58.3169	58.3169	79.2224	79.0866	79.0866	78.8403	78.8403	0.2463	1.2
4	M1712-19DUP	57.1841	57.1841	78.0725	77.9342	77.9342	77.6147	77.6147	0.3195	1.5
5	M1712-21	55.8875	55.8875	77.2022	76.9203	76.9203	76.7179	76.7179	0.2024	1
6	M1712-23	59.9788	59.9788	80.6417	80.4583	80.4583	80.2984	80.2984	0.1599	0.8

A = Sample Weight (g)

B = Final Dish + Samplewt Drying @550 (±50) °C (g)

C = Final Dish + SampleWt Drying @103-@105°C (g)

D = Weight (g)

E = Final Empty Dish Weight (g)

F = Final Dish + SampleWt Drying @103-@105°C (g)

Weight D = C - B

Result % = $\frac{D}{F - E} \star 100$

113566

WORKLIST(Hardcopy Internal Chain)

WorkList Name : TVS M1712

WorkList ID : 147251

Department : Wet-Chemistry

Date : 03-18-2021 11:08:30

Due Date	Matrix	Sample	Test	Preservative	Customer	Storage Location	Customer Sample	Collect Date	Method
03/30/2021	Solid	M1712-17	TVS	Cool 4 deg C	PSEG03	I13	EXTERNAL-PAD-COMP	03/17/2021	160.4
03/30/2021	Solid	M1712-19	TVS	Cool 4 deg C	PSEG03	I13	RED-BRICK-COMP	03/17/2021	160.4
03/30/2021	Solid	M1712-21	TVS	Cool 4 deg C	PSEG03	I13	NEW-BLOCK-FLOOR-PAT	03/17/2021	160.4
03/30/2021	Solid	M1712-23	TVS	Cool 4 deg C	PSEG03	I13	YELLOW-WALL-COMP	03/17/2021	160.4

Date/Time 03-18-21 14:00
 Received by: JP Wet Chem
 Relinquished by: OR PM L

Date/Time 03-18-21 16:20
 Received by: CP SM 1
 Relinquished by: JP Wet Chem