



TOTAL SOLIDS - SM2540B

SUPERVISOR: apatelANALYST: JIGNESHDate: 03/25/2021OVEN IN TEMP1: 104 °COVEN OUT TEMP1: 103 °CDATE & TIME IN1: 03/24/2021 16:00 DATE & TIME OUT1: 03/25/2021 08:00OVEN IN TEMP2: 103 °COVEN OUT TEMP2: 103 °CDATE & TIME IN2: 03/25/2021 08:30 DATE & TIME OUT2: 03/25/2021 10:10Run Number: LB113661BalanceID: WC SC-3OvenID: WC OVEN-1

Dish #	Lab ID	Client ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Dish + Sample Weight (g)	1st Dish+Sample weight after Drying @103-@105°C (g)	2nd Dish+Sample weight after Drying @103-@105°C (g)	Final Dish+Sample weight after Drying @103-@105°C (g)	Weight (g)	Result %
1	LB113661BL	LB113661BL	65.1478	65.1478	65.1478	65.1479	65.1479	65.1479	0.0001	0
2	M1791-15	EXTERIOR-SLAB-BRICK-1	59.5610	59.5610	80.0866	79.0854	79.0854	79.0854	19.5244	95.1
3	M1791-15DUP	EXTERIOR-SLAB-BRICK-1DUP	58.3166	58.3166	78.0971	77.1372	77.1372	77.1372	18.8206	95.1
4	M1791-18	EXTERIOR-SLAB-BRICK-2	57.1834	57.1834	72.5417	71.6266	71.6266	71.6266	14.4432	94
5	M1791-21	GRAY-INTERIOR-BLOCK-1-2	55.8873	55.8873	76.3394	75.9275	75.9275	75.9275	20.0402	98
6	M1791-26	ROSE-BRICK-INTERIOR	59.9788	59.9788	70.6635	70.5804	70.5804	70.5804	10.6016	99.2

A = Final Empty Dish Weight (g)

B = Dish + Sample Weight (g)

C = Final Dish+Sample weight after Drying @103-@105°C (g)

$$\text{Result \%} = (C - A) * 100 / (B - A)$$

WORKLIST(Hardcopy Internal Chain)

2013661

WorkList Name : ts m1791 WorkList ID : 147436 Department : Wet-Chemistry Date : 03-24-2021 16:32:10

Due Date	Matrix	Sample	Test	Preservative	Customer	Storage Location	Customer Sample	Collect Date	Method
04/06/2021	Solid	M1791-15	TS	Cool 4 deg C	PSEG03	J51	EXTERIOR-SLAB-BRICK-1	03/24/2021	SM2540 B
04/06/2021	Solid	M1791-18	TS	Cool 4 deg C	PSEG03	J51	EXTERIOR-SLAB-BRICK-2	03/24/2021	SM2540 B
04/06/2021	Solid	M1791-21	TS	Cool 4 deg C	PSEG03	J51	GRAY-INTERIOR-BLOCK-1-2	03/24/2021	SM2540 B
04/06/2021	Solid	M1791-26	TS	Cool 4 deg C	PSEG03		ROSE-BRICK-INTERIOR	03/24/2021	SM2540 B

Date/Time 03/24/21 16:35
 Received by: JP (wet Chem)
 Relinquished by: RJ CFLT-146)

Date/Time 03/24/21 17:40
 Received by: RJ CFLT-146)
 Relinquished by: JP (wet Chem)