



TOTAL SOLIDS - SM2540B

SUPERVISOR: apatel

ANALYST: jignesh

Date: 08/12/2021

OVEN IN TEMP1: 104 °C

OVEN OUT TEMP1: 104 °C

DATE & TIME IN1: 08/11/2021 17:10 DATE & TIME OUT1: 08/12/2021 08:00

OVEN IN TEMP2: 103 °C

OVEN OUT TEMP2: 103 °C

DATE & TIME IN2: 08/12/2021 08:30 DATE & TIME OUT2: 08/12/2021 10:00

Run Number: LB115795

BalanceID: Wc Sc-06

OvenID: Wc Oven-1

Dish #	Lab ID	Client ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Dish + Sample Weight (g)	1st Dish+Sample weight after Drying @103-@105°C (g)	2nd Dish+Sample weight after Drying @103-@105°C (g)	Final Dish+Sample weight after Drying @103-@105°C (g)	Weight (g)	Result %
1	LB115795BL	LB115795BL	64.8967	64.8967	85.2576	64.8968	64.8968	64.8968	0.0001	0
2	M3371-03	JET-GROUT	59.3967	59.3967	81.2855	72.9028	72.9028	72.9028	13.5061	61.7
3	M3371-03DUP	JET-GROUTDUP	58.3209	58.3209	80.167	71.6159	71.6159	71.6159	13.2950	60.9

A = Final Empty Dish Weight (g)

B = Dish + Sample Weight (g)

C = Final Dish+Sample weight after Drying @103-@105°C (g)

Result % = (C - A) * 100 / (B - A)

LB 115795

WORKLIST(Hardcopy Internal Chain)

WorkList Name : TS M3371

WorkList ID : 151336

Department : Wet-Chemistry

Date : 08-11-2021 16:39:51

Due Date	Matrix	Sample	Test	Preservative	Customer	Raw Sample Storage Location	Customer Sample	Collect Date	Method
08/24/2021	Solid	M3371-03	TS		TULL02	D11	JET-GROUT	08/10/2021	SM2540 B

Date/Time 08-11-21 16:40
 Raw Sample Received by: JP (WC)
 Raw Sample Relinquished by: JP (WC)

Date/Time 08-11-21 17:40
 Raw Sample Received by: JP (WC)
 Raw Sample Relinquished by: JP (WC)