

OVEN IN TEMP1: 104 °C

OVEN OUT TEMP1: 104 °C

DATE & TIME IN1: 08/11/2021 17:10

DATE & TIME OUT1: 08/12/2021 08:00

OVEN IN TEMP2: 103 °C

OVEN OUT TEMP2: 103 °C

DATE & TIME IN2: 08/12/2021 08:30

DATE & TIME OUT2: 08/12/2021 10:00

Run Number: LB116021

BalanceID: Wc Sc-06

OvenID: Wc Oevn-01

Dish #	Lab ID	Client ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Dish + Sample Weight (g)	1st Dish+Sample weight after Drying @103-@105°C (g)	2nd Dish+Sample weight after Drying @103-@105°C (g)	Final Dish+Sample weight after Drying @103-@105°C (g)	Weight (g)	Result %
1	LB116021BL	LB116021BL	64.8967	64.8967	85.2576	64.8968	64.8968	64.8968	0.0001	0
2	M3371-01	JET-GROUT	59.3967	59.3967	81.2855	72.9028	72.9028	72.9028	13.5061	61.7
3	M3371-01DUP	JET-GROUTDUP	58.3209	58.3209	80.167	71.6159	71.6159	71.6159	13.2950	60.9

A = Final Empty Dish Weight (g)

B = Dish + Sample Weight (g)

C = Final Dish+Sample weight after Drying @103-@105°C (g)

Result % = (C - A) * 100 / (B - A)

WB 116021

WORKLIST(Hardcopy Internal Chain)

WorkList Name : TS M3371 WorkList ID : 151336 Department : Wet-Chemistry Date : 08-11-2021 16:39:51

Due Date	Matrix	Sample	Test	Preservative	Customer	Raw Sample Storage Location	Customer Sample	Collect Date	Method
08/24/2021	Solid	M3371-01	TS	Cool 4 deg C	TULL02	D11	JET-GROUT	08/10/2021	SM2540 B

Date/Time 08-11-21 16:40
Raw Sample Received by: JP (WC)
Raw Sample Relinquished by: Cp Sm

Date/Time 08-11-21 18:00
Raw Sample Received by: JP (WC)
Raw Sample Relinquished by: JP (WC)