



TOTAL VOLATILE SOLIDS 160.4

TEMP1 IN: 104 °C 08/11/2021 17:10 TEMP1 OUT: 104 °C 08/12/2021 08:00
TEMP2 IN: 103 °C 08/12/2021 08:30 TEMP2 OUT: 103 °C 08/12/2021 10:00
TEMP3 IN: 540 °C 08/12/2021 11:00 TEMP3 OUT: 540 °C 08/12/2021 12:30
TEMP4 IN: 560 °C 08/12/2021 13:00 TEMP4 OUT: 560 °C 08/12/2021 14:30

Run Number: LB116022

SUPERVISOR: mohammad

ANALYST: jignesh

BalanceID: Wc Sc-06

OvenID: Wc Oven-01

Dish #	Lab ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Empty Dish + Sample Weight (g)	1st Dish + SampleWt Drying @103-@105°C (g)	Final Dish + SampleWt Drying @103-@105°C (g)	Dish + Samplewt Drying @550 (±50) °C (g)	Final Dish + Samplewt Drying @550 (±50) °C (g)	Weight Diff (g)	Result (%)
1	LB116022BL	64.8967	64.8967	85.2576	64.8968	64.8968	64.8968	64.8968	0.0000	0
2	M3371-01	59.3967	59.3967	81.2855	72.9028	72.9028	72.3522	72.3522	0.5506	4.1
3	M3371-01DUP	58.3209	58.3209	80.167	71.6159	71.6159	71.0456	71.0456	0.5703	4.3

A = Sample Weight (g)

B = Final Dish + Samplewt Drying @550 (±50) °C (g)

C = Final Dish + SampleWt Drying @103-@105°C (g)

D = Weight (g)

E = Final Empty Dish Weight (g)

F = Final Dish + SampleWt Drying @103-@105°C (g)

Weight D = C - B

Result % = $\frac{D}{F - E} \star 100$

116022

WORKLIST(Hardcopy Internal Chain)

WorkList Name : TVS M3371 WorkList ID : 151337 Department : Wet-Chemistry Date : 08-11-2021 16:40:38

Due Date	Matrix	Sample	Test	Preservative	Customer	Raw Sample Storage Location	Customer Sample	Collect Date	Method
08/17/2021	Solid	M3371-01	TVS	Cool 4 deg C	TULL02	D11	JET-GROUT	08/10/2021	160.4

Date/Time 08-11-21 16:40
Raw Sample Received by: JP (WC)
Raw Sample Relinquished by: JP SM

Date/Time 08-11-21 18:00
Raw Sample Received by: JP SM
Raw Sample Relinquished by: JP (WC)