



TOTAL SOLIDS - SM2540B

SUPERVISOR: apatel

ANALYST: JIGNESH

Date: 04/20/2022

OVEN IN TEMP1: 103 °C

OVEN OUT TEMP1: 103 °C

DATE & TIME IN1: 04/19/2022 16:10 DATE & TIME OUT1: 04/20/2022 07:30

OVEN IN TEMP2: 103 °C

OVEN OUT TEMP2: 103 °C

DATE & TIME IN2: 04/20/2022 08:00 DATE & TIME OUT2: 04/20/2022 09:30

Run Number: LB119754

BalanceID: WC SC-6

OvenID: WC OVEN-1

Dish #	Lab ID	Client ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Dish + Sample Weight (g)	1st Dish+Sample weight after Drying @103-@105°C (g)	2nd Dish+Sample weight after Drying @103-@105°C (g)	Final Dish+Sample weight after Drying @103-@105°C (g)	Weight (g)	Result %
1	LB119754BL	LB119754BL	65.2387	65.2387	65.2387	65.2387	65.2387	65.2387	0.0000	0
2	N2474-01	TMS-JET-GROUT-SPOILS-A	59.3927	59.3927	80.9188	73.2046	73.2046	73.2046	13.8119	64.2
3	N2474-04	TMS-JET-GROUT-SPOILS-B	59.5533	59.5533	80.9273	72.8732	72.8732	72.8732	13.3199	62.3
4	N2474-04DUP	TMS-JET-GROUT-SPOILS-BDUP	58.3154	58.3154	81.2441	72.5704	72.5704	72.5704	14.2550	62.2

A = Final Empty Dish Weight (g)

B = Dish + Sample Weight (g)

C = Final Dish+Sample weight after Drying @103-@105°C (g)

$$\text{Result \%} = (C - A) * 100 / (B - A)$$

WORKLIST(Hardcopy Internal Chain)

119754

WorkList Name : TS S N2474

WorkList ID : 158812

Department : Wet-Chemistry

Date : 04-19-2022 14:23:00

Due Date	Matrix	Sample	Test	Preservative	Customer	Raw Sample Storage Location	Customer Sample	Collect Date	Method
04/26/2022	Solid	N2474-01	TS	Cool 4 deg C	TULL02	P11	TMS-JET-GROUT-SPOILS-A	04/19/2022	SM2540 B
04/26/2022	Solid	N2474-04	TS	Cool 4 deg C	TULL02	P11	TMS-JET-GROUT-SPOILS-B	04/19/2022	SM2540 B

Date/Time

Raw Sample Received by:

Raw Sample Relinquished by:

04-19-22 16130

JP/WG

CP SAN

Date/Time

Raw Sample Received by:

Raw Sample Relinquished by:

04-19-22

CP SAN

JP/WG

16135