



PERCENT SOLID

Supervisor: Sohil
Analyst: jignesh
Date: 8/23/2022

OVENTEMP IN Celsius(°C): 107
Time IN: 17:00
In Date: 08/22/2022
Weight Check 1.0g: 1.00
Weight Check 10g: 10.00
OvenID: M OVEN-1

OVENTEMP OUT Celsius(°C): 103
Time OUT: 08:25
Out Date: 08/23/2022
Weight Check 1.0g: 1.00
Weight Check 10g: 10.00
BalanceID: M SC-4
Thermometer ID: %SOLIDS-OVEN

QC:LB121631

Lab ID	Client SampleID	Dish #	Dish Wt(g) (A)	Sample Wt(g)	Dish + Sample Wt(g) (B)	Dish+Dry Sample Wt(g) (C)	% Solid	Comments
N4270-01	SASP2-T-4-(25-37)	1	0.91	8.98	9.89	8.23	81.5	
N4277-01	B-2	2	0.91	8.85	9.76	9.08	92.3	
N4283-01	337	3	0.91	8.86	9.77	9.01	91.4	
N4292-01	TR-04-082222	4	0.92	8.74	9.66	9.52	98.4	
N4292-02	TR-04-082222-EPH-2	5	0.92	8.74	9.66	9.52	98.4	
N4293-01	CON1-8-22-2022	6	1.00	1.00	2.00	2.00	100.0	CONCRETE SAMPLE
N4294-01	44-A	7	1.00	1.00	2.00	2.00	100.0	PILC REEL
N4294-02	44-B	8	1.00	1.00	2.00	2.00	100.0	PILC REEL
N4294-03	45	9	1.00	1.00	2.00	2.00	100.0	PILC REEL
N4294-04	45	10	1.00	1.00	2.00	2.00	100.0	PILC REEL
N4294-05	46	11	1.00	1.00	2.00	2.00	100.0	PILC REEL
N4294-06	47	12	1.00	1.00	2.00	2.00	100.0	
N4295-01	XRDS-RECYCLED-SAND-SP-A-COMP	13	0.9	8.68	9.58	9.05	93.9	
N4295-02	XRDS-RECYCLED-SAND-SP-A-GRAB	14	0.93	8.90	9.83	9.34	94.5	

$$\% \text{ Solid} = \frac{(C-A) * 100}{(B-A)}$$