

TOTAL VOLATILE SOLIDS 160.4

TEMP1 IN: 104 °C 08/27/2024 15:00 **TEMP1 OUT:** 103 °C 08/28/2024 07:00
TEMP2 IN: 104 °C 08/28/2024 07:30 **TEMP2 OUT:** 103 °C 08/28/2024 09:00
TEMP3 IN: 540 °C 08/28/2024 09:30 **TEMP3 OUT:** 560 °C 08/28/2024 11:00
TEMP4 IN: 560 °C 08/28/2024 11:30 **TEMP4 OUT:** 540 °C 08/28/2024 13:00

Run Number: LB132180

SUPERVISOR: Iwona

ANALYST: jignesh

BalanceID: WC SC-6

OvenID: WC OVEN-1

Dish #	Lab ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Empty Dish + Sample Weight (g)	1st Dish + SampleWt Drying @103-@105°C (g)	Final Dish + SampleWt Drying @103-@105°C (g)	Dish + Samplewt Drying @550 (±50) °C (g)	Final Dish + Samplewt Drying @550 (±50) °C (g)	Weight Diff (g)	Result (%)
1	LB132180BL	85.6036	85.6036	85.6036	85.6036	85.6036	85.6036	85.6036	0.0000	0
2	P3751-03	75.0387	75.0387	96.8528	95.6599	95.6599	94.2587	94.2587	1.4012	6.8
3	P3751-03DUP	78.3911	78.3911	99.6175	98.4802	98.4802	97.1793	97.1793	1.3009	6.5

A = Sample Weight (g)

B = Final Dish + Samplewt Drying @550 (±50) °C (g)

C = Final Dish + SampleWt Drying @103-@105°C (g)

D = Weight (g)

E = Final Empty Dish Weight (g)

F = Final Dish + SampleWt Drying @103-@105°C (g)

Weight D = C - B

Result % = $\frac{D}{F - E} \star 100$

U71322180

WORKLIST(Hardcopy Internal Chain)

WorkList Name : tvs p3751 s WorkList ID : 183011 Department : Wet-Chemistry Date : 08-27-2024 13:49:09

Sample	Customer Sample	Matrix	Test	Preservative	Customer	Raw Sample Storage Location	Collect Date	Method
P3751-03	WC-CMC-ESLAG-1	Solid	TVS	Cool 4 deg C	ENTA05	D21	08/26/2024	160.4

Date/Time 08/27/24 14:00
Raw Sample Received by: JD wege
Raw Sample Relinquished by: JD (SM)

Date/Time 08/27/24 16:00
Raw Sample Received by: JD (SM)
Raw Sample Relinquished by: JD (SM)