

TOTAL VOLATILE SOLIDS 160.4

TEMP1 IN: 104 °C 10/29/2024 17:00 **TEMP1 OUT:** 103 °C 10/30/2024 08:30
TEMP2 IN: 104 °C 10/30/2024 09:00 **TEMP2 OUT:** 103 °C 10/30/2024 10:30
TEMP3 IN: 540 °C 10/30/2024 11:00 **TEMP3 OUT:** 540 °C 10/30/2024 11:40
TEMP4 IN: 560 °C 10/30/2024 12:10 **TEMP4 OUT:** 560 °C 10/30/2024 12:50

Run Number: LB133215

SUPERVISOR: Iwona

ANALYST: Niha

BalanceID: WC SC-6

OvenID: WC OVEN-1

Dish #	Lab ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Empty Dish + Sample Weight (g)	1st Dish + SampleWt Drying @103-@105°C (g)	Final Dish + SampleWt Drying @103-@105°C (g)	Dish + Samplewt Drying @550 (±50) °C (g)	Final Dish + Samplewt Drying @550 (±50) °C (g)	Weight Diff (g)	Result (%)
1	LB133215BL	58.4132	58.4132	58.4132	58.4132	58.4132	58.4132	58.4132	0.0000	0
2	P4617-03	59.4128	59.4128	79.4455	78.3622	78.3622	76.9327	76.9327	1.4295	7.5
3	P4617-03DUP	53.5400	53.5400	74.0624	73.0734	73.0734	71.6012	71.6012	1.4722	7.5

A = Sample Weight (g)
B = Final Dish + Samplewt Drying @550 (±50) °C (g)
C = Final Dish + SampleWt Drying @103-@105 °C (g)
D = Weight (g)
E = Final Empty Dish Weight (g)
F = Final Dish + SampleWt Drying @103-@105 °C (g)

Weight D = C - B

Result % = $\frac{D}{F - E} \star 100$

WORKLIST(Hardcopy Internal Chain)

LB133215

WorkList Name : TVS-10292024 WorkList ID : 184924 Department : Wet-Chemistry Date : 10-29-2024 16:31:42

Sample	Customer Sample	Matrix	Test	Preservative	Customer	Raw Sample Storage Location	Collect Date	Method
P4617-03	CONCRETE-PILE	Solid	TVS	Cool 4 deg C	PSEG03	K61	10/29/2024	160.4

Date/Time 10.29.2024, 16:40
Raw Sample Received by: NF(wc)
Raw Sample Relinquished by: NF(wc)

Date/Time 10.29.2024, 17:15
Raw Sample Received by: NF(wc)
Raw Sample Relinquished by: NF(wc)