

TOTAL VOLATILE SOLIDS 160.4

TEMP1 IN: 104 °C 06/11/2025 15:30 **TEMP1 OUT:** 103 °C 06/12/2025 07:30
TEMP2 IN: 104 °C 06/12/2025 08:00 **TEMP2 OUT:** 103 °C 06/12/2025 09:30
TEMP3 IN: 550 °C 06/13/2025 10:00 **TEMP3 OUT:** 550 °C 06/12/2025 11:30
TEMP4 IN: 540 °C 06/12/2025 12:00 **TEMP4 OUT:** 540 °C 06/12/2025 13:30

Run Number: LB136106

SUPERVISOR: Iwona

ANALYST: jignesh

BalanceID: WC SC-6

OvenID: WC OVEN-1

Dish #	Lab ID	Empty Dish Weight (g)	Final Empty Dish Weight (g)	Empty Dish + Sample Weight (g)	1st Dish + SampleWt Drying @103-@105°C (g)	Final Dish + SampleWt Drying @103-@105°C (g)	Dish + Samplewt Drying @550 (±50) °C (g)	Final Dish + Samplewt Drying @550 (±50) °C (g)	Weight Diff (g)	Result (%)
1	LB136106BL	86.3523	86.3523	86.3523	86.3523	86.3523	86.3523	86.3523	0.0000	0
2	Q2285-04	82.3644	82.3644	103.4481	101.5149	101.5149	101.0314	101.0314	0.4835	2.5
3	Q2285-04DUP	78.4797	78.4797	105.5014	103.0701	103.0701	102.4759	102.4759	0.5942	2.4

A = Sample Weight (g)

B = Final Dish + Samplewt Drying @550 (±50) °C (g)

C = Final Dish + SampleWt Drying @103-@105 °C (g)

D = Weight (g)

E = Final Empty Dish Weight (g)

F = Final Dish + SampleWt Drying @103-@105 °C (g)

Weight D = C - B

Result % = $\frac{D}{F - E} \star 100$

WORKLIST(Hardcopy Internal Chain)

WB 136106

WorkList Name : tvs s q2285

WorkList ID : 190107

Department : Wet-Chemistry

Date : 06-11-2025 11:12:31

Sample	Customer Sample	Matrix	Test	Preservative	Customer	Raw Sample Storage Location	Collect Date	Method
Q2285-04	HAM-CONCRETE	Solid	TVS	Cool 4 deg C	PSEG03	D41	06/10/2025	160.4

Date/Time 06-11-25 11:30

Raw Sample Received by: SB 0001

Raw Sample Relinquished by: [Signature]

Date/Time

Raw Sample Received by:

Raw Sample Relinquished by: